
Spojke in prirobnične prilagoditve široke uporabe za cevi iz različnih materialov: duktilne litine, sive litine (z lamelastim grafitom), jekla, PVC-U, PE, vlaknatega cementa

Ductile iron wide tolerance couplings and flange adaptors for use with pipes of different materials: ductile iron, Grey iron, Steel, PVC-U, PE, Fibre-cement

Großbereichskupplungen und -flanschadapter aus duktilem Gusseisen zur Verbindung von Rohren aus unterschiedlichen Werkstoffen: Duktiles Gusseisen, Grauguss, Stahl, PVC-U, PE, Faserzement

Adaptateurs de brides et manchons à larges tolérances en fonte ductile destinés à être utilisés avec des tuyaux faits de différents matériaux : fonte ductile, fonte grise, acier, PVC-U, PE, fibre-ciment

Ta slovenski standard je istoveten z: prEN 14525

ICS:

23.040.10	Železne in jeklene cevi	Iron and steel pipes
23.040.60	Prirobnice, oglavki in spojni elementi	Flanges, couplings and joints

oSIST prEN 14525:2020

en,fr,de

iTeh STANDARD PREVIEW
(standards.iteh.ai)

oSIST prEN 14525:2020

<https://standards.iteh.ai/catalog/standards/sist/1f05946f-9d14-4917-ab17-d6d3ba9877d2/osist-pren-14525-2020>

EUROPEAN STANDARD
NORME EUROPÉENNE
EUROPÄISCHE NORM

DRAFT
prEN 14525

August 2020

ICS 23.040.60

Will supersede EN 14525:2004

English Version

Ductile iron wide tolerance couplings and flange adaptors for use with pipes of different materials: ductile iron, Grey iron, Steel, PVC-U, PE, Fibre-cement

Großbereichskupplungen und -flanschadapter aus
duktilen Gusseisen zur Verbindung von Rohren aus
unterschiedlichen Werkstoffen: Duktiles Gusseisen,
Grauguss, Stahl, PVC-U, PE, Faserzement

This draft European Standard is submitted to CEN members for enquiry. It has been drawn up by the Technical Committee CEN/TC 203.

If this draft becomes a European Standard, CEN members are bound to comply with the CEN/CENELEC Internal Regulations which stipulate the conditions for giving this European Standard the status of a national standard without any alteration.

This draft European Standard was established by CEN in three official versions (English, French, German). A version in any other language made by translation under the responsibility of a CEN member into its own language and notified to the CEN-CENELEC Management Centre has the same status as the official versions.

CEN members are the national standards bodies of Austria, Belgium, Bulgaria, Croatia, Cyprus, Czech Republic, Denmark, Estonia, Finland, France, Germany, Greece, Hungary, Iceland, Ireland, Italy, Latvia, Lithuania, Luxembourg, Malta, Netherlands, Norway, Poland, Portugal, Republic of North Macedonia, Romania, Serbia, Slovakia, Slovenia, Spain, Sweden, Switzerland, Turkey and United Kingdom.

Recipients of this draft are invited to submit, with their comments, notification of any relevant patent rights of which they are aware and to provide supporting documentation.

Warning : This document is not a European Standard. It is distributed for review and comments. It is subject to change without notice and shall not be referred to as a European Standard.



EUROPEAN COMMITTEE FOR STANDARDIZATION
COMITÉ EUROPÉEN DE NORMALISATION
EUROPÄISCHES KOMITEE FÜR NORMUNG

CEN-CENELEC Management Centre: Rue de la Science 23, B-1040 Brussels

Contents	Page
European foreword	3
1 Scope	4
2 Normative references	5
3 Terms and definitions	6
4 Technical requirements	9
4.1 General	9
4.2 Dimensional requirements	11
4.3 Material Characteristics	14
4.4 Coatings	15
4.5 Product information	15
4.6 Leak tightness	16
5 Performance requirements for joints	16
5.1 General	16
5.2 Pressure rating	17
5.3 Leak tightness of flexible joints	17
5.4 Restrained flexible joints	18
5.5 Long term hydrostatic strength test	21
5.6 Flanged joints	22
6 Test methods	23
6.1 Tensile testing	23
6.2 Brinell hardness	24
6.3 Works leak tightness test	24
7 Performance tests	24
7.1 Leak tightness of joints to positive internal pressure	24
7.2 Leak tightness of joints to negative internal pressure	26
7.3 Leak tightness of joints to dynamic internal pressure	26
7.4 Long term hydrostatic strength test for joints for PE pipes	27
7.5 Pull out test at 25 °C for restrained joints for PE pipes	27
7.6 Long term hydrostatic strength test for joints of fittings for PVC-U pipe	28
Annex A (informative) Outside diameters of existing pipes	29
Annex B (informative) Quality assurance	31
Bibliography	32

European foreword

This document (prEN 14525:2020) has been prepared by Technical Committee CEN/TC 203 “Cast iron pipes, fittings and accessories”, the secretariat of which is held by AFNOR.

This document is currently submitted to the CEN Enquiry.

This document will supersede EN 14525:2004.

The significant changes made since the previous version are:

- Allowance of steel as material (as EN 12842);
- Introduction of type test for ductile iron in delivery conditions;
- Introduction of long term testing for PVC-U and PE (as per EN 12842);
- Correction on pressure testing depending on pipe material (as per EN 12842);
- Wording and paragraphs harmonized with EN 12842 and EN 545.

This document is in conformity with the general requirements already established by CEN/TC 164 in the field of water supply.

In respect of potential adverse effects on the quality of water intended for human consumption caused by the product covered by this document:

- this document provides no information as to whether the product may be used without restriction in any of the member states of the EU or EFTA;
- it should be noted that, while awaiting the adoption of verifiable European criteria, existing national regulations concerning the use and/or the characteristics of these product remain in force.

prEN 14525:2020 (E)**1 Scope**

This document specifies the requirements and associated test methods applicable to wide tolerance ductile iron and steel couplings, stepped/reducing couplings and flange adaptors intended for use with pipe components made from a number of pipe materials (ductile iron, grey iron, PE in conformity with EN 12201-1 to EN 12201-5, PVC-U in conformity with EN ISO 1452-1 to EN ISO 1452-5, steel, fibre-cement), for providing a leak tight seal over a wide range of pipe outside diameters:

- to convey water (e.g. water intended for human consumption);
- with or without pressure;
- to be installed below or above ground, inside or outside buildings.

This document is not intended to cover sewerage or gas applications, where additional requirements may be necessary.

This document specifies requirements for materials, dimensions and tolerances, mechanical properties and standard coatings of products.

This document covers wide tolerance couplings, stepped/reducing couplings and flange adaptors:

- Manufactured with socketed or flanged ends;
- Supplied externally and internally coated;
- Suitable for ductile iron in conformity with EN 545, grey iron, PE in conformity with EN 12201-1 to EN 12201-5, PVC-U in conformity with EN ISO 1452-1 to EN ISO 1452-5, steel, fibre-cement in a size range extending from DN 40 to DN 700, for an allowable operating pressure (PFA) up to 16 bar, for fluid temperatures between 0 °C and 25 °C excluding frost. For higher temperatures, (up to 45 °C for PVC-U or 40 °C for PE) the PFA is derated as given in EN ISO 1452 and EN 12201;
- Not intended for use in areas subjected to reaction to fire regulations.

NOTE 1 This does not preclude special arrangements for the products to be used at higher temperatures. Temperature limitations and pressure limitations are those coming from the PVC-U or PE pipes.

This document covers ductile iron couplings, stepped/reducing couplings and flange adaptors cast by any type of foundry process or manufactured by fabrication of cast components, as well as corresponding joints, in a size range extending from DN 40 to DN 700, to be used with pipes of external diameter from 40 mm to 710 mm.

As long as no equivalent European Standard exists for steel accessories, this document also covers couplings and flange adaptors which are fabricated partly or entirely from steel as well as corresponding joints, in a size range extending from DN 60 to DN 700, to be used with pipes of external diameter from 63 mm to 710 mm.

This document specifies requirements for materials, dimensions and tolerances, mechanical properties and standard coatings. It also gives minimum performance requirements for all components, including restrained and non-restrained flexible joints. Joint design and gasket shapes are outside the scope of this document.

NOTE 2 PFA can be limited depending on pipe materials effectively connected.

NOTE 3 In this document, if not specified, all pressures are relative gauge pressures, expressed in bars (100 kPa = 1 bar).

2 Normative references

The following documents are referred to in the text in such a way that some or all of their content constitutes requirements of this document. For dated references, only the edition cited applies. For undated references, the latest edition of the referenced document (including any amendments) applies.

EN 545, *Ductile iron pipes, fittings, accessories and their joints for water pipelines - Requirements and test methods*

EN 681-1, *Elastomeric seals - Materials requirements for pipe joint seals used in water and drainage applications - Part 1: Vulcanized rubber*

EN 805, *Water supply - Requirements for systems and components outside buildings*

EN 1092-2, *Flanges and their joints - Circular flanges for pipes, valves, fittings and accessories, PN designated - Part 2: Cast iron flanges*

EN 1514 (all parts), *Flanges and their joints - Dimensions of gaskets for PN-designated flanges.*

EN 10025-1:2004, *Hot rolled products of structural steels - Part 1: General technical delivery conditions*

EN 10310, *Steel tubes and fittings for onshore and offshore pipelines - Internal and external polyamide powder based coatings*

EN 12201 (all parts), *Plastics piping systems for water supply, and for drainage and sewerage under pressure - Polyethylene (PE)*

EN 14901-1, *Ductile iron pipes, fittings and accessories - Requirements and test methods for organic coatings of ductile iron fittings and accessories - Part 1: Epoxy coating (heavy duty)*

EN 15189, *Ductile iron pipes, fittings and accessories - External polyurethane coating for pipes - Requirements and test methods*

EN 15655-1, *Ductile iron pipes, fittings and accessories - Requirements and test methods for organic linings of ductile iron pipes and fittings - Part 1: Polyurethane lining of pipes and fittings*

EN ISO 1452(all parts), *Plastic piping systems for water supply and for buried and above-ground drainage and sewerage under pressure - Unplasticized poly(vinyl chloride) (PVC-U)*

EN ISO 4016, *Hexagon head bolts - Product grade C (ISO 4016)*

EN ISO 4034, *Hexagon regular nuts (style 1) - Product grade C (ISO 4034)*

EN ISO 6506-1, *Metallic materials - Brinell hardness test - Part 1: Test method (ISO 6506-1)*

EN ISO 6892-1, *Metallic materials - Tensile testing - Part 1: Method of test at room temperature (ISO 6892-1)*

EN ISO 7091, *Plain washers - Normal series - Product grade C (ISO 7091)*

EN ISO 11177, *Vitreous and porcelain enamels - Inside and outside enamelled valves and pressure pipe fittings for untreated and potable water supply - Quality requirements and testing (ISO 11177)*

prEN 14525:2020 (E)**3 Terms and definitions**

For the purposes of this document, the following terms and definitions apply.

ISO and IEC maintain terminological databases for use in standardization at the following addresses:

- ISO Online browsing platform: available at <https://www.iso.org/obp>
- IEC Electropedia: available at <http://www.electropedia.org/>

3.1**ductile iron**

cast iron used for pipes, fittings and accessories in which graphite is present substantially in spheroidal form

3.2**fitting and accessory**

casting or manufactured steel component other than a pipe which allows pipeline deviation, change of direction or bore

Note 1 to entry: Flanged-socket pieces, flanged spigot pieces are also classified as fittings (EN 545) as far as their dimension are defined in EN 545. As they have no dimensional requirement in EN 545 couplings, stepped/reducing couplings and flange adaptors are defined as accessories in EN 545.

3.3**flange**

end of a pipe or fitting extending perpendicular to its axis, with bolt holes equally spaced on a circle

Note 1 to entry: A flange may be fixed (e.g. integrally cast or welded-on) or adjustable; an adjustable flange comprises a ring, in one or several parts assembled together, which bears on an end joint hub and can be freely rotated around the axis before jointing. See EN 545.

3.4**spigot**

male end of a pipe or fitting

3.5**socket**

female end of a pipe or fitting to make the connection with the spigot of the next component

3.6**gasket**

sealing component of a joint

3.7**joint**

connection between the ends of two pipes and/or fittings in which a gasket is used to effect a seal

3.8**flexible joint**

joint which permits significant angular deflection both during and after installation and which can accept a slight offset of the centreline

3.9**push-in flexible joint**

flexible joint assembled by pushing the spigot through the gasket in the socket of the mating component

3.10**mechanical flexible joint**

flexible joint in which sealing is obtained by applying pressure to the gasket by mechanical means, e.g. a gland

3.11**restrained flexible joint**

flexible joint in which a means is provided to prevent axial separation of the assembled joint

3.12**flanged joint**

joint between two flanged ends

3.13**joint angular deflection**

angle between the axis of two connected pipeline components which a flexible joint can accommodate

3.14**joint gap/ withdrawal**

axial distance between any point of the spigot ends of the pipes to be connected, when aligned (couplings, stepped/reducing couplings), or, axial distance between any point of the spigot end of the pipe and the flange face, when aligned (flange adaptor)

Note 1 to entry: See also 4.2.3. The word **joint gap** is used for accessories where withdrawal is used for socketed pipes as per EN 545. <https://standards.iteh.ai/catalog/standards/sist/1f05946f-9d14-4917-ab17-d6d3ba9877d2/osist-pren-14525-2020>

3.15**depth of engagement**

when jointed, the distance between the end of the spigot and the face of the socket on a couplings, stepped/reducing couplings and flange adaptors

Note 1 to entry: See also 4.2.3.

3.16**outside diameter****OD**

outside diameter of the pipe(s) to be connected and current designation of PVC-U and PE diameter designation

3.17**nominal size****DN**

alphanumerical designation of size for components of a pipework system, which is used for reference purposes

Note 1 to entry: It comprises the letters DN followed by a dimensionless whole number which is indirectly related to the physical size, in millimetres, of the bore or outside diameter of the end connections.

Note 2 to entry: See EN ISO 6708.

prEN 14525:2020 (E)**3.18****nominal pressure****PN**

alphanumeric designation used for reference purposes related to a combination of mechanical and dimensional characteristics of a component of a pipework system

Note 1 to entry: It comprises the letters PN followed by a dimensionless number. (See EN 1333.)

Note 2 to entry: All equipment of the same nominal size DN designated by the same PN number have compatible mating dimensions.

3.19**leak tightness test pressure**

pressure applied to a component during manufacture in order to ensure its leak tightness

3.20**allowable operating pressure****PFA**

maximum hydrostatic pressure that a component is capable of withstanding continuously in service

Note 1 to entry: See EN 805.

Note 2 to entry: In EN ISO 1452 and EN 12201, the term nominal pressure (PN) at 20 °C is used in place of PFA.

3.21**allowable maximum operating pressure****PMA**

maximum pressure occurring from time to time, including surge, that a component is capable of withstanding in service

Note 1 to entry: See EN 805.

3.22**allowable test pressure****PEA**

maximum hydrostatic pressure that a newly installed component is capable of withstanding for a relatively short duration, in order to insure the integrity and tightness of the pipeline

Note 1 to entry: See EN 805.

3.23**performance test**

proof of design test which is done once and is repeated after change of design or change of elastomeric or plastic components (source or grade)

3.24**wide tolerance flange adaptor**

accessory intended for use with pipes of various materials which:

- is used in a pipeline to make the connection with a spigot of a pipe or a fitting and the flange of another component of the pipeline (e.g. pipe, fitting, valve, etc.); and
- allows for angular and axial displacements for unrestrained joints and angular displacements for restrained flexible joints

Note 1 to entry: Some flange adaptors are designed such that they can be slid over the pipes in order to facilitate easy assembly.

3.25

wide tolerance coupling

accessory intended for use with pipes of various materials which:

- is used in a pipeline to make the connection between two spigots of pipes, fittings or valves, etc. of the same nominal size; and
- allows for angular and axial displacements for unrestrained joints and angular displacements for restrained flexible joints

3.26

wide tolerance stepped or reducer coupling

wide tolerance coupling intended for use with pipeline components of different nominal sizes

3.27

annulus gap

gap between the sealing surfaces of the gasket chamber and of the outside diameter of the pipe that is inserted into the socket of the coupling, stepped / reducing coupling or flange adaptor

4 Technical requirements

4.1 General

4.1.1 Diameter range

The diameter range of wide tolerance couplings and flange adaptors is defined by the maximum and minimum outside diameters of the pipes to be connected. Within this diameter range the performance shall be guaranteed at the Manufacturers declared PFA.

The preferred PFA's are 6 bars, 10 bars and 16 bars.

The minimum diameter range of wide tolerance couplings and flange adaptors is given in Table 1.

NOTE The diameter range of wide tolerance couplings, stepped/reducing couplings and flange adaptors is applicable to the accessory and is not to be confused with the diameter tolerances of the pipes.

Table 1 — Minimum diameter range

Maximum OD or DN of the pipes to be connected		Minimum diameter range (mm)
OD (mm)	DN	
OD ≤ 110	DN ≤ 100	10
110 < OD ≤ 225	100 < DN ≤ 200	15
225 < OD ≤ 315	200 < DN ≤ 300	20
315 < OD ≤ 400	300 < DN ≤ 400	25
400 < OD ≤ 710	400 < DN ≤ 700	30

The working range defined by the minimum and the maximum outside diameter range shall be specified by the manufacturer.

prEN 14525:2020 (E)

Informative Annex A gives the outside diameters of existing pipes, according to current ISO, EN or national standards.

4.1.2 Surface condition and repairs

Wide tolerance couplings, stepped / reducing couplings and wide tolerance flange adaptors shall be free from defects and surface imperfections which could lead to non-compliance with Clauses 4 and 5.

When necessary, couplings, stepped / reducing couplings and wide tolerance flange adaptors may be repaired, for example by welding, in order to remove surface imperfections and localised defects which do not extend through the entire wall thickness, provided that:

- the repairs are carried out according to the manufacturer's written procedure;
- the repaired couplings and flange adaptors comply with all the requirements of Clauses 4 and 5.

4.1.3 Types of joints and interconnection**4.1.3.1 General**

Rubber gasket materials shall comply with the requirements of EN 681-1 for the type WA.

4.1.3.2 Flexible joints

Flexible joints, restrained or non-restrained, shall meet the performance requirements detailed in Clause 5.

The manufacturer shall declare for which pipe materials restrained joints may be used.

Due to the effect that temperature and pressure has on PE pipe and the associated tensile loads, all joints intended for use on this pipe material shall be restrained and meet the requirements of 5.4 and 5.5.

Supporting sleeves (inserts) may be necessary depending on pipe material, on pipe wall thickness, on joint design and on local authorities. They shall provide adequate support over the entire compression area of the gasket and restraining mechanism.

4.1.3.3 Flanged joints

Flanged joints shall be constructed in such a way that they may be attached to flanges whose dimensions and tolerances comply with EN 1092-2. This ensures interconnection between all flanged components (pipes, fittings, valves, etc.) of the same PN and DN and adequate joint performance.

Bolts and nuts shall comply as a minimum with the requirements of EN ISO 4016 and EN ISO 4034, grade 4.6. Where washers are required they shall comply with EN ISO 7091.

Although it does not affect interconnection, the manufacturer shall state whether their products are normally delivered with fixed flanges or adjustable flanges.

Flange gaskets may be one of any type given in EN 1514 (all parts).

Flanges may be designed to be compatible with different DN (e.g. DN 50-60-65) and/or different PN (e.g. PN 10/16).

Certain flange adaptors, especially for repair purposes, are designed to cater for flanges other than EN 1092-2. Consequently, some dimensions (e.g. thickness, bolt holes) may be designed to suit. Such flange adaptors shall not compromise functionality or compatibility with EN 1092-2 flanges.

4.1.4 Materials in contact with water intended for human consumption

Wide tolerance couplings, stepped / reducing couplings and wide tolerance flange adaptors include several materials given in this document. When used under the conditions for which they are designed, in permanent or in temporary contact with water intended for human consumption, wide tolerance