

SLOVENSKI STANDARD oSIST prEN 413-1:2018

01-oktober-2018

Zidarski cement - 1. del: Sestava, zahteve in merila skladnosti

Masonry cement - Part 1: Composition, specifications and conformity criteria

Putz- und Mauerbinder - Teil 1: Zusammensetzung, Anforderungen und Konformitätskriterien

Ciment à maçonner - Partie 1 : Composition, spécifications et critères de conformité (standards.iteh.ai)

Ta slovenski standard je istoveten z: prEN 413-1

https://standards.iteh.ai/catalog/standards/sist/e7d06e65-b047-4456-a2c8dd76213cac77/osist-pren-413-1-2018

<u>ICS:</u>

91.100.10 Cement. Mavec. Apno. Malta Cement. Gypsum. Lime. Mortar

oSIST prEN 413-1:2018

en,fr,de



iTeh STANDARD PREVIEW (standards.iteh.ai)

oSIST prEN 413-1:2018 https://standards.iteh.ai/catalog/standards/sist/e7d06e65-b047-4456-a2c8dd76213cac77/osist-pren-413-1-2018



EUROPEAN STANDARD NORME EUROPÉENNE EUROPÄISCHE NORM

DRAFT prEN 413-1

ICS 91.100.10

July 2018

Will supersede EN 413-1:2011

English Version

Masonry cement - Part 1: Composition, specifications and conformity criteria

Ciment à maçonner - Partie 1 : Composition, spécifications et critères de conformité

Putz- und Mauerbinder - Teil 1: Zusammensetzung, Anforderungen und Konformitätskriterien

This draft European Standard is submitted to CEN members for enquiry. It has been drawn up by the Technical Committee CEN/TC 51.

If this draft becomes a European Standard, CEN members are bound to comply with the CEN/CENELEC Internal Regulations which stipulate the conditions for giving this European Standard the status of a national standard without any alteration.

This draft European Standard was established by CEN in three official versions (English, French, German). A version in any other language made by translation under the responsibility of a CEN member into its own language and notified to the CEN-CENELEC Management Centre has the same status as the official versions.

CEN members are the national standards bodies of Austria, Belgiun, Bulgaria, Croatia, Cyprus, Czech Republic, Denmark, Estonia, Finland, Former Yugoslav Republic of Macedonia, France, Germany, Greece, Hungary, Iceland, Ireland, Italy, Latvia, Lithuania, Luxembourg, Malta, Netherlands, Norway, Poland, Portugal, Romania, Serbia, Slovakia, Slovenia, Spain, Sweden, Switzerland, Turkey and United Kingdom.

Recipients of this draft are invited to submit, with their comments, notification of any relevant patent rights of which they are aware and to provide supporting documentation.

Warning : This document is not a European Standard. It is distributed for review and comments. It is subject to change without notice and shall not be referred to as a European Standard.



EUROPEAN COMMITTEE FOR STANDARDIZATION COMITÉ EUROPÉEN DE NORMALISATION EUROPÄISCHES KOMITEE FÜR NORMUNG

CEN-CENELEC Management Centre: Rue de la Science 23, B-1040 Brussels

Contents

Europ	ean foreword	4
Introd	luction	5
1	Scope	6
2	Normative references	6
3	Terms and definitions	6
4	Notation	
5	Requirements	
5 5.1	General	
5.2	Constituents and composition	-
5.3	Physical and mechanical requirements	
5.3.1	Fineness (sieve residue)	
5.3.2	Initial setting time	
5.3.3	Final setting time	
5.3.4	Soundness	
5.3.5		
5.3.6	Fresh mortar requirements Compressive strength	
5.3.0 5.4	Chamical requirements	
5.4 5.5	Chemical requirements standards.iten.ai) Durability requirements	
5.5		
6	Standard designation	
7	Conformity criteria	
7.1	General requirements	
7.2	Conformity criteria for physical, mechanical and chemical properties and	
	evaluation procedure	
7.2.1	General	
7.2.2	Statistical conformity criteria	
7.2.3	Single result conformity criteria	
7.3	Conformity criteria for masonry cement composition	
Annez	x ZA (informative) Relationship of this European Standard with Regulation (EU)	
	No. 305/2011	
ZA.1	Scope and relevant characteristics	
ZA.2	System of Assessment and Verification of Constancy of Performance (AVCP)	
ZA.3	Assignment of AVCP tasks	
Biblio	graphy	

Tables

Table 1 — Composition of masonry cements	9
Table 2 — Fresh mortar requirements given as characteristic values	10
Table 3 — Compressive strength requirements given as characteristic values	10
Table 4 — Chemical requirements given as characteristic values	11

Table 5 — Properties, test methods and minimum testing frequencies for the	
autocontrol testing by the manufacturer, and the statistical assessment procedure	12
Table 6 — Required values of P_k and CR	14
Table 7 — Acceptability constant	15
Table 8 — Values of <i>c</i> _A	16
Table 9 — Limit values for single results	16
Table ZA.1 — Relevant clauses for product Masonry cement and intended use: Preparation of mortar for bricklaying and blocklaying and rendering and plastering	19
Table ZA.3 — Assignment of AVCP tasks for Masonry cements under system 1+	22

iTeh STANDARD PREVIEW (standards.iteh.ai)

oSIST prEN 413-1:2018 https://standards.iteh.ai/catalog/standards/sist/e7d06e65-b047-4456-a2c8dd76213cac77/osist-pren-413-1-2018

European foreword

This document (prEN 413-1:2018) has been prepared by Technical Committee CEN/TC 51 "Cement and building limes", the secretariat of which is held by NBN.

This document will supersede EN 413-1:2011.

The European standard, EN 413, *Masonry cement*, consists of the following parts:

- Part 1: Composition, specifications and conformity criteria;
- *Part 2: Test methods.*

This document has been prepared under a mandate given to CEN by the European Commission and the European Free Trade Association, and supports essential requirements of EU Directive(s).

For relationship with EU Directive(s), see informative Annex ZA, which is an integral part of this document.

EN 413-1 has been prepared to provide a range of materials from which users of EN 998-1, EN 998-2 and EN 1996-1-1 (Eurocode 6) can select with confidence to achieve the level of strength and durability required of masonry and rendering.

The main changes from EN 413-1:2011 are as follows:

 a new Annex ZA addressing the provisions of the EU Construction Products Regulation (EU) No: 305/2011. https://standards.iteh.ai/catalog/standards/sist/e7d06e65-b047-4456-a2c8-dd76213cac77/osist-pren-413-1-2018

Introduction

Masonry cement should be defined and specified precisely with sufficiently stringent requirements to satisfy those who are responsible for the design and construction of buildings and other structures for maximum safety and durability.

This European standard is a carefully balanced document that has been thoroughly discussed, taking into account the need to provide clear definitions and specifications and to arrive at a usable standard.

The requirements of this European standard are, where appropriate, based on the results from tests on masonry cement in accordance with EN 196 *Methods of testing cement*. Strength is measured on a standard mortar prepared in accordance with EN 196-1 with a fixed water/cement ratio and compacted using the equipment described in EN 196-1. However, some additional tests have been found necessary and these tests are described in EN 413-2.

CEN/TC 51 recognizes the importance of workability (cohesivity at standard consistence) of mortars prepared from masonry cements. A test method is available in CR 13933, and in which results of a test programme are also given. This test method was not found valid for standard requirement purposes due to its lack of reproducibility, however it provides valuable information for the manufacturers and users on the property in use of masonry cements.

The properties of bond and durability (resistance to frost and/or chemical attack) of mortars are very important and appropriate mortar tests are being developed by CEN/TC 125, *Masonry*. In many applications, particularly in severe environmental conditions, the choice of the type/class of masonry cement from EN 413-1 can influence the durability of mortar, e.g. in respect of frost and chemical resistance **Carcis**.**Iten.al**

oSIST prEN 413-1:2018 https://standards.iteh.ai/catalog/standards/sist/e7d06e65-b047-4456-a2c8dd76213cac77/osist-pren-413-1-2018

1 Scope

This document specifies the definition and composition of masonry cements as commonly used in Europe for the production of mortar for bricklaying and blocklaying and for rendering and plastering. It includes physical, mechanical and chemical requirements and defines strength classes. EN 413-1 also states the conformity criteria and the related rules. Necessary durability requirements are also given.

NOTE For normal applications the information given in EN 413-1, in EN 998-1 and in EN 998-2 is generally sufficient. However, in special cases, an exchange of additional information between the masonry cement producer and user can be helpful. The details of such an exchange are not within the scope of EN 413-1 but should be dealt with in accordance with national standards or other regulations or can be agreed between the parties concerned.

2 Normative references

The following documents are referred to in the text in such a way that some or all of their content constitutes requirements of this document. For dated references, only the edition cited applies. For undated references, the latest edition of the referenced document (including any amendments) applies.

EN 196-1, Methods of testing cement — Part 1: Determination of strength

EN 196-2, Method of testing cement — Part 2: Chemical analysis of cement

EN 196-3, Methods of testing cement — Part 3: Determination of setting times and soundness

EN 196-6, Methods of testing cement — Part 6: Determination of fineness oSIST prEN 413-1:2018

EN 196-7, Methods of testing cementatalo Part Methods of taking and preparing samples of cement dd76213cac77/osist-pren-413-1-2018

EN 197-1, Cement — Part 1: Composition, specifications and conformity criteria for common cements

EN 413-2, Masonry cement — Part 2: Test methods

EN 459-1, Building lime — Part 1: Definitions, specifications and conformity criteria

EN 12878, Pigments for the colouring of building materials based on cement and/or lime — Specifications and methods of test

3 Terms and definitions

For the purposes of this document, the following terms and definitions apply.

ISO and IEC maintain terminological databases for use in standardization at the following addresses:

— IEC Electropedia: available at <u>http://www.electropedia.org/</u>

ISO Online browsing platform: available at http://www.iso.org/obp

3.1

masonry cement

factory made finely powdered hydraulic binder which relies essentially upon the presence of Portland cement clinker to develop strength

Note to entry1: When mixed with sand and water only and without the addition of further materials it produces a workable mortar suitable for use in rendering, plastering and masonry work.

3.2

additives

constituents which are added to improve the manufacture or the properties of the masonry cement, e.g. grinding aids, air-entraining agents

3.3

autocontrol testing

continual testing by the manufacturer, of masonry cement spot samples taken at the point(s) of release from the factory/depot

3.4

control period

period of production and despatch identified for the evaluation of the autocontrol test results

3.5

characteristic value iTeh STANDARD PREVIEW value of a required property outside of which lies a specified percentage, the percentile P_k , of all the values of the population (standards.iteh.ai)

3.6

oSIST prEN 413-1:2018

specified characteristic value. iteh ai/catalog/standards/sist/e7d06e65-b047-4456-a2c8characteristic value of a mechanical physical or chemical property which in the case of an upper limit is not to be exceeded or, in the case of a lower limit is, as a minimum, to be reached

3.7

single result limit value

value of a mechanical, physical or chemical property which, for any single test result as in the case of an upper limit is not to be exceeded or, in the case of a lower limit is, as a minimum, to be reached

3.8

allowable probability of acceptance CR

for a given sampling plan, the allowed probability of acceptance of masonry cement with a characteristic value outside the specified characteristic value

3.9

sampling plan

specific plan which states the (statistical) sample size(s) to be used, the percentile P_k and the allowable probability of acceptance CR

3.10

spot sample

sample taken at the same time and from one and the same place, relating to the intended tests

Note to entry 1: It can be obtained by combining one or more immediately consecutive increments (see EN 196-7).

4 Notation

Masonry cement is designated by the term 'MC'.

There are three strength classes of masonry cement, 5, 12,5 and 22,5.

The term 'X' designates masonry cements in which an air entraining agent is not incorporated.

5 Requirements

5.1 General

The physical, mechanical and chemical properties of masonry cements shall be measured by the test methods described in EN 413-2 and in the relevant parts of EN 196. These European standards give alternative test methods for some properties but in the event of a dispute only the reference methods shall be used. Where allowed in the relevant part of EN 196, different methods may be used provided they give correlated and equivalent values to those obtained using the reference method.

The CEN standard sand (see EN 196-1) used to make the mortars for the tests required by 5.3.5 and 5.3.6 shall have a silica content (as quartz) of not less than 93 %.

NOTE EN 196-1 permits the use of CEN standard sands that have been assessed against the CEN reference sand in respect of their strength characteristics. According to this standard the CEN standard sand is used in mortar for tests other than that for strength. These tests have only been evaluated using CEN standard sand based essentially on silical DARD PREVIEW

All requirements are specified as characteristic values. They serve to define the performance level and classification of the masonry cements.

5.2 Constituents and compositionSIST prEN 413-1:2018

https://standards.iteh.ai/catalog/standards/sist/e7d06e65-b047-4456-a2c8-

Masonry cement shall comprise Portland cement clinker, Ohorganic constituents and where appropriate additive(s) as given in Table 1. Calcium sulfate is added in small quantities to the other constituents of masonry cement during its manufacture to control setting.

The inorganic constituents of masonry cements conforming to EN 413-1 shall be materials selected from:

- natural mineral materials;
- mineral materials used for or derived from the clinker production process;
- hydrated and/or hydraulic building limes conforming to EN 459-1;
- constituents specified in EN 197-1;
- inorganic pigments (except those containing carbon black) conforming to EN 12878.

NOTE Carbon black has a detrimental effect upon the air entrainment.

Additives shall not promote corrosion of embedded metal such as reinforcement and wall ties or impair the properties, including behaviour in fire, of the mortar made from the masonry cement. Organic pigments are not permitted.

Туре	Content % by mass			
	Portland cement clinker	Additives		
MC 5	≥ 25	≤ 1 ª		
MC 12,5; MC 12,5 X MC 22,5; MC 22,5 X	≥ 40			
^a The quantity of organic additives on a dry basis shall not exceed 0,5 % by mass of the masonry cement.				

Table 1 — Composition of masonry cements

The manufacturing process and its control shall ensure that the composition of masonry cement is kept within the limits fixed in EN 413-1. Masonry cements consist ultimately of individual small grains of different materials and are statistically homogeneous in composition resulting from quality ensured production and material handling processes.

A high degree of uniformity in all masonry cement properties shall be obtained through mass production processes, in particular, adequate grinding and homogenization. Qualified and skilled personnel and the facilities to test, evaluate and adjust product quality are indispensable for producing masonry cement in accordance with this European standard.

5.3 Physical and mechanical requirements D PREVIEW

5.3.1 Fineness (sieve residue)(standards.iteh.ai)

The residue on a 90 µm sieve shall <u>bes not more than</u> 15 % by mass when determined in accordance with ENttp96s6ndards.iteh.ai/catalog/standards/sist/e7d06e65-b047-4456-a2c8dd76213cac77/osist-pren-413-1-2018

5.3.2 Initial setting time

The initial setting time shall be not less than 60 min when determined in accordance with EN 413-2.

5.3.3 Final setting time

Where the initial setting time is less than 6 h, there is no requirement for final setting time. Where the initial setting time is 6 h or more, the final setting time shall be not more than 15 h when determined in accordance with EN 413-2.

5.3.4 Soundness

The expansion shall be not more than 10 mm when determined in accordance with EN 196-3.

5.3.5 Fresh mortar requirements

The properties of air content and water retention of fresh mortar shall be measured in accordance with EN 413-2, on a mortar of standard consistence that shall have a value of penetration of (35 ± 3) mm using the plunger apparatus as the reference method. The flow table test is the alternative method. The test results shall meet the requirements given in Table 2.