
**Wrought aluminium and aluminium
alloys — Sheets, strips and plates —**

**Part 4:
Sheets and plates: Tolerances on
shape and dimensions**

iTeh STANDARD PREVIEW
(standards.iteh.ai)
*Aluminium et alliages d'aluminium corroyés — Tôles, bandes et tôles
épaisses —
Partie 4: Tôles et tôles épaisses: Tolérances sur forme et dimensions*

[ISO 6361-4:2014](https://standards.iteh.ai/catalog/standards/sist/71684632-7793-4211-aa60-0b44358a111c/iso-6361-4-2014)

<https://standards.iteh.ai/catalog/standards/sist/71684632-7793-4211-aa60-0b44358a111c/iso-6361-4-2014>



iTeh STANDARD PREVIEW
(standards.iteh.ai)

ISO 6361-4:2014

<https://standards.iteh.ai/catalog/standards/sist/71684632-7793-4211-aa60-0b44358a111c/iso-6361-4-2014>



COPYRIGHT PROTECTED DOCUMENT

© ISO 2014

All rights reserved. Unless otherwise specified, no part of this publication may be reproduced or utilized otherwise in any form or by any means, electronic or mechanical, including photocopying, or posting on the internet or an intranet, without prior written permission. Permission can be requested from either ISO at the address below or ISO's member body in the country of the requester.

ISO copyright office
Case postale 56 • CH-1211 Geneva 20
Tel. + 41 22 749 01 11
Fax + 41 22 749 09 47
E-mail copyright@iso.org
Web www.iso.org

Published in Switzerland

Contents

	Page
Foreword	iv
1 Scope	1
2 Normative references	1
3 Dimensional tolerances	1
3.1 Thickness.....	1
3.2 Width.....	5
3.3 Length.....	6
4 Shape tolerances	7
4.1 Lateral curvature.....	7
4.2 Flatness tolerances.....	7
4.3 Squareness tolerances.....	10
Bibliography	12

iTeh STANDARD PREVIEW (standards.iteh.ai)

[ISO 6361-4:2014](https://standards.iteh.ai/catalog/standards/sist/71684632-7793-4211-aa60-0b44358a111c/iso-6361-4-2014)

<https://standards.iteh.ai/catalog/standards/sist/71684632-7793-4211-aa60-0b44358a111c/iso-6361-4-2014>

Foreword

ISO (the International Organization for Standardization) is a worldwide federation of national standards bodies (ISO member bodies). The work of preparing International Standards is normally carried out through ISO technical committees. Each member body interested in a subject for which a technical committee has been established has the right to be represented on that committee. International organizations, governmental and non-governmental, in liaison with ISO, also take part in the work. ISO collaborates closely with the International Electrotechnical Commission (IEC) on all matters of electrotechnical standardization.

The procedures used to develop this document and those intended for its further maintenance are described in the ISO/IEC Directives, Part 1. In particular the different approval criteria needed for the different types of ISO documents should be noted. This document was drafted in accordance with the editorial rules of the ISO/IEC Directives, Part 2 (see www.iso.org/directives).

Attention is drawn to the possibility that some of the elements of this document may be the subject of patent rights. ISO shall not be held responsible for identifying any or all such patent rights. Details of any patent rights identified during the development of the document will be in the Introduction and/or on the ISO list of patent declarations received (see www.iso.org/patents).

Any trade name used in this document is information given for the convenience of users and does not constitute an endorsement.

For an explanation on the meaning of ISO specific terms and expressions related to conformity assessment, as well as information about ISO's adherence to the WTO principles in the Technical Barriers to Trade (TBT) see the following URL: Foreword - Supplementary information

The committee responsible for this document is ISO/TC 79, *Light metals and their alloys*, Subcommittee SC 6, *Wrought aluminium and aluminium alloys*.

This third edition cancels and replaces the second edition (ISO 6361-4:2011), which has been technically revised.

ISO 6361 consists of the following parts, under the general title *Wrought aluminium and aluminium alloys — Sheets, strips and plates*:

- *Part 1: Technical conditions for inspection and delivery*
- *Part 2: Mechanical properties*
- *Part 3: Strips: Tolerances on shape and dimensions*
- *Part 4: Sheets and plates: Tolerances on shape and dimensions*
- *Part 5: Chemical composition*

Wrought aluminium and aluminium alloys — Sheets, strips and plates —

Part 4: Sheets and plates: Tolerances on shape and dimensions

1 Scope

This part of ISO 6361 specifies the tolerances on shape and dimensions for wrought aluminium and aluminium alloy sheet and plate by hot-rolling or cold-rolling for general engineering applications.

It applies to products with a thickness over 0,15 mm up to and including 203 mm.

It does not apply to semi-finished rolled products in coiled form to be subjected to further rolling (reroll stock) or to special products, such as those that are corrugated or embossed.

Technical conditions for inspection and delivery of products covered by this part of ISO 6361 are specified in ISO 6361-1.

2 Normative references

No normative references cited in this document.

3 Dimensional tolerances

3.1 Thickness

Thickness tolerances for a cold-rolled product are specified in [Table 1](#) and [Table 2](#).

Thickness tolerances for a hot-rolled product are specified in [Table 3](#) and [Table 4](#).

When the tolerance is specified as either all plus or minus side, the value in [Table 1](#), [Table 2](#), [Table 3](#), or [Table 4](#) shall be doubled.

Tolerances for the products exceeding the range of specified thickness and width shall be agreed upon between the purchaser and the supplier.

Table 1 — Thickness tolerances for cold-rolled product

Dimensions in millimetres

Specified thickness		Alloy number 1050, 1050A, 1070, 1070A, 1080, 1080A, 1085, 1100, 1100A, 1200, 1230A, 3003, 3103, 3203, 3005, 3105, 4006, 4007, 4015, 5005, 5010, 5110A, 5050, 8011A, 8021, 8079					
		Specified width					
Over	Up to and including	Up to and including 450	Over 450, up to and including 900	Over 900, up to and including 1 400	Over 1 400, up to and including 1 800	Over 1 800, up to and including 2 300	Over 2 300, up to and including 2 600
Tolerance							
≥0,15	0,20	±0,03	±0,03	±0,05			

Table 1 (continued)

Specified thickness		Alloy number					
		1050, 1050A, 1070, 1070A, 1080, 1080A, 1085, 1100, 1100A, 1200, 1230A, 3003, 3103, 3203, 3005, 3105, 4006, 4007, 4015, 5005, 5010, 5110A, 5050, 8011A, 8021, 8079					
Over	Up to and including	Specified width					
		Up to and including 450	Over 450, up to and including 900	Over 900, up to and including 1 400	Over 1 400, up to and including 1 800	Over 1 800, up to and including 2 300	Over 2 300, up to and including 2 600
		Tolerance					
0,20	0,25	±0,03	±0,04	±0,05			
0,25	0,45	±0,04	±0,04	±0,05	±0,06		
0,45	0,70	±0,04	±0,05	±0,06	±0,08		
0,70	0,90	±0,05	±0,05	±0,06	±0,09	±0,13	
0,90	1,1	±0,05	±0,06	±0,08	±0,10	±0,13	
1,1	1,7	±0,06	±0,08	±0,10	±0,13	±0,15	
1,7	1,9	±0,06	±0,08	±0,10	±0,15	±0,20	
1,9	2,4	±0,08	±0,08	±0,10	±0,15	±0,20	
2,4	2,7	±0,09	±0,10	±0,13	±0,18	±0,23	
2,7	3,6	±0,11	±0,11	±0,13	±0,18	±0,23	±0,25
3,6	4,5	±0,15	±0,15	±0,20	±0,23	±0,28	±0,30
4,5	5,0	±0,18	±0,18	±0,23	±0,28	±0,33	±0,38
5,0	6,5	±0,23	±0,23	±0,28	±0,33	±0,38	±0,43
6,5	8,0	±0,33	±0,33	±0,33	±0,38	±0,43	±0,51
8,0	11	±0,48	±0,48	±0,48	±0,48	±0,58	±0,66
11	16	±0,64	±0,64	±0,64	±0,64	±0,76	±0,89

Table 2 — Thickness tolerances for cold-rolled product

Dimensions in millimetres

Specified thickness		Alloy number											
		2014, 2014A, 2017, 2017A, 2618A, 2219, 2024, 2124, 3004, 3104, 5021, 5026, 5040, 5042, 5049, 5449, 5251, 5052, 5154, 5154A, 5254, 5454, 5754, 5456, 5059, 5070, 5082, 5182, 5083, 5383, 5086, 6016, 6025, 6061, 6082, 7204, 7010, 7020, 7021, 7022, 7050, 7075, 7475, 7178											
Over	Up to and including	Specified width											
		Up to and including 450	Over 450, up to and including 900	Over 900, up to and including 1 200	Over 1 200, up to and including 1 400	Over 1 400, up to and including 1 500	Over 1 500, up to and including 1 700	Over 1 700, up to and including 1 800	Over 1 800, up to and including 2 000	Over 2 000, up to and including 2 100	Over 2 100, up to and including 2 300	Over 2 300, up to and including 2 400	Over 2 400, up to and including 2 600
		Tolerance											
≥0,20	0,25	±0,03	±0,04	±0,06	±0,06								
0,25	0,45	±0,04	±0,04	±0,06	±0,09								
0,45	0,70	±0,04	±0,05	±0,06	±0,09	±0,10	±0,10	±0,10					
0,70	0,90	±0,05	±0,05	±0,06	±0,10	±0,13	±0,13	±0,13	±0,15				
0,90	1,1	±0,05	±0,06	±0,08	±0,10	±0,13	±0,13	±0,13	±0,15				
1,1	1,7	±0,06	±0,08	±0,10	±0,13	±0,15	±0,15	±0,15	±0,18				
1,7	1,9	±0,08	±0,08	±0,10	±0,13	±0,15	±0,15	±0,15	±0,18				
1,9	2,4	±0,09	±0,09	±0,10	±0,13	±0,15	±0,15	±0,15	±0,18	±0,18	±0,30		

Table 2 (continued)

Specified thickness		Alloy number											
		2014, 2014A, 2017, 2017A, 2618A, 2219, 2024, 2124, 3004, 3104, 5021, 5026, 5040, 5042, 5049, 5449, 5251, 5052, 5154, 5154A, 5254, 5454, 5754, 5456, 5059, 5070, 5082, 5182, 5083, 5383, 5086, 6016, 6025, 6061, 6082, 7204, 7010, 7020, 7021, 7022, 7050, 7075, 7475, 7178											
Over	Up to and including	Specified width											
		Up to and including 450	Over 450, up to and including 900	Over 900, up to and including 1 200	Over 1 200, up to and including 1 400	Over 1 400, up to and including 1 500	Over 1 500, up to and including 1 700	Over 1 700, up to and including 1 800	Over 1 800, up to and including 2 000	Over 2 000, up to and including 2 100	Over 2 100, up to and including 2 300	Over 2 300, up to and including 2 400	Over 2 400, up to and including 2 600
		Tolerance											
2,4	2,7	±0,10	±0,10	±0,13	±0,13	±0,18	±0,18	±0,18	±0,20	±0,20	±0,41		
2,7	3,2	±0,11	±0,11	±0,13	±0,13	±0,18	±0,18	±0,18	±0,20	±0,20	±0,41	±0,46	±0,51
3,2	3,6	±0,11	±0,11	±0,13	±0,13	±0,18	±0,25	±0,30	±0,33	±0,36	±0,41	±0,46	±0,51
3,6	4,5	±0,15	±0,15	±0,20	±0,20	±0,23	±0,30	±0,36	±0,38	±0,41	±0,43	±0,48	±0,58
4,5	5,0	±0,18	±0,18	±0,25	±0,25	±0,28	±0,36	±0,41	±0,43	±0,43	±0,43	±0,56	±0,66
5,0	6,5	±0,23	±0,23	±0,28	±0,28	±0,33	±0,41	±0,46	±0,46	±0,46	±0,46	±0,61	±0,71
6,5	8,0	±0,33	±0,33	±0,33	±0,33	±0,38	±0,46	±0,51	±0,51	±0,51	±0,51	±0,64	±0,76
8,0	11	±0,48	±0,48	±0,48	±0,48	±0,51	±0,51	±0,58	±0,58	±0,64	±0,64	±0,66	±0,84
11	16	±0,64	±0,64	±0,64	±0,64	±0,64	±0,64	±0,64	±0,76	±0,76	±0,76	±0,89	±0,89

Table 3 — (standards.iteh.ai) Thickness tolerances for hot-rolled product

Dimensions in millimetres

Specified thickness		Alloy number					
		1050, 1050A, 1070, 1070A, 1080, 1080A, 1085, 1100, 1100A, 1200, 1230A, 3003, 3103, 3203, 3005, 3105, 4006, 4007, 4015, 5005, 5010, 5110A, 5050, 8011A					
Over	Up to and including	Specified width					
		Up to and including 900	Over 900, up to and including 1 400	Over 1 400, up to and including 1 800	Over 1 800, up to and including 2 300	Over 2 300, up to and including 2 600	Over 2 600, up to and including 3 400
		Tolerance					
≥4	5	±0,25	±0,30	±0,35	±0,40		
5	6	±0,30	±0,40	±0,45	±0,50		
6	8	±0,45	±0,45	±0,55	±0,65	±0,75	±0,85
8	11	±0,55	±0,55	±0,65	±0,75	±0,85	±0,95
11	16	±0,65	±0,65	±0,75	±0,85	±0,95	±1,0
16	22	±0,80	±0,80	±0,80	±0,90	±1,1	±1,1
22	29	±0,90	±0,90	±0,90	±1,1	±1,4	±1,4
29	35	±1,0	±1,0	±1,0	±1,3	±1,7	±1,7
35	40	±1,1	±1,1	±1,1	±1,5	±1,9	±1,9
40	50	±1,3	±1,3	±1,3	±1,8	±2,2	±2,2
50	55	±1,5	±1,5	±1,5	±2,0	±2,5	±2,5

NOTE This specification shall be applied to the products of temper grade H112 and those finished by the hot-rolled condition.

Table 3 (continued)

Specified thickness		Alloy number 1050, 1050A, 1070, 1070A, 1080, 1080A, 1085, 1100, 1100A, 1200, 1230A, 3003, 3103, 3203, 3005, 3105, 4006, 4007, 4015, 5005, 5010, 5110A, 5050, 8011A					
		Specified width					
Over	Up to and including	Up to and including 900	Over 900, up to and including 1 400	Over 1 400, up to and including 1 800	Over 1 800, up to and including 2 300	Over 2 300, up to and including 2 600	Over 2 600, up to and including 3 400
		Tolerance					
55	70	±1,9	±1,9	±1,9	±2,5	±3,2	±3,2
70	75	±2,3	±2,3	±2,3	±3,0	±3,8	±3,8
75	100	±2,8	±2,8	±2,8	±3,6	±4,1	±4,1
100	150	±3,2	±3,2	±3,8	±4,1		
150	203	±4,1	±4,1	±4,1	±4,1		

NOTE This specification shall be applied to the products of temper grade H112 and those finished by the hot-rolled condition.

Table 4 — Thickness tolerances for hot-rolled product

iTeh STANDARD PREVIEW

Dimensions in millimetres

Specified thickness		Alloy number 2014, 2014A, 2017, 2017A, 2618A, 2219, 2024, 2124, 3004, 3104, 5021, 5026, 5040, 5042, 5049, 5449, 5251, 5052, 5154, 5154A, 5254, 5454, 5754, 5456, 5059, 5070, 5082, 5182, 5083, 5383, 5086, 6016, 6025, 6061, 6082, 7204, 7010, 7020, 7021, 7022, 7050, 7075, 7475, 7178					
		Specified width					
Over	Up to and including	Up to and including 900	Over 900, up to and including 1 400	Over 1 400, up to and including 1 800	Over 1 800, up to and including 2 300	Over 2 300, up to and including 2 600	Over 2 600, up to and including 3 400
		Tolerance					
≥4	5	±0,30	±0,35	±0,50	±0,60		
5	6	±0,40	±0,45	±0,55	±0,65		
6	8	±0,50	±0,50	±0,60	±0,70	±0,80	±0,90
8	11	±0,60	±0,60	±0,70	±0,80	±0,90	±1,0
11	16	±0,70	±0,70	±0,80	±0,90	±1,0	±1,1
16	22	±0,80	±0,80	±0,80	±0,90	±1,1	±1,1
22	29	±0,90	±0,90	±0,90	±1,1	±1,4	±1,4
29	35	±1,0	±1,0	±1,0	±1,3	±1,7	±1,7
35	40	±1,1	±1,1	±1,1	±1,5	±1,9	±1,9
40	50	±1,3	±1,3	±1,3	±1,8	±2,2	±2,2
50	55	±1,5	±1,5	±1,5	±2,0	±2,5	±2,5
55	70	±1,9	±1,9	±1,9	±2,5	±3,2	±3,2
70	75	±2,3	±2,3	±2,3	±3,0	±3,8	±3,8

NOTE This specification shall be applied to the products of temper grade H112 and those finished by the hot-rolled condition.

Table 4 (continued)

Specified thickness		Alloy number					
		2014, 2014A, 2017, 2017A, 2618A, 2219, 2024, 2124, 3004, 3104, 5021, 5026, 5040, 5042, 5049, 5449, 5251, 5052, 5154, 5154A, 5254, 5454, 5754, 5456, 5059, 5070, 5082, 5182, 5083, 5383, 5086, 6016, 6025, 6061, 6082, 7204, 7010, 7020, 7021, 7022, 7050, 7075, 7475, 7178					
Over	Up to and including	Specified width					
		Up to and including 900	Over 900, up to and including 1 400	Over 1 400, up to and including 1 800	Over 1 800, up to and including 2 300	Over 2 300, up to and including 2 600	Over 2 600, up to and including 3 400
		Tolerance					
75	100	±2,8	±2,8	±2,8	±3,6	±4,1	±4,1
100	150	±3,2	±3,2	±3,6	±4,1	±4,1	
150	203	±4,1	±4,1	±4,1	±4,1	±4,1	

NOTE This specification shall be applied to the products of temper grade H112 and those finished by the hot-rolled condition.

3.2 Width

Width tolerances for shared sheet and plate are specified in [Table 5](#).

Width tolerances for sawed sheet and plate are specified in [Table 6](#).

Width is measured at room temperature during cutting. The allowable maximum deviation shall be 0,23 mm per 1 000 mm in width, by a temperature difference of 10 °C against the reference temperature of 20 °C.

<https://standards.iteh.ai/catalog/standards/sist/71684632-7793-4211-aa60->

When the width tolerance for the product with a thickness of up to and including 6,5 mm is specified as either all plus or minus side, the value in [Table 5](#) or [Table 6](#) shall be doubled.

Tolerances for the products exceeding the range of specified thickness and width shall be agreed upon between the purchaser and the supplier.

Table 5 — Width tolerance for sheared sheet and plate

Dimensions in millimetres

Specified thickness		Specified width			
Over	Up to and including	Up to and including 150	Over 150, up to and including 600	Over 600, up to and including 2 500	Over 2 500, up to and including 3 500
		Tolerance			
≥0,15	3,2	±2	±3	±3	±4
3,2	6,5	±3	±3	±3	±5
6,5	16	+7 0	+8 0	+10 0	+11 0