



Designation: D 5402 – 93 (Reapproved 1999)

## Standard Practice for Assessing the Solvent Resistance of Organic Coatings Using Solvent Rubs<sup>1</sup>

This standard is issued under the fixed designation D 5402; the number immediately following the designation indicates the year of original adoption or, in the case of revision, the year of last revision. A number in parentheses indicates the year of last reapproval. A superscript epsilon ( $\epsilon$ ) indicates an editorial change since the last revision or reapproval.

### 1. Scope

1.1 This practice describes a solvent rub technique for assessing the solvent resistance of an organic coating that chemically changes during the curing process. This technique can be used in the laboratory, in the field, or in the fabricating shop. Test Method D 4752 is the preferred method for ethyl silicate zinc-rich primers.

1.2 This practice does not specify the solvent, number of double rubs, or expected test results.

1.3 The values stated in SI units are to be regarded as the standard. The values given in parentheses are for information only.

1.4 *This standard does not purport to address all of the safety concerns, if any, associated with its use. It is the responsibility of the user of this standard to establish appropriate safety and health practices and determine the applicability of regulatory limitations prior to use.* Consult the supplier's Material Safety Data Sheet for specific hazard information relating to the solvent used.

### 2. Referenced Documents

#### 2.1 ASTM Standards:

- D 235 Specification for Mineral Spirits (Petroleum Spirits) (Hydrocarbon Dry Cleaning Solvent)<sup>2</sup>
- D 523 Test Method for Specular Gloss<sup>3</sup>
- D 740 Specification for Methyl Ethyl Ketone<sup>2</sup>
- D 843 Specification for Nitration Grade Xylene<sup>2</sup>
- D 1186 Test Methods for Nondestructive Measurement of Dry Film Thickness of Nonmagnetic Coatings Applied to a Ferrous Base<sup>3</sup>
- D 1400 Test Method for Nondestructive Measurement of Dry Film Thickness of Nonconductive Coatings Applied to a Nonferrous Metal Base<sup>3</sup>
- D 3363 Test Method for Film Hardness by Pencil Test<sup>3</sup>
- D 4138 Test Method for Measurement of Dry Film Thickness of Protective Coating System by Destructive Means<sup>4</sup>

<sup>1</sup> This practice is under the jurisdiction of ASTM D-1 on Paint and Related Coatings, Materials, and Applications and is the direct responsibility of Subcommittee D01.46 on Industrial Protective Coatings.

Current edition approved May 15, 1993. Published July 1993.

<sup>2</sup> Annual Book of ASTM Standards, Vol 06.04.

<sup>3</sup> Annual Book of ASTM Standards, Vol 06.01.

<sup>4</sup> Annual Book of ASTM Standards, Vol 06.02.

D 4752 Test Method for Measuring MEK Resistance of Ethyl Silicate (Inorganic) Zinc-Rich Primers by Solvent Rub<sup>4</sup>

### 3. Terminology

#### 3.1 Definitions of Terms Specific to This Standard:

3.1.1 *double rub*—the act of rubbing a cloth in one complete forward and back motion over a coated surface.

### 4. Significance and Use

4.1 Coatings that chemically change during the curing process, such as epoxies, vinyl esters, polyesters, alkyds and urethanes, become more resistance to solvents as they cure. These coatings should reach specific levels of solvent resistance prior to being topcoated and prior to placing in service; the levels of solvent resistance necessary vary with the type of coating and the intended service. Rubbing with a cloth saturated with the appropriate solvent is one way to determine when a specific level of solvent resistance is reached. However, the level of solvent resistance by itself does not indicate full cure and some coatings become solvent resistant before they become sufficiently cured for service.

4.2 The time required to reach a specific level of solvent resistance can be influenced by temperature, film thickness, air movement and, for water-borne or water-reactive coatings, humidity.

4.3 The test solvent's effect upon the coating varies with coating type and solvent used. The coating manufacturer may specify the solvent, the number of double rubs, and the specific test results needed.

### 5. Materials and Equipment

#### 5.1 Solvent:

5.1.1 *Methyl Ethyl Ketone (MEK)*, conforming to Specification D 740, or

5.1.2 *Mineral Spirits*, conforming to Specification D 235, or

5.1.3 *Xylene*, conforming to Specification D 843, or

5.1.4 *Other Solvents*, as specified by the coating manufacturer or user.

5.2 *Cheesecloth*, 100 % cotton mesh size grade 28 by 24, approximately 300 by 300 mm (12 by 12 in.) and contrasting in color to the coating being evaluated, or other mutually agreed upon cloth.