

SLOVENSKI STANDARD
oSIST prEN ISO 24598:2018
01-junij-2018

Dodajni materiali za varjenje - Žične elektrode, polnjene žice in kombinacije žic in praškov za varjenje pod praškom jekel, odpornih proti lezenju - Razvrstitev (ISO/DIS 24598:2018)

Welding consumables - Solid wire electrodes, tubular cored electrodes and electrode-flux combinations for submerged arc welding of creep-resisting steels - Classification (ISO/DIS 24598:2018)

Schweißzusätze - Drahtelektroden, Fülldrahtelektroden und Draht-Pulver-Kombinationen für das Unterpulverschweißen von warmfesten Stählen - Einteilung (ISO/DIS 24598:2018)

Produits consommables pour le soudage - Fils-électrodes pleins, fils-électrodes fourrés et couples électrodes-flux pour le soudage à l'arc sous flux des aciers résistant au fluage - Classification (ISO/DIS 24598:2018)

Ta slovenski standard je istoveten z: prEN ISO 24598

ICS:

25.160.20 Potrošni material pri varjenju Welding consumables

oSIST prEN ISO 24598:2018

en,fr,de

DRAFT INTERNATIONAL STANDARD

ISO/DIS 24598

ISO/TC 44/SC 3

Secretariat: ANSI

Voting begins on:
2018-04-23Voting terminates on:
2018-07-16

Welding consumables — Solid wire electrodes, tubular cored electrodes and electrode-flux combinations for submerged arc welding of creep-resisting steels — Classification

Produits consommables pour le soudage — Fils-électrodes pleins, fils-électrodes fourrés et couples électrodes-flux pour le soudage à l'arc sous flux des aciers résistant au fluage — Classification

ICS: 25.160.20

iTeh STANDARD PREVIEW
(standards.iteh.ai)

SIST EN ISO 24598:2019

<https://standards.iteh.ai/catalog/standards/sist/7eb67081-1813-4441-ac08-42b15f6ef944/sist-en-iso-24598-2019>

THIS DOCUMENT IS A DRAFT CIRCULATED FOR COMMENT AND APPROVAL. IT IS THEREFORE SUBJECT TO CHANGE AND MAY NOT BE REFERRED TO AS AN INTERNATIONAL STANDARD UNTIL PUBLISHED AS SUCH.

IN ADDITION TO THEIR EVALUATION AS BEING ACCEPTABLE FOR INDUSTRIAL, TECHNOLOGICAL, COMMERCIAL AND USER PURPOSES, DRAFT INTERNATIONAL STANDARDS MAY ON OCCASION HAVE TO BE CONSIDERED IN THE LIGHT OF THEIR POTENTIAL TO BECOME STANDARDS TO WHICH REFERENCE MAY BE MADE IN NATIONAL REGULATIONS.

RECIPIENTS OF THIS DRAFT ARE INVITED TO SUBMIT, WITH THEIR COMMENTS, NOTIFICATION OF ANY RELEVANT PATENT RIGHTS OF WHICH THEY ARE AWARE AND TO PROVIDE SUPPORTING DOCUMENTATION.

This document is circulated as received from the committee secretariat.

ISO/CEN PARALLEL PROCESSING



Reference number
ISO/DIS 24598:2018(E)

© ISO 2018

iTeh STANDARD PREVIEW (standards.iteh.ai)

SIST EN ISO 24598:2019

<https://standards.iteh.ai/catalog/standards/sist/7eb67081-1813-4441-ac08-42b15f6ef944/sist-en-iso-24598-2019>



COPYRIGHT PROTECTED DOCUMENT

© ISO 2018

All rights reserved. Unless otherwise specified, or required in the context of its implementation, no part of this publication may be reproduced or utilized otherwise in any form or by any means, electronic or mechanical, including photocopying, or posting on the internet or an intranet, without prior written permission. Permission can be requested from either ISO at the address below or ISO's member body in the country of the requester.

ISO copyright office
CP 401 • Ch. de Blandonnet 8
CH-1214 Vernier, Geneva
Phone: +41 22 749 01 11
Fax: +41 22 749 09 47
Email: copyright@iso.org
Website: www.iso.org

Published in Switzerland

Contents

Page

Foreword	iv
Introduction	v
1 Scope	1
2 Normative references	1
3 Terms and definitions	2
4 Classification	2
5 Symbols and requirements	3
5.1 General.....	3
5.2 Symbol for the product/process.....	3
5.3 Symbols for the tensile properties of the all-weld metal deposit.....	3
5.4 Symbols for impact properties of all-weld metal deposits.....	3
5.5 Symbol for type of welding flux.....	5
5.6 Symbol for the chemical composition of solid wire electrodes and of all-weld metal deposits.....	5
6 Mechanical tests	11
6.1 Preheating, interpass and post-weld heat treatment temperatures.....	11
6.2 Welding conditions and pass sequence.....	16
7 Chemical analysis	18
8 Rounding procedure	18
9 Retests	18
10 Technical delivery conditions	19
11 Examples of designation	20
Bibliography	23

ISO/DIS 24598:2018(E)

Foreword

ISO (the International Organization for Standardization) is a worldwide federation of national standards bodies (ISO member bodies). The work of preparing International Standards is normally carried out through ISO technical committees. Each member body interested in a subject for which a technical committee has been established has the right to be represented on that committee. International organizations, governmental and non-governmental, in liaison with ISO, also take part in the work. ISO collaborates closely with the International Electrotechnical Commission (IEC) on all matters of electrotechnical standardization.

The procedures used to develop this document and those intended for its further maintenance are described in the ISO/IEC Directives, Part 1. In particular the different approval criteria needed for the different types of ISO documents should be noted. This document was drafted in accordance with the editorial rules of the ISO/IEC Directives, Part 2 (see www.iso.org/directives).

Attention is drawn to the possibility that some of the elements of this document may be the subject of patent rights. ISO shall not be held responsible for identifying any or all such patent rights. Details of any patent rights identified during the development of the document will be in the Introduction and/or on the ISO list of patent declarations received (see www.iso.org/patents).

Any trade name used in this document is information given for the convenience of users and does not constitute an endorsement.

For an explanation on the meaning of ISO specific terms and expressions related to conformity assessment, as well as information about ISO's adherence to the World Trade Organization (WTO) principles in the Technical Barriers to Trade (TBT) see the following URL: www.iso.org/iso/foreword.html.

The committee responsible for this document is Technical Committee ISO/TC 44, *Welding and allied processes* Subcommittee SC 3, *Welding consumables*.

This third edition cancels and replaces the second edition (ISO 24598:2012), which has been technically revised.

The main changes compared to the previous edition are as follows:

- to be completed closer to publication

Requests for official interpretations of any aspect of this document should be directed to the Secretariat of ISO/TC 44/SC 3 via your national standards body. A complete listing of these bodies can be found at www.iso.org.

Introduction

This document recognizes that there are two somewhat different approaches in the global market to classifying a given wire electrode, tubular cored electrode or electrode/flux combination, and allows for either or both to be used to suit a particular market need. Application of either type of classification designation (or of both where suitable) identifies a product as classified in accordance with this document. The classification in accordance with system A was mainly based on EN 12070:1999. The classification in accordance with system B is mainly based upon standards used around the Pacific Rim.

This document provides a classification system for solid wire electrodes in terms of their chemical composition, solid wire electrodes and tubular cored electrodes in terms of the chemical composition of the deposit obtained with a particular submerged arc flux and, where required, electrode-flux combinations in terms of the yield strength, tensile strength and elongation of the all-weld metal deposit. The ratio of yield to tensile strength of weld metal is generally higher than that of parent metal. Users should note that matching weld metal yield strength to parent metal yield strength does not necessarily ensure that the weld metal tensile strength matches that of the parent material. Where the application requires matching tensile strength, therefore, selection of the consumable should be made by reference to column 3 of Table 1A or [Table 1B](#), as appropriate.

Although combinations of wire electrodes and fluxes supplied by individual companies can have the same classification, the individual wire electrodes and fluxes from different companies are not interchangeable unless verified in accordance with this document.

It should be noted that the mechanical properties of all-weld metal test pieces used to classify the wire electrodes vary from those obtained in production joints because of differences in welding procedure, such as electrode size, welding position and material composition.

(standards.iteh.ai)

SIST EN ISO 24598:2019

<https://standards.iteh.ai/catalog/standards/sist/7eb67081-1813-4441-ac08-42b15f6ef944/sist-en-iso-24598-2019>

Welding consumables — Solid wire electrodes, tubular cored electrodes and electrode-flux combinations for submerged arc welding of creep-resisting steels — Classification

1 Scope

This document specifies requirements for classification of solid wire electrodes, tubular cored electrodes and electrode/flux combinations (all-weld metal deposits) for submerged arc welding of creep resisting and low-alloy elevated-temperature application steels. One electrode can be tested and classified with different fluxes. The solid wire electrode is also classified separately based on its chemical composition.

This document is a combined specification providing a classification system based on either the chemical composition of the solid wire electrode and all-weld metal deposit, or a system based on the tensile strength of the all-weld metal deposit and the chemical composition of the solid wire electrode and all-weld metal deposit obtained with the electrode/flux combination.

- a) Clauses, subclauses and tables which carry the suffix letter “A” are applicable only to solid wire electrodes, tubular cored electrodes and all-weld metal deposits classified in accordance with the system based upon chemical composition.
- b) Clauses, subclauses and tables which carry the suffix letter “B” are applicable only to solid wire electrodes, tubular cored electrodes and all-weld metal deposits classified in accordance with the system based upon the tensile strength of all-weld metal deposits and the chemical composition of solid wire electrodes and all-weld metal deposits.
- c) Clauses, subclauses and tables which do not have either the suffix letter “A” or the suffix letter “B” are applicable to all solid wire electrodes, tubular cored electrodes and electrode/flux combinations classified under this document.

2 Normative references

The following documents are referred to in the text in such a way that some or all of their content constitutes requirements of this document. For dated references, only the edition cited applies. For undated references, the latest edition of the referenced document (including any amendments) applies.

ISO 544, *Welding consumables — Technical delivery conditions for filler materials and fluxes — Type of product, dimensions, tolerances and markings*

ISO 6847, *Welding consumables — Deposition of a weld metal pad for chemical analysis*

ISO 13916, *Welding — Measurement of preheating temperature, interpass temperature and preheat maintenance temperature*

ISO 14174, *Welding consumables — Fluxes for submerged arc welding and electroslag welding — Classification*

ISO 14344, *Welding consumables — Procurement of filler materials and fluxes*

ISO 15792-1, *Welding consumables — Test methods — Part 1: Test methods for all-weld metal test specimens in steel, nickel and nickel alloys*. Amended by ISO 15792-1:2000/Amd 1:2011

ISO 80000-1:2009, *Quantities and units — Part 1: General*

3 Terms and definitions

No terms and definitions are listed in this document.

ISO and IEC maintain terminological databases for use in standardization at the following addresses:

- ISO Online browsing platform: available at <http://www.iso.org/obp>
- IEC Electropedia: available at <http://www.electropedia.org/>

4 Classification

Classification designations are based upon two approaches to indicate the chemical composition of the solid wire electrode, the chemical composition of the all-weld metal deposit obtained with a solid wire electrode or tubular cored electrode, and the tensile properties and impact properties of the all-weld metal deposits obtained with a given electrode/flux combination. The two designation approaches include additional designators for some other classification requirements, but not all, as is clear from the provisions given in this document. In many cases, a given commercial product can be classified in accordance with both systems. Then either or both classification designations can be used for the product.

A solid wire electrode shall be classified in accordance with its chemical composition as given in Table 3.

An all-weld metal deposit from a solid wire electrode or tubular cored electrode shall be classified in accordance with the all-weld metal deposit composition, as given in Table 4, obtained with a particular flux.

When the solid wire electrode or tubular cored electrode is classified in combination with a flux for submerged arc welding, the classification shall be prefixed with a symbol in accordance with [Clause 4](#) as appropriate.

SIST EN ISO 24598:2019

3A Classification by chemical composition 3B Classification by tensile strength and chemical composition

The classification is divided into three parts:

- 1) the first part gives a symbol indicating the product or process to be identified;
- 2) the second part gives a symbol indicating the chemical composition of the solid wire electrode (see Table 3) and all-weld metal deposit (see Table 4);
- 3) the third part gives a symbol indicating the type of flux used (see [5.5](#)).

The classification is divided into five parts:

- 1) the first part gives a symbol indicating the product or process to be identified;
- 2) the second part gives a symbol indicating the strength and elongation of the all-weld metal deposit in the post-weld heat-treated condition (see [Table 1B](#));
- 3) the third part gives a symbol indicating the impact properties of all-weld metal deposits in the same condition as specified for the tensile strength (see Table 2B);
- 4) the fourth part gives a symbol indicating the type of flux used (see [5.5](#));
- 5) the fifth part gives a symbol indicating the chemical composition of the solid wire electrode, if used (see Table 3), and of the all-weld metal deposited by an electrode/flux combination (see Table 4).

5 Symbols and requirements

5.1 General

A solid wire electrode can be classified separately based upon its chemical composition, as specified in Table 3. The all-weld metal deposit composition and mechanical properties obtained with a particular solid wire electrode or tubular cored electrode vary somewhat depending upon the flux used. Accordingly, the classification of the all-weld metal deposit obtained with a particular solid wire electrode or tubular cored electrode can be different for different fluxes.

5.2 Symbol for the product/process

The symbol for the weld deposit produced by a solid or tubular electrode using the submerged arc welding process with a particular flux, shall be the letter “S” placed at the beginning of the designation.

5.2A Classification by chemical composition

The symbol for the solid wire electrode for use in the submerged arc welding process shall be the letter “S” placed at the beginning of the wire electrode designation.

The symbol for the tubular wire electrode for use in the submerged arc welding process shall be the letter “T” placed at the beginning of the wire electrode designation.

5.2B Classification by tensile strength and chemical composition

The symbol for the solid wire electrode for use in the submerged arc welding process shall be the letters “SU” placed at the beginning of the solid wire electrode designation.

The symbol for the tubular wire electrode for use in the submerged arc welding process shall be the letters “TU” placed at the beginning of the tubular wire electrode designation.

5.3 Symbols for the tensile properties of the all-weld metal deposit

5.3A Classification by chemical composition

No symbol shall be used for the mechanical properties of the all-weld metal deposit. The all-weld metal deposit produced in combination with a particular flux shall fulfil the tensile property requirements specified in Table 1A.

5.3B Classification by tensile strength and chemical composition

The symbols in Table 1B indicate the tensile strength, yield strength and elongation of the all-weld metal deposit in the post-weld heat-treated condition determined in accordance with 5.1, with a particular flux.

5.4 Symbols for impact properties of all-weld metal deposits

5.4A Classification by chemical composition

No symbol shall be used for the impact properties of the all-weld metal deposits. The all-weld metal deposits produced in combination with a particular flux shall fulfil the impact property requirements specified in Table 1A.

5.4B Classification by tensile strength and chemical composition

The symbols in Table 2B indicate the temperature at which an impact energy of 27 J is achieved in the post-weld heat-treated condition under the conditions given in Clause 5. Five test pieces shall be tested. The lowest and highest values obtained shall be disregarded. Two of the three remaining values shall be greater than the specified 27 J level; one of the three may be lower but shall be no less than 20 J. The average of the three remaining values shall be at least 27 J.

When an all-weld metal deposit has been classified for a certain temperature, it automatically covers any higher temperature listed in Table 2B.

Table 1 — A — Mechanical properties of all-weld metal deposits (Classification by chemical composition)

Alloy symbol	Minimum proof strength $R_{p0,2}$ MPa	Minimum tensile strength R_m MPa	Minimum ^a elongation A %	Impact energy at +20 °C J		Heat treatment		
				Minimum average from three test pieces	Minimum single ^b value	Preheat and inter-pass temperature °C	Post-weld heat treatment of test piece	
							Temperature ^c °C	Time ^d min
Mo MnMo	355	510	22	47	38	< 200	—	—
MoV	355	510	18	47	38	200 to 300	690 to 730	60
CrMo1	355	510	20	47	38	150 to 250	660 to 700	60
CrMoV1	435	590	15	24	21	200 to 300	680 to 730	60
CrMo2 CrMo2Mn	400	500	18	47	38	200 to 300	690 to 750	60
CrMo2L	400	500	18	47	38	200 to 300	690 to 750	60
CrMo5	400	590	17	47	38	200 to 300	730 to 760	60
CrMo9	435	590	18	34	27	200 to 300	740 to 780	120
CrMo91	415	585	17	47	38	250 to 350	750 to 760	180
CrMoWV12	550	690	15	34	27	250 to 350 ^e or 400 to 500 ^e	740 to 780	120
Z	Any other agreed mechanical properties							
a	The gauge length is equal to five times the test piece diameter.							
b	Only one single value lower than the minimum average is permitted.							
c	The test piece shall be cooled in the furnace to 300 °C at a rate not exceeding 200 °C/h. The test piece may be removed from the furnace at any temperature below 300 °C and allowed to cool in still air to room temperature.							
d	Tolerance ± 10 min.							
e	Immediately after welding the test piece shall be cooled down to 120 °C to 100 °C and kept at this temperature for at least 1 h.							