



Designation: C1091-03 Designation: C 1091 – 03a (Reapproved 2008)

Standard Test Method for Hydrostatic Infiltration and Exfiltration Testing of Vitrified Clay Pipe Lines¹

This standard is issued under the fixed designation C 1091; the number immediately following the designation indicates the year of original adoption or, in the case of revision, the year of last revision. A number in parentheses indicates the year of last reapproval. A superscript epsilon (ϵ) indicates an editorial change since the last revision or reapproval.

1. Scope

1.1 This test method defines procedures for ~~hydrostatically~~ hydrostatic infiltration testing of new installations of vitrified clay pipe lines, to demonstrate the structural integrity of the installed line. Refer to Practice C 12.

1.2 This test method is suitable for testing gravity-flow pipe lines constructed of vitrified clay pipe or combinations of clay pipe and other pipe materials.

1.3 This test method is applicable to the testing of the pipe lines only. Manholes or other structures should be tested separately.

~~1.4 The values stated in inch-pound units are to be regarded as the standard. The values given in parentheses are provided for information only.~~

~~1.4 The values stated in inch-pound units are to be regarded as standard. The values given in parentheses are mathematical conversions to SI units that are provided for information only and are not considered standard.~~

1.5 *This standard does not purport to address all of the safety problems, if any, associated with its use. It is the responsibility of the user of this standard to establish appropriate safety and health practices and determine the applicability of regulatory limitations prior to use.*

2. Referenced Documents

2.1 *ASTM Standards:*²

C 12 Practice for Installing Vitrified Clay Pipe Lines

C 828 Test Method for Low-Pressure Air Test of Vitrified Clay Pipe Lines

C 896 Terminology Relating to Clay Products

3. Terminology

3.1 Terminology C 896 can be used for clarifications of terminology in this test method.

4. Summary of Test Method

~~4.1 This test method shall be performed on lines after connection laterals, if any, have been plugged and adequately braced to withstand the test pressure, and after the trenches have been backfilled for a sufficient time to generate a significant portion of the ultimate trench load on the pipe line. The time between completion of the backfill operation and hydrostatic testing shall be established by the approving authority.~~

~~4.1 This test method shall be performed on lines after connection laterals, if any, have been plugged and adequately braced to withstand the test pressure, and after the trenches have been backfilled and compacted.~~

5. Significance and Use

5.1 The tests called for herein, for their results, indicate the acceptability of installed vitrified clay pipelines.

6. Preparation of the Line

6.1 To ensure the proper seating of the test plugs and the accuracy of the test, the lines should be cleaned prior to testing.

6.2 Examples of methods for cleaning the lines are the sewer cleaning ball and high pressure flushing equipment.

¹ This test method is under the jurisdiction of ASTM Committee C04 on Vitrified Clay Pipe and is the direct responsibility of Subcommittee C04.20 on Methods of Test and Specifications.

Current edition approved February 10, 2003. Published May 2003. Originally published in 1988. Last previous edition approved in 1999 as C1091-99.

Current edition approved Nov. 1, 2008. Published November 2008. Originally published in 1988. Last previous edition approved in 2003 as C 1091 – 03a.

² Annual Book of ASTM Standards, Vol 04.05.

² For referenced ASTM standards, visit the ASTM website, www.astm.org, or contact ASTM Customer Service at service@astm.org. For Annual Book of ASTM Standards volume information, refer to the standard's Document Summary page on the ASTM website.