

SLOVENSKI STANDARD
oSIST prEN ISO 11961:2017
01-november-2017

Industrija nafte in zemeljskega plina - Jeklene vrtalne cevi (ISO/DIS 11961:2017)

Petroleum and natural gas industries - Steel drill pipe (ISO/DIS 11961:2017)

Erdöl- und Erdgasindustrie - Stahl-Bohrrohre (ISO/DIS 11961:2017)

Industries du pétrole et du gaz naturel - Tiges de forage en acier (ISO/DIS 11961:2017)

Ta slovenski standard je istoveten z: prEN ISO 11961

ICS:

75.180.10	Oprema za raziskovanje, vrtanje in odkopavanje	Exploratory, drilling and extraction equipment
77.140.75	Jeklene cevi in cevni profili za posebne namene	Steel pipes and tubes for specific use

oSIST prEN ISO 11961:2017

en,fr,de

DRAFT INTERNATIONAL STANDARD

ISO/DIS 11961

ISO/TC 67/SC 5

Secretariat: JISC

Voting begins on:
2017-08-29Voting terminates on:
2017-11-20

Petroleum and natural gas industries — Steel drill pipe

Industries du pétrole et du gaz naturel — Tiges de forage en acier

ICS: 77.140.75; 75.180.10

iTeh Standards
(<https://standards.iteh.ai>)
Document Preview

SIST EN ISO 11961:2019<https://standards.iteh.ai/catalog/standards/sist/2a64b851-6c1e-4546-9292-f3b1fcb66bc9/sist-en-iso-11961-2019>

THIS DOCUMENT IS A DRAFT CIRCULATED FOR COMMENT AND APPROVAL. IT IS THEREFORE SUBJECT TO CHANGE AND MAY NOT BE REFERRED TO AS AN INTERNATIONAL STANDARD UNTIL PUBLISHED AS SUCH.

IN ADDITION TO THEIR EVALUATION AS BEING ACCEPTABLE FOR INDUSTRIAL, TECHNOLOGICAL, COMMERCIAL AND USER PURPOSES, DRAFT INTERNATIONAL STANDARDS MAY ON OCCASION HAVE TO BE CONSIDERED IN THE LIGHT OF THEIR POTENTIAL TO BECOME STANDARDS TO WHICH REFERENCE MAY BE MADE IN NATIONAL REGULATIONS.

RECIPIENTS OF THIS DRAFT ARE INVITED TO SUBMIT, WITH THEIR COMMENTS, NOTIFICATION OF ANY RELEVANT PATENT RIGHTS OF WHICH THEY ARE AWARE AND TO PROVIDE SUPPORTING DOCUMENTATION.

This document is circulated as received from the committee secretariat.

ISO/CEN PARALLEL PROCESSING



Reference number
ISO/DIS 11961:2017(E)

© ISO 2017

iTeh Standards
(<https://standards.iteh.ai>)
Document Preview

SIST EN ISO 11961:2019

<https://standards.iteh.ai/catalog/standards/sist/2a64b851-6c1e-4546-9292-f3b1fcb66bc9/sist-en-iso-11961-2019>



COPYRIGHT PROTECTED DOCUMENT

© ISO 2017, Published in Switzerland

All rights reserved. Unless otherwise specified, no part of this publication may be reproduced or utilized otherwise in any form or by any means, electronic or mechanical, including photocopying, or posting on the internet or an intranet, without prior written permission. Permission can be requested from either ISO at the address below or ISO's member body in the country of the requester.

ISO copyright office
Ch. de Blandonnet 8 • CP 401
CH-1214 Vernier, Geneva, Switzerland
Tel. +41 22 749 01 11
Fax +41 22 749 09 47
copyright@iso.org
www.iso.org

Contents

Foreword	v
Introduction.....	vi
1 Scope.....	1
2 Conformance.....	1
2.1 Dual citing of normative references	1
2.2 Units of measurement	2
3 Normative references	2
4 Terms, definitions, symbols and abbreviated terms	4
4.1 Terms and definitions	4
4.2 Symbols and abbreviated terms	8
5 Information to be supplied when placing orders for drill-pipe.....	10
5.1 Grades D95 and F105	10
5.2 General Information	10
5.3 Additional Information	11
6 Requirements for drill-pipe	12
6.1 General.....	12
6.2 Dimensions, masses and connections.....	12
6.3 Material requirements	13
6.4 Process of manufacture for drill-pipe	15
6.5 Traceability.....	17
6.6 Inspection and testing — General	17
6.7 Testing of welds.....	18
6.8 Tensile test.....	18
6.9 Hardness test.....	19
6.10 Charpy V-notch impact test.....	20
6.11 Transverse side-bend test.....	21
6.12 Imperfections and defects in drill-pipe	22
6.13 Visual inspection of the drill-pipe weld zone	22
6.14 Non-destructive examination of the weld zone.....	23
6.15 Marking of drill-pipe	24
6.16 Minimum facility requirements for drill-pipe manufacturers.....	26
6.17 Documentation requirements of drill-pipe	26
7 Requirements for drill-pipe body	27
7.1 Information to be supplied when placing orders for drill-pipe bodies	27
7.2 Dimensional and mass requirements.....	27
7.3 Material requirements	29
7.4 Process of manufacture	30
7.5 Traceability.....	31
7.6 Inspection and testing — General	31
7.7 Testing of chemical composition	32
7.8 Tensile tests	32
7.9 Charpy V-notch impact tests.....	34
7.10 Drill-pipe-body wall thickness	35
7.11 Drill-pipe-body length.....	35
7.12 Internal upset	35
7.13 Internal profile.....	35
7.14 Straightness	36
7.15 Upset alignment.....	36
7.16 Mass determination.....	36

7.17	Imperfections and defects of drill-pipe body	36
7.18	Visual inspection of drill-pipe body	37
7.19	Non-destructive examination	38
7.20	Marking	41
7.21	Minimum facility requirements for drill-pipe-body manufacturer	42
7.22	Documentation requirements	42
8	Requirements for tool joints	43
8.1	Information to be supplied when placing orders for tool joints	43
8.2	Dimensional requirements	44
8.3	Material requirements	44
8.4	Process of manufacture	45
8.5	Traceability	46
8.6	Inspection and testing — General	46
8.7	Testing of chemical composition	47
8.8	Tensile tests	47
8.9	Hardness tests	48
8.10	Charpy V-notch impact tests	49
8.11	Imperfections and defects	50
8.12	Non-destructive examination	51
8.13	Marking	51
8.14	Minimum facility requirements for tool-joint manufacturers	52
8.15	Documentation requirements for tool joints	52
Annex A (normative)	Tables in SI units	54
Annex B (normative)	Figures in SI (USC) units	73
Annex C (normative)	Tables in USC units	87
Annex D (normative)	Purchaser inspection	105
Annex E (informative)	Supplementary requirements	106
Annex F (informative)	Procedures used to convert from USC units to SI units for drill-pipe	109
Annex G (normative)	Product specification levels	113
Bibliography	115

Foreword

ISO (the International Organization for Standardization) is a worldwide federation of national standards bodies (ISO member bodies). The work of preparing International Standards is normally carried out through ISO technical committees. Each member body interested in a subject for which a technical committee has been established has the right to be represented on that committee. International organizations, governmental and non-governmental, in liaison with ISO, also take part in the work. ISO collaborates closely with the International Electrotechnical Commission (IEC) on all matters of electrotechnical standardization.

The procedures used to develop this document and those intended for its further maintenance are described in the ISO/IEC Directives, Part 1. In particular the different approval criteria needed for the different types of ISO documents should be noted. This document was drafted in accordance with the editorial rules of the ISO/IEC Directives, Part 2 (see www.iso.org/directives).

Attention is drawn to the possibility that some of the elements of this document may be the subject of patent rights. ISO shall not be held responsible for identifying any or all such patent rights. Details of any patent rights identified during the development of the document will be in the Introduction and/or on the ISO list of patent declarations received (see www.iso.org/patents).

Any trade name used in this document is information given for the convenience of users and does not constitute an endorsement.

For an explanation on the voluntary nature of standards, the meaning of ISO specific terms and expressions related to conformity assessment, as well as information about ISO's adherence to the World Trade Organization (WTO) principles in the Technical Barriers to Trade (TBT) see the following URL: www.iso.org/iso/foreword.html.

ISO 11961 was prepared by Technical Committee ISO/TC 67, Materials, equipment and offshore structures for petroleum, petrochemical and natural gas industries, Subcommittee SC 5, Casing, tubing and drill pipe.

This third edition cancels and replaces the second edition (ISO 11961:2008), which has been extensively technically revised.

It is the intention of ISO/TC 67 that either this edition or the previous edition of ISO 11961 be applicable, at the option of the purchaser (as defined in 4.1.31), for a period of six months from the first day of the calendar quarter immediately following the date of publication of this edition, after which period the previous edition will no longer be applicable.

Introduction

Users of this International Standard should be aware that further or differing requirements may be needed for individual applications. This International Standard is not intended to inhibit a vendor from offering, or the purchaser from accepting, alternative equipment or engineering solutions for the individual application. This may be particularly applicable where there is innovative or developing technology. Where an alternative is offered, the vendor should identify any variations from this International Standard and provide details.

This International Standard includes provisions of various natures. These are identified by the use of certain verbal forms:

- a) SHALL is used to indicate that a provision is MANDATORY;
- b) SHOULD is used to indicate that a provision is not mandatory, but RECOMMENDED as good practice;
- c) MAY is used to indicate that a provision is OPTIONAL.

iTeh Standards
(<https://standards.iteh.ai>)
Document Preview

SIST EN ISO 11961:2019

<https://standards.iteh.ai/catalog/standards/sist/2a64b851-6c1e-4546-9292-f3b1fcb66bc9/sist-en-iso-11961-2019>

Petroleum and natural gas industries — Steel drill pipe

1 Scope

This International Standard specifies the technical delivery conditions for steel drill-pipes with upset pipe-body ends and weld-on tool joints for use in drilling and production operations in petroleum and natural gas industries for three product specification levels (PSL-1, PSL-2 and PSL-3). The requirements for PSL-1 form the basis of this International Standard. The requirements that define different levels of standard technical requirements for PSL-2 and PSL-3 are in Annex G.

This International Standard covers the following grades of drill-pipe:

grade E drill-pipe;

high-strength grades of drill-pipe, grades X, G and S;

enhanced H₂S resistance drill pipe, grades D and F.

A typical drill-pipe configuration is given, showing main elements and lengths (see Figure B.1). The main dimensions and masses of the grades of drill-pipe are given in both SI units (see Table A.1) and in USC units (see Table C.1).

This International Standard can also be used for drill-pipe with tool joints not specified by ISO or API standards.

By agreement between purchaser and manufacturer, this International Standard can also be applied to other drill-pipe body and/or tool-joint dimensions. This International Standard lists supplementary requirements that can optionally be agreed between purchaser and manufacturer, for testing, performance verification and non-destructive examination (see Annex E).

This International Standard does not consider performance properties, nor performance degradation of the product when in service.

NOTE 1 In this International Standard, drill-pipe is designated by label 1, label 2, grade of material (E, X, G, S, D and F), upset type and type of rotary shouldered connection. Designations are used for the purpose of identification in ordering.

NOTE 2 Reference can be made to ISO 10424-2 or API Spec 7-2 for the detailed requirements for the threading of drill-pipe tool joints.

NOTE 3 Reference can be made to API RP 7G for the performance properties of the drill-pipe.

2 Conformance

2.1 Dual citing of normative references

In the interests of world-wide application of this International Standard, Technical Committee ISO/TC 67 has decided, after detailed technical analysis, that certain of the normative documents listed in Clause 3 and prepared by ISO/TC 67 or another ISO Technical Committee are interchangeable in the context of the relevant requirement with the relevant document prepared by the American Petroleum Institute (API), the American Society for Testing and Materials (ASTM) and the American National Standards Institute (ANSI). These latter documents are cited in the running text following the ISO reference and preceded by “or”, for example “ISO XXXX or API YYYY”. Application of an alternative normative document cited in this manner will lead to technical results different from the use of the preceding ISO reference. However, both results are acceptable and these documents are thus considered interchangeable in practice.

2.2 Units of measurement

In this International Standard, data are expressed in both the International System (SI) of units and the United States Customary (USC) system of units. Separate tables for data expressed in SI units and USC units are in Annex A and Annex C, respectively. Figures are in Annex B and express data in both SI and USC units. For a specific order item, it is intended that only one system of units be used, without combining data expressed in the other system.

Products manufactured to specifications expressed in either of these unit systems shall be considered equivalent and totally interchangeable. Consequently, compliance with the requirements of this International Standard as expressed in one system provides compliance with requirements expressed in the other system.

For data expressed in the SI system, a comma is used as the decimal separator and a space as the thousands separator. For data expressed in the USC system, a dot (on the line) is used as the decimal separator and a space as the thousands separator.

In the text, data in SI units are followed by data in USC units in brackets.

NOTE The procedures used to convert from USC units to SI units are given in informative Annex F.

3 Normative references

The following referenced documents are indispensable for the application of this document. For dated references, only the edition cited applies. For undated references, the latest edition of the referenced document (including any amendment) applies.

ISO 6506-1, *Metallic materials — Brinell Hardness test — Part 1: Test method*

ISO 6507-1, *Metallic materials — Vickers hardness test — Part 1: Test method*

ISO 6508-1, *Metallic materials — Rockwell hardness test — Part 1: Test method (scales A, B, C, D, E, F, G, H, K, N, T)*

ISO 6892, *Metallic materials — Tensile testing*

ISO 7500-1, *Metallic materials — Verification of static uni-axial testing machines — Part 1: Tension/compression testing machines — Verification and calibration of the force-measuring system*

ISO 9303, *Seamless and welded (except submerged arc-welded) steel tubes for pressure purposes — Full peripheral ultrasonic testing for the detection of longitudinal imperfections*

ISO 9304, *Seamless and welded (except submerged arc-welded) steel tubes for pressure purposes — Eddy current testing for the detection of imperfections*

ISO 9305, *Seamless steel tubes for pressure purposes — Full peripheral ultrasonic testing for the detection of transverse imperfections*

ISO 9402, *Seamless and welded (except submerged arc-welded) steel tubes for pressure purposes — Full peripheral magnetic transducer/flux leakage testing of ferromagnetic steel tubes for the detection of longitudinal imperfections*

ISO 9513, *Metallic materials — Calibration of extensometers used in uniaxial testing*

ISO 9598, *Seamless steel tubes for pressure purposes — Full peripheral magnetic transducer/flux leakage testing of ferromagnetic steel tubes for the detection of transverse imperfections*

ISO/TR 9769, *Steel and iron — Review of available methods of analysis*

ISO/TR 10400, *Petroleum and natural gas industries — Equations and calculations for the properties of casing, tubing, drill-pipe and line pipe used as casing or tubing*

ISO 10424-2, *Petroleum and natural gas industries — Rotary drilling equipment — Part 2: Threading and gauging of rotary shouldered thread connections*

ISO 11484, *Steel tubes for pressure purposes — Qualification and certification of non-destructive (NDT) personnel*

ISO 13665, *Seamless and welded steel tubes for pressure purposes — Magnetic particle inspection of the tube body for the detection of surface imperfections*

ISO 15156-2/ANSI/NACE MR0175, *Petroleum and Natural Gas Industries – Materials for use in H₂S-containing environments in Oil and Gas Production – Part 2: Cracking resistant Carbon and Low-Alloy Steels, and the use of Cast Irons*

API Spec 7-2, *Specification for Threading and Gauging of Rotary Shouldered Thread Connections*

API RP 7G, *Recommended Practice for Drill Stem Design and Operating Limits*

API RP13B-1/ISO 10414-1, *Field Testing for Water-Based Drilling Fluids*.

ANSI/API 5C3, *Bulletin on Formulas and Calculations for Casing, Tubing, Drill-pipe, and Line Pipe Properties (including Supplement 1)*

ANSI/NACE TM0177, *Laboratory testing of metals for Resistance to Sulfide Stress Cracking and Stress Corrosion Cracking in H₂S Environments*

ASME *Boiler and Pressure Vessel Code, Section IX*

ASNT SNT-TC-1A, *Recommended Practice, Personnel Qualification and Certification in Non-Destructive Testing*

ASTM A370, *Standard Test Methods and Definitions for Mechanical Testing of Steel Products*

ASTM A751, *Standard Test Methods, Practices and Terminology for Chemical Analysis of Steel Products*

ASTM A941, *Terminology Relating to Steel, Stainless Steel, Related Alloys, and Ferroalloys*

ASTM E4, *Standard Practices for Force Verification of Testing Machines*

ASTM E10, *Standard Test Method for Brinell Hardness of Metallic Materials*

ASTM E18, *Standard Test Methods for Rockwell Hardness of Metallic Materials*

ASTM E23, *Standard Test Methods for Notched Bar Impact Testing of Metallic Materials*

ASTM E83, *Standard Practice for Verification and Classification of Extensometer Systems*

ASTM E92, *Standard Test Method for Vickers Hardness of Metallic Materials*

ASTM E213, *Standard Practice for Ultrasonic Examination of Metal Pipe and Tubing*

ASTM E309, *Standard Practice for Eddy-Current Examination of Steel Tubular Products Using Magnetic Saturation*

ASTM E570, *Standard Practice for Flux Leakage Examination of Ferromagnetic Steel Tubular Products*

ASTM E709, *Standard Guide for Magnetic Particle Testing*

4 Terms, definitions, symbols and abbreviated terms

4.1 Terms and definitions

For the purposes of this document, the terms and definitions in ASTM A941 for heat treatment operations and the following apply.

4.1.1

bevel diameter

outer diameter of the sealing shoulder of a rotary shouldered connection

4.1.2

defect

imperfection of sufficient magnitude to warrant rejection of the product based on criteria defined in this International Standard

[ISO 11960:2004, definition 4.1.11]

4.1.3

drill-pipe

drill-pipe body with weld-on tool joints

4.1.4

drill-pipe body

seamless pipe with upset ends

See Figure B.1.

4.1.5

drill-pipe-body manufacturer

firm, company or corporation that operates facilities for making drill-pipe bodies and is responsible for compliance with the requirements of this International Standard applicable to the drill-pipe body

<https://standards.iteh.ai/catalog/standards/sist/2a64b851-6c1e-4546-9292-f3b1fcb66bc9/sist-en-iso-11961-2019>

See 7.21.

4.1.6

drill-pipe manufacturer

firm, company or corporation responsible for compliance with all the applicable requirements of this International Standard

See 6.16.

4.1.7

drill-pipe torsion-strength ratio

torsion strength of the tool-joint connection divided by the drill-pipe-body torsion strength

4.1.8

drill-pipe weld neck

machined part of the drill-pipe comprising the tool-joint weld neck, the weld and the drill-pipe-body upset

See Figure B.1.

iTeh Standards
(<https://standards.iteh.ai>)
Document Preview

4.1.9**elephant hide**

wrinkled outside diameter surfaces of the drill-pipe body caused by the upsetting process

4.1.10**enhanced H₂S resistance**

classification of drill pipe that includes Sulfide Stress Cracking testing as part of its qualification and quality control

4.1.11**essential variable**

variable parameter in which a change affects the mechanical properties of the weld joint

4.1.12**gouge**

elongated groove or cavity caused by mechanical removal of metal

4.1.13**hard banding**

application of material onto tool joints to reduce external wear of the tool joint

NOTE Also known as hard facing.

4.1.14**hardness number**

result from a single hardness impression

4.1.15**heat****heat of steel**

metal produced by a single cycle of a batch-melting process

4.1.16**heat analysis**

chemical analysis representative of a heat as reported by the metal producer

[ISO 11960:2004, definition 4.1.15]

4.1.17**imperfection**

discontinuity in the product wall or on the product surface that can be detected by an NDE method included in this International Standard

[ISO 11960:2004, definition 4.1.16]

4.1.18**indication**

evidence of a discontinuity that requires interpretation to determine its significance

4.1.19**inspection**

process of measuring, examining, testing, gauging or otherwise comparing the product with the applicable requirements

4.1.20**label 1**

dimensionless designation for the drill-pipe-body size that may be used when ordering

4.1.21**label 2**

dimensionless designation for the drill-pipe-body mass per unit length that may be used when ordering

4.1.22**linear imperfection**

imperfection that includes, but is not limited to, seams, laps, cracks, plug scores, cuts, gouges and elephant hide

NOTE See API 5T1.

[ISO 11960:2004, definition 4.1.25]

4.1.23**lot**

definite quantity of product manufactured under conditions that are considered uniform for the attribute being inspected

4.1.24**lot size**

number of units in a lot

4.1.25**manufacturer**

one or more of the following, depending on the context: the maker of drill-pipe, the maker of drill-pipe body or the maker of tool joints

4.1.26**mean hardness number**

result of averaging the hardness numbers for the single specimen or location being evaluated

4.1.27**non-essential variable**

variable parameter in which a change may be made in the WPS without re-qualification

4.1.28**non-linear imperfection**

imperfection that includes, but is not limited to, pits

See API Std 5T1.

4.1.29**pipe body**

seamless pipe excluding upset and upset-affected areas

See Figure B.1.

4.1.30**procedure qualification record****PQR**

written documentation stating an assessment that a specific WPS produces welds in accordance with the requirements of this International Standard.

4.1.31**product**

drill-pipe, drill-pipe body or tool joint