



# SLOVENSKI STANDARD

## oSIST prEN ISO 10271:2019

01-julij-2019

---

**Zobozdravstvo - Preskusne metode ugotavljanja korozije za kovinske materiale  
(ISO/DIS 10271:2019)**

Dentistry - Corrosion test methods for metallic materials (ISO/DIS 10271:2019)

Zahnheilkunde - Korrosionsprüfverfahren für metallische Werkstoffe (ISO/DIS  
10271:2019)

Médecine bucco-dentaire - Méthodes d'essai de corrosion des matériaux métalliques  
(ISO/DIS 10271:2019)

[SIST EN ISO 10271:2020](https://standards.iteh.ai/catalog/standards/sist/956cbf2c-b5c9-4c1c-8373-10271-2019/sist-956cbf2c-b5c9-4c1c-8373-10271-2019)

<https://standards.iteh.ai/catalog/standards/sist/956cbf2c-b5c9-4c1c-8373-10271-2019/sist-956cbf2c-b5c9-4c1c-8373-10271-2019>

**Ta slovenski standard je istoveten z: prEN ISO 10271**

---

**ICS:**

11.060.10      Zobotehnični materiali      Dental materials

**oSIST prEN ISO 10271:2019**

**en**



# DRAFT INTERNATIONAL STANDARD

## ISO/DIS 10271

ISO/TC 106/SC 2

Secretariat: ANSI

Voting begins on:  
2019-04-24Voting terminates on:  
2019-07-17

## Dentistry — Corrosion test methods for metallic materials

*Médecine bucco-dentaire — Méthodes d'essai de corrosion des matériaux métalliques*

ICS: 11.060.10

iTeh STANDARD PREVIEW  
(standards.iteh.ai)

SIST EN ISO 10271:2020

<https://standards.iteh.ai/catalog/standards/sist/956cbf2c-b5c9-4c1c-8373-7040a86b5662/sist-en-iso-10271-2020>

THIS DOCUMENT IS A DRAFT CIRCULATED FOR COMMENT AND APPROVAL. IT IS THEREFORE SUBJECT TO CHANGE AND MAY NOT BE REFERRED TO AS AN INTERNATIONAL STANDARD UNTIL PUBLISHED AS SUCH.

IN ADDITION TO THEIR EVALUATION AS BEING ACCEPTABLE FOR INDUSTRIAL, TECHNOLOGICAL, COMMERCIAL AND USER PURPOSES, DRAFT INTERNATIONAL STANDARDS MAY ON OCCASION HAVE TO BE CONSIDERED IN THE LIGHT OF THEIR POTENTIAL TO BECOME STANDARDS TO WHICH REFERENCE MAY BE MADE IN NATIONAL REGULATIONS.

RECIPIENTS OF THIS DRAFT ARE INVITED TO SUBMIT, WITH THEIR COMMENTS, NOTIFICATION OF ANY RELEVANT PATENT RIGHTS OF WHICH THEY ARE AWARE AND TO PROVIDE SUPPORTING DOCUMENTATION.

This document is circulated as received from the committee secretariat.

**ISO/CEN PARALLEL PROCESSING**



Reference number  
ISO/DIS 10271:2019(E)

© ISO 2019

# iTeh STANDARD PREVIEW (standards.iteh.ai)

SIST EN ISO 10271:2020

<https://standards.iteh.ai/catalog/standards/sist/956cbf2c-b5c9-4c1c-8373-7040a86b5662/sist-en-iso-10271-2020>



## **COPYRIGHT PROTECTED DOCUMENT**

© ISO 2019

All rights reserved. Unless otherwise specified, or required in the context of its implementation, no part of this publication may be reproduced or utilized otherwise in any form or by any means, electronic or mechanical, including photocopying, or posting on the internet or an intranet, without prior written permission. Permission can be requested from either ISO at the address below or ISO's member body in the country of the requester.

ISO copyright office  
CP 401 • Ch. de Blandonnet 8  
CH-1214 Vernier, Geneva  
Phone: +41 22 749 01 11  
Fax: +41 22 749 09 47  
Email: [copyright@iso.org](mailto:copyright@iso.org)  
Website: [www.iso.org](http://www.iso.org)

Published in Switzerland

# Contents

Page

<b>Foreword</b>	<b>v</b>
<b>Introduction</b>	<b>vi</b>
<b>1 Scope</b>	<b>1</b>
<b>2 Normative references</b>	<b>1</b>
<b>3 Terms and definitions</b>	<b>1</b>
<b>4 Test methods</b>	<b>3</b>
4.1 Static immersion test	3
4.1.1 Information required	3
4.1.2 Application	3
4.1.3 Reagents	3
4.1.4 Apparatus	3
4.1.5 Solution preparation	4
4.1.6 Samples	4
4.1.7 Test procedure	5
4.1.8 Elemental analysis	6
4.1.9 Test report	6
4.2 Electrochemical test	6
4.2.1 Information required	6
4.2.2 Application	6
4.2.3 Reagents	6
4.2.4 Apparatus	7
4.2.5 Solution preparation	7
4.2.6 Samples	7
4.2.7 Test procedure	9
4.2.8 Test report	12
4.3 Sulfide tarnish test (cyclic immersion)	13
4.3.1 Information required	13
4.3.2 Application	13
4.3.3 Reagents	13
4.3.4 Apparatus	13
4.3.5 Solution preparation	14
4.3.6 Samples	14
4.3.7 Test procedure	14
4.3.8 Inspection	15
4.3.9 Test report	15
4.4 Sulfide tarnish test (static immersion)	15
4.4.1 Information required	15
4.4.2 Application	15
4.4.3 Reagents	15
4.4.4 Apparatus	15
4.4.5 Solution preparation	15
4.4.6 Samples	16
4.4.7 Test procedure	16
4.4.8 Inspection	17
4.4.9 Test report	17
4.5 Static immersion test with periodic analysis	17
4.5.1 Information required	17
4.5.2 Application	17
4.5.3 Reagents	18
4.5.4 Apparatus	18
4.5.5 Solution preparation	18
4.5.6 Samples	18
4.5.7 Test procedure	20

**ISO/DIS 10271:2019(E)**

	4.5.8	Elemental analysis.....	21
	4.5.9	Test report.....	21
4.6		Dental Amalgam.....	21
4.7		Crevice Corrosion.....	21
	4.7.1	Principle.....	21
	4.7.2	Application.....	22
	4.7.3	Test medium.....	22
	4.7.4	Materials.....	22
	4.7.5	Apparatus.....	22
	4.7.6	Test piece.....	22
	4.7.7	Procedure.....	23
	4.7.8	Inspection.....	23
	4.7.9	Test report.....	23
<b>Annex A (informative) Corrosion test method development.....</b>			<b>25</b>
<b>Bibliography.....</b>			<b>31</b>

**iTeh STANDARD PREVIEW**  
**(standards.iteh.ai)**

SIST EN ISO 10271:2020

<https://standards.iteh.ai/catalog/standards/sist/956cbf2c-b5c9-4c1c-8373-7040a86b5662/sist-en-iso-10271-2020>

## Foreword

ISO (the International Organization for Standardization) is a worldwide federation of national standards bodies (ISO member bodies). The work of preparing International Standards is normally carried out through ISO technical committees. Each member body interested in a subject for which a technical committee has been established has the right to be represented on that committee. International organizations, governmental and non-governmental, in liaison with ISO, also take part in the work. ISO collaborates closely with the International Electrotechnical Commission (IEC) on all matters of electrotechnical standardization.

International Standards are drafted in accordance with the rules given in the ISO/IEC Directives, Part 2.

The main task of technical committees is to prepare International Standards. Draft International Standards adopted by the technical committees are circulated to the member bodies for voting. Publication as an International Standard requires approval by at least 75 % of the member bodies casting a vote.

Attention is drawn to the possibility that some of the elements of this document may be the subject of patent rights. ISO shall not be held responsible for identifying any or all such patent rights.

ISO 10271 was prepared by Technical Committee ISO/TC 106, *Dentistry*, Subcommittee SC 2, *Prosthodontic materials*.

This third edition cancels and replaces the second edition (ISO 10271:2011), which has been technically revised, in particular by removing the statement in the Scope about the standard not being applicable to “appliances for orthodontics” and adding a NOTE to the static immersion test method acknowledging that “measuring the total surface area of orthodontic appliances can be difficult” and “this test method may be referenced by other standards with appropriate modifications”. Also, since sodium sulfide hydrate (approximately 35% Na<sub>2</sub>S) analytical grade is not available in every country, a NOTE was added to the appropriate test methods indicating that sodium sulphide nonahydrate (Na<sub>2</sub>S·9H<sub>2</sub>O), ≤98% may be used. Furthermore, this third edition of ISO 10271 was harmonized with ISO 22674:2016 by making changes in the Preparation sections of the various test methods that reflect changes that were made for the preparation of metals supplied for metal-ceramic restorations in ISO 22674:2016.

## Introduction

This document was developed from the original Technical Report (ISO/TR 10271) as a result of worldwide demand for standard test methods to determine the acceptability of metallic materials for oral restorations in relation to corrosion.

Specific qualitative and quantitative requirements for freedom from biological hazard are not included in this document, but it is recommended that reference be made to ISO 10993-1 and ISO 7405 for assessing possible biological or toxicological hazards.

The testing of the corrosion behaviour of metallic materials in dentistry is complicated by the diversity of the materials themselves, their applications and the environment to which they are exposed. Variation occurs between devices and within the same device during the exposure time. The type of corrosion behaviour or effect can also vary with exposure time. Accordingly, it is not possible to specify a single test capable of covering all situations, nor is it a practical proposition to define a test for each situation. This document, therefore, gives detailed procedures for test methods that have been found to be of merit as evidenced by considerable use.

In the second edition, two new test methods were added. To supplement the existing static immersion test, a static immersion test with periodic analysis was added. A major reason for the addition of this test is that the rate of corrosion of most dental metallic materials varies over time. Thus, the aim of this supplementary test is to provide information on this variation in the corrosion of a dental metallic material. A classification scheme to interpret the rate of corrosion of a tested material with time (i.e. steady, decreasing, increasing) was not included as part of the static immersion test with periodic analysis. It is intended to monitor the use of the test through appropriate working groups of ISO/TC 106 to ascertain whether a classification scheme is needed in a future revision of this document. In this third edition, a classification scheme is still not included.

To supplement the sulfide tarnish test (cyclic immersion), a sulfide tarnish test (static immersion) was also added to the second edition of ISO 10271. This test has been used successfully for many years to evaluate the corrosion of silver alloys.

In addition, the second addition added an informative annex ([Annex A](#)) that sets out a procedure for each element of the test system such that a consistent approach can be taken for the development of further test methods. Equally, it is recognized that any element can represent only the current recommendation, but changes in the future are unlikely to change the framework.

The third edition differs from the second by the removal of the statement in the Scope about the standard not being applicable to “appliances for orthodontics”. With this change in mind, a NOTE was added to the static immersion test acknowledging that “measuring the total surface area of orthodontic appliances can be difficult” and “this test method may be referenced by other standards with appropriate modifications”.

Besides updating the Normative References and Terms and definitions according to the newest version of the ISO Directives, the third edition of ISO 10271 was harmonized with ISO 22674:2016 by adding to the Preparation sections of the various test methods the following change concerning metals supplied for metal-ceramic restorations:

“Simulate the oxidation procedure and four ceramic firings at the highest temperature allowed for the ceramics recommended for fusing to the metallic material in accordance with the manufacturer’s instructions. Remove and place the specimens on a ceramic plate (which is at room temperature) to cool to room temperature after the oxidation and ceramic firing simulation.”

Additionally, since sodium sulfide hydrate (approximately 35% Na<sub>2</sub>S) analytical grade is not available in every country, this third edition includes a NOTE, which was added to the appropriate test methods, indicating that sodium sulphide nonahydrate (Na<sub>2</sub>S·9H<sub>2</sub>O), ≤98% may be used.

It is not the purpose of this document to propose corrosion test methods for specific applications or to set limits as precise as those that may be required in a standard relating to a type of product and its application.



# Dentistry — Corrosion test methods for metallic materials

## 1 Scope

This document provides test methods and procedures to determine the corrosion behaviour of metallic materials used in the oral cavity. It is intended that these test methods and procedures be referred to in individual International Standards specifying such metallic materials.

This document is not applicable to instruments and dental amalgam (see ISO TS 17988).

## 2 Normative references

The following documents are referred to in the text in such a way that some or all of their content constitutes requirements of this document. For dated references, only the edition cited applies. For undated references, the latest edition of the referenced document (including any amendments) applies.

ISO 1042, *Laboratory glassware — One-mark volumetric flasks*

ISO 1942, *Dentistry — Vocabulary*

ISO 3585, *Borosilicate glass 3.3 — Properties*

ISO 3696, *Water for analytical laboratory use — Specification and test methods*

ISO 6344-1, *Coated abrasives — Grain size analysis — Part 1: Grain size distribution test*

ISO 7183, *Compressed-air dryers — Specifications and testing*

ISO/TS 17988, *Dentistry — Corrosion test methods for dental amalgam*

## 3 Terms and definitions

For the purposes of this document, the terms and definitions given in ISO 1942 and the following apply.

ISO and IEC maintain terminological databases for use in standardization at the following addresses:

ISO Online browsing platform: available at <https://www.iso.org/obp/ui>

IEC Electropedia: available at [www.electropedia.org](http://www.electropedia.org)

### 3.1

#### breakdown potential

$E_p$

least noble potential at which pitting or crevice corrosion, or both, initiates and propagates

### 3.2

#### corrosion

physicochemical interaction between a metallic material and its environment that results in a partial or total destruction of the material or in a change of its properties

### 3.3

#### corrosion potential

$E_{corr}$

open-circuit potential measured under either service conditions, or laboratory conditions that closely approximate service conditions

## ISO/DIS 10271:2019(E)

**3.4****corrosion product**

substance formed as a result of corrosion

**3.5****crevice corrosion**

corrosion associated with and taking place in or near a narrow aperture or crevice

**3.6****current density**

value of electric current per unit surface area flowing through a conductor

**3.7****dynamic immersion test**

test in which the specimen is exposed to a corrosive solution under conditions of relative motion between specimen and solution

**3.8****electrode potential**

potential difference between the specimen and a reference electrode

**3.9****electrolyte**

solution or liquid that conducts an electrical current by means of ions

**3.10****open-circuit potential**

$E_{ocp}$   
potential of an electrode measured with respect to a reference electrode or another electrode when no current flows

**3.11****pitting corrosion**

localized corrosion which results in pits

**3.12****potentiodynamic test**

test in which the electrode potential is varied at a predetermined rate and the relationship between current density and electrode potential is recorded

**3.13****potentiostatic test**

test in which the electrode potential is maintained constant

**3.14****sample**

totality of material for one type being tested, the group of all such specimens

**3.15****set**

subgroup of the specimens of a sample

**3.16****specimen****test piece**

individual single example of an object for testing

**3.17****static immersion test**

test in which the specimen is exposed to a corrosive solution under conditions of effectively no relative motion between specimen and solution

**3.18****stress corrosion**

corrosion resulting from the combined action of static tensile stress and an electrolyte

**3.19****synthetic saliva**

test medium that approximates the relevant chemistry of natural saliva

**3.20****tarnish**

surface discoloration due to the chemical reaction between a metallic material and its environment

**3.21****zero-current potential**

potential at which cathodic and anodic currents are equal

**4 Test methods****4.1 Static immersion test****4.1.1 Information required**

Composition, including hazardous elements, in accordance with the appropriate ISO standard, shall be provided.

**4.1.2 Application**

This is an accelerated test that is intended to provide quantitative data on the metal ions released from metallic materials under in vitro conditions relevant to those expected in the oral cavity.

**4.1.3 Reagents**

**4.1.3.1 Lactic acid** (2-hydroxypropanoic acid,  $C_3H_6O_3$ ), 90 %, analytical grade.

**4.1.3.2 Sodium chloride** (NaCl), analytical grade.

**4.1.3.3 Water**, complying with grade 2 of ISO 3696.

**4.1.3.4 Ethanol** or **methanol** ( $C_2H_5OH$  or  $CH_3OH$ ), analytical grade.

**4.1.3.5 Compressed air**, oil- and water-free, complying with ISO 7183.

**4.1.4 Apparatus**

**4.1.4.1 Containers**, of borosilicate glass, complying with ISO 3585 and with dimensions of approximately 16 mm inner diameter by 160 mm in height.

**4.1.4.2 pH meter**, calibrated, with a sensitivity of at least  $\pm 0,05$  pH.

**4.1.4.3 Chemical analysis instrumentation**, capable of measuring ion concentration in  $\mu\text{g/mL}$  (e.g. inductively-coupled plasma atomic emission spectroscopy (ICP-AES), alias inductively-coupled plasma optical emission spectrometry (ICP-OES), or atomic absorption spectroscopy (AAS)).

**4.1.4.4 Micrometer screw gauge**, accurate and reading to 0,01 mm.

## ISO/DIS 10271:2019(E)

**4.1.4.5 Silicon carbide paper**, complying with ISO 6344-1.

**4.1.4.6 Volumetric flasks**, of borosilicate glass, 1 000 mL, class A, complying with ISO 1042.

#### 4.1.5 Solution preparation

Prepare an aqueous solution comprising 0,1 mol/L lactic acid and 0,1 mol/L sodium chloride within 2 hours of use. For example, dissolve  $(10,0 \pm 0,1)$  g 90 %  $C_3H_6O_3$  (4.1.3.1) and  $(5,850 \pm 0,005)$  g NaCl (4.1.3.2) in approximately 300 mL of water (4.1.3.3). Transfer into a 1 000 mL volumetric flask (4.1.4.6) and fill to mark. The pH shall be  $2,3 \pm 0,1$ . If it is not, the solution shall be discarded and the reagents checked.

#### 4.1.6 Samples

##### 4.1.6.1 Fabrication

###### 4.1.6.1.1 Cast

Specimens shall be cast in accordance with the manufacturer's recommendations.

###### 4.1.6.1.2 Prefabricated

Prefabricated parts or devices shall be used in the as-received condition.

###### 4.1.6.1.3 Other

Specimens prepared by other methods, e.g. machined, sintered, eroded, etc., shall be tested in the as-manufactured condition after suitable cleaning.

###### 4.1.6.2 Sampling

The number of specimens shall be sufficient to provide at least two parallel sets (the number of specimens in a set may vary).

###### 4.1.6.3 Sample surface area

The total surface area of the sample shall be at least 10 cm<sup>2</sup> after preparation.

**NOTE** In this latest revision of this document, the Scope has been changed to eliminate the exclusion of appliances for orthodontics. However, it is recognized that measuring the total surface area of orthodontic appliances can be difficult. Therefore, this note acknowledges that this test method may be referenced by other standards with appropriate modifications. As an example, it is acceptable for the ion release for each element of a set of orthodontic brackets to be reported in terms of  $\mu\text{g}/7\text{d}$  for a specified number of orthodontic brackets, as required in the appropriate orthodontic brackets standard.

##### 4.1.6.4 Preparation

###### 4.1.6.4.1 Cast samples

Remove any sprues, runners or other projections from the surface. Blast all surfaces with 125  $\mu\text{m}$  pure alumina to remove investment.

**NOTE** Removal should be done cold (i.e., under running water) to prevent transformations.

If recommended, heat-treat according to the manufacturer's instructions.

In the case of metals supplied for metal-ceramic restorations, test after the following simulated ceramic-firing schedule has been applied: