

INTERNATIONAL ORGANIZATION FOR STANDARDIZATION •МЕЖДУНАРОДНАЯ ОРГАНИЗАЦИЯ ПО СТАНДАРТИЗАЦИИ • ORGANISATION INTERNATIONALE DE NORMALISATION

# Information processing – Unrecorded magnetic tapes for interchange instrumentation applications – General dimensional requirements

## iTeh STANDARD PREVIEW (standards.iteh.ai)

First edition - 1973-12-01

<u>ISO 1859:1973</u> https://standards.iteh.ai/catalog/standards/sist/18fbd421-1f06-43a3-b93fa327ec05c21b/iso-1859-1973

#### FOREWORD

ISO (the International Organization for Standardization) is a worldwide federation of national standards institutes (ISO Member Bodies). The work of developing International Standards is carried out through ISO Technical Committees. Every Member Body interested in a subject for which a Technical Committee has been set up has the right to be represented on that Committee. International organizations, governmental and non-governmental, in liaison with ISO, also take part in the work.

Draft International Standards adopted by the Technical Committees are circulated to the Member Bodies for approval before their acceptance as International Standards by the ISO Council.

Prior to 1972, the results of the work of the Technical Committees were published. VIEW as ISO Recommendations; these documents are now in the process of being transformed into International Standards. As part of this process, Technical Committee ISO/TC 97, *Computers and information processing*, has reviewed ISO Recommendation R 1859-1971 and found it technically suitable for transformation. International Standard ISO 1859 therefore replaces ISO Recommendation R 1859-1971, which was approved by the Member Bodies of the following countries :

Australia
Belgium
Czechoslovakia
France
Greece
Italy

Japan New Zealand Portugal Romania South Africa, Rep. of Spain Sweden Switzerland Thailand United Kingdom U.S.A. U.S.S.R.

The Member Body of the following country expressed disapproval of the Recommendation on technical grounds :

Germany\*

\* Subsequently, this Member Body approved the Recommendation.

International Organization for Standardization, 1973 •

Printed in Switzerland

## Information processing – Unrecorded magnetic tapes for interchange instrumentation applications - General dimensional requirements

## iTeh STANDARD PREVIEW

1 SCOPE AND FIELD OF APPLICATION 4.2 The tape shall be wound with the magnetic coated This International Standard specifies the materials, the tape):1973

wind, and the dimensions, //ofanmagnetic atape loused ndrds/sist/18fbd421-1f06-43a3-b93finterchange instrumentation applications. a327ec05c21b/iso-1859-1973

NOTE - Physical properties and test methods are specified in ISO 2690.

#### 2 REFERENCES

ISO/R 1858, General purpose hubs and reels, with 76 mm (3 in) centrehole, for magnetic tape used in interchange instrumentation applications.

ISO/R 1860, Precision reels for magnetic tape used in interchange instrumentation application.

ISO 2690, Unrecorded magnetic tapes for instrumentation applications - Physical properties and test methods.

#### **3 MATERIALS**

The tape shall consist of a suitable, continuous and splice-free base material coated on one side with a durable, yet flexible layer of ferromagnetic material.

#### 4 TAPE WIND

4.1 The tape shall be wound on hubs or reels complying with the specifications for precision reels or general purpose hubs and reels stated in ISO/R 1860 and ISO/R 1858.

NOTE - Smaller reels with 8 mm (5/16 in) centreholes are under consideration.

### **5 DIMENSIONS**

#### 5.1 Standard widths

The standard widths shall be as listed in table 1.

#### 5.2 Thickness

Maximum total thickness is controlled by standard reel dimensions, length and E value.

NOTE - The maximum total thickness of the base plus the coating shall not exceed 0,055 mm (0.002 2 in). The nominal base thickness is given in table 2.

#### 5.3 Length

Tape shall be supplied in the minimum lengths given in table 2.

#### 5.4 E value

The minimum E value shall be 2,5 mm (0.10 in). (The E value is the radial distance by which the reel flanges extend beyond the outermost layer of the tape.)

Standard widths									
mm	in								
<b>6,25</b> ± 0,05	0.246 ± 0.002								
0 12,70 0 0,10	0.500 _ 0 _ 0.004								
* <b>19,05</b> _ 0 _ 0,10	*0.750 _ 0 _ 0.004								
<b>25,40</b> 0,10	0 1.000 _ 0.004								
<b>50,80</b> _ 0,10	$2.000 \stackrel{0}{-0.004}$								

TABLE 1

 $^{\ast}$  Although shown in this table, this dimension is not a preferred width.

## Teh STANDARD PREVIEW

	minal Dase		Tape lengths by reel diameters														
			203 mm (8 in) reel		266 mm (10.5 in) reel			<b>356</b> mm (14 in) reel			381 mm (15 in) recl			406 mm (16 in) reel			
thic	ckness	Coating thickness		1		Nominal a <b>lehgths</b> tit			Nominal stlengthets/	27Mini strt/€8		Nominal Jength*	1	imum length	Nominal length*		imum length
mm	in		m	m	ft	m	a32 m	ft	c21b/iso- m	1859- m	973 ft	m	m	ft	m	m	ft
0,038	0.001 5	normal	365	366	1 200	760	762	2 500	1 520	1 524	5 000		-	_	-		-
0,025	0.001 0	normal	-	-		1 100	1 097	3 600	2 200	2 195	7 200	_	-	-	-	-	-
0,025	0.001 0	fine	-	-	-	1 400	1 402	4 600	2 800	2 804	9 200	3 300	3 292	10 800	3 800	3 780	12 400

\* These nominal lengths are metric conversions, rounded for convenience of description, of original values in feet.

NOTE - Tape lengths for smaller reels with 8 mm (5/16 in) centreholes are under consideration.