



SLOVENSKI STANDARD

SIST EN 12846-2:2023

01-april-2023

Nadomešča:
SIST EN 12846-2:2011

Bitumen in bitumenska veziva - Določanje viskoznosti z iztočnim viskozimetrom - 2. del: Rezana in fluksirana bitumenska veziva

Bitumen and bituminous binders - Determination of efflux time by the efflux viscometer -
Part 2: Cut-back and fluxed bituminous binders

Bitumen und bitumenhaltige Bindemittel - Bestimmung der Ausflusszeit mittels
Ausflussviskosimeter - Teil 2: Verschnittene und gefluxte bitumenhaltige Bindemittel

Bitumes et liants bitumineux - Détermination du temps d'écoulement à l'aide d'un
viscosimètre à écoulement - Partie 2 : Bitumes fluidifiés et fluxés

Ta slovenski standard je istoveten z: EN 12846-2:2022

ICS:

75.140	Voski, bitumni in drugi naftni proizvodi	Waxes, bituminous materials and other petroleum products
91.100.50	Veziva. Tesnilni materiali	Binders. Sealing materials

SIST EN 12846-2:2023 **en,fr,de**

EUROPEAN STANDARD

EN 12846-2

NORME EUROPÉENNE

EUROPÄISCHE NORM

December 2022

ICS 91.100.50

Supersedes EN 12846-2:2011

English Version

Bitumen and bituminous binders - Determination of efflux time by the efflux viscometer - Part 2: Cut-back and fluxed bituminous binders

Bitumes et liants bitumineux - Détermination du temps d'écoulement à l'aide d'un viscosimètre à écoulement -
Partie 2 : Bitumes fluidifiés et fluxés

Bitumen und bitumenhaltige Bindemittel -
Bestimmung der Ausflusszeit mittels
Ausflussviskosimeter - Teil 2: Verschnittene und
gefluxte bitumenhaltige Bindemittel

This European Standard was approved by CEN on 21 November 2022.

CEN members are bound to comply with the CEN/CENELEC Internal Regulations which stipulate the conditions for giving this European Standard the status of a national standard without any alteration. Up-to-date lists and bibliographical references concerning such national standards may be obtained on application to the CEN-CENELEC Management Centre or to any CEN member.

This European Standard exists in three official versions (English, French, German). A version in any other language made by translation under the responsibility of a CEN member into its own language and notified to the CEN-CENELEC Management Centre has the same status as the official versions.

CEN members are the national standards bodies of Austria, Belgium, Bulgaria, Croatia, Cyprus, Czech Republic, Denmark, Estonia, Finland, France, Germany, Greece, Hungary, Iceland, Ireland, Italy, Latvia, Lithuania, Luxembourg, Malta, Netherlands, Norway, Poland, Portugal, Republic of North Macedonia, Romania, Serbia, Slovakia, Slovenia, Spain, Sweden, Switzerland, Türkiye and United Kingdom.



EUROPEAN COMMITTEE FOR STANDARDIZATION
COMITÉ EUROPÉEN DE NORMALISATION
EUROPÄISCHES KOMITEE FÜR NORMUNG

CEN-CENELEC Management Centre: Rue de la Science 23, B-1040 Brussels

Contents	Page
European foreword.....	3
1 Scope.....	4
2 Normative references.....	4
3 Terms and definitions	4
4 Principle	5
5 Reagents and materials.....	5
6 Apparatus.....	5
7 Sampling.....	6
8 Procedure.....	6
8.1 General.....	6
8.2 Preparation of apparatus.....	6
8.3 Measurement.....	7
9 Expression of results.....	8
10 Precision.....	8
10.1 Repeatability.....	8
10.2 Reproducibility.....	8
11 Test report.....	9
Bibliography.....	13

iTeH STANDARD PREVIEW
(standards.iteh.ai)

SIST EN 12846-2:2023

<https://standards.iteh.ai/catalog/standards/sist/1ca90106-a51e-4c4a-8cd6-011a017ccc5c/sist-en-12846-2-2023>

European foreword

This document (EN 12846-2:2022) has been prepared by Technical Committee CEN/TC 336 “Bituminous binders”, the secretariat of which is held by AFNOR.

This European Standard shall be given the status of a national standard, either by publication of an identical text or by endorsement, at the latest by June 2023, and conflicting national standards shall be withdrawn at the latest by June 2023.

Attention is drawn to the possibility that some of the elements of this document may be the subject of patent rights. CEN shall not be held responsible for identifying any or all such patent rights.

This document supersedes EN 12846-2:2011.

EN 12846-2:2022 includes the following significant technical changes with respect to EN 12846-2:2011:

- possibility to use a vegetal oil, requirement on density replaces requirement on viscosity (Clause 5);
- Figures 1 and 2 have been modified to be in line with the evolution of test equipment (6.1 and 6.2);
- possibility to use alternative working apparatus that meet the requirements of this document, such as an integrated block viscometer (6.1);
- mercury stem thermometers are no longer specified as reference thermometers (6.4) and Annex A has been removed;
- more accurate description of measurement procedure (8.3).

The EN 12846 series consists of the following parts under the general title *Bitumen and bituminous binders — Determination of efflux time by the efflux viscometer*:

- *Part 1: Bituminous emulsions*;
- *Part 2: Cut-back and fluxed bituminous binders*.

Any feedback and questions on this document should be directed to the users' national standards body. A complete listing of these bodies can be found on the CEN website.

According to the CEN-CENELEC Internal Regulations, the national standards organisations of the following countries are bound to implement this European Standard: Austria, Belgium, Bulgaria, Croatia, Cyprus, Czech Republic, Denmark, Estonia, Finland, France, Germany, Greece, Hungary, Iceland, Ireland, Italy, Latvia, Lithuania, Luxembourg, Malta, Netherlands, Norway, Poland, Portugal, Republic of North Macedonia, Romania, Serbia, Slovakia, Slovenia, Spain, Sweden, Switzerland, Türkiye and the United Kingdom.

EN 12846-2:2022 (E)

1 Scope

This document specifies a method for the determination of the efflux time at 25 °C of petroleum cut-back and fluxed bituminous binders in seconds using an efflux viscometer. Alternative test temperatures are 40 °C, 50 °C and 60 °C.

WARNING — The use of this document involves hazardous materials, operations and equipment. This document does not purport to address all of the safety problems associated with its use. It is the responsibility of the user of this document to establish appropriate safety and health practices and to determine the applicability of regulatory limitations prior to use.

2 Normative references

The following documents are referred to in the text in such a way that some or all of their content constitutes requirements of this document. For dated references, only the edition cited applies. For undated references, the latest edition of the referenced document (including any amendments) applies.

EN 58, *Bitumen and bituminous binders — Sampling bituminous binders*

EN 12594, *Bitumen and bituminous binders — Preparation of test samples*

EN 13302, *Bitumen and bituminous binders — Determination of dynamic viscosity of bituminous binder using a rotating spindle apparatus*

EN ISO 4788:2005, *Laboratory glassware — Graduated measuring cylinders (ISO 4788:2005)*

3 Terms and definitions

For the purposes of this document, the following terms and definitions apply.

ISO and IEC maintain terminology databases for use in standardization at the following addresses:

- ISO Online browsing platform: available at <https://www.iso.org/obp>
- IEC Electropedia: available at <https://www.electropedia.org>

3.1

viscosity

internal resistance of a fluid to flow

3.2

efflux time

time needed for a specified volume of a material to flow through a specified orifice at a specified temperature

Note 1 to entry: The efflux time is an indirect measure of the viscosity and is also referred to as “pseudo-viscosity”.

4 Principle

The efflux time of a petroleum cut-back or fluxed bituminous binder is determined using an efflux viscometer known as the Standard Tar Viscometer (STV) which determines the time of efflux of a 50 ml sample through a 10 mm or a 4 mm orifice at a specified temperature.

Whatever temperatures or orifice diameters used, the efflux time shall not exceed 600 s. For highly viscous cut-back or fluxed bituminous binders, EN 13302 shall be used.

5 Reagents and materials

Light mineral or vegetal oil having a density lower or equal to 930 kg/m³ at 15 °C.

6 Apparatus

Usual laboratory apparatus and glassware, together with the following.

6.1 Efflux viscometer (example of assembled viscometer on Figure 1) consisting essentially of a cup with an orifice in the centre of the base that may be closed by a ball-and-socket valve (Figure 3).

Two forms are required, differing only in the size of the orifice (10 mm and 4 mm). For other dimensions of the cup and the ball valve, see Figure 3 and Table 3. The cup cylinder shall be made of brass. The ball valve should be made of corrosion-resistant metal, with a ball on a rod, a levelling peg attached to the rod and a hemispherical top by means of which the valve may be supported in a vertical position

The viscometer cups can be provided with suitable corks or caps for closing the orifices with the ball valve in position (the closing with corks or caps is only required when conditioning the viscometer in a separate bath). The viscometer cups shall be provided with some means of covering the cups (e.g. lids) to minimize surface cooling effects. This lid shall not touch the test material when the cup is filled. It is provided with a central hole through which the temperature measuring device can pass and with a groove on one side through which the rod of the valve can pass.

The viscometer-cup holder shall be capable of:

- supporting one or more cups in a vertical position;
- providing a valve support to hold the valve at least 16 mm vertically above the orifice of the cup during efflux of the test material (Figure 2).

To enhance resistance to wear and corrosion of the ball and socket valve, the bottom of the cup may be made from a different, corrosion resistant, material and screwed to the brass tube. It is then advised to use the same material, such as for instance phosphor-bronze, for the cup bottom and the ball valve. Wrought nickel alloy with copper or metals NiCu30 in accordance with ISO 9722:1992 [1] are possible materials for the rod of the ball valve.

It is allowed to use working apparatus with other technical solutions that meet the requirements of this document, such as for example an integrated block viscometer, which is a combination of a specific efflux viscometer, thermostating element and temperature controller.

6.2 Viscometer water bath, capable of maintaining the test temperature of 25,0 °C, 40,0 °C, 50,0 °C or 60,0 °C (8.3.1, 3), 4) and 5)) constant to within ±0,5 °C. Cups shall be separated from each other and from the walls of the bath by at least 55 mm.

EN 12846-2:2022 (E)

6.3 Separate temperature controlled water bath. A water bath (6.2), capable of maintaining the test temperature constant to within $\pm 0,5$ °C, and in which one or more of the filled viscometer cups can be immersed up to the rim of the cup.

Cups shall be separated from each other and from the walls of the bath by at least 55 mm.

A suitable support shall be provided to maintain the cup(s) in a vertical position.

The viscometer water bath (6.2) may also be used to directly condition the test sample in the cup.

6.4 Temperature measuring devices (combining sensor and reading unit), two, which shall:

- have a range from at least 10 °C to 70 °C;
- have a maximum permissible measurement error of $\pm 0,2$ °C or better;
- have a suitable length so that the measuring tip may be immersed at mid-height of the viscometer water bath, separate water bath and viscometer-cup (8.3.5).

Sensors based on platinum resistance thermometers have been found suitable but other principles are also allowed.

6.5 Receiver, consisting of a 100 ml cylinder with graduations at 20 ml, 25 ml and 75 ml, complying with the requirement Type 1a of EN ISO 4788:2005.

6.6 Timing device, capable of measuring the efflux time with a maximum permissible error of $\pm 0,2$ s.

7 Sampling

The material under test shall be sampled in accordance with EN 58 and prepared in accordance with EN 12594.

A viscometer cup with hot binder should not be plunged into cool water as this shock cooling will radically affect the viscosity result.

The test shall be carried out in duplicate.

8 Procedure

8.1 General

Carry out the procedure in laboratory at room temperature between 18 °C to 28 °C.

8.2 Preparation of apparatus

Clean the viscometer cup (6.1) with a suitable solvent, to remove any mark of binder, and thoroughly dry it to remove all traces of solvent. If necessary, rub the interior of the cup and/or clean the orifice. Use soft tissue-paper or some similar material that will not leave particles behind or abrade the metal.

When cleaning, care shall be taken not to damage the orifice.

8.3 Measurement

8.3.1 If the efflux time is unknown, measure it at 25 °C with the 10 mm orifice viscometer cup and refer to Table 1.

According to the efflux time obtained, 5 main cases are possible. Choose the diameter of the orifice of the cup and the temperature of the test as follows:

- 1) if the efflux time is lower than 5 s, perform another determination at 25 °C with 4 mm orifice;
- 2) if the efflux time is between 5 s and 600 s with still a continuous flow, no change in the experimental conditions (25 °C with 10 mm orifice) is necessary;
- 3) in case of a non-continuous flow or if the efflux time is greater than 600 s, perform another determination at 40 °C with the 10 mm orifice;
- 4) in case of a non-continuous flow or if the efflux time determined at 40 °C is greater than 600 s, perform another determination at 50 °C with the 10 mm orifice;
- 5) in case of a non-continuous flow or if the efflux time determined at 50 °C is greater than 600 s, perform another determination at 60 °C with the 10 mm orifice.

Table 1 — Temperature up to 40 °C and diameter of the cup

25 °C 10 mm		
Select the temperature and the orifice diameter of the cup depending on t value		
if $t < 5$ s	if $5 \text{ s} \leq t \leq 600$ s and continuous flow	if $t > 600$ s or non-continuous flow
T = 25 °C $\varnothing = 4$ mm	T = 25 °C $\varnothing = 10$ mm	T = 40 °C (see 4) and 5) if needed) $\varnothing = 10$ mm

For highly viscous cut-back or fluxed bituminous binders having efflux time at 60 °C with the 10 mm orifice higher than 600 s, test shall be performed by means of dynamic viscosity measurement (EN 13302).

8.3.2 Condition the viscometer water bath (6.2) and, if used, the separate controlled water bath (6.3), by stirring the water in the bath with the relevant device and check that the temperature is at the required value for the test, maintained within $\pm 0,5$ °C.

8.3.3 Close the lower part of the cup orifice with a cork or a cap if the viscometer-cup is to be filled and maintained within the separate water bath prior to its transfer into the viscometer (see 8.3.5).

8.3.4 Place the ball valve on top of the orifice. Carefully fill the cup with the prepared sample to such a height that the levelling peg on the valve is just immersed when the latter is vertical. Cover the top of the cup for example with a suitable lid. It shall be provided with a central hole and a groove on one side through which the rod of the valve (Figure 3, Key element 2) may be passed into the upper end of the cup. Pass the temperature measuring device (6.4) through the central hole so that its bulb is approximately at the geometric centre of the sample.

EN 12846-2:2022 (E)

8.3.5 Suspend the cup up to its rim in the separate water bath (6.3) or directly into the viscometer water bath (6.2) maintained within $\pm 0,5$ °C of the test temperature for the minimum period of time necessary to reach the test temperature.

8.3.6 If a separate water bath is used (6.3), remove the filled cup from the water bath and place it into the viscometer cup holder. Check that the sample has maintained the required temperature. If not, wait till equilibrium is reached again.

8.3.7 Remove any excess sample while removing the temperature measuring device so that the final level of the binder is on the centre line of the levelling peg when the valve is in a vertical position. Remove the cork or stopper if used.

8.3.8 Pour the light mineral or vegetal oil (Clause 5) into the receiver (6.5) up to the 20 ml graduation mark and place the receiver directly under the orifice of the viscometer cup. Lift the valve rod and suspend it on the valve rod support so as to hold the valve at least 16 mm vertically above the orifice. Start the timing device (6.6) when the liquid in the receiver reaches the 25 ml graduation mark and stop it when the liquid reaches the 75 ml graduation mark.

Record the efflux time to the nearest 0,2 s.

8.3.9 Repeat Sampling (Clause 7) and Procedure (Clause 8) steps on a second test sample.

9 Expression of results

Express the result as the arithmetic mean of the two results obtained in accordance with Clause 8 to the nearest second, provided that individual results do not differ by more than the value for repeatability given in Table 2 under Clause 10.

If the two results differ by more than the above specified values, repeat the whole procedure.

10 Precision

10.1 Repeatability

The difference between two successive test results, obtained by the same operator with the same apparatus under constant operating conditions on identical test material would, in the long run, in the normal and correct operation of the test method, exceed the value given in Table 2 in only one case in twenty.

10.2 Reproducibility

The difference between two single and independent results obtained by different operators working in different laboratories on identical test material would, in the long run, in the normal and correct operation of the test method, exceed the value given in Table 2 in only one case in twenty.

Table 2 — Precision

Efflux time s	Repeatability	Reproducibility
Below or equal to 20	1 s	2 s
above 20	5 % of the mean	10 % of the mean