
**Footwear — Critical substances
potentially present in footwear
and footwear components —
Determination of Nitrosamines**

*Chaussure — Substances critiques potentiellement présentes dans
les chaussures et les composants de chaussure — Détermination des
nitrosamines*

iTeh STANDARD PREVIEW
(standards.iteh.ai)

[ISO 19577:2019](https://standards.iteh.ai/catalog/standards/sist/923752bb-8f8d-49b6-be34-7f77b163f198/iso-19577-2019)

<https://standards.iteh.ai/catalog/standards/sist/923752bb-8f8d-49b6-be34-7f77b163f198/iso-19577-2019>



iTeh STANDARD PREVIEW
(standards.iteh.ai)

ISO 19577:2019

<https://standards.iteh.ai/catalog/standards/sist/923752bb-8f8d-49b6-be34-7f77b163f198/iso-19577-2019>



COPYRIGHT PROTECTED DOCUMENT

© ISO 2019

All rights reserved. Unless otherwise specified, or required in the context of its implementation, no part of this publication may be reproduced or utilized otherwise in any form or by any means, electronic or mechanical, including photocopying, or posting on the internet or an intranet, without prior written permission. Permission can be requested from either ISO at the address below or ISO's member body in the country of the requester.

ISO copyright office
CP 401 • Ch. de Blandonnet 8
CH-1214 Vernier, Geneva
Phone: +41 22 749 01 11
Fax: +41 22 749 09 47
Email: copyright@iso.org
Website: www.iso.org

Published in Switzerland

Contents

	Page
Foreword.....	iv
1 Scope	1
2 Normative references	1
3 Terms and definitions	1
4 Principle	1
5 Reagents and materials	1
6 Apparatus	2
7 Preparation of test samples	3
8 Procedure	3
8.1 Extraction.....	3
8.2 Purification.....	3
8.3 Chromatographic analysis.....	3
8.3.1 The chromatography parameters for GC-MS.....	3
8.3.2 Qualitative and quantitative analysis by GC-MS.....	4
9 Expression of results	4
9.1 Calculation of results.....	4
9.2 Limit of Quantification.....	5
10 Test report	5
Annex A (informative) Names of 12 kinds of Nitrosamines and the Standard selective GC-MS ions	6
Annex B (informative) The chromatography parameters for GC-MS	7
Annex C (informative) GC-MS total ion current of Nitrosamine standard sample	8
Annex D (normative) Confirmation of detected Nitrosamines	9
Annex E (normative) Alternative methods	10
Annex F (informative) Results of the interlaboratory tests	11
Bibliography	12

Foreword

ISO (the International Organization for Standardization) is a worldwide federation of national standards bodies (ISO member bodies). The work of preparing International Standards is normally carried out through ISO technical committees. Each member body interested in a subject for which a technical committee has been established has the right to be represented on that committee. International organizations, governmental and non-governmental, in liaison with ISO, also take part in the work. ISO collaborates closely with the International Electrotechnical Commission (IEC) on all matters of electrotechnical standardization.

The procedures used to develop this document and those intended for its further maintenance are described in the ISO/IEC Directives, Part 1. In particular, the different approval criteria needed for the different types of ISO documents should be noted. This document was drafted in accordance with the editorial rules of the ISO/IEC Directives, Part 2 (see www.iso.org/directives).

Attention is drawn to the possibility that some of the elements of this document may be the subject of patent rights. ISO shall not be held responsible for identifying any or all such patent rights. Details of any patent rights identified during the development of the document will be in the Introduction and/or on the ISO list of patent declarations received (see www.iso.org/patents).

Any trade name used in this document is information given for the convenience of users and does not constitute an endorsement.

For an explanation of the voluntary nature of standards, the meaning of ISO specific terms and expressions related to conformity assessment, as well as information about ISO's adherence to the World Trade Organization (WTO) principles in the Technical Barriers to Trade (TBT), see www.iso.org/iso/foreword.html.

This document was prepared by Technical Committee ISO/TC 216, *Footwear*.

Any feedback or questions on this document should be directed to the user's national standards body. A complete listing of these bodies can be found at www.iso.org/members.html.

Footwear — Critical substances potentially present in footwear and footwear components — Determination of Nitrosamines

WARNING — The use of this document can involve hazardous materials, operations and equipment. It does not purport to address all of the safety or environmental problems associated with its use. It is the responsibility of users of this document to take appropriate measures to ensure the safety and health of personnel and the environment prior to application of the document.

1 Scope

This document specifies a method for the determination of the content of 12 kinds of Nitrosamines (see [Annex A](#)) in footwear and footwear components by using solvent extraction and Gas chromatography with mass selective detector (GC-MS).

This document is applicable to rubber in footwear materials.

NOTE ISO/TR 16178 defines which materials are concerned by this determination.

2 Normative references

The following documents are referred to in the text in such a way that some or all of their content constitutes requirements of this document. For dated references, only the edition cited applies. For undated references, the latest edition of the referenced document (including any amendments) applies.

ISO 4787, *Laboratory glassware — Volumetric instruments — Methods for testing of capacity and for use*

3 Terms and definitions

No terms and definitions are listed in this document.

ISO and IEC maintain terminological databases for use in standardization at the following addresses:

- ISO Online browsing platform: available at <https://www.iso.org/obp>
- IEC Electropedia: available at <http://www.electropedia.org/>

4 Principle

Extract Nitrosamines in the sample with methanol using an ultrasonic bath. The extract is concentrated in a rotary vacuum evaporator and purified by passing through C₁₈ solid-phase separation column. The Nitrosamines in test solutions are analysed by GC-MS, using full scan detection mode for qualitative analysis and selected ion monitoring (SIM) mode for quantitative analysis with an external standard solution.

5 Reagents and materials

Unless otherwise specified, all the reagents used are chromatographic grade.

5.1 Methanol, CAS number: 67-56-1.

5.2 C₁₈ solid-phase extraction column, 500 mg/3 ml freshly made in lab or obtained from commercial sources.

5.3 Standard stock-solution, prepare stock solutions containing 200 mg/l of each Nitrosamine (see [Annex A](#)) in methanol ([5.1](#)) respectively. These solutions should be stored in amber glassware in a refrigerator at (-18 ± 3) °C. Under these conditions, the solutions can be used for 15 days.

NOTE Nitrosamines are susceptible to UV degradation, so extract and standard solutions cannot be exposed to sunlight or fluorescent light sources. Test solutions or standard solutions can be wrapped in aluminium foil or be stored in amber glassware in the dark at (-18 ± 3) °C.

5.4 Standard working-solutions, freshly prepared by mixing standard stock-solutions ([5.3](#)) and diluting to 10 mg/l with methanol ([5.1](#)). This solution should be stored in the absence of light at (-18 ± 3) °C.

5.5 Internal standard for chromatographic analysis, see [8.3.2](#).

6 Apparatus

The usual laboratory apparatus and amber laboratory glassware, according to ISO 4787, shall be used, in addition to the following.

6.1 Analytical balance, with a readability of at least 0,1 mg.

6.2 Conical flask, amber, which can be tightly sealed, (e.g. volume of 100 ml).

6.3 Ultrasonic bath, with the working frequency of $40 \text{ kHz} \pm 5 \text{ kHz}$.

6.4 Round-bottomed flask, amber, (e.g. volume of 25 ml, 100 ml).

6.5 Rotary vacuum evaporator or Nitrogen evaporator, with adjustable temperature, suitable for operation up to 40 °C.

6.6 Vortex mixer.

6.7 Volumetric flask, amber, (e.g. volume of 2 ml, 5 ml).

6.8 Solid phase extraction device, with a vacuum pump.

6.9 Centrifuge tube, amber, (e.g. volume of 2 ml).

6.10 Centrifuge, $2\ 000 \times g$.

6.11 Syringe filter, 0,45 µm, for example PTFE.

6.12 GC vial, amber, (e.g. volume of 2 ml).

6.13 Gas chromatograph with a mass selective detector (GC-MS).

Other chromatographic technics may be used, provided that they have been validated for this analysis.

7 Preparation of test samples

Take a representative sample, cut into piece of less than 3 mm of length with appropriate tools.

8 Procedure

WARNING — Most Nitrosamines are potent carcinogens and every possible precaution shall be taken to avoid human exposure.

8.1 Extraction

Weigh 5,0 g (accurate to 0,01 g) samples into a conical flask (6.2). Add 30 ml of methanol (5.1) and extract in an ultrasonic bath (6.3) for (30 ± 2) min at room temperature. The temperature shall not exceed 40 °C. If the test sample is not sufficiently immersed in the extraction solvent, add more solvent and report the final volume for calculation of Nitrosamines amount.

Filter the extract into a round-bottomed flask (6.4).

Add 20 ml of methanol (5.1) into the conical flask (6.2) and repeat extraction again and combine the extracts.

Concentrate the methanol extract to less than 2 ml with rotary vacuum evaporator at 40 °C in a vacuum of 21,3 kPa to 16,3 kPa or nitrogen evaporator (6.5).

Remove the round-bottomed flask (6.4) from the evaporator (6.5) and shake vigorously with the vortex mixer (6.6) for 1 min (so that the adhesive substance stuck to the bottle wall can be dissolved in methanol).

After evaporation, transfer the remaining liquid and the residue quantitatively into a 5 ml amber volumetric flask (6.7) by using methanol (5.1) as rinsing solvent. Fill up the flask to the mark with methanol (5.1).

8.2 Purification

Pre-rinse the C₁₈ column (5.2) with methanol (5.1). Accurately transfer 2,0 ml of the test solution (see 8.1) into the C₁₈ column (5.2) and collect eluate. When the solution drains off (the surface of sample solution drops to filler's surface), add 2 ml of methanol (5.1) into C₁₈ column (5.2) twice. Collect and combine all the eluate in a round-bottomed flask (6.4).

Concentrate this solution to approximately 1 ml (not to dryness) in a rotary vacuum evaporator or nitrogen evaporator (6.5) at no more than 40 °C. Then remove the remainder of methanol to dryness by a slow flow of inert gas. Dissolve the residue with methanol (5.1) and transfer it to an amber volumetric flask (6.7) and make up the volume with methanol (5.1).

Transfer this solution into an amber sample vial (6.12) after filtration with 0,45 µm syringe filter (6.11) and perform chromatographic analysis. If necessary (viscous solution), centrifuge this solution in centrifuge tube (6.9) before transferring.

8.3 Chromatographic analysis

8.3.1 The chromatography parameters for GC-MS

See an example in [Annex B](#).

8.3.2 Qualitative and quantitative analysis by GC-MS

Inject an aliquot of standard working solution (5.4) and the test solution (see 8.2) separately into the column for determination of Nitrosamines. Analyse qualitatively by external standard method through selected characteristic ions (see Table A.1).

Within the linear range use at least five measurements at different concentrations. Example for calibration solutions, see Table 1.

Table 1 — Calibration solutions (examples)

Standard	L1	L2	L3	L4	L5
Volume of the standard working-solution (µl) (5.4)	50	100	250	500	1 000
Volume of solution (µl) (5.1)	950	900	750	500	0
Concentration of Nitrosamine (mg/l)	0,5	1,0	2,5	5,0	10,0

If the response value of test solution is out of the linear range of the detector, dilute the solution appropriately before measurement.

NOTE Under the above analysis conditions, GC-MS total ion chromatogram of 12 kinds of Nitrosamine standards is given in Annex C.

For N-nitroso-N-methylaniline, N-nitroso-N-ethylaniline and N-nitroso-diphenylamine, those decompose at injector temperature. If peaks of their characteristic ions in the chromatogram are found, these Nitrosamines shall be confirmed according to Annex D and E and reported in test report.

This analysis should also be performed using an internal standard for the quantification. The following two been proved as usable:

- N-nitroso-N,N,-dimethylamine-d6, CAS number: 17829-05-9;
- N-nitroso-N,N,-di-n-propylamine-d14, CAS number: 93951-96-3.

9 Expression of results

9.1 Calculation of results

The content of each Nitrosamine in the sample is calculated by Formula (1):

$$X_i = \frac{A_i \times c_i \times V}{A_{is} \times m} \quad (1)$$

where

- X_i is the content of Nitrosamine i in the sample;
- A_i is the peak area of Nitrosamine i in the test solution, in area units;
- A_{is} is the peak area of Nitrosamine i in the standard working solution, in area units;
- c_i is the concentration of Nitrosamine i in the standard working solution, in µg/ml;
- V is the volume of the test solution (see 8.1), in ml;
- m is mass of the sample (see 8.1), in g.

Results are rounded to 0,1 mg/kg. When the result exceeds 100 mg/kg, express the result to the nearest 1 mg/kg.

For determination using internal standard method. Set up the linear regression function by using the following ratio (A_i/A_{is}) and (C_i/C_{is}) with the help of [Formula \(2\)](#):

$$\frac{A_i}{A_{is}} = a \times \frac{C_i}{C_{is}} + b \quad (2)$$

where

- A_i is the peak area of Nitrosamine i in the test solution, in area units;
- A_{is} is the peak area of internal standard in the working solution, in area units;
- C_i is the concentration of Nitrosamine i in the standard working solution, in $\mu\text{g/ml}$;
- C_{is} is the concentration of internal standard in the working solution, in $\mu\text{g/ml}$
- a is the slope of the linear function;
- b is the ordinate intercept of the calibration curve. The units depend of the evaluation.

9.2 Limit of Quantification

This method is able to detect the Nitrosamines listed in [Table A.1](#) with a limit of quantification of 0,5 mg/kg or lower. Results below 0,5 mg/kg should be reported as below limit of quantification (LOQ).

See results of the inter-laboratories tests in [Annex F](#).

10 Test report iTeh STANDARD PREVIEW

The test report shall include at least the following information:

- a) a reference to this document, i.e. ISO 19577:2019;
- b) all information necessary for complete identification of the sample tested;
- c) test results;
- d) information on confirmation and method used;
- e) any deviation from this document.