



Standard Test Method for Ash In Analysis of Petroleum Coke¹

This standard is issued under the fixed designation D 4422; the number immediately following the designation indicates the year of original adoption or, in the case of revision, the year of last revision. A number in parentheses indicates the year of last reapproval. A superscript epsilon (ϵ) indicates an editorial change since the last revision or reapproval.

1. Scope

1.1 This test method covers the determination of the ash content of petroleum coke.

~~1.2 The values stated in SI units are to be regarded as the standard. The values in parentheses are for information only.~~

1.2 The values stated in SI units are to be regarded as standard. No other units of measurement are included in this standard.

1.3 *This standard does not purport to address all of the safety concerns, if any, associated with its use. It is the responsibility of the user of this standard to establish appropriate safety and health practices and determine the applicability of regulatory limitations prior to use.*

2. Referenced Documents

2.1 *ASTM Standards:*²

D 346 Practice for Collection and Preparation of Coke Samples for Laboratory Analysis

~~D 2013 Test Method~~ Practice for Preparing Coal Samples for Analysis

3. Summary of Test Method

3.1 A representative sample of petroleum coke is dried, ground, and ashed in a muffle furnace at 700 to 750°C (~~1292 to 1383°F~~); 750°C. The residue or ash is expressed as a percentage of the dry petroleum coke.

4. Significance and Use

4.1 The ash content is one of the properties used to evaluate petroleum coke and indicates the amount of undesirable residue present. Acceptable ash content varies with the intended use.

5. Interferences

5.1 High sulfur content of the furnace gases, regardless of the source of the sulfur, can react with an alkaline ash to produce erratic results. The furnace must be swept with air to achieve oxidation and to decrease the sulfur content of the gases.

5.2 Preparation and testing of the analysis sample must neither remove nor add ash. Improper dividing, sieving, and crushing equipment, and some muffle furnace lining material can contaminate the sample.

6. Apparatus

6.1 *Crucibles*, low wide form glazed porcelain or platinum, 30-mL capacity.

6.2 *Muffle Furnace*, with temperature control between 700 and 750°C and equipped with a means to regulate air circulation.

6.3 *Analytical Balance* capable of weighing to 0.1 mg.

6.4 *Drying Oven* controlled at $110 \pm 5^\circ\text{C}$.

6.5 *Desiccator*.

7. Sample Preparation

7.1 Crush the laboratory sample to pass a ~~in. (6.3 mm)~~ 6.3-mm sieve. If the quantity exceeds 2.3 kg (5 lb), kg, divide the sample to obtain about 2.3 kg (5 lb) and crush this fraction to pass a 850- μm (No. 20) sieve. Further divide the sample to obtain a portion of approximately 200 g and crush to pass a 250- μm (No. 60) sieve. Divide again to obtain approximately 50 g and pulverize this fraction such that 95 % or more passes a 75- μm (No. 200) sieve. This is the analysis sample which is dried to constant weight at $110 \pm 5^\circ\text{C}$.

¹ This test method is under the jurisdiction of ASTM Committee ~~D-2D02~~ on Petroleum Products and Lubricants and is the direct responsibility of Subcommittee D02.05 on Properties of Fuels, Petroleum Coke, Coke and ~~Oil Shale~~ Carbon Material.

Current edition approved ~~Sept. Oct. 15, 1994~~ 2008. Published November ~~1994~~ 2008. Originally published as ~~D4422-84~~ approved in 1984. Last previous edition ~~D4422-89~~ approved in 2003 as D 4422-03.

² For referenced ASTM standards, visit the ASTM website, www.astm.org, or contact ASTM Customer Service at service@astm.org. For *Annual Book of ASTM Standards* Vol 05.05 volume information, refer to the standard's Document Summary page on the ASTM website.