



~~Designation: A 667/A 667M-87 (Reapproved 2003)~~ Designation: A667/A667M – 87 (Reapproved 2008)

Standard Specification for Centrifugally Cast Dual Metal (Gray and White Cast Iron) Cylinders¹

This standard is issued under the fixed designation A667/A667M; the number immediately following the designation indicates the year of original adoption or, in the case of revision, the year of last revision. A number in parentheses indicates the year of last reapproval. A superscript epsilon (ϵ) indicates an editorial change since the last revision or reapproval.

This standard has been approved for use by agencies of the Department of Defense.

1. Scope

1.1 This specification² covers centrifugally cast cylinders with an outer layer of white cast iron and the remainder of the material of gray cast iron. These castings are suitable for pressure containing parts the design strength of which is based on the gray iron portion of the cylinder. These castings are suitable for service at temperatures up to 450°F [230°C].

1.2 The values stated in either ~~inch-pound~~SI units or ~~SI~~inch-pound units are to be regarded separately as standard. ~~Within the text, the SI units are shown in brackets. The values stated in each system are~~may not be exact equivalents; therefore, each system ~~must~~shall be used independently of the other. Combining values from the two systems may result in non-conformance with the ~~specification standard.~~

1.3 The following safety hazards caveat pertains only to the test method portion, Section 8, of this specification: *This standard does not purport to address all of the safety concerns, if any, associated with its use. It is the responsibility of the user of this standard to establish appropriate safety and health practices and determine the applicability of regulatory limitations prior to use.*

2. Referenced Documents

2.1 ASTM Standards:³

~~A278M Specification for Gray Iron Castings for Pressure-Containing Parts for Temperatures Up to 650°F (350°C)~~

~~A278M Specification for Gray Iron Castings for Pressure-Containing Parts for Temperatures Up to 345°C [Metric] 278/~~
A278M Specification for Gray Iron Castings for Pressure-Containing Parts for Temperatures Up to 650F (350C)

3. Materials and Manufacture

3.1 The melting procedures shall be optional with the foundry.

3.2 The white iron portion of the cylinder shall be made to a minimum hardness of 55 Scleroscope “C”. The gray iron portion of the cylinder shall conform to Specification ~~A-278A-278A278/A278M~~, Class 20 ~~{A-278M, or Class 150} 150~~. ~~667m-872008~~

3.3 The casting process shall be controlled to produce a metallurgical bond between the two metal layers.

4. Finish

4.1 All surfaces shall be machined prior to the cylinders being placed into service.

5. Physical Requirements

5.1 *Tensile Requirements*—Tension test specimens removed from the casting shall have a tensile strength not less than 80 % of that specified in 3.2.

5.2 Thickness of White Cast Iron:

5.2.1 The thickness of the white cast iron shall be not less than 5 % nor more than 30 % of the total finished wall thickness.

5.2.2 The thickness of the white cast iron shall be determined by ultrasonic testing.

¹ This specification is under the jurisdiction of Committee A04 on Iron Castings and is the direct responsibility of Subcommittee A04.01 on Grey and White Iron Castings. Current edition approved May 10, 2003. Published May 2003. Originally approved in 1972. Last previous edition approved in 1998 as A 667/A 667M-87 (1998). Current edition approved Oct. 1, 2008. Published November 2008. Originally approved in 1972. Last previous edition approved in 2003 as A667/A667M – 87 (2003). DOI: 10.1520/A0667_A0667M-87R08.

² For ASME Boiler and Pressure Vessel Code applications see related Specification SA-667 in Section II of that Code.

³ Annual Book of ASTM Standards, Vol. 01.02.

³ For referenced ASTM standards, visit the ASTM website, www.astm.org, or contact ASTM Customer Service at service@astm.org. For Annual Book of ASTM Standards volume information, refer to the standard’s Document Summary page on the ASTM website.