



Designation: A 790/A 790M – 08a

# Standard Specification for Seamless and Welded Ferritic/Austenitic Stainless Steel Pipe<sup>1</sup>

This standard is issued under the fixed designation A 790/A 790M; the number immediately following the designation indicates the year of original adoption or, in the case of revision, the year of last revision. A number in parentheses indicates the year of last reappraisal. A superscript epsilon ( $\epsilon$ ) indicates an editorial change since the last revision or reappraisal.

## 1. Scope\*

1.1 This specification<sup>2</sup> covers seamless and straight-seam welded ferritic/austenitic steel pipe intended for general corrosive service, with particular emphasis on resistance to stress corrosion cracking. These steels are susceptible to embrittlement if used for prolonged periods at elevated temperatures.

1.2 Optional supplementary requirements are provided for pipe when a greater degree of testing is desired. These supplementary requirements call for additional tests to be made and, when desired, one or more of these may be specified in the order.

1.3 **Appendix X1** of this specification lists the dimensions of welded and seamless stainless steel pipe as shown in ANSI **B36.19**. Pipe having other dimensions may be furnished provided such pipe complies with all other requirements of this specification.

1.4 The values stated in either inch-pound units or SI units are to be regarded separately as standard. Within the text, the SI units are shown in brackets. The values stated in each system are not exact equivalents; therefore, each system must be used independently of the other. Combining values from the two systems may result in nonconformance with the specification. The inch-pound units shall apply unless the *M* designation of this specification is specified in the order.

NOTE 1—The dimensionless designator NPS (nominal pipe size) has been substituted in this standard for such traditional terms as nominal diameter, size, and nominal size.

## 2. Referenced Documents

### 2.1 *ASTM Standards*:<sup>3</sup>

<sup>1</sup> This specification is under the jurisdiction of ASTM Committee A01 on Steel, Stainless Steel and Related Alloys and is the direct responsibility of Subcommittee A01.10 on Stainless and Alloy Steel Tubular Products.

Current edition approved Oct. 1, 2008. Published November 2008. Originally approved in 1981. Last previous edition approved in 2008 as A 790/A 790M – 08.

<sup>2</sup> For ASME Boiler and Pressure Vessel Code applications see related Specification SA-790 in Section II of that Code.

<sup>3</sup> For referenced ASTM standards, visit the ASTM website, [www.astm.org](http://www.astm.org), or contact ASTM Customer Service at [service@astm.org](mailto:service@astm.org). For *Annual Book of ASTM Standards* volume information, refer to the standard's Document Summary page on the ASTM website.

**A 370** Test Methods and Definitions for Mechanical Testing of Steel Products

**A 923** Test Methods for Detecting Detrimental Intermetallic Phase in Duplex Austenitic/Ferritic Stainless Steels

**A 941** Terminology Relating to Steel, Stainless Steel, Related Alloys, and Ferroalloys

**A 999/A 999M** Specification for General Requirements for Alloy and Stainless Steel Pipe

**E 213** Practice for Ultrasonic Examination of Metal Pipe and Tubing

**E 309** Practice for Eddy-Current Examination of Steel Tubular Products Using Magnetic Saturation

**E 381** Method of Macroetch Testing Steel Bars, Billets, Blooms, and Forgings

**E 426** Practice for Electromagnetic (Eddy-Current) Examination of Seamless and Welded Tubular Products, Austenitic Stainless Steel and Similar Alloys

**E 527** Practice for Numbering Metals and Alloys in the Unified Numbering System (UNS)

### 2.2 *ANSI Standards*:<sup>4</sup>

**B1.20.1** Pipe Threads, General Purpose

**B36.10** Welded and Seamless Wrought Steel Pipe

**B36.19** Stainless Steel Pipe

### 2.3 *SAE Standard*:<sup>5</sup>

**SAE J 1086**

### 2.4 *Other Standard*:<sup>6</sup>

**SNT-TC-1A** Personal Qualification and Certification in Nondestructive Testing

### 2.5 *AWS Standard*

**A5.9** Corrosion-Resisting Chromium and Chromium-Nickel Steel Welding Rods and Electrodes

## 3. Terminology

3.1 *Definitions*—For definitions of terms used in this specification refer to Terminology **A 941**.

<sup>4</sup> Available from American National Standards Institute (ANSI), 25 W. 43rd St., 4th Floor, New York, NY 10036, <http://www.ansi.org>.

<sup>5</sup> Available from Society of Automotive Engineers (SAE), 400 Commonwealth Dr., Warrendale, PA 15096-0001, <http://www.sae.org>.

<sup>6</sup> Available from American Society for Nondestructive Testing (ASNT), P.O. Box 28518, 1711 Arlingate Ln., Columbus, OH 43228-0518, <http://www.asnt.org>.

\*A Summary of Changes section appears at the end of this standard.

#### 4. Ordering Information

4.1 Orders for material under this specification should include the following, as required, to describe the desired material adequately:

- 4.1.1 Quantity (feet, [metres], or number of lengths),
- 4.1.2 Name of material (ferritic/austenitic steel pipe),
- 4.1.3 Process (seamless or welded),
- 4.1.4 Grade (see **Table 1**),
- 4.1.5 Size (NPS designator or outside diameter and schedule number of average wall thickness),
- 4.1.6 Length (specific or random) (see Section 11),
- 4.1.7 End finish (section on ends of Specification **A 999/A 999M**),
- 4.1.8 Optional requirements (product analysis, Section 9; hydrostatic test or nondestructive electric test, Section 14),
- 4.1.9 Test report required (section on certification of Specification **A 999/A 999M**),
- 4.1.10 Specification designation, and
- 4.1.11 Special requirements and any supplementary requirements selected.

#### 5. General Requirements

5.1 Material furnished under this specification shall conform to the applicable requirements of the current edition of Specification **A 999/A 999M** unless otherwise provided herein.

#### 6. Materials and Manufacture

##### 6.1 Manufacture:

6.1.1 The pipe shall be made by the seamless or an automatic welding process, with no addition of filler metal in the welding operation.

6.1.2 At the manufacturer's option, pipe may be either hot-finished or cold-finished.

6.1.3 The pipe shall be pickled free of scale. When bright annealing is used, pickling is not necessary.

6.2 *Discard*—A sufficient discard shall be made from each ingot to secure freedom from injurious piping and undue segregation.

6.3 Unless otherwise stated in the order, all pipe shall be furnished in the heat-treated condition as shown in **Table 1**.

**TABLE 1 Heat Treatment**

UNS Designation	Type <sup>A</sup>	Temperature °F [°C]	Quench
S31200		1920–2010 [1050–1100]	Rapid cooling in water
S31260		1870–2010 [1020–1100]	Rapid cooling in air or water
S31500		1800–1900 [980–1040]	Rapid cooling in air or water
S31803		1870–2010 [1020–1100]	Rapid cooling in air or water
S32003		1850–2050 [1010–1120]	Rapid cooling in air or water
S32101		1870 [1020]	Quenched in water or rapidly cooled by other means
S32202		1800–1975 [980–1080]	Rapid cooling in air or water
S32205	2205	1870–2010 [1020–1100]	Rapid cooling in air or water
S32304	2304	1700–1920 [925–1050]	Rapid cooling in air or water
S32506		1870–2050 [1020–1120]	Rapid cooling in air or water
S32520		1975–2050 [1080–1120]	Rapid cooling in air or water
S32550	255	1900 [1040] min	Rapid cooling in air or water
S32707		1975–2050 [1080–1120]	Rapid cooling in air or water
S32750	2507	1880–2060 [1025–1125]	Rapid cooling in air or water
S32760		1960–2085 [1070–1140]	Rapid cooling in air or water
S32808		1920–2100 [1050–1150]	Rapid cooling in air or water
S32900	329	1700–1750 [925–955]	Rapid cooling in air or water
S32906		1870–2100 [1020–1150]	Rapid cooling in air or water
S32950		1820–1880 [990–1025]	Air cool
S33207		1905–2085 [1040–1140]	Rapid cooling in water or by other means
S39274		1920–2060 [1025–1125]	Rapid cooling in air or water
S39277		1975–2155 [1080–1180]	Rapid cooling in air or water

<sup>A</sup>Common name, not a trademark, widely used, not associated with any one producer. 329 is na AISI number.

6.3.1 For seamless pipe, as an alternate to final heat treatment in a continuous furnace or batch-type furnace, immediately following hot forming while the temperature of the pipes is not less than the specified minimum solution treatment temperature, pipes shall be individually quenched in water or rapidly cooled by other means, except for UNS S32950, which shall be air cooled.

6.3.2 If the purchaser desires pipe without heat treatment subsequent to welding, the purchase order shall specify the following condition:

6.3.2.1 No final heat treatment of pipe fabricated from plate that has been heat treated as required by **Table 1** for the particular grade is required, *provided a sample of that heat of finished pipe or material representative of that heat of pipe as a prolongation of the weld passes the Test Methods A 923 Method B or C (See Note 2), including base metal, weld metal, and heat affected zone per heat.* Each pipe supplied under this requirement shall be stenciled with the suffix “HT-O.”

6.3.2.2 For materials not listed in **Table 3** of Test Methods **A 923**, the HT-O provision does not apply.

NOTE 2—The Test Methods **A 923** test method (B or C) is at the manufacturer’s option, unless otherwise specified by the purchaser.

## 7. Chemical Composition

7.1 The steel shall conform to the chemical requirements as prescribed in **Table 2**.

## 8. Heat Analysis

8.1 An analysis of each heat of steel shall be made by the steel manufacturer to determine the percentages of the elements specified.

## 9. Product Analysis

9.1 At the request of the purchaser’s inspector, an analysis of one billet or one length of flat-rolled stock from each heat, or two pipes from each lot, shall be made by the manufacturer. A lot of pipe shall consist of the following number of lengths of the same size and wall thickness from any one heat of steel:

NPS Designator	Lengths of Pipe in Lot
Under 2	400 or fraction thereof
2 to 5, incl	200 or fraction thereof
6 and over	100 or fraction thereof

9.2 The results of these analyses shall be reported to the purchaser or the purchaser’s representative and shall conform to the requirements specified in **Section 7**.

9.3 If the analysis of one of the tests specified in **8.1** or **9.1** does not conform to the requirements specified in **Section 7**, an analysis of each billet or pipe from the same heat or lot may be made, and all billets or pipe conforming to the requirements shall be accepted.

## 10. Tensile and Hardness Properties

10.1 The material shall conform to the tensile and hardness properties prescribed in **Table 3**.

**TABLE 2 Chemical Requirements<sup>A</sup>**

UNS Designation <sup>B</sup>	Type <sup>C</sup>	C	Mn	P	S	Si	Ni	Cr	Mo	N	Cu	Others
S31200		0.030	2.00	0.045	0.030	1.00	5.5–6.5	24.0–26.0	1.20–2.00	0.14–0.20	...	...
S31260		0.030	1.00	0.030	0.030	0.75	5.5–7.5	24.0–26.0	2.5–3.5	0.10–0.30	0.20–0.80 W	0.10–0.50
S31500		0.030	1.20–2.00	0.030	0.030	1.40–2.00	4.2–5.2	18.0–19.0	2.50–3.00	0.05–0.10	...	...
S31803		0.030	2.00	0.030	0.020	1.00	4.5–6.5	21.0–23.0	2.5–3.5	0.08–0.20	...	...
S32003		0.030	2.00	0.030	0.020	1.00	3.0–4.0	19.5–22.5	1.50–2.00	0.14–0.20	...	...
S32101		0.040	4.0–6.0	0.040	0.030	1.00	1.35–1.70	21.0–22.0	0.10–0.80	0.20–0.25	0.10–0.80	...
S32202		0.030	2.00	0.040	0.010	1.00	1.00–2.80	21.5–24.0	0.45	0.18–0.26	...	...
S32205	2205	0.030	2.00	0.030	0.020	1.00	4.5–6.5	22.0–23.0	3.0–3.5	0.14–0.20	...	...
S32304	2304	0.030	2.50	0.040	0.040	1.00	3.0–5.5	21.5–24.5	0.05–0.60	0.05–0.20	0.05–0.60	...
S32506		0.030	1.00	0.040	0.015	0.90	5.5–7.2	24.0–26.0	3.0–3.5	0.08–0.20	...	W 0.05–0.30
S32520		0.030	1.5	0.035	0.020	0.80	5.5–8.0	24.0–26.0	3.0–5.0	0.20–0.35	0.5–3.00	...
S32550	255	0.04	1.50	0.040	0.030	1.00	4.5–6.5	24.0–27.0	2.9–3.9	0.10–0.25	1.50–2.50	...
S32707		0.030	1.50	0.035	0.010	0.50	5.5–9.5	26.0–29.0	4.0–5.0	0.30–0.50	1.0	Co 0.5–2.0
S32750	2507	0.030	1.20	0.035	0.020	0.80	6.0–8.0	24.0–26.0	3.0–5.0	0.24–0.32	0.5	...
S32760		0.05	1.00	0.030	0.010	1.00	6.0–8.0	24.0–26.0	3.0–4.0	0.20–0.30	0.50–1.00 W	0.50–1.00 40 min <sup>D</sup>
S32808		0.030	1.10	0.030	0.030	0.50	7.0–8.2	27.0–27.9	0.80–1.20	0.30–0.40	...	W 2.10–2.50
S32900	329	0.08	1.00	0.040	0.030	0.75	2.5–5.0	23.0–28.0	1.00–2.00	...	...	...
S32906		0.030	0.80–1.50	0.030	0.030	0.80	5.8–7.5	28.0–30.0	1.50–2.60	0.30–0.40	0.80	...
S32950		0.030	2.00	0.035	0.010	0.60	3.5–5.2	26.0–29.0	1.00–2.50	0.15–0.35	...	...
S33207		0.030	1.50	0.035	0.010	0.80	6.0–9.0	29.0–33.0	3.0–5.0	0.40–0.60	1.0	...
S39274		0.030	1.00	0.030	0.020	0.80	6.0–8.0	24.0–26.0	2.5–3.5	0.24–0.32	0.20–0.80 W	1.50–2.50
S39277		0.025	0.80	0.025	0.002	0.80	6.5–8.0	24.0–26.0	3.0–4.0	0.23–0.33	1.20–2.00 W	0.8–1.2

<sup>A</sup>Maximum, unless a range or minimum is indicated. Where ellipses (...) appear in this table, there is no minimum and analysis for the element need not be determined or reported.

<sup>B</sup>New designation established in accordance with Practice **E 527** and **SAE J 1086**.

<sup>C</sup>Common name, not a trademark, widely used, not associated with any one producer. 329 is na AISI number.

<sup>D</sup>% Cr + 3.3 × % Mo + 16 × % N.

**TABLE 3 Tensile and Hardness Requirements**

UNS Designation	Type <sup>A</sup>	Tensile Strength, min, ksi [MPa]	Yield Strength, min, ksi [MPa]	Elongation in 2 in. or 50 mm, min, %	Hardness, max	
					HBW	HRC
S31200		100 [690]	65 [450]	25	280	...
S31260		100 [690]	65 [450]	25	...	...
S31500		92 [630]	64 [440]	30	290	30
S31803		90 [620]	65 [450]	25	290	30
S32003		90 [620]	65 [450]	25	290	30
S32101						
t ≤ 0.187 in. [5.00 mm]		101 [700]	77 [530]	30	290	...
t > 0.187 in. [5.00 mm]		94 [650]	65 [450]	30	290	...
S32202		94 [650]	65 [450]	30	290	30
S32205	2205	95 [655]	65 [450]	25	290	30
S32304	2304	87 [600]	58 [400]	25	290	30
S32506		90 [620]	65 [450]	18	302	32
S32520		112 [770]	80 [550]	25	310	...
S32550	255	110 [760]	80 [550]	15	297	31
S32707		133 [920]	101 [700]	25	318	34
S32750	2507	116 [800]	80 [550]	15	300	32
S32760 <sup>B</sup>		109 [750]	80 [550]	25	300	...
S32808		116 [800]	80 [550]	15	310	32
S32900	329	90 [620]	70 [485]	20	271	28
S32906						
Wall below 0.40 in. [10 mm]		116 [800]	94 [650]	25	300	32
Wall 0.40 in. [10 mm] and above		109 [750]	80 [550]	25	300	32
S32950		100 [690]	70 [480]	20	290	30
S33207						
Wall below 0.157 in. (4 mm)		138 [950]	112 [770]	15	336	36
Wall 0.157 in. (4 mm) and above		123 [850]	101 [700]	15	336	36
S39274		116 [800]	80 [550]	15	310	32
S39277		120 [825]	90 [620]	25	290	30

<sup>A</sup>Common name, not a trademark, widely used, not associated with any one producer. 329 is an AISI number.

<sup>B</sup>Prior to A 790/A 790M – 04, the tensile strength value for UNS 32760 was 109–130 ksi [750–895 MPa].

<https://standards.iteh.ai/catalog/standards/astm-a790-a790m-08a>

## 11. Lengths

11.1 Pipe lengths shall be in accordance with the following regular practice:

11.1.1 Unless otherwise agreed upon, all sizes from NPS ½ to and including NPS 8 are available in a length up to 24 ft (see **Note 3**) with the permissible range of 15 to 24 ft (see **Note 3**). Short lengths are acceptable and the number and minimum length shall be agreed upon between the manufacturer and the purchaser.

NOTE 3—This value applies when the inch-pound designation of this specification is the basis of purchase. When the *M* designation of this specification is the basis of purchase, the corresponding metric value(s) shall be agreed upon between the manufacturer and purchaser.

11.1.2 If definite cut lengths are desired, the lengths required shall be specified in the order. No pipe shall be less than the specified length and no more than ¼ in. [6 mm] over it.

11.1.3 No jointers are permitted unless otherwise specified.