



Designation: A 860/A 860M – 08

Standard Specification for Wrought High-Strength Ferritic Steel Butt-Welding Fittings¹

This standard is issued under the fixed designation A 860/A 860M; the number immediately following the designation indicates the year of original adoption or, in the case of revision, the year of last revision. A number in parentheses indicates the year of last reapproval. A superscript epsilon (ϵ) indicates an editorial change since the last revision or reapproval.

1. Scope*

1.1 This specification covers wrought high-strength ferritic steel butt-welding fittings of seamless and electric fusion-welded construction covered by the latest revisions of ASME B16.9, ASME B16.28, and MSS-SP-75. Butt-welding fittings differing from these ASME and MSS standards shall be furnished in accordance with Supplementary Requirement S58 of Specification A 960/A 960M. These fittings are for use in high-pressure gas and oil transmission and distribution systems.

1.2 Optional supplementary requirements are provided for fittings when a greater degree of examination is desired. One or more of the supplementary requirements may be specified in the order.

1.3 This specification does not cover cast-welding fittings or fittings machined from castings.

1.4 The values stated in either inch-pound units or SI units are to be regarded separately as standard. Within the text, the SI units are shown in brackets. The values stated in each system are not exact equivalents; therefore, each system must be used independently of the other. Combining values from the two systems may result in nonconformance with this specification. Unless the order specifies the applicable “M” specification designation (SI units), the material shall be furnished to inch-pound units.

2. Referenced Documents

2.1 ASTM Standards:²

A 370 Test Methods and Definitions for Mechanical Testing of Steel Products

A 751 Test Methods, Practices, and Terminology for Chemical Analysis of Steel Products

A 960/A 960M Specification for Common Requirements for Wrought Steel Piping Fittings

¹ This specification is under the jurisdiction of ASTM Committee A01 on Steel, Stainless Steel and Related Alloys and is the direct responsibility of Subcommittee A01.22 on Steel Forgings and Wrought Fittings for Piping Applications and Bolting Materials for Piping and Special Purpose Applications.

Current edition approved Nov. 1, 2008. Published December 2008. Originally approved in 1986. Last previous edition approved in 2005 as A 860/A 860M – 00(2005).

² For referenced ASTM standards, visit the ASTM website, www.astm.org, or contact ASTM Customer Service at service@astm.org. For *Annual Book of ASTM Standards* volume information, refer to the standard's Document Summary page on the ASTM website.

2.2 ASME Standards:³

B16.9 Steel Butt-Welding Fittings

B16.28 Wrought Steel Butt-welding Short Radius Elbows and Returns

2.3 ASME Boiler and Pressure Vessel Code:³

Section V, Nondestructive Examination

Section VIII, Division 1, Pressure Vessels

Section IX, Welding and Brazing Qualifications

2.4 MSS Standards:⁴

MSS SP-25 The Standard Marking System of Valves, Fittings, Flanges and Unions

MSS-SP-75 Specification for High Test Wrought Butt-Welding Fittings

2.5 American Society of Nondestructive Testing:⁵

SNT-TC-1A Recommended Practice for Nondestructive Testing Personnel Qualification and Certification

3. Ordering Information

3.1 In addition to the requirements of Specification A 960/A 960M, the following ordering information applies:

3.1.1 Grade Symbol,

3.1.2 Requirements for certification of test report.

4. General Requirements

4.1 Product furnished to this specification shall conform to the requirements of Specification A 960/A 960M, including any supplementary requirements that are indicated in the purchase order. Failure to comply with the general requirements of Specification A 960/A 960M constitutes nonconformance with this specification. In case of conflict between the requirements of this specification and Specification A 960/A 960M, this specification shall prevail.

5. Materials and Manufacture

5.1 The material for fittings shall be fully killed fine-grain material made by a melting process that is intended to produce rounded, well dispersed, fine sulphide inclusions, that promote

³ Available from American Society of Mechanical Engineers (ASME), ASME International Headquarters, Three Park Ave., New York, NY 10016-5990, <http://www.asme.org>.

⁴ Available from Manufacturers Standardization Society of the Valve and Fittings Industry (MSS), 127 Park St., NE, Vienna, VA 22180-4602, <http://www.mss-hq.com>.

⁵ Available from American Society for Nondestructive Testing (ASNT), P.O. Box 28518, 1711 Arlingate Ln., Columbus, OH 43228-0518, <http://www.asnt.org>.

*A Summary of Changes section appears at the end of this standard.

good notch toughness, assists in the resistance to hydrogen induced cracking, and for weldability suitable for field welding.

5.2 Starting materials shall consist of plate, sheet, forgings, forging quality bar, and seamless or fusion-welded tubular products with filler metal added. The chemical composition shall conform to **Table 1**.

5.3 A starting material that specifically requires the addition of any element beyond those listed in **Table 1** is not permitted. This does not preclude the use of deoxidizers.

5.4 Starting material shall not require a preheat for field welding provided that the restrictions of ASME Boiler and Pressure Vessel Code, Section VIII, Paragraph UW-30 are complied with.

5.5 Forging or shaping operations may be performed by hammering, pressing, piercing, extruding, upsetting, rolling, bending, fusion, welding, machining, or by a combination of these operations.

5.6 All welds including welds in tubular products from which the fittings are made shall be:

5.6.1 Made by welders, welding operators, and welding procedures qualified under the provisions of ASME Boiler and Pressure Vessel Code, **Section IX**,

5.6.2 Heat treated in accordance with **Section 6** of this specification, and

5.6.3 Radiographically examined throughout the entire length of each weld in accordance with Articles 1 and 2 of ASME Boiler and Pressure Vessel Code, Section V with acceptance limits in accordance with Paragraph UW-51 of ASME Boiler and Pressure Vessel Code, Section VIII.

5.7 The welded joints of the fittings shall be furnished in accordance with the requirements of Paragraph UW-35(a) of ASME Boiler and Pressure Vessel Code, Section VIII.

5.8 All butt-weld tees manufactured by cold-forming methods shall be liquid penetrant or magnetic particle examined by one of the methods specified in Supplementary Requirements

S69 or S70 of Specification **A 960/A 960M**. This examination shall be performed in accordance with a written procedure and shall be performed after final heat treatment. Only the side wall area of the tees need be examined. This area is defined by a circle that covers the area from the weld bevel of the branch outlet to the center line of the body or run. Internal and external surfaces shall be examined when size permits accessibility. No cracks shall be permitted. Other imperfections shall be treated in accordance with **12.1** on finish. After the removal of any cracks, the tees shall be re-examined by the original method. Acceptable tees shall be marked with the symbol PT or MT, as applicable, to indicate compliance. NDE personnel shall be qualified in accordance with **SNT-TC-1A**.

5.9 All caps machined from bar stock shall be examined by liquid penetrant or magnetic particle in accordance with Supplementary Requirements S69 or S70 of Specification **A 960/A 960M**, and with personnel qualifications, acceptance criteria, and marking as in **5.8**.

6. Heat Treatment

6.1 All fittings shall be furnished in the heat-treated condition. Fittings formed above the transformation temperature or upon which welding is performed, shall be cooled to below the lower critical temperature prior to heat treatment. Fittings shall subsequently be heat treated by normalizing, quenching, and tempering or stress relieving in accordance with Specification **A 960/A 960M**.

7. Chemical Composition

7.1 The chemical composition of the steel shall conform to the requirements prescribed in **Table 1**.

7.2 The steel shall not contain any unspecified elements for the ordered grade to the extent that it conforms to the requirements of another grade for which that element is a specified element having a required minimum content.

7.3 Analysis of each heat of steel shall be made from a sample taken preferably during the pouring of the heat. The results shall conform to **Table 1** for either heat or Specification **A 960/A 960M** for product analysis limits as applicable.

7.4 The fittings manufacturer shall make a product analysis per heat from either the starting material or from a fitting. The chemical composition thus determined shall conform to **Table 1**. The product analysis shall be the basis for rejection. For referee purposes, Test Methods, Practices, and Terminology **A 751** shall apply.

7.5 The carbon equivalent of the base metal, as determined by the following formula, shall not exceed 0.42 % for the product analysis:

$$CE = C + \frac{Mn}{6} + \frac{Cr + Mo + V}{5} + \frac{Ni + Cu}{15}$$

7.6 Weld metal used in the construction of the fittings shall conform to the tensile and impact requirements of **9.4** and **8.1** after heat treatment in accordance with **Section 6**. A chemical analysis shall be performed on deposited weld metal for each heat of filler metal or, for submerged arc welding, each heat of filler metal and batch of flux. The weld metal shall be deposited in accordance with the qualified weld procedure.

TABLE 1 Chemical Requirements

	Composition %	
	Heat Analysis	
Carbon	0.20 ^A	All values are maximum unless a range is stated
Manganese	1.00–1.45	
Phosphorus	0.030	
Sulfur	0.010	
Silicon	0.15–0.40 ^B	
Nickel	0.50 ^C	
Chromium	0.30 ^C	
Molybdenum	0.25 ^C	
Copper	0.35 ^C	
Titanium	0.05	
Vanadium	0.10	
Columbium	0.04	
Vanadium plus Columbium	0.12	
Aluminum	0.06	

^A The carbon equivalent, as calculated by the following formula, shall not exceed 0.42 %:

$$CE = C + \frac{Mn}{6} + \frac{Cr + Mo + V}{5} + \frac{Ni + Cu}{15}$$

^B If vacuum carbon deoxidation is used, silicon shall not exceed 0.10 % by heat analysis and 0.12 % by product analysis.

^C The sum of Ni + Cr + Mo + Cu shall not exceed 1.0 %.