



**SLOVENSKI STANDARD  
SIST-TP ISO/TR 10657:2022**

**01-april-2022**

---

**Zapisek razlag k standardu ISO 76**

Explanatory notes on ISO 76

Notes explicatives sur l'ISO 76

**iTeh STANDARD  
PREVIEW**

**Ta slovenski standard je istoveten z: ISO/TR 10657:2021**

**(standards.iteh.ai)**

---

[SIST-TP ISO/TR 10657:2022](https://standards.iteh.ai/catalog/standards/sist/a1d47d45-6f4a-4073-817a-15b64116ee55/sist-tp-iso-tr-10657-2022)

**ICS:**

21.100.20

Kotalni ležaji

<https://standards.iteh.ai/catalog/standards/sist/a1d47d45-6f4a-4073-817a-15b64116ee55/sist-tp-iso-tr-10657-2022>

Rolling bearings

**SIST-TP ISO/TR 10657:2022**

**en,fr,de**

**iTeh STANDARD  
PREVIEW  
(standards.iteh.ai)**

[SIST-TP ISO/TR 10657:2022](https://standards.iteh.ai/catalog/standards/sist/a1d47d45-6f4a-4073-817a-15b64116ee55/sist-tp-iso-tr-10657-2022)

<https://standards.iteh.ai/catalog/standards/sist/a1d47d45-6f4a-4073-817a-15b64116ee55/sist-tp-iso-tr-10657-2022>

# TECHNICAL REPORT

# ISO/TR 10657

Second edition  
2021-11

---

---

## Explanatory notes on ISO 76

*Notes explicatives sur l'ISO 76*

**iTeh STANDARD  
PREVIEW  
(standards.iteh.ai)**

[SIST-TP ISO/TR 10657:2022](https://standards.iteh.ai/catalog/standards/sist/a1d47d45-6f4a-4073-817a-15b64116ee55/sist-tp-iso-tr-10657-2022)

<https://standards.iteh.ai/catalog/standards/sist/a1d47d45-6f4a-4073-817a-15b64116ee55/sist-tp-iso-tr-10657-2022>



Reference number  
ISO/TR 10657:2021(E)

© ISO 2021

**iTeh STANDARD  
PREVIEW  
(standards.iteh.ai)**

SIST-TP ISO/TR 10657:2022

<https://standards.iteh.ai/catalog/standards/sist/a1d47d45-6f4a-4073-817a-15b64116ee55/sist-tp-iso-tr-10657-2022>



**COPYRIGHT PROTECTED DOCUMENT**

© ISO 2021

All rights reserved. Unless otherwise specified, or required in the context of its implementation, no part of this publication may be reproduced or utilized otherwise in any form or by any means, electronic or mechanical, including photocopying, or posting on the internet or an intranet, without prior written permission. Permission can be requested from either ISO at the address below or ISO's member body in the country of the requester.

ISO copyright office  
CP 401 • Ch. de Blandonnet 8  
CH-1214 Vernier, Geneva  
Phone: +41 22 749 01 11  
Email: [copyright@iso.org](mailto:copyright@iso.org)  
Website: [www.iso.org](http://www.iso.org)

Published in Switzerland

# Contents

Page

<b>Foreword</b> .....	<b>iv</b>
<b>Introduction</b> .....	<b>v</b>
<b>1 Scope</b> .....	<b>1</b>
<b>2 Normative references</b> .....	<b>1</b>
<b>3 Terms, definitions and symbols</b> .....	<b>1</b>
3.1 Terms and definitions.....	1
3.2 Symbols.....	1
<b>4 Basic static load ratings</b> .....	<b>3</b>
4.1 General.....	3
4.1.1 Basic formula for point contact.....	3
4.1.2 Basic formula for line contact.....	5
4.2 Basic static radial load rating $C_{0r}$ for radial ball bearings.....	6
4.2.1 Radial and angular contact groove ball bearings.....	6
4.2.2 Self-aligning ball bearings.....	8
4.3 Basic static axial load rating $C_{0a}$ for thrust ball bearings.....	8
4.4 Basic static radial load rating $C_{0r}$ for radial roller bearings.....	10
4.5 Basic static axial load rating $C_{0a}$ for thrust roller bearings.....	10
<b>5 Static equivalent load</b> .....	<b>11</b>
5.1 Theoretical static equivalent radial load $P_{0r}$ for radial bearings.....	11
5.1.1 Single-row radial bearings and radial contact groove ball bearings (nominal contact angle $\alpha = 0^\circ$ ).....	11
5.1.2 Double-row radial bearings.....	17
5.2 Theoretical static equivalent axial load $P_{0a}$ for thrust bearings.....	18
5.2.1 Single-direction thrust bearings.....	18
5.2.2 Double-direction thrust bearings.....	21
5.3 Approximate formulae for theoretical static equivalent load.....	23
5.3.1 Radial bearings.....	23
5.3.2 Thrust bearings.....	24
5.4 Practical formulae of static equivalent load.....	24
5.4.1 Radial bearings.....	24
5.4.2 Thrust bearings.....	28
5.5 Static radial load factor $X_0$ and static axial load factor $Y_0$ .....	29
5.5.1 Radial bearings.....	29
5.5.2 Thrust bearings.....	33
<b>Annex A (normative) Values for <math>\gamma</math>, <math>\kappa</math> and <math>E(\kappa)</math></b> .....	<b>35</b>
<b>Bibliography</b> .....	<b>38</b>

## ISO/TR 10657:2021(E)

## Foreword

ISO (the International Organization for Standardization) is a worldwide federation of national standards bodies (ISO member bodies). The work of preparing International Standards is normally carried out through ISO technical committees. Each member body interested in a subject for which a technical committee has been established has the right to be represented on that committee. International organizations, governmental and non-governmental, in liaison with ISO, also take part in the work. ISO collaborates closely with the International Electrotechnical Commission (IEC) on all matters of electrotechnical standardization.

The procedures used to develop this document and those intended for its further maintenance are described in the ISO/IEC Directives, Part 1. In particular, the different approval criteria needed for the different types of ISO documents should be noted. This document was drafted in accordance with the editorial rules of the ISO/IEC Directives, Part 2 (see [www.iso.org/directives](http://www.iso.org/directives)).

Attention is drawn to the possibility that some of the elements of this document may be the subject of patent rights. ISO shall not be held responsible for identifying any or all such patent rights. Details of any patent rights identified during the development of the document will be in the Introduction and/or on the ISO list of patent declarations received (see [www.iso.org/patents](http://www.iso.org/patents)).

Any trade name used in this document is information given for the convenience of users and does not constitute an endorsement.

For an explanation of the voluntary nature of standards, the meaning of ISO specific terms and expressions related to conformity assessment, as well as information about ISO's adherence to the World Trade Organization (WTO) principles in the Technical Barriers to Trade (TBT), see [www.iso.org/iso/foreword.html](http://www.iso.org/iso/foreword.html).

This document was prepared by Technical Committee ISO/TC 4, *Rolling bearings*, Subcommittee SC 8, *Load ratings and life*.

This second edition cancels and replaces the first edition (ISO 10657:1991), which has been technically revised.

The main changes compared to the previous edition are as follows:

- New subclause 0.4 and 0.5 included with explanations concerning the 2006 edition of ISO 76:2006 and ISO 76/Amd.1:2017;
- Inclusion of [Clause 3](#) for symbols;
- [Table 16](#) and [Table 18](#) amended according to additional values in ISO 76:2006 (values of  $X_0$  and  $Y_0$  at contact angles  $5^\circ$  and  $10^\circ$  of angular contact ball bearings).

Any feedback or questions on this document should be directed to the user's national standards body. A complete listing of these bodies can be found at [www.iso.org/members.html](http://www.iso.org/members.html).

## Introduction

### 0.1 ISO/R 76:1958

ISO/R 76, *Ball and Roller Bearings — Methods of Evaluating Static Load Ratings*, was drawn up by Technical Committee ISO/TC 4, *Ball and Roller Bearings*.

ISO/R 76 was based on the studies of A. Palmgren et al<sup>[2],[3]</sup>. The basic static load ratings were defined to correspond to a total permanent deformation of rolling element and raceway at the most heavily stressed rolling element/raceway contact of 0,000 1 of the rolling element diameter. Then the standard values confined to the basic static load ratings for special inner design rolling bearings were laid down.

ISO/R 76:1958 was approved by 28 (out of a total of 38) member bodies and was then submitted to the ISO Council, which decided, in December 1958, to accept it as an ISO Recommendation.

### 0.2 ISO 76:1978

ISO/TC 4 decided to include the revision of ISO/R 76 in its programme of work and ISO/TC 4/SC 8 secretariat was requested to prepare a draft proposal. As a result, the secretariat submitted a draft proposal<sup>[3]</sup> in January 1976.

The draft proposal was accepted by 6 of the 8 members of ISO/TC 4/SC 8. Of the remaining two, Japan preferred further study and USA, its counter proposal, document ISO/TC 4/SC 8 N 64<sup>[4]</sup>. The draft was then submitted to the ISO Central Secretariat. After the draft had been approved by the ISO member bodies, the ISO Council decided in June 1978 to accept it as an International Standard.

ISO 76:1978 adopted the SI unit newton and was revised in total, but without essential changes of substance. However, values of  $X_0$  and  $Y_0$  for the nominal contact angles 15° and 45° for angular contact groove ball bearings were added to the table to calculate the static equivalent radial loads of radial ball bearings (see ISO 76:1978, Table 2).

### 0.3 ISO 76:1987

[SIST-TP ISO/TR 10657:2022](https://standards.iteh.ai/catalog/standards/sist/a1d47d45-014a-4073-817a-15b04110ee55/sist-tp-iso-t-10657-2022)

During the revision of ISO/R 76:1958, USA had in 1975 submitted a counter proposal<sup>[4]</sup> for the basic static load ratings based on a calculated contact stress.

The secretariat requested a vote on the revision of the static load ratings based on a contact stress level in January 1978 and afterward circulated the voted results in June 1978, and the item No. of revision work had become No. 157 of the programme of work of TC 4.

ISO/TC 4/SC 8, considering the proposals made in the documents TC 4/SC 8 N 75<sup>[5]</sup> and TC 4 N 865<sup>[6]</sup>, as well as the comments made by TC 4 members and that several SC 8 members expressed a need for updating ISO 76, agreed to continue its study taking into account the possibility of using either permanent deformation or stress level as a basis for static load ratings, and ISO/TC 4/SC 8 requested its secretariat to prepare a new draft. The new draft was intended to be prepared with the principles and formulae of the document TC 4/SC 8 N 75, and to include levels of contact stress for various rolling element contact stated to be generally corresponding to a permanent deformation of 0,000 1 of the rolling element diameter at the centre of the most heavily stressed rolling element/raceway contact. For roller bearings a stress level of 4 000 MPa was agreed and then ISO/TC 4/SC 8 agreed, by a majority vote, that static load ratings should correspond to calculated contact stresses of

4 000 MPa for roller bearings,

4 600 MPa for self-aligning ball bearings, and

4 200 MPa for all other ball bearings to which the standard applies.

For these calculated contact stresses, a total permanent deformation occurs at the centre of the most heavily stressed rolling element/raceway contact, and its deformation is approximately 0,000 1 of the rolling element diameter.

## ISO/TR 10657:2021(E)

ISO 76 was submitted to the ISO Central Secretariat in 1985, and after it had been approved by the ISO members, the ISO Council decided in February 1987 to accept it as an International Standard.

Furthermore, ISO/TC 4/SC 8 decided that supplementary background information, regarding the derivation of formulae and factors given in ISO 76, should be published as a Technical Report. This Technical report was published as ISO/TR 10657:1991.

An Amendment to ISO 76:1987 that explains the discontinuities in load ratings between radial- and axial bearings was published as ISO 76:1987/Amd.1:1999.

### 0.4 ISO 76:2006

A systematic review of ISO 76:1987 was agreed in 2003, based on the prior held balloting process and documents TC 4/SC 8 N 233 and N 235.

ISO 76:2006 includes editorial adaptations and updates as well as an extension by the static safety factor  $S_0$ . Furthermore, ISO 76:1987/Amd.1:1999 was integrated and became the informative [Annex A](#) "Discontinuities in the calculation of basic static load ratings".

### 0.5 ISO 76:2006/Amd.1:2017

ISO 76:2006/Amd.1:2017 includes the following items:

- graphs for the factors  $f_0$ ,  $X_0$  and  $Y_0$  taken from draft ÖNORM M 6320 to be included in an informative annex;
- formulae for the calculation of the load rating factor  $f_0$  from ISO/TR 10657 to be introduced in the normative part of the standard;
- the tables for the load rating factor  $f_0$  will stay in the normative part of the standard, however a sentence will be introduced stating that the results obtained from formulae are preferred.

[SIST-TP ISO/TR 10657:2022](https://standards.iteh.ai/catalog/standards/sist/a1d47d45-6f4a-4073-817a-15b64116ee55/sist-tp-iso-tr-10657-2022)

<https://standards.iteh.ai/catalog/standards/sist/a1d47d45-6f4a-4073-817a-15b64116ee55/sist-tp-iso-tr-10657-2022>



## Explanatory notes on ISO 76

### 1 Scope

This document specifies supplementary background information regarding the derivation of formulae and factors given in ISO 76:2006.

### 2 Normative references

There are no normative references in this document.

### 3 Terms, definitions and symbols

#### 3.1 Terms and definitions

No terms and definitions are listed in this document.

ISO and IEC maintain terminology databases for use in standardization at the following addresses:

- ISO Online browsing platform: available at <https://www.iso.org/obp>
- IEC Electropedia: available at <https://www.electropedia.org/>

#### 3.2 Symbols

$C_{0a}$	basic static axial load rating, in newtons
$C_{0r}$	basic static radial load rating, in newtons
$D_{pw}$	pitch diameter of ball or roller set, in millimetres
$D_w$	nominal ball diameter, in millimetres
$D_{we}$	roller diameter applicable in the calculation of load ratings, in millimetres
$E$	modulus of elasticity (Young's modulus), in megapascals
$E_1, E_2$	modulus of elasticity of body 1 (rolling element) and of body 2 (raceway), in megapascals
$E(\kappa)$	complete elliptic integral of the second kind
$E_0$	$E/(1 - \nu^2)$
$F_a$	bearing axial load (axial component of actual bearing load), in newtons
$F_r$	bearing radial load (radial component of actual bearing load), in newtons
$F(\rho)$	relative curvature difference
$J_a(\varepsilon)$	axial load integral
$J_r(\varepsilon)$	radial load integral
$K(\kappa)$	complete elliptic integral of the first kind

## ISO/TR 10657:2021(E)

$L_{we}$	length of roller applicable in the calculation of load ratings, in millimetres
$P_{0a}$	theoretical static equivalent axial load for thrust bearing, general speaking, called static equivalent axial load, in newtons
$P_{0r}$	theoretical static equivalent radial load for radial bearing, general speaking, called static equivalent radial load, in newtons
$Q$	normal force between rolling element and raceway, in newtons
$Q_{max}$	maximum normal force between rolling element and raceway, in newtons
$S$	Stribeck number
$X_0$	static radial load factor
$Y_0$	static axial load factor
$Z$	number of balls carrying load in one direction, number of balls or rollers per row, or number of rolling elements per row
$a$	semi-major axis of the projected contact ellipse, semilength of the contact surface
$b$	semi-minor axis of the projected contact ellipse, semi-width of the contact surface
$c$	compression constant, in $1/\text{megapascals}^{2/3}$
$f$	osculation = $r/D_w$
$f_e$	osculation at the outer ring = $r_e/D_w$
$f_i$	osculation at the inner ring = $r_i/D_w$
$f_0$	factor which depends on the geometry of the bearing components and on applicable stress level
$i$	number of rows of balls or rollers in a bearing
$k_0$	load distribution parameter
$r$	curvature radius of a raceway cross-section, in millimetres
$r_e$	outer ring groove radius, in millimetres
$r_i$	inner ring groove radius, in millimetres
$t$	exponent in load-deflection formula
$x$	distance in direction of the semi-major axis, in millimetres
$y$	distance in direction of the semi-minor axis, in millimetres
$\alpha$	nominal contact angle, in degrees
$\alpha'$	actual contact angle, in degrees

ITEH STANDARD  
 PREVIEW  
 (standards.iteh.ai)

SIST-TP ISO/TR 10657:2022

<https://standards.iteh.ai/en/standards/sist/11447345-6f4a-4073-817a-15b64116ee55/sist-tp-iso-tr-10657-2022>

$\gamma$	auxiliary parameter, $\gamma = D_w \cos \alpha / D_{pw}$	for ball bearings with $\alpha \neq 90^\circ$
	$\gamma = D_w / D_{pw}$	for ball bearings with $\alpha = 90^\circ$
	$\gamma = D_{we} \cos \alpha / D_{pw}$	for roller bearings with $\alpha \neq 90^\circ$
	$\gamma = D_{we} / D_{pw}$	for roller bearings with $\alpha = 90^\circ$
$\varepsilon$	parameter indicating the width of the loaded zone	
$\kappa$	ratio of semi-major to semi-minor axis = $a/b$	
$\nu$	Poisson's ratio	
$\nu_1$	Poisson's ratio of body 1 (rolling element)	
$\nu_2$	Poisson's ratio of body 2 (raceway)	
$\Sigma\rho$	curvature sum	
$\rho_{11}, \rho_{12}$	principal curvature of body 1 (rolling element)	
$\rho_{21}, \rho_{22}$	principal curvature of body 2 (raceway)	
$\sigma$	calculated contact stress, in megapascals	
$\sigma_{\max}$	maximum calculated contact stress, in megapascals	
$\phi$	auxiliary angle, in radians	
$\psi_0$	one half of the loaded arc	

SIST-TP ISO/TR 10657:2022

## 4 Basic static load ratings

### 4.1 General

#### 4.1.1 Basic formula for point contact

The relationship between a calculated contact stress and a rolling element load within an elliptical contact area is given in Reference [8] as [Formula \(1\)](#),

$$\sigma = \frac{3Q}{2\pi ab} \left[ 1 - \left( \frac{x}{a} \right)^2 - \left( \frac{y}{b} \right)^2 \right]^{1/2} \quad (1)$$

It is concluded that the maximum calculated contact stress ( $\sigma_{\max}$ ) occurs at the point of  $x = 0$  and  $y = 0$ ,

$$\sigma_{\max} = \frac{3Q}{2\pi ab} \text{ or } Q = \frac{2\pi ab}{3} \sigma_{\max} \quad (2)$$

According to the Hertz's theory,

$$a = \left( \frac{2\kappa^2 E(\kappa)}{\pi} \right)^{1/3} \left[ \frac{3Q}{2\Sigma\rho} \left( \frac{1-\nu_1^2}{E_1} + \frac{1-\nu_2^2}{E_2} \right) \right]^{1/3} \quad (3)$$

$$b = \left( \frac{2E(\kappa)}{\pi\kappa} \right)^{1/3} \left[ \frac{3Q}{2\Sigma\rho} \left( \frac{1-\nu_1^2}{E_1} + \frac{1-\nu_2^2}{E_2} \right) \right]^{1/3} \quad (4)$$

## ISO/TR 10657:2021(E)

where

$$\begin{aligned}\kappa &= a/b \\ E(\kappa) &= \int_0^{\pi/2} \left[ 1 - \left( 1 - \frac{1}{\kappa^2} \right) \sin^2 \phi \right]^{1/2} d\phi \\ \Sigma\rho &= \rho_{11} + \rho_{12} + \rho_{21} + \rho_{22} \\ \rho_{11} = \rho_{12} &= \frac{2}{D_w}\end{aligned}$$

Substituting [Formula \(3\)](#) and [Formula \(4\)](#) into [Formula \(2\)](#) for the case of  $E_1 = E_2 = E$  and  $\nu_1 = \nu_2 = \nu$ ,

$$Q = \sigma_{\max}^3 \frac{32\pi}{3E_0^2} \kappa \left( \frac{E(\kappa)}{\Sigma\rho} \right)^2 \quad (5)$$

and

$$1 - \frac{2}{\kappa^2 - 1} \left( \frac{K(\kappa)}{E(\kappa)} - 1 \right) - F(\rho) = 0 \quad (6)$$

where

$$\begin{aligned}E_0 &= \frac{E}{1-\nu^2} \\ E &= 2,07 \times 10^5 \text{ MPa} \\ \nu &= 0,3\end{aligned}$$

**iTeh STANDARD  
PREVIEW  
(standards.iteh.ai)**

$$\begin{aligned}K(\kappa) &= \int_0^{\pi/2} \left[ 1 - \left( 1 - \frac{1}{\kappa^2} \right) \sin^2 \phi \right]^{-1/2} d\phi \\ F(\rho) &= \frac{\rho_{11} - \rho_{12} + \rho_{21} - \rho_{22}}{\rho_{11} + \rho_{12} + \rho_{21} + \rho_{22}}\end{aligned}$$

Consequently, from [Formula \(5\)](#),

$$Q = 6,476\,206\,5 \times 10^{-10} \kappa \left( \frac{E(\kappa)}{\Sigma\rho} \right)^2 \sigma_{\max}^3 \quad (7)$$

#### 4.1.2 Basic formula for line contact

The relationship between a calculated contact stress and a rolling element load for a line contact is given in Reference [9] as follows,

$$\sigma = \frac{2Q}{\pi L_{we} b} \left[ 1 - \left( \frac{y}{b} \right)^2 \right]^{1/2} \quad (8)$$

It is concluded that the maximum calculated contact stress ( $\sigma_{\max}$ ) from [Formula \(8\)](#) occurs at the line of  $y = 0$ ,

$$\sigma_{\max} = \frac{2Q}{\pi L_{we} b} \text{ or } Q = \frac{\pi L_{we} b}{2} \sigma_{\max} \quad (9)$$

And also  $b$  is given by the following formula,

$$b = \left[ \frac{4Q}{\pi L_{we} \Sigma \rho} \left( \frac{1 - \nu_1^2}{E_1} + \frac{1 - \nu_2^2}{E_2} \right) \right]^{1/2} \quad (10)$$

where

$$\begin{aligned} \Sigma \rho &= \rho_{11} + \rho_{12} + \rho_{21} + \rho_{22} \\ \rho_{11} &= \frac{2}{D_{we}} \\ \rho_{21} &= \pm \frac{2}{D_{we}} \frac{\gamma}{1 \mp \gamma}; \text{ the upper sign applies to inner ring contact and the lower to outer ring contact;} \\ \rho_{12} &= 0 \\ \rho_{22} &= 0 \\ \gamma &= \frac{D_{we} \cos \alpha}{D_{pw}} \end{aligned}$$

**TeH STANDARD**

**PREVIEW**

(standards.iteh.ai)

[SIST-TP ISO/TR 10657:2022](https://standards.iteh.ai/catalog/standards/sist/a1d47d45-6f4a-4073-817a-15b64116ee55/sist-tp-iso-tr-10657-2022)

<https://standards.iteh.ai/catalog/standards/sist/a1d47d45-6f4a-4073-817a-15b64116ee55/sist-tp-iso-tr-10657-2022>

Substituting [Formula \(10\)](#) into [Formula \(9\)](#) for the case of  $E_1 = E_2 = E$  and  $\nu_1 = \nu_2 = \nu$ ,

$$Q = 2\pi \sigma_{\max}^2 \frac{L_{we}}{E_0 \Sigma \rho}$$

where

$$\begin{aligned} E_0 &= \frac{E}{1 - \nu^2} \\ E &= 2,07 \times 10^5 \text{ MPa} \\ \nu &= 0,3 \end{aligned}$$

Consequently,

$$Q = 2,7621732 \times 10^{-5} \frac{L_{we}}{\Sigma \rho} \sigma_{\max}^2 \quad (11)$$