INTERNATIONAL STANDARD

Second edition 2018-02

Jewellery — Colours of gold alloys — Definition, range of colours and designation

Joaillerie, bijouterie — Couleurs des alliages d'or — Définition, gamme de couleurs et désignation

iTeh STANDARD PREVIEW (standards.iteh.ai)

ISO 8654:2018 https://standards.iteh.ai/catalog/standards/sist/6f0aad7c-ce6d-4930-a0cd-3361fd8f5728/iso-8654-2018



Reference number ISO 8654:2018(E)

iTeh STANDARD PREVIEW (standards.iteh.ai)

ISO 8654:2018 https://standards.iteh.ai/catalog/standards/sist/6f0aad7c-ce6d-4930-a0cd-3361fd8f5728/iso-8654-2018



COPYRIGHT PROTECTED DOCUMENT

© ISO 2018

All rights reserved. Unless otherwise specified, or required in the context of its implementation, no part of this publication may be reproduced or utilized otherwise in any form or by any means, electronic or mechanical, including photocopying, or posting on the internet or an intranet, without prior written permission. Permission can be requested from either ISO at the address below or ISO's member body in the country of the requester.

ISO copyright office CP 401 • Ch. de Blandonnet 8 CH-1214 Vernier, Geneva, Switzerland Tel. +41 22 749 01 11 Fax +41 22 749 09 47 copyright@iso.org www.iso.org

Published in Switzerland

Page

Contents

Forew	vord		iv		
Intro	duction		v		
1	Scope		1		
2	Norm	ative references			
3	Terms	s and definitions			
4	Desig	nation	1		
5	Colour measurement				
	5.1	General			
	5.2	Quantitative method			
		5.2.1 Preparation of the samples			
		5.2.2 Measurement apparatus			
		5.2.3 Measurement method			
	5.3	Qualitative method			
6	Gold a	illoy colours			
Annex	x A (info	ormative) Recommended chemical composition of colour slips	8		
Biblio	graphy	7	9		

iTeh STANDARD PREVIEW (standards.iteh.ai)

ISO 8654:2018 https://standards.iteh.ai/catalog/standards/sist/6f0aad7c-ce6d-4930-a0cd-3361fd8f5728/iso-8654-2018

Foreword

ISO (the International Organization for Standardization) is a worldwide federation of national standards bodies (ISO member bodies). The work of preparing International Standards is normally carried out through ISO technical committees. Each member body interested in a subject for which a technical committee has been established has the right to be represented on that committee. International organizations, governmental and non-governmental, in liaison with ISO, also take part in the work. ISO collaborates closely with the International Electrotechnical Commission (IEC) on all matters of electrotechnical standardization.

The procedures used to develop this document and those intended for its further maintenance are described in the ISO/IEC Directives, Part 1. In particular the different approval criteria needed for the different types of ISO documents should be noted. This document was drafted in accordance with the editorial rules of the ISO/IEC Directives, Part 2 (see www.iso.org/directives).

Attention is drawn to the possibility that some of the elements of this document may be the subject of patent rights. ISO shall not be held responsible for identifying any or all such patent rights. Details of any patent rights identified during the development of the document will be in the Introduction and/or on the ISO list of patent declarations received (see www.iso.org/patents).

Any trade name used in this document is information given for the convenience of users and does not constitute an endorsement.

For an explanation on the voluntary nature of standards, the meaning of ISO specific terms and expressions related to conformity assessment, as well as information about ISO's adherence to the World Trade Organization (WTO) principles in the Technical Barriers to Trade (TBT) see the following URL: www.iso.org/iso/foreword.html. (standards.iteh.ai)

This document was prepared by Technical Committee ISO/TC 174, Jewellery.

This second edition cancels and replaces the first/edition/(ISO(8654:1987)) which has been technically revised with the following changes: 3361fd8f5728/iso-8654-2018

- add a new colour definition: dark red (6N);
- describe a detailed metallographic preparation for the colour measurement;
- add tables for nominal values and tolerances for L*a*b* and L*C*h;
- add figures representing de tolerances in different colour spaces;
- the document was editorially revised.

Introduction

In the manufacture and sale of articles made of or coated with gold alloys, the colour of the surface of the product is an important characteristic.

This document will enable the purchaser to define his requirements with precision by referring to the designations given within this document and so avoids the need for purchasing orders to be accompanied by colour samples.

iTeh STANDARD PREVIEW (standards.iteh.ai)

ISO 8654:2018 https://standards.iteh.ai/catalog/standards/sist/6f0aad7c-ce6d-4930-a0cd-3361fd8f5728/iso-8654-2018

iTeh STANDARD PREVIEW (standards.iteh.ai)

ISO 8654:2018 https://standards.iteh.ai/catalog/standards/sist/6f0aad7c-ce6d-4930-a0cd-3361fd8f5728/iso-8654-2018

Jewellery — Colours of gold alloys — Definition, range of colours and designation

1 Scope

This document specifies a limited number of colours of gold alloy and the method to measure colours.

It applies to objects made of gold alloys or coated by gold alloys.

2 Normative references

The following documents are referred to in the text in such a way that some or all of their content constitutes requirements of this document. For dated references, only the edition cited applies. For undated references, the latest edition of the referenced document (including any amendments) applies.

CIE Publication No. 15, Colorimetry

3 Terms and definitions

For the purposes of this document, the following terms and definitions apply.

ISO and IEC maintain terminological databases for use in standardization at the following addresses:

- ISO Online browsing platform: available at https://www.iso.org/obp
- IEC Electropedia: available at http://www.electropedia.org/d-4930-a0cd-

3.1

colour

three-dimensional space represented by the chromaticity coordinates x and y and Y

Note 1 to entry: As defined in CIE Publication No. 15, the values of Y correspond to the percentage values of the luminous reflectance factor.

Note 2 to entry: When necessary for special purposes or in the field of national standardization, the chromaticity coordinates may be converted according to CIE Publication No. 15 to other nationally or internationally agreed systems (e.g. CIE 1976 $L^*a^*b^*$ colour space or CIE 1976 $L^*u^*v^*$ colour space).

4 Designation

Seven designations of colours according to chromaticity coordinates are defined in <u>Table 1</u>.

Colour	Designation			
0N	yellow green			
1N	pale yellow			
2N	light yellow			
3N	yellow			
4N	pink			
5N	red			
6N	dark red			

Table 1 — Designation of colours

5 Colour measurement

5.1 General

Two methods are available to determine the colour, a quantitative method (see 5.2) and a qualitative method by visual comparison (see 5.3).

5.2 Quantitative method

5.2.1 Preparation of the samples

5.2.1.1 General

The samples to be measured shall have a flat and polished surface to be used as a measurement area.

The measurement area shall be exempt of defect.

The finishing (polishing and washing) shall be (re)done until a mirror surface is achieved (Y reaches a constant value).

After polishing, the sample colour measurement shall be made within 120 min maximum.

NOTE Polishing, washing and environment conditions can greatly affect the colour.

5.2.1.2 Metallographic preparation TANDARD PREVIEW

Metallographic preparation is made with a final polishing with broadcloth charged with an abrasive solution. The solution contains 1 μ m sized abrasive particles.

ISO 8654:2018

5.2.1.3 Sample cleaninghttps://standards.iteh.ai/catalog/standards/sist/6f0aad7c-ce6d-4930-a0cd-

3361fd8f5728/iso-8654-2018

The recommended sample cleaning is done by gently wiping the surface with a clean soft cloth (microfibre) and some isopropylalcohol (IPA).

5.2.2 Measurement apparatus

5.2.2.1 General

The measurement apparatus for the colour measurement of a gold alloy shall be in accordance to CIE Publication No. 15.

5.2.2.2 Reference apparatus

The reference apparatus for the colour measurement of a gold alloy is an integrating sphere spectrophotometer able to measure spectral reflectance, with a measurement geometry compatible with designation di:8° or 8°:di (specular component included).

NOTE Other measurement geometries can be used as long as they do not affect significantly the colour results compared to the described measurement geometry.

5.2.2.3 Spectrophotometer setup

Before making any measurement, the apparatus shall be set up with the following parameters:

- Specular Component Included (SCI);
- Standard illuminant D65;

Standard observer 2°.

5.2.3 Measurement method

Measure the spectral reflectance.

The measured values in the xyY colour space shall be expressed with 4 significant digits for x and y and 1 significant digit for Y.

The measured or converted values in the $L^*a^*b^*$ colour space shall be indicated with 2 significant digits for a^* and b^* or C^* and h and 1 significant digit for L^* .

The colour measure is an average of 5 distinct measurements of the sample (after repositioning) ensuring to revolve it between each measurement.

5.3 Qualitative method

For (visual) comparison purposes of the sample, it is possible to use a range of polished colour slips.

A preparation of colour slips is described in <u>Annex A</u>.

6 Gold alloy colours

Nominal values and tolerances of colours are given in <u>Table 2</u>, 3 and <u>4</u> in accordance with <u>5.2</u>. Figures 1, 2, 3, <u>4</u> illustrate graphically nominal and tolerances values.

NOTE The eye of a trained person can see colour differences even within a tolerance range.

	ups://standards.iter	3361 fd8f5728/i	sachter	-ceou-4950-aucu	-	
Colour	Nominal values			Tolerances		
	X	y	Y	x	y	Y (max/min)
	0,346 3	0,371 4	84,9	0,351 3	0,373 6	88,6
				0,344 8	0,366 0	
UN				0,341 5	0,368 9	81,2
				0,347 4	0,377 0	
	0,353 2	0,370 8	81,5	0,357 4	0,372 5	85,2
1.1				0,351 3	0,366 6	
				0,349 1	0,369 0	77,8
				0,354 8	0,375 2	
	0,361 0	0,376 9	78,8	0,365 0	0,378 2	82,5
2N				0,359 3	0,372 9	
21				0,357 1	0,375 4	75,0
				0,362 4	0,381 0	
	0,361 6	0,371 4	76,2	0,366 2	0,373 0	79,9
3N				0,359 1	0,367 2	
51				0,357 1	0,369 7	72,4
				0,363 9	0,375 9	

Table 2 — Nominal values and tolerances for xyY