

---

---

**Fine ceramics (advanced ceramics,  
advanced technical ceramics) —  
Silicon nitride materials for rolling  
bearing balls and rollers**

*Céramiques techniques — Matériaux en nitrure de silicium pour billes  
utilisées dans les roulements à billes*

**iTeh STANDARD PREVIEW**  
**(standards.iteh.ai)**

[ISO 26602:2017](https://standards.iteh.ai/catalog/standards/sist/ab41af89-0bfe-43f0-a358-f635e527b263/iso-26602-2017)

[https://standards.iteh.ai/catalog/standards/sist/ab41af89-0bfe-43f0-a358-  
f635e527b263/iso-26602-2017](https://standards.iteh.ai/catalog/standards/sist/ab41af89-0bfe-43f0-a358-f635e527b263/iso-26602-2017)



**iTeh STANDARD PREVIEW**  
**(standards.iteh.ai)**

[ISO 26602:2017](https://standards.iteh.ai/catalog/standards/sist/ab41af89-0bfe-43f0-a358-f635e527b263/iso-26602-2017)

<https://standards.iteh.ai/catalog/standards/sist/ab41af89-0bfe-43f0-a358-f635e527b263/iso-26602-2017>



**COPYRIGHT PROTECTED DOCUMENT**

© ISO 2017, Published in Switzerland

All rights reserved. Unless otherwise specified, no part of this publication may be reproduced or utilized otherwise in any form or by any means, electronic or mechanical, including photocopying, or posting on the internet or an intranet, without prior written permission. Permission can be requested from either ISO at the address below or ISO's member body in the country of the requester.

ISO copyright office  
Ch. de Blandonnet 8 • CP 401  
CH-1214 Vernier, Geneva, Switzerland  
Tel. +41 22 749 01 11  
Fax +41 22 749 09 47  
[copyright@iso.org](mailto:copyright@iso.org)  
[www.iso.org](http://www.iso.org)

# Contents

	Page
Foreword .....	iv
<b>1 Scope</b> .....	<b>1</b>
<b>2 Normative references</b> .....	<b>1</b>
<b>3 Terms and definitions</b> .....	<b>1</b>
<b>4 Physical and mechanical properties</b> .....	<b>2</b>
<b>5 Material classification</b> .....	<b>2</b>
<b>6 Test</b> .....	<b>3</b>
6.1 Density .....	3
6.2 Elastic modulus .....	3
6.3 Poisson's ratio .....	3
6.4 Coefficient of thermal expansion .....	3
6.5 Flexural strength and Weibull modulus .....	3
6.6 Hardness .....	3
6.7 Indentation fracture resistance .....	3
6.8 Microstructure .....	3
<b>7 Test report</b> .....	<b>4</b>
<b>Annex A (normative) Microstructure observation procedure</b> .....	<b>5</b>
<b>Annex B (normative) Material classification for silicon nitride materials</b> .....	<b>6</b>
<b>Bibliography</b> .....	<b>7</b>

ITeH STANDARD PREVIEW  
(standards.iteh.ai)

[ISO 26602:2017](https://standards.iteh.ai/catalog/standards/sist/ab41af89-0bfe-43f0-a358-f635e527b263/iso-26602-2017)

<https://standards.iteh.ai/catalog/standards/sist/ab41af89-0bfe-43f0-a358-f635e527b263/iso-26602-2017>

## Foreword

ISO (the International Organization for Standardization) is a worldwide federation of national standards bodies (ISO member bodies). The work of preparing International Standards is normally carried out through ISO technical committees. Each member body interested in a subject for which a technical committee has been established has the right to be represented on that committee. International organizations, governmental and non-governmental, in liaison with ISO, also take part in the work. ISO collaborates closely with the International Electrotechnical Commission (IEC) on all matters of electrotechnical standardization.

The procedures used to develop this document and those intended for its further maintenance are described in the ISO/IEC Directives, Part 1. In particular the different approval criteria needed for the different types of ISO documents should be noted. This document was drafted in accordance with the editorial rules of the ISO/IEC Directives, Part 2 (see [www.iso.org/directives](http://www.iso.org/directives)).

Attention is drawn to the possibility that some of the elements of this document may be the subject of patent rights. ISO shall not be held responsible for identifying any or all such patent rights. Details of any patent rights identified during the development of the document will be in the Introduction and/or on the ISO list of patent declarations received (see [www.iso.org/patents](http://www.iso.org/patents)).

Any trade name used in this document is information given for the convenience of users and does not constitute an endorsement.

For an explanation on the voluntary nature of standards, the meaning of ISO specific terms and expressions related to conformity assessment, as well as information about ISO's adherence to the World Trade Organization (WTO) principles in the Technical Barriers to Trade (TBT) see the following URL: [www.iso.org/iso/foreword.html](http://www.iso.org/iso/foreword.html). (standards.iteh.ai)

This document was prepared by Technical Committee ISO/TC 206, *Fine ceramics*.

This second edition cancels and replaces the first edition (ISO 26602:2009), which has been technically revised.

The main changes compared to the previous edition are as follows:

- the title has been revised;
- [Clauses 1, 2, 3, 5, 6](#) have been revised;
- [Annex A](#) has been revised;
- [Table B.1](#) has been revised;
- bibliography has been revised.

# Fine ceramics (advanced ceramics, advanced technical ceramics) — Silicon nitride materials for rolling bearing balls and rollers

## 1 Scope

This document specifies the requirements for preprocessed silicon nitride materials for rolling bearing balls and rollers.

This document provides a classification defining physical and mechanical properties of silicon nitride preprocessed bearing rolling element materials. The materials are classified in three categories by the specification of characteristics and microstructures. Methods for sample preparation and observation of microstructures are provided in [Annex A](#).

NOTE 1 The silicon nitride product means the sintered body of which the main component is silicon nitride material.

NOTE 2 This document can be used for processed rolling bearing balls and rollers upon consultation between the parties concerned.

## 2 Normative references

iTeh STANDARD PREVIEW  
(standards.iteh.ai)

The following documents are referred to in the text in such a way that some or all of their content constitutes requirements of this document. For dated references, only the edition cited applies. For undated references, the latest edition of the referenced document (including any amendments) applies.

ISO 14627, *Fine ceramics (advanced ceramics, advanced technical ceramics) — Test method for fracture resistance of silicon nitride materials for rolling bearing balls at room temperature by indentation fracture (IF) method*

ISO 14704, *Fine ceramics (advanced ceramics, advanced technical ceramics) — Test method for flexural strength of monolithic ceramics at room temperature*

ISO 14705, *Fine ceramics (advanced ceramics, advanced technical ceramics) — Test method for hardness of monolithic ceramics at room temperature*

ISO 17561, *Fine ceramics (advanced ceramics, advanced technical ceramics) — Test method for elastic moduli of monolithic ceramics at room temperature by sonic resonance*

ISO 17562, *Fine ceramics (advanced ceramics, advanced technical ceramics) — Test method for linear thermal expansion of monolithic ceramics by push-rod technique*

ISO 18754, *Fine ceramics (advanced ceramics, advanced technical ceramics) — Determination of density and apparent porosity*

ISO 20501, *Fine ceramics (advanced ceramics, advanced technical ceramics) — Weibull statistics for strength data*

ISO 20507, *Fine ceramics (advanced ceramics, advanced technical ceramics) — Vocabulary*

## 3 Terms and definitions

For the purposes of this document, the terms and definitions given in ISO 20507 and the following apply.

ISO and IEC maintain terminological databases for use in standardization at the following addresses:

- ISO Online browsing platform: available at <http://www.iso.org/obp>
- IEC Electropedia: available at <http://www.electropedia.org/>

**3.1 fracture resistance**

$K_{I, IFR}$   
resistance measured in accordance with the indentation fracture (IF) method

Note 1 to entry: This method is specified in ISO 14627.

**3.2 inclusion**  
region that differs from the normal silicon nitride microstructure

Note 1 to entry: Typical inclusions in the Si<sub>3</sub>N<sub>4</sub> ceramics for rolling bearing balls and rollers are coarser agglomerates of sintering additives and impurities of foreign composition than the normal Si<sub>3</sub>N<sub>4</sub> constituents.

**3.3 material lot**  
defined quantity of raw material ready for the shaping and densification of roller shapes and/or test items

**3.4 material class**  
specific combination of physical and mechanical properties of the silicon nitride material

**3.5 preprocessed rolling bearing balls and rollers**  
densified unit of material from a material lot before final shaping and finishing

**3.6 processed rolling bearing balls and rollers**  
rolling bearing balls and rollers after final shaping and finishing

iTech STANDARD PREVIEW  
(standards.iteh.ai)  
ISO 26602:2017

**4 Physical and mechanical properties**

Typical ranges of physical and mechanical properties of a preprocessed rolling element are given in [Table 1](#). Physical and mechanical properties shall be measured in accordance with [6.1](#) to [6.4](#). Values for thermal conductivity, specific heat and electrical resistivity are subject to agreement between the parties concerned.

**Table 1 — Physical and mechanical properties**

Properties	Minimum	Maximum
Density (g/cm <sup>3</sup> )	3,0	3,6
Elastic modulus (GPa)	270	330
Poisson's ratio	0,23	0,29
Coefficient of thermal expansion, × 10 <sup>-6</sup> /°C (applicable range: room temperature to 500 °C)	2,0	3,7

**5 Material classification**

Silicon nitride materials for rolling bearing balls and rollers shall be divided into three classes according to the physical and mechanical properties of the material, as specified in [Annex B](#).

## 6 Test

### 6.1 Density

Preprocessed rolling bearing balls or rollers shall be used as the test specimens.

The test shall be conducted in accordance with ISO 18754.

### 6.2 Elastic modulus

Test pieces shall be fabricated from the same material lot as the preprocessed rolling bearing balls and rollers.

The test shall be conducted in accordance with ISO 17561.

### 6.3 Poisson's ratio

Test pieces shall be fabricated from the same material lot as the preprocessed rolling bearing balls and rollers.

The test shall be conducted in accordance with ISO 17561.

### 6.4 Coefficient of thermal expansion

Test pieces shall be fabricated from the same material lot as the preprocessed rolling bearing balls and rollers.

The test shall be conducted in accordance with ISO 17562.

### 6.5 Flexural strength and Weibull modulus

Test pieces shall be fabricated from the same material lot as the preprocessed rolling bearing balls and rollers.

Average values for flexural strength at room temperature and Weibull modulus shall be evaluated in accordance with ISO 14704 and ISO 20501. Either 4-point or 3-point test methods may be used for flexural strength.

### 6.6 Hardness

Polished sections of the preprocessed rolling bearing balls and rollers shall be used for the test.

Average values for Vickers hardness shall be evaluated in accordance with ISO 14705. The recommended test force shall be HV20, and HV5 and HV10 are also allowed if the sample is too small to be indented.

### 6.7 Indentation fracture resistance

**6.7.1** Polished sections of the preprocessed rolling bearing balls and rollers shall be used for the indentation fracture (IF) method. The surface finishing shall be carried out to avoid residual stress.

**6.7.2** Average values for fracture resistance in the indentation fracture (IF) method shall be evaluated in accordance with ISO 14627.

### 6.8 Microstructure

Polished sections of the preprocessed rolling bearing balls and rollers shall be used for microstructure inspection. Sample preparation and observation shall be conducted as described in [Annex A](#).

## 7 Test report

The test report shall include the following information:

- a) a reference to this document, i.e. ISO 26602;
- b) the date of the test;
- c) the raw powder lot;
- d) the test results:
  - 1) density;
  - 2) elastic modulus;
  - 3) Poisson's ratio;
  - 4) coefficient of thermal expansion;
  - 5) average flexural strength and average Weibull modulus;
  - 6) Vickers hardness (test conditions, average hardness);
  - 7) average fracture toughness and fracture resistance (test method, average fracture toughness or fracture resistance);
  - 8) microstructure (sizes and numbers of pores and inclusions);
- e) the material class;
- f) any additional information relevant to the evaluation.

**ITeCh STANDARD PREVIEW**  
**(standards.iteh.ai)**  
ISO 26602:2017  
<https://standards.iteh.ai/catalog/standards/sist/ab41af89-0bfe-43f0-a358-f635e527b263/iso-26602-2017>



## Annex A (normative)

### Microstructure observation procedure

**WARNING — This annex describes general methods for sample preparation and the observation methods for silicon nitride rolling bearing element materials. However, because there is no formally standardized ISO procedure and definitive methods for microstructure observation are not available, some aspects of evaluation may need to be agreed between parties.**

#### A.1 Sample preparation

Sections of silicon nitride rolling bearing balls and rollers shall be prepared by cutting, grinding and lapping. The sections shall be polished using either of the following two methods.

- a) After rough polishing with diamond powders of less than 50 µm in diameter, the sections shall be polished using abrasive powders such as alumina or diamond with sizes of less than or equal to 1 µm.
- b) After rough polishing with diamond powders of less than 50 µm in diameter, the sections shall be chemically polished with abrasive powders such as cerium oxide, chromium oxide or iron oxide.

In either case, the sections shall be polished until grinding scratches disappear, and shall then be ultrasonically cleaned.

**iTeh STANDARD PREVIEW**  
**(standards.iteh.ai)**

#### A.2 Observation

ISO 26602:2017

[https://standards.iteh.ai/catalog/standards/sist/ab41af89-0bfe-43f0-a358-](https://standards.iteh.ai/catalog/standards/sist/ab41af89-0bfe-43f0-a358-635e527b263/iso-26602-2017)

[635e527b263/iso-26602-2017](https://standards.iteh.ai/catalog/standards/sist/ab41af89-0bfe-43f0-a358-635e527b263/iso-26602-2017)

The section shall be placed on the stage of an optical microscope. The number or total area of sections to be examined shall be agreed between parties depending on the bearing size and the application conditions. Pores and inclusions shall be searched for with a 100x to 200x magnification. The number and size of any pores and inclusions found shall be determined, and the pore size and inclusion size shall be identified by their maximum size in the section. Alternatively, the size and number of pores and inclusions may be determined by a scanning electron microscope (SEM), secondary electron image or backscatter electron image, as necessary.

#### A.3 Additional remarks

The observed portion depends on the size and shape of the ball and roller and the application condition of the bearing; it may be recommended that these be determined between parties to the characterization.

Colour variation is a very difficult problem to be clarified, which may also require discussion between suppliers and their customers. If the volume rating of porosity is required, it is recommended that the methodology in ISO 4499-4 for hard metals be adopted. Observation of the macrostructure at lower magnification may be useful for reviewing visible cracks and defects.