



SLOVENSKI STANDARD

SIST EN 13601:2021

01-september-2021

Nadomešča:
SIST EN 13601:2013

Baker in bakrove zlitine - Drogovi, palice in žice za splošno uporabo v elektrotehniki

Copper and copper alloys - Copper rod, bar and wire for general electrical purposes

Kupfer und Kupferlegierungen - Stangen und Drähte aus Kupfer für die allgemeine Anwendung in der Elektrotechnik

Cuivre et alliages de cuivre - Barres et fils en cuivre pour usages électriques généraux

[SIST EN 13601:2021](https://standards.iteh.ai/catalog/standards/sist/828df151-21e4-4485-a5b9-c67d05c1cbb7/sist-en-13601-2021)

Ta slovenski standard je istoveten z: EN 13601:2021

ICS:

77.150.30 Bakreni izdelki Copper products

SIST EN 13601:2021 **en,fr,de**

iTeh STANDARD PREVIEW
(standards.iteh.ai)

SIST EN 13601:2021

<https://standards.iteh.ai/catalog/standards/sist/828dfd51-21e4-4485-a5b9-cb9d03cfcbb7/sist-en-13601-2021>

EUROPEAN STANDARD

EN 13601

NORME EUROPÉENNE

EUROPÄISCHE NORM

May 2021

ICS 77.150.30

Supersedes EN 13601:2013

English Version

Copper and copper alloys - Copper rod, bar and wire for general electrical purposes

Cuivre et alliages de cuivre - Barres et fils en cuivre
pour usages électriques généraux

Kupfer und Kupferlegierungen - Stangen und Drähte
aus Kupfer für die allgemeine Anwendung in der
Elektrotechnik

This European Standard was approved by CEN on 12 April 2021.

CEN members are bound to comply with the CEN/CENELEC Internal Regulations which stipulate the conditions for giving this European Standard the status of a national standard without any alteration. Up-to-date lists and bibliographical references concerning such national standards may be obtained on application to the CEN-CENELEC Management Centre or to any CEN member.

This European Standard exists in three official versions (English, French, German). A version in any other language made by translation under the responsibility of a CEN member into its own language and notified to the CEN-CENELEC Management Centre has the same status as the official versions.

CEN members are the national standards bodies of Austria, Belgium, Bulgaria, Croatia, Cyprus, Czech Republic, Denmark, Estonia, Finland, France, Germany, Greece, Hungary, Iceland, Ireland, Italy, Latvia, Lithuania, Luxembourg, Malta, Netherlands, Norway, Poland, Portugal, Republic of North Macedonia, Romania, Serbia, Slovakia, Slovenia, Spain, Sweden, Switzerland, Turkey and United Kingdom.



EUROPEAN COMMITTEE FOR STANDARDIZATION
COMITÉ EUROPÉEN DE NORMALISATION
EUROPÄISCHES KOMITEE FÜR NORMUNG

CEN-CENELEC Management Centre: Rue de la Science 23, B-1040 Brussels

Contents	Page
European foreword	4
Introduction	5
1 Scope.....	6
2 Normative references.....	6
3 Terms and definitions	7
4 Designations	7
4.1 Material	7
4.1.1 General.....	7
4.1.2 Symbol	7
4.1.3 Number	7
4.2 Material condition	8
4.3 Product	8
5 Ordering information.....	9
6 Requirements.....	11
6.1 Composition.....	11
6.2 Mechanical properties	11
6.3 Bending characteristics.....	11
6.4 Electrical properties	11
6.5 Freedom from hydrogen embrittlement.....	11
6.6 Dimensions and tolerances.....	11
6.6.1 Diameter or width across flats.....	11
6.6.2 Corner configuration	11
6.6.3 Length.....	13
6.7 Form tolerances	13
6.7.1 General.....	13
6.7.2 Twist	13
6.7.3 Straightness	14
6.7.4 Flatness of bar	15
6.8 Wire in coils	15
6.9 Mass tolerances	15
6.10 Surface condition	15
7 Sampling.....	15
7.1 General.....	15
7.2 Analysis	15
7.3 Mechanical and electrical tests.....	16
8 Test methods	16
8.1 Analysis	16
8.2 Tensile test.....	16
8.3 Hardness test.....	16
8.4 Bend test	16
8.5 Electrical resistivity test.....	17
8.6 Hydrogen embrittlement test.....	17
8.7 Retests.....	17

8.8	Rounding of results.....	17
9	Declaration of conformity and inspection documentation	18
9.1	Declaration of conformity	18
9.2	Inspection documentation	18
10	Marking, packaging, labelling	18
Annex A (informative) Characteristics of coppers for electrical purposes		27
A.1	General grouping of copper types	27
A.2	General characteristics.....	27
A.3	Particular characteristics	27
Bibliography		29

iTeh STANDARD PREVIEW **(standards.iteh.ai)**

[SIST EN 13601:2021](#)

<https://standards.iteh.ai/catalog/standards/sist/828dfd51-21e4-4485-a5b9-cb9d03cfcbb7/sist-en-13601-2021>

EN 13601:2021 (E)**European foreword**

This document (EN 13601:2021) has been prepared by Technical Committee CEN/TC 133 “Copper and copper alloys”, the secretariat of which is held by DIN.

This European Standard shall be given the status of a national standard, either by publication of an identical text or by endorsement, at the latest by November 2021, and conflicting national standards shall be withdrawn at the latest by November 2021.

Attention is drawn to the possibility that some of the elements of this document may be the subject of patent rights. CEN shall not be held responsible for identifying any or all such patent rights.

This document supersedes EN 13601:2013.

In comparison with the previous edition, the following technical modifications have been made:

- maximum diameters or widths across flats for bar, square, hexagonal and rectangular have been expanded;
- the Scope has been modified;
- in Clause 6.5, Freedom from hydrogen embrittlement, the alloys Cu-OFE (CW009A) and Cu-PHCE (CW022A) have been added;
- Table 3 has been modified to correct incongruent values;
- tolerances on width and thickness of bar and rectangular wire and maximum twist of square or hexagonal rod or rectangular bar have been modified (see Table 6 and Table 10).

According to the CEN-CENELEC Internal Regulations, the national standards organisations of the following countries are bound to implement this European Standard: Austria, Belgium, Bulgaria, Croatia, Cyprus, Czech Republic, Denmark, Estonia, Finland, France, Germany, Greece, Hungary, Iceland, Ireland, Italy, Latvia, Lithuania, Luxembourg, Malta, Netherlands, Norway, Poland, Portugal, Republic of North Macedonia, Romania, Serbia, Slovakia, Slovenia, Spain, Sweden, Switzerland, Turkey and the United Kingdom.

Introduction

The products specified in this document are those which are especially suitable for electrical purposes, i.e. with specified electrical properties. Copper rod, bar and wire for general purposes are specified in EN 12163, EN 12166 and EN 12167.

Annex A (informative) gives guidance on the characteristics of coppers for electrical purposes.

This is one document of a series of European Standards for copper products for electrical purposes. Other copper products are specified as follows:

- EN 13599, *Copper and copper alloys — Copper plate, sheet and strip for electrical purposes*
- EN 13600, *Copper and copper alloys — Seamless copper tubes for electrical purposes*
- EN 13602, *Copper and copper alloys — Drawn, round copper wire for the manufacture of electrical conductors*
- EN 13604, *Copper and copper alloys — Semiconductor devices, electronic and vacuum products made from high conductivity copper*
- EN 13605, *Copper and copper alloys — Copper profiles and profiled wire for electrical purposes*

iTeh STANDARD PREVIEW (standards.iteh.ai)

[SIST EN 13601:2021](https://standards.iteh.ai/catalog/standards/sist/828dfd51-21e4-4485-a5b9-cb9d03cfcbb7/sist-en-13601-2021)

<https://standards.iteh.ai/catalog/standards/sist/828dfd51-21e4-4485-a5b9-cb9d03cfcbb7/sist-en-13601-2021>

EN 13601:2021 (E)**1 Scope**

This document specifies the composition, property requirements including electrical properties, and tolerances on dimensions and form for copper rod, bar and wire for general electrical purposes. Cross-sections and size ranges are:

- round, square and hexagonal rod with diameters or widths across-flats from 2 mm up to and including 160 mm;
- bar with thicknesses from 2 mm up to and including 40 mm and widths from 3 mm up to and including 250 mm;
- round, square, hexagonal and rectangular wire with diameters or widths across-flats from 2 mm up to and including 25 mm, as well as thicknesses from 0,5 mm up to and including 12 mm with widths from 1 mm up to and including 250 mm.

The sampling procedures and test methods for verification of conformity to the requirements of this document are also specified.

NOTE Drawn, round copper wire, plain or tinned, single or multilined, for the manufacture of electrical conductors is specified in EN 13602.

2 Normative references

The following documents are referred to in the text in such a way that some or all of their content constitutes requirements of this document. For dated references, only the edition cited applies. For undated references, the latest edition of the referenced document (including any amendments) applies.

EN 1976, *Copper and copper alloys - Cast unwrought copper products*

<https://standards.iteh.ai/catalog/standards/sist/828dfd51-21e4-4485-a5b9->

EN ISO 2626, *Copper - Hydrogen embrittlement test (ISO 2626)* 1-2021

EN ISO 6506-1, *Metallic materials - Brinell hardness test - Part 1: Test method (ISO 6506-1)*

EN ISO 6507-1, *Metallic materials - Vickers hardness test - Part 1: Test method (ISO 6507-1)*

EN ISO 6892-1, *Metallic materials - Tensile testing - Part 1: Method of test at room temperature (ISO 6892-1)*

EN ISO 7438, *Metallic materials - Bend test (ISO 7438)*

IEC 60468, *Method of measurement of resistivity of metallic materials*

3 Terms and definitions

For the purposes of this document, the following terms and definitions apply.

ISO and IEC maintain terminological databases for use in standardization at the following addresses:

- ISO Online browsing platform: available at <https://www.iso.org/obp>
- IEC Electropedia: available at <https://www.electropedia.org/>

3.1

bar

straight product of uniform rectangular cross-section along its whole length

[SOURCE: EN 12167:2016, 3.2]

3.2

rod

straight product of uniform cross-section along its whole length

[SOURCE: EN 12163:2016, 3.1]

3.3

wire

wound product of uniform cross-section along its whole length

Note 1 to entry: Rectangles may have round or sharp corners.

[SOURCE: EN 12166:2016, 3.1]

[SIST EN 13601:2021](https://standards.iteh.ai/catalog/standards/sist/828dfd51-21e4-4485-a5b9-cb9d03cfcbb7/sist-en-13601-2021)

<https://standards.iteh.ai/catalog/standards/sist/828dfd51-21e4-4485-a5b9-cb9d03cfcbb7/sist-en-13601-2021>

3.4

deviation from circular form

difference between the maximum and the minimum diameters measured at any one cross-section of a round product

[SOURCE: EN 12163:2016, 3.2]

4 Designations

4.1 Material

4.1.1 General

The material is designated either by symbol or by number (see Table 1 and Table 2).

4.1.2 Symbol

The material symbol designation is based on the designation system given in ISO 1190-1.

NOTE Although material symbol designations used in this document might be the same as those in other standards using the designation system given in ISO 1190-1, the detailed composition requirements are not necessarily the same.

4.1.3 Number

The material number designation is in accordance with the system given in EN 1412.

EN 13601:2021 (E)**4.2 Material condition**

For the purposes of this document, the following designations, which are in accordance with the system given in EN 1173, apply for the material condition:

- D Material condition for the product as cold worked without specified mechanical properties;
- H... Material condition designated by the minimum value of hardness requirement for the product with mandatory hardness requirements;
- R... Material condition designated by the minimum value of tensile strength requirement for the product with mandatory tensile strength, 0,2 % proof strength and elongation requirements.

Products in the H... condition may be specified to Vickers or Brinell hardness. The material condition designation H... is the same for both hardness test methods.

Exact conversion between the material conditions designated H... and R... is not possible.

Material condition is designated by only one of the above designations.

4.3 Product

The product designation provides a standardized pattern of designation from which a rapid and unequivocal description of a product can be conveyed in communication. It provides mutual comprehension at the international level with regard to products which meet the requirements of the relevant European Standard.

The product designation is no substitute for the full content of the standard.

The product designation for products to this document shall consist of:

- a) denomination (rod, bar or wire); [SIST EN 13601:2021](https://standards.iteh.ai/catalog/standards/sist/828dfd51-21e4-4485-a5b9-ch9d03cfcbb7/sist-en-13601-2021)
- b) number of this document (EN 13601); <https://standards.iteh.ai/catalog/standards/sist/828dfd51-21e4-4485-a5b9-ch9d03cfcbb7/sist-en-13601-2021>
- c) material designation, either symbol or number (see Table 1 and Table 2);
- d) material condition designation (see Table 3);
- e) cross-sectional shape (the following designations shall be used as appropriate: RND for round, SQR for square, HEX for hexagonal);
- f) nominal cross-sectional dimensions:
 - 1) round rod or wire: diameter;
 - 2) square or hexagonal rod or wire: width across-flats;
 - 3) bar or rectangular wire: thickness × width;
- g) tolerance class for round, square or hexagonal rod or wire (see Table 5);
- h) corner type for square or hexagonal rod, bar or rectangular wire (the following designations shall be used as appropriate: SH for sharp, RD for rounded, CE for semi-circular edges) (see 6.6.2).


The derivation of a product designation is shown in Example 1 and other typical product designations are shown in Example 2 and Example 3.

EXAMPLE 1 Rod for electrical purposes conforming to this document, in material designated either Cu-ETP or CW004A, in material condition H085, round, with nominal diameter 15 mm and tolerance Class A, will be designated as follows:

Rod—EN 13601—Cu-ETP—H085—RND15A

or

Rod — EN 13601 — CW004A — H085 — RND15A



EXAMPLE 2 Bar for electrical purposes conforming to this document, in material designated either CuAg0,10 or CW013A, in material condition R280, rectangular, nominal thickness 15 mm, nominal width 100 mm, semi-circular edge, will be designated as follows:

Bar EN 13601—CuAg0,10—R280—15 × 100—CE

or

Bar EN 13601—CW013A—R280—15 × 100—CE

iTeh STANDARD PREVIEW
(standards.iteh.ai)

EXAMPLE 3 Wire for electrical purposes conforming to this document, in material designated either Cu-OF or CW008A, in material condition H035, hexagonal, with nominal width across-flats 8 mm, tolerance Class B and sharp corners, will be designated as follows:

Wire EN 13601—Cu-OF—H035—HEX8B—SH

or

Wire EN 13601—CW008A—H035—HEX8B—SH

5 Ordering information

In order to facilitate the enquiry, order and confirmation of order procedures between the purchaser and the supplier, the purchaser shall state on his enquiry and order the following information:

- quantity of product required (mass, number of rods or bars or coils of wire);
- denomination (rod, bar or wire);
- number of this document (EN 13601);
- material designation (see Table 1 and Table 2);
- material condition designation (see 4.2 and Table 3);
- cross-sectional shape (round, square, hexagonal or rectangular);
- nominal dimensions (diameter, width across-flats or thickness × width);

EN 13601:2021 (E)

- h) tolerance class for round, square or hexagonal rod or wire: either Class A (minus tolerance only) or Class B (plus/minus tolerance) (see Table 5);
- i) type of corner (see 6.6.2);
- j) for rod or bar, the length required (see 6.6.3);
- k) for wire, the coil type: pancake, traverse wound, bunch or on drums (see 6.8);
- l) coil size requirements: inside and/or outside diameter and width or mass.

It is recommended that the product designation, as described in 4.3, is used for b) to i).

In addition, the purchaser shall also state on the enquiry and order any of the following, if required:

- m) test method to be used for measurement of hardness, i.e. Brinell or Vickers (see 8.3) unless the test method is to be left to the discretion of the supplier;
- n) whether sawn or sheared ends are required (see 6.6.3);
- o) whether special surface conditions are required (see 6.10);
- p) whether a bend test is required (see 6.3);
- q) whether form tolerances for wire are required (see 6.7.1);
- r) whether length of wire is required (see 6.6.3);
- s) whether sampling is required (see Clause 7);
- t) whether a declaration of conformity is required (see 9.1);
- u) whether an inspection document is required, and if so, which type (see 9.2);
- v) whether there are any special requirements for marking, packaging or labelling (see Clause 10).

EXAMPLE 1 Ordering details for 250 pieces bar for general electrical purposes conforming to EN 13601, in material designated either CuAg0,10 or CW013A, in material condition R280, rectangular, nominal thickness 15 mm, nominal width 100 mm, semi-circular edge, fixed length 4 500 mm:

250 pieces Bar EN 13601—CuAg0,10—R280—15 × 100—CE—4500 FL

or

250 pieces Bar EN 13601—CW013A—R280—15 × 100—CE—4500 FL

EXAMPLE 2 Ordering details for 1 000 kg wire for general electrical purposes conforming to EN 13601, in material designated either Cu-OF or CW008A, in material condition H035, hexagonal, nominal width across flats 8 mm, tolerance Class B, with sharp corners, nominal inside diameter of coil 500 mm:

1 000 kg Wire EN 13601—Cu-OF—H035—HEX8B—SH—nominal inside diameter of coil 500 mm

or

**1 000 kg Wire EN 13601—CW008A—H035—HEX8B—SH—nominal inside diameter of coil
500 mm**