



SLOVENSKI STANDARD
SIST EN 16511:2014/oprA1:2018
01-oktober-2018

Prosto položene plošče - Večslojne poltoge talne obloge plošč z zgornjim delom, odpornim proti obrabi

Loose-laid panels - Semi-rigid multilayer modular floor covering (MMF) panels with wear resistant top layer

Paneele für schwimmende Verlegung - Halbstarre, mehrlagige, modulare Fußbodenbeläge (MMF) mit abriebbeständiger Decklage

Panneaux pour pose flottante - Panneaux de revêtement de sol semi-rigides, multicouches et modulaires (MMF) avec couche supérieure résistante à l'usure

Ta slovenski standard je istoveten z: EN 16511:2014/prA1

ICS:

97.150 Talne obloge Floor coverings

SIST EN 16511:2014/oprA1:2018 en,fr,de

EUROPEAN STANDARD
NORME EUROPÉENNE
EUROPÄISCHE NORM

DRAFT
EN 16511:2014
prA1

June 2018

ICS 97.150

English Version

Loose-laid panels - Semi-rigid multilayer modular floor covering (MMF) panels with wear resistant top layer

Panneaux pour pose flottante - Panneaux de revêtement de sol semi-rigides, multicouches et modulaires (MMF) avec couche supérieure résistante à l'usure

Paneele für schwimmende Verlegung - Halbstarre, mehrlagige, modulare Fußbodenbeläge (MMF) mit abriebbeständiger Decklage

This draft amendment is submitted to CEN members for enquiry. It has been drawn up by the Technical Committee CEN/TC 134.

This draft amendment A1, if approved, will modify the European Standard EN 16511:2014. If this draft becomes an amendment, CEN members are bound to comply with the CEN/CENELEC Internal Regulations which stipulate the conditions for inclusion of this amendment into the relevant national standard without any alteration.

This draft amendment was established by CEN in three official versions (English, French, German). A version in any other language made by translation under the responsibility of a CEN member into its own language and notified to the CEN-CENELEC Management Centre has the same status as the official versions.

CEN members are the national standards bodies of Austria, Belgium, Bulgaria, Croatia, Cyprus, Czech Republic, Denmark, Estonia, Finland, Former Yugoslav Republic of Macedonia, France, Germany, Greece, Hungary, Iceland, Ireland, Italy, Latvia, Lithuania, Luxembourg, Malta, Netherlands, Norway, Poland, Portugal, Romania, Serbia, Slovakia, Slovenia, Spain, Sweden, Switzerland, Turkey and United Kingdom.

Recipients of this draft are invited to submit, with their comments, notification of any relevant patent rights of which they are aware and to provide supporting documentation.

Warning : This document is not a European Standard. It is distributed for review and comments. It is subject to change without notice and shall not be referred to as a European Standard.



EUROPEAN COMMITTEE FOR STANDARDIZATION
COMITÉ EUROPÉEN DE NORMALISATION
EUROPÄISCHES KOMITEE FÜR NORMUNG

CEN-CENELEC Management Centre: Rue de la Science 23, B-1040 Brussels

Contents		Page
European foreword		3
1	Modification to Clause 2, Normative references.....	4
2	Modification to Table 2 (subclause 4.2)	4

European foreword

This document (EN 16511:2014/prA1:2018) has been prepared by Technical Committee CEN/TC 134 “Resilient, textile and laminate floor coverings”, the secretariat of which is held by NBN.

This document is currently submitted to the CEN Enquiry.

EN 16511:2014/ prA1:2018 (E)**1 Modification to Clause 2, Normative references**

Replace "EN 425" with "EN 425:2002".

2 Modification to Table 2 (subclause 4.2)

In "Table 2 — Classification":

Replace rows 4, 5 and 6 with the respective lines below. In the footer, modify the text in footnote c as shown below and add footnotes e and f.

Class (EN ISO 10874)	21/22	23	31	32	33	34	Reference test method
Impact resistance [mm] (big ball)	≥ 400 mm	≥ 600 mm	≥ 800 mm	≥ 1 200 mm	≥ 1 600 mm	≥ 1 800 mm	EN 13329:2006+A1:2008, Annex F ^f
Micro-scratch resistance [class]				≤ MSR-A3 ^e	≤ MSR-A2 ^e	≤ MSR-A2 ^e	EN 16094
Castor chair resistance			10 000 cycles ^{a,c}	25 000 cycles ^{a,c}	25 000 cycles ^{a,c}	25 000 cycles ^{a,c}	EN 425:2002

^c Tested with soft wheels on loose laid panels without underlay material.

^e Due to detected inhomogeneity of the scrub materials SB 7440 (medium fine), the test results of EN 16094 procedure B shall not be used for classification.

^f Only the assessment of cracks on the surface shall be carried out. The deformation is not to be taken into consideration.