## DRAFT INTERNATIONAL STANDARD **ISO/DIS 1161**

ISO/TC 104/SC 1

Voting begins on: 2015-10-06

Secretariat: AFNOR

Voting terminates on: 2016-01-06

## Series 1 freight containers — Corner and intermediate fittings — Specification

Conteneurs de la série 1 — Pièces de coin et pièces de fixation intermédiaires — Spécifications

ICS: 55.180.10



THIS DOCUMENT IS A DRAFT CIRCULATED FOR COMMENT AND APPROVAL. IT IS THEREFORE SUBJECT TO CHANGE AND MAY NOT BE REFERRED TO AS AN INTERNATIONAL STANDARD UNTIL PUBLISHED AS SUCH.

IN ADDITION TO THEIR EVALUATION AS BEING ACCEPTABLE FOR INDUSTRIAL, TECHNOLOGICAL, COMMERCIAL AND USER PURPOSES, DRAFT INTERNATIONAL STANDARDS MAY ON OCCASION HAVE TO BE CONSIDERED IN THE LIGHT OF THEIR DECOMPOSITION TO DESCONT GRANDADOC TO POTENTIAL TO BECOME STANDARDS TO WHICH REFERENCE MAY BE MADE IN NATIONAL REGULATIONS.

RECIPIENTS OF THIS DRAFT ARE INVITED TO SUBMIT, WITH THEIR COMMENTS, NOTIFICATION OF ANY RELEVANT PATENT RIGHTS OF WHICH THEY ARE AWARE AND TO PROVIDE SUPPORTING DOCUMENTATION.



**Reference number** ISO/DIS 1161:2015(E)





#### © ISO 2015, Published in Switzerland

All rights reserved. Unless otherwise specified, no part of this publication may be reproduced or utilized otherwise in any form or by any means, electronic or mechanical, including photocopying, or posting on the internet or an intranet, without prior written permission. Permission can be requested from either ISO at the address below or ISO's member body in the country of the requester.

ISO copyright office Ch. de Blandonnet 8 • CP 401 CH-1214 Vernier, Geneva, Switzerland Tel. +41 22 749 01 11 Fax +41 22 749 09 47 copyright@iso.org www.iso.org

### Contents

Page

Forewo	ordi	iv	
Introductionvi			
1	Scope	1	
2	Normative references	1	
3 3.1 3.2	Dimensional requirements General Detailed dimensional and manufacturing requirements	1	
4	Strength requirements	2	
5 5.1	Design requirements	3	
5.1.1 5.1.2	General	3	
5.1.3	Lifting	3	
5.1.4 5.1.5	Longitudinal restraint	4 4	
5.1.6	Lashing and securing	4	
5.1.7 5.2	Misgather (offset loading)	4	
6	Stacking Lifting Longitudinal restraint Vertical restraint Lashing and securing Misgather (offset loading) Compulsory features Minimum bearing area – Top and bottom corner and intermediate fittings	5	
7	Corner and intermediate fitting marking	5	
8	Required tests	5	
Annex A (normative) Testing methodology			
	B (informative) Typical examples of twistlock lifting devices		

### Foreword

ISO (the International Organization for Standardization) is a worldwide federation of national standards bodies (ISO member bodies). The work of preparing International Standards is normally carried out through ISO technical committees. Each member body interested in a subject for which a technical committee has been established has the right to be represented on that committee. International organizations, governmental and non-governmental, in liaison with ISO, also take part in the work. ISO collaborates closely with the International Electrotechnical Commission (IEC) on all matters of electrotechnical standardization.

International Standards are drafted in accordance with the rules given in the ISO/IEC Directives, Part 2.

The main task of technical committees is to prepare International Standards. Draft International Standards adopted by the technical committees are circulated to the member bodies for voting. Publication as an International Standard requires approval by at least 75 % of the member bodies casting a vote.

Attention is drawn to the possibility that some of the elements of this document may be the subject of patent rights. ISO shall not be held responsible for identifying any or all such patent rights.

ISO 1161 was prepared by Technical Committee ISO/TC 104, Freight containers, Subcommittee SC 1, General purpose containers.

The fourth edition of ISO 1161 was published in 1984. This fifth edition cancels and replaces the fourth, following incorporation of:

- 1) Technical Corrigendum 1, 1990
- 2) Amendment 1, 2007
- 3) Para.2, Normative References: Added ISQ 148-1 Metallic Materials, Charpy Pendulum Impact Test
- 4) Para. 4, Strength Requirements: Added Mechanical Properties and reference to Heat Treatment
- Para. 5, Design Requirements: Para 5.1.1 para 5.1.3 Revised design load values for top, bottom, Intermediate fittings in accordance with the maximum superimposed mass represented in ISO 1496-1.
- 6) Added new Para. 5.1.4. Vertical Restraint renumbered subsequent paragraphs
- 7) 5.2 Compulsory features: added interior walls, top and bottom plates as new compulsory features.
- 8) Para 7 Corner fitting marking: Added new compulsory markings
- 9) Added Clause 8 Required Tests: New Paras 8.1 to 8.14
- 10) Figure 1 Top Corner fitting (millimetres): Added Interior wall thickness and bottom plate thickness, hitherto unspecified
- 11) Figure 2 Top Corner fitting (inches): Added Interior wall thickness and bottom plate thickness, hitherto unspecified
- 12) Figure 3 Bottom Corner fitting (millimetres): Added Interior wall thickness and top plate thickness, hitherto unspecified

- 13) Figure 4 Bottom Corner fitting (inches): Added Interior wall thickness and top plate thickness, hitherto unspecified
- 14) Figure 1a) Top Intermediate fitting (millimetres): Added wall thickness, hitherto unspecified
- 15) Figure 2a) Top Intermediate fitting (inches): Added wall thickness, hitherto unspecified
- 16) Figure 3a) Bottom Intermediate fitting (millimetres): Added wall thickness, hitherto unspecified
- 17) Figure 4a) Bottom Intermediate fitting (inches): Added wall thickness, hitherto unspecified
- 18) Figure 5 Limits of loads due to lashing and securing: Revised diagram for Internal Lashing
- 19) Removed existing Annex A "Examples of overall dimensions..."
- 20) Added New Annex A "Testing Methodology"
- 21) Removed Annex C "Guide on the choice of sizes for... carrying vehicles" (intent to transfer to ISO 3874 as more appropriate home for this information)

Les for... car, imaion

v

### Introduction

This International Standard on corner fittings is the result of the efforts of technical and operational personnel drawn from all phases of the transportation industry. The figures show the fittings for the top and bottom corners of series 1 freight containers which will provide compatibility in interchange between transportation modes. Care has been taken to limit consideration only to those details vital to this function.

The size and configuration of corner and intermediate fitting apertures are specified. The faces of the corner and intermediate fittings having apertures for the engagement of handling and securing devices have specified thickness and tolerances as shown in Figures 1, 2, 3 and 4. The minimum thickness of the blank walls is specified even though they are not involved in the engagement of the handling and securing devices. they may be thicker than the minimum provided that their inner surfaces do not protrude into the corner fitting cavity reserved for the engaging device.

The purpose of this International Standard is to define some details of design vital to container interchange in automatic, semi-automatic and conventional systems.

Tensilsandarding of content The strength and testing requirements specified in this International Standard do not take any account of the stresses which may result from the practice of end-to-end coupling of containers.

The requirements of this International Standard do not preclude the Provision of additional facilities for lifting NOTE either from the top or at the base of the freight container.

# Series 1 freight containers — Corner and intermediate fittings — Specification

#### 1 Scope

This International Standard establishes the basic dimensions and the functional and strength requirements of corner and intermediate fittings for series 1 freight containers, i.e. containers which conform to ISO 668 and ISO 1496 with the exception of air mode containers (see ISO 8323).

#### 2 Normative references

The following documents, in whole or in part, are normatively referenced in this document and are indispensable for its application. For dated references, only the edition cited applies. For undated references, the latest edition of the referenced document (including any amendments) applies.

ISO 668, Series 1 freight containers – Classification, external dimensions and ratings

ISO 1496/1-5, Series 1 freight containers - Specification and testing

https

ISO 148-1, Metallic Materials Charpy Pendulum Impact Test

ISO 8323, Freight containers - Air/surface (intermodal) general purpose containers - Specification and tests

## 3 Dimensional requirements

#### 3.1 General

**3.1.1** The dimensions and tolerances of the corner and intermediate fittings shall conform to Figures 1, 1a, 2, 2a, 3, 3a, 4 and 4a.

Each series 1 container shall have two right-hand top corner fittings (on the right as the observer faces either end of the container) and two left-hand top corner fittings which are the mirror image of the right-hand fittings.

The bottom corner fittings shall have a similar configuration except in respect of the end aperture.

Apart from the above, 45 ft containers shall have four top intermediate fittings in the 40 ft position [see Figures 1a) and 2a)] and four bottom intermediate fittings in the 40 ft position [see Figures 3a) and 4a)].

The corner fittings shown in Figures 1 to 4 illustrate right-hand top and bottom fittings only; for the left-hand corner fittings, the dimensions are simply transposed.

#### 3.2 Detailed dimensional and manufacturing requirements .

**3.2.2** Where the dimensions are not specified for inner and outer edges of apertures, these edges shall be given a radius of:

$$3 = {0 \atop 1.5} \text{ mm} (1/8 = {0 \atop 1/16} \text{ in}).$$

**3.2.3** At the junction of the two 6 mm (1/4 in) outside edge radii with the 14,5 mm (9/16 in) edge radius, the corner should be rounded by blending the radiused edges, removing minimum amounts of material from the flat outer faces and walls.

**3.2.4** Where a corner or intermediate fitting has an optional inner side wall and is made to the minimum dimension of 149 mm (5  $_{7/8}$  in), the junction of the mandatory horizontal face to the optional inner side wall may be provided with a radius not exceeding 5,5 mm (7/32 in).

If a greater radius is required, the 149 mm (5 7/8 in) dimensions shall be increased accordingly.

#### 4 Strength requirements

The corner or intermediate fittings shall be designed, constructed and tested in such a manner and of such materials as to enable them to pass the operating and testing requirements laid down in ISO 1496-1 and Clause 5 and Clause 8 below.

The mechanical properties of raw materials used to produce corner fittings shall meet or exceed the following:

10

	26078
Yield Strength:	275 MPa
Tensile strength:	480 Mpa
Impact Energy at -20°C	275 MPa 480 Mpa 27 KV (Joule) <sup>1)</sup> 21 KV (Joule) <sup>2</sup> /
Impact Energy at -40°C:	21 KV (Joule) 21 Structure Full Catholication
Elongation:	21 KV (Joule) 21 C the strate of the strate
Reduction of area:	40 %
	nthesill 28th

The above is to be regarded as the minimum values for strength requirements, Certification societies may approve higher values but not lower.

Manufacturers are responsible for ensuring that quantities of undesirable elements in the raw materials used to produce corner fittings are kept to an absolute minimum and that the composition of the resultant material is such as to ensure good weldability.

All corner or intermediate fittings produced by a casting process are to be suitably heat treated to comply with the specified mechanical properties above. Heat treatment batches are to be limited to the size required so as to ensure that all fittings receive a comparable treatment regime and that there are no cold or hot spots in the batch.

<sup>1)</sup> Impact tests in accordance with ISO 148-1 Charpy V-notch impact specimens.

#### 5 Design requirements

#### 5.1 Loading

#### 5.1.1 General

The following container design loadings and criteria were used in establishing the dimensional design of corner or intermediate fittings specified in this International Standard.

Corner and intermediate fittings for series 1 freight containers shall be capable of withstanding the loads calculated in accordance with the requirements of ISO 1496-1 and the lifting methods of ISO 3874 for 1AA, 1A, 1AX, 1EEE and 1EE containers. The calculated design loads are listed in the following sub clauses.

# WARNING — Recognising that there are containers that have ratings in excess of those specified in ISO 668 special arrangements for certification of corner or intermediate fittings for such containers may be required.

#### 5.1.2 Stacking

AN AN	Design loads
Top corner fitting [superimposed load offset 25,4 mm (1 in) laterally and 38 mm (1 1/2 in longitudinally] Top Intermediate fitting [superimposed load offset 25,4 mm (1 in) laterally and 38 mm (1 1/2 in longitudinally] Bottom corner fitting (resting on flat support)	942 kN
Top Intermediate fitting [superimposed load offset 25,4 mm (1 in)) have been superimposed load offset 25,4 mm (1 in)) have been superimposed load offset 25,4 mm (1 in)) have been superimposed load offset 25,4 mm (1 in)) have been superimposed load offset 25,4 mm (1 in)) have been superimposed load offset 25,4 mm (1 in)) have been superimposed load offset 25,4 mm (1 in)) have been superimposed load offset 25,4 mm (1 in)) have been superimposed load offset 25,4 mm (1 in)) have been superimposed load offset 25,4 mm (1 in)) have been superimposed load offset 25,4 mm (1 in) have been superimposed load offset	423 kN
Bottom corner fitting (resting on flat support)	1200 kN
Bottom intermediate fitting (resting on flat support)	560 kN
Bottom corner fitting offset 25,4 mm (1 in) laterally and 38 mm (1 $_{1/2}$ in) longitudinally (to reflect the situation in cell guides) 5.1.3 Lifting	942 kN
uttps. 2t	Design loads
	0
Top corner or intermediate fitting [twistlock (see also Clause 6), hook or shackle]	195 kN
Bottom corner or intermediate fitting sling at 30° to horizontal	390 kN

NOTE Lifting from the bottom corner or intermediate fitting:

- a) The line of action of the sling is assumed to be parallel to and not more than 38 mm (1 112 in) from the outer face of the corner fitting.
- b) The load values quoted are for slings at the angles stated, but it is recognized that slings may be used at any angle between the angle stated and the vertical.

#### 5.1.4 Longitudinal restraint

**Design** loads Bottom corner or intermediate fittings (two fittings carrying load) 300 kN  $(2 g \times 1 R)$ 5.1.5 Vertical restraint Design loads Top and bottom corner fittings or Intermediate top and bottom 250 kN fittings

#### 5.1.6 Lashing and securing

The force, or resultant of any combination of forces, imparted on the aperture in the end or the side of a bottom corner or bottom intermediate fitting as a result of the use of a lashing or a securing device, or a combination of such devices, is assumed not to exceed the value indicated by the point on the "envelope" shown in Figure 5 which is appropriate to the angle at which the force, or resultant force, is applied. It is further assumed that the force or resultant force lies in a plane parallel to and no more than 38 mm (1 1/2 in) from the face of the corner or intermediate fitting.

#### 5.1.7 Misgather (offset loading)

Localized loading of bottom corner or intermediate fittings caused by lowering of the container onto locating stan fittings which are not gathered into the hole. 0

All corner and intermediate fittings shall be capable of withstanding a load of 190 kN applied normally to the contact area of 25 mm (1 in) x 6 mm (1/4 in) on the top and bottom faces (see Figure 6). andardsit

5.2 Compulsory features Minimum thicknesses are prescribed for the following walls or faces in the corner or intermediate fittings: nttp

Top corner or intermediate fittings:

- the top face,
- the exterior side wall,
- the exterior end wall,
- the interior side wall.
- the interior end wall,
- the bottom plate.

Bottom corner or intermediate fittings:

- the bottom face,
- the exterior side wall,