



SLOVENSKI STANDARD SIST EN ISO 15512:2019

01-september-2019

Nadomešča:
SIST EN ISO 15512:2017

Polimerni materiali - Določevanje vode (ISO 15512:2019)

Plastics - Determination of water content (ISO 15512:2019)

Kunststoffe - Bestimmung des Wassergehaltes (ISO 15512:2019)

Plastiques - Dosage de l'eau (ISO 15512:2019)

ITeH STANDARD PREVIEW
(standards.iteh.ai)

Ta slovenski standard je istoveten z: EN ISO 15512:2019

<https://standards.iteh.ai/catalog/standards/sist/4ef009d4-e678-4c36-85ca-b88a05bd87c2/sist-en-iso-15512-2019>

ICS:

83.080.01	Polimerni materiali na splošno	Plastics in general
-----------	--------------------------------	---------------------

SIST EN ISO 15512:2019

en,fr,de

iTeh STANDARD PREVIEW
(standards.iteh.ai)

SIST EN ISO 15512:2019

<https://standards.iteh.ai/catalog/standards/sist/4ef009d4-e678-4c36-85ca-b88a05bd87c2/sist-en-iso-15512-2019>

EUROPEAN STANDARD
NORME EUROPÉENNE
EUROPÄISCHE NORM

EN ISO 15512

May 2019

ICS 83.080.01

Supersedes EN ISO 15512:2016

English Version

Plastics - Determination of water content (ISO 15512:2019)

Plastiques - Dosage de l'eau (ISO 15512:2019)

Kunststoffe - Bestimmung des Wassergehaltes (ISO
15512:2019)

This European Standard was approved by CEN on 4 May 2019.

CEN members are bound to comply with the CEN/CENELEC Internal Regulations which stipulate the conditions for giving this European Standard the status of a national standard without any alteration. Up-to-date lists and bibliographical references concerning such national standards may be obtained on application to the CEN-CENELEC Management Centre or to any CEN member.

This European Standard exists in three official versions (English, French, German). A version in any other language made by translation under the responsibility of a CEN member into its own language and notified to the CEN-CENELEC Management Centre has the same status as the official versions.

CEN members are the national standards bodies of Austria, Belgium, Bulgaria, Croatia, Cyprus, Czech Republic, Denmark, Estonia, Finland, Former Yugoslav Republic of Macedonia, France, Germany, Greece, Hungary, Iceland, Ireland, Italy, Latvia, Lithuania, Luxembourg, Malta, Netherlands, Norway, Poland, Portugal, Romania, Serbia, Slovakia, Slovenia, Spain, Sweden, Switzerland, Turkey and United Kingdom.

<https://standards.iteh.ai/catalog/standards/sist/4ef009d4-e678-4c36-85ca-b88a05bd87c2/sist-en-iso-15512-2019>



EUROPEAN COMMITTEE FOR STANDARDIZATION
COMITÉ EUROPÉEN DE NORMALISATION
EUROPÄISCHES KOMITEE FÜR NORMUNG

CEN-CENELEC Management Centre: Rue de la Science 23, B-1040 Brussels

Contents	Page
European foreword.....	3

iTeh STANDARD PREVIEW
(standards.iteh.ai)

[SIST EN ISO 15512:2019](https://standards.iteh.ai/catalog/standards/sist/4ef009d4-e678-4c36-85ca-b88a05bd87c2/sist-en-iso-15512-2019)
<https://standards.iteh.ai/catalog/standards/sist/4ef009d4-e678-4c36-85ca-b88a05bd87c2/sist-en-iso-15512-2019>

European foreword

This document (EN ISO 15512:2019) has been prepared by Technical Committee ISO/TC 61 "Plastics" in collaboration with Technical Committee CEN/TC 249 "Plastics" the secretariat of which is held by NBN.

This European Standard shall be given the status of a national standard, either by publication of an identical text or by endorsement, at the latest by November 2019, and conflicting national standards shall be withdrawn at the latest by November 2019.

Attention is drawn to the possibility that some of the elements of this document may be the subject of patent rights. CEN shall not be held responsible for identifying any or all such patent rights.

This document supersedes EN ISO 15512:2016.

According to the CEN-CENELEC Internal Regulations, the national standards organizations of the following countries are bound to implement this European Standard: Austria, Belgium, Bulgaria, Croatia, Cyprus, Czech Republic, Denmark, Estonia, Finland, Former Yugoslav Republic of Macedonia, France, Germany, Greece, Hungary, Iceland, Ireland, Italy, Latvia, Lithuania, Luxembourg, Malta, Netherlands, Norway, Poland, Portugal, Romania, Serbia, Slovakia, Slovenia, Spain, Sweden, Switzerland, Turkey and the United Kingdom.

iTeh STANDARD PREVIEW
Endorsement notice
(standards.iteh.ai)

The text of ISO 15512:2019 has been approved by CEN as EN ISO 15512:2019 without any modification.

<https://standards.iteh.ai/catalog/standards/sist/4ef009d4-e678-4c36-85ca-b88a05bd87c2/sist-en-iso-15512-2019>

iTeh STANDARD PREVIEW
(standards.iteh.ai)

SIST EN ISO 15512:2019

<https://standards.iteh.ai/catalog/standards/sist/4ef009d4-e678-4c36-85ca-b88a05bd87c2/sist-en-iso-15512-2019>

INTERNATIONAL
STANDARD

ISO
15512

Fifth edition
2019-05

**Plastics — Determination of water
content**

Plastiques — Dosage de l'eau

iTeh STANDARD PREVIEW
(standards.iteh.ai)

[SIST EN ISO 15512:2019](https://standards.iteh.ai/catalog/standards/sist/4ef009d4-e678-4c36-85ca-b88a05bd87c2/sist-en-iso-15512-2019)

<https://standards.iteh.ai/catalog/standards/sist/4ef009d4-e678-4c36-85ca-b88a05bd87c2/sist-en-iso-15512-2019>



Reference number
ISO 15512:2019(E)

© ISO 2019

iTeh STANDARD PREVIEW (standards.iteh.ai)

[SIST EN ISO 15512:2019](https://standards.iteh.ai/catalog/standards/sist/4ef009d4-e678-4c36-85ca-b88a05bd87c2/sist-en-iso-15512-2019)

<https://standards.iteh.ai/catalog/standards/sist/4ef009d4-e678-4c36-85ca-b88a05bd87c2/sist-en-iso-15512-2019>



COPYRIGHT PROTECTED DOCUMENT

© ISO 2019

All rights reserved. Unless otherwise specified, or required in the context of its implementation, no part of this publication may be reproduced or utilized otherwise in any form or by any means, electronic or mechanical, including photocopying, or posting on the internet or an intranet, without prior written permission. Permission can be requested from either ISO at the address below or ISO's member body in the country of the requester.

ISO copyright office
CP 401 • Ch. de Blandonnet 8
CH-1214 Vernier, Geneva
Phone: +41 22 749 01 11
Fax: +41 22 749 09 47
Email: copyright@iso.org
Website: www.iso.org

Published in Switzerland

Contents

Page

Foreword	v
Introduction	vi
1 Scope	1
2 Normative references	2
3 Terms and definitions	2
4 Method A — Extraction with anhydrous methanol	2
4.1 Principle.....	2
4.2 Reagents.....	2
4.3 Apparatus.....	2
4.4 Preparation of test sample.....	3
4.4.1 Granules or powder.....	3
4.4.2 Finished articles.....	3
4.5 Procedure.....	3
4.5.1 Precautions.....	3
4.5.2 Preparation of test portions.....	3
4.5.3 Determination.....	3
4.6 Expression of results.....	4
4.7 Precision.....	4
5 Method B1 — Water vaporization using a heating tube oven	4
5.1 Principle.....	4
5.2 Reagents.....	4
5.3 Apparatus.....	5
5.4 Preparation of test sample.....	7
5.5 Procedure.....	7
5.5.1 Precautions.....	7
5.5.2 Preparation of apparatus.....	7
5.5.3 Equipment checks.....	7
5.5.4 Determination.....	8
5.6 Expression of results.....	8
5.7 Precision.....	9
6 Method B2 — Water vaporization using a heated sample vial	9
6.1 Principle.....	9
6.2 Reagents.....	9
6.3 Apparatus.....	10
6.4 Preparation of test sample.....	11
6.5 Procedure.....	12
6.5.1 Preparation of apparatus.....	12
6.5.2 Equipment check.....	12
6.5.3 Determination.....	12
6.6 Expression of results.....	14
6.7 Precision.....	14
7 Method C — Manometric method	15
7.1 Principle.....	15
7.2 Reagents.....	15
7.3 Apparatus.....	15
7.4 Preparation of test sample.....	16
7.5 Procedure.....	16
7.5.1 Equipment.....	16
7.5.2 Outgassing.....	17
7.5.3 Calibration.....	17
7.5.4 Determination.....	19
7.6 Expression of results.....	20

ISO 15512:2019(E)

7.7	Precision.....	20
8	Method D — Water detection by using a diphosphorus pentoxide cell.....	20
8.1	Principle.....	20
8.2	Reagents.....	21
8.3	Apparatus.....	21
8.4	Preparation of test sample.....	22
8.5	Procedure.....	23
8.5.1	Preparation of apparatus.....	23
8.5.2	Rinsing the system.....	23
8.5.3	Tare measurement.....	23
8.5.4	Cell factor.....	23
8.5.5	Equipment check.....	23
8.5.6	Determination.....	24
8.6	Expression of results.....	24
8.7	Precision.....	25
9	Method E — Determination of water content by calcium hydride method.....	25
9.1	Principle.....	25
9.2	Reagents.....	26
9.3	Apparatus.....	26
9.4	Preparation of test sample.....	27
9.5	Procedure.....	27
9.5.1	Equipment check.....	27
9.5.2	Calibration.....	28
9.5.3	Determination.....	28
9.5.4	Expression of results.....	29
9.6	Precision.....	29
10	Test report.....	29
Annex A	(informative) Alternative sample preparation methods and titration methods.....	30
Annex B	(informative) Selection of the optimum heating temperature and heating time for the water content determination.....	31
Annex C	(normative) Determination of the water content of a water standard.....	33
Bibliography	34

SIST EN ISO 15512:2019
<https://standards.iteh.ai/catalog/standards/sist/4c1009d4-c678-4c30-83ca-b88195b18731/iso-15512-2019>
 ITCH STANDARD PREVIEW
 (standards.iteh.ai)

Foreword

ISO (the International Organization for Standardization) is a worldwide federation of national standards bodies (ISO member bodies). The work of preparing International Standards is normally carried out through ISO technical committees. Each member body interested in a subject for which a technical committee has been established has the right to be represented on that committee. International organizations, governmental and non-governmental, in liaison with ISO, also take part in the work. ISO collaborates closely with the International Electrotechnical Commission (IEC) on all matters of electrotechnical standardization.

The procedures used to develop this document and those intended for its further maintenance are described in the ISO/IEC Directives, Part 1. In particular, the different approval criteria needed for the different types of ISO documents should be noted. This document was drafted in accordance with the editorial rules of the ISO/IEC Directives, Part 2 (see www.iso.org/directives).

Attention is drawn to the possibility that some of the elements of this document may be the subject of patent rights. ISO shall not be held responsible for identifying any or all such patent rights. Details of any patent rights identified during the development of the document will be in the Introduction and/or on the ISO list of patent declarations received (see www.iso.org/patents).

Any trade name used in this document is information given for the convenience of users and does not constitute an endorsement.

For an explanation of the voluntary nature of standards, the meaning of ISO specific terms and expressions related to conformity assessment, as well as information about ISO's adherence to the World Trade Organization (WTO) principles in the Technical Barriers to Trade (TBT) see www.iso.org/iso/foreword.html.

This document was prepared by Technical Committee ISO/TC 61, *Plastics*, Subcommittee SC 5, *Physical-chemical properties*.

This fifth edition cancels and replaces the fourth edition (ISO 15512:2016), which has been technically revised. The main change compared to the previous edition is as follows:

- addition of two alternative methods for water determination (Methods D and E).

Any feedback or questions on this document should be directed to the user's national standards body. A complete listing of these bodies can be found at www.iso.org/members.html.

ISO 15512:2019(E)**Introduction**

The interlaboratory comparability of the water content determination of plastics is often low. Major causes for this are the sample packaging, sample handling, and differences between equipment and settings. Samples should, e.g. be packed in special glass containers or water barrier sealed bags. Sample handling is preferably to be carried out in a dry nitrogen or air environment. For improving the repeatability and reproducibility, the procedure prescribed in this document is intended to be followed strictly.

The temperature settings for the vaporization method are not specified in this document. For the manometric method, a temperature of 200 °C is often used. However, for some condensation materials, this might be too high and could, e.g. cause generation of water due to a condensation reaction.

The heating temperature needs to be optimized depending on the material to be tested, the equipment in use, and the practical circumstances. If the temperature is too low, the total amount of water in the material to be tested will not be evaporated completely, whereas too high temperatures cause water generation due to effects like degradation and condensation reactions.

In this document, a procedure is included for optimization of the heating temperature in order to choose the correct temperature for the water content determination and to improve the interlaboratory comparability.

**iTeh STANDARD PREVIEW
(standards.iteh.ai)**

[SIST EN ISO 15512:2019](https://standards.iteh.ai/catalog/standards/sist/4ef009d4-e678-4c36-85ca-b88a05bd87c2/sist-en-iso-15512-2019)

<https://standards.iteh.ai/catalog/standards/sist/4ef009d4-e678-4c36-85ca-b88a05bd87c2/sist-en-iso-15512-2019>

Plastics — Determination of water content

1 Scope

This document specifies methods for the determination of the water content of plastics in the form of powder, granules, and finished articles. These methods do not test for water absorption (kinetics and equilibrium) of plastics as measured by ISO 62.

Method A is suitable for the determination of water content as low as 0,1 % with an accuracy of 0,1 %. Method B and Method C are suitable for the determination of water content as low as 0,01 % with an accuracy of 0,01 %. Method D is suitable for the determination of water content as low as 0,01 % with an accuracy of 0,01 %. Method E is suitable for the determination of water content as low as 0,001 % with an accuracy of 0,001 %. The stated accuracies are detection limits which depend also on the maximal possible sample mass. The water content is expressed as a percentage mass fraction of water.

Method D is suitable for polyamide (PA), polycarbonate (PC), polypropylene (PP), polyethylene (PE), epoxy resin, polyethylene terephthalate (PET), polyester, polytetrafluoroethylene (PTFE), polyvinyl chloride (PVC), polylactide (PLA), polyamidimid (PAI), it is especially not recommended for samples which can release NH_3 . Methods A, B, C and E are generally suitable for all types of plastic and moisture level.

Water content is an important parameter for processing materials and is expected to remain below the level specified in the appropriate material standard.

Six alternative methods are specified in this document.

- **Method A** is an extraction method using anhydrous methanol followed by a Karl Fischer titration of the extracted water. It can be used for all plastics and is applicable to granules smaller than $4 \text{ mm} \times 4 \text{ mm} \times 3 \text{ mm}$. The method can also be used for, e.g. prepolymer materials in the form of a powder that are insoluble in methanol.
- **Method B1** is a vaporization method using a tube oven. The water contained in the test portion is vaporized and carried to the titration cell by a dry air or nitrogen carrier gas, followed by a Karl Fischer titration or a coulometric determination by means of a moisture sensor of the collected water. It can be used for all plastics and is applicable to granules smaller than $4 \text{ mm} \times 4 \text{ mm} \times 3 \text{ mm}$.
- **Method B2** is a vaporization method using a heated sample vial. The water contained in the test portion is vaporized and carried to the titration cell by a dry air or nitrogen carrier gas, followed by a Karl Fischer titration of the collected water. It can be used for all plastics and is applicable to granules smaller than $4 \text{ mm} \times 4 \text{ mm} \times 3 \text{ mm}$.
- **Method C** is a manometric method. The water content is determined from the increase in pressure, which results when the water is evaporated under a vacuum. This method is not applicable to plastic samples containing volatile compounds, other than water, in amounts contributing significantly to the vapour pressure at room temperature. Checks for the presence of large amounts of volatile compounds are to be carried out periodically, for example by gas chromatography. Such checks are particularly required for new types or grades of material.
- **Method D** is a thermocoulometric method using a diphosphorus pentoxide (P_2O_5) cell for the detection of the vaporized water. The water contained in the test portion is vaporized and carried to the sensor cell by a dry air or nitrogen carrier gas, followed by a coulometric determination of the collected water. This method is not applicable to plastic samples containing volatile compounds, other than water, in amounts contributing significantly to the vapour pressure at room temperature. This is specially related to volatile components which can react with the acidic coating of the diphosphorus pentoxide sensor, e.g. ammonia or any kind of amines. Checks for the presence of large amounts of volatile compounds are to be carried out periodically. Such checks are particularly required for new types or grades of material.