



Designation: F136 – 08<sup>ε1</sup>

# Standard Specification for Wrought Titanium-6Aluminum-4Vanadium ELI (Extra Low Interstitial) Alloy for Surgical Implant Applications (UNS R56401)<sup>1</sup>

This standard is issued under the fixed designation F136; the number immediately following the designation indicates the year of original adoption or, in the case of revision, the year of last revision. A number in parentheses indicates the year of last reapproval. A superscript epsilon ( $\epsilon$ ) indicates an editorial change since the last revision or reapproval.

<sup>ε1</sup> NOTE—Subsection 8.3.1 was editorially corrected in December 2008.

## 1. Scope\*

1.1 This specification covers the chemical, mechanical, and metallurgical requirements for wrought annealed titanium-6aluminum-4vanadium ELI (extra low interstitial) alloy (R56401) to be used in the manufacture of surgical implants.

1.2 The values stated in inch-pound units are to be regarded as standard. The values given in parentheses are mathematical conversions to SI units that are provided for information only and are not considered standard.

## 2. Referenced Documents

### 2.1 ASTM Standards:<sup>2</sup>

**E8/E8M** Test Methods for Tension Testing of Metallic Materials

**E29** Practice for Using Significant Digits in Test Data to Determine Conformance with Specifications

**E290** Test Methods for Bend Testing of Material for Ductility

**E539** Test Method for X-Ray Fluorescence Spectrometric Analysis of 6Al-4V Titanium Alloy

**E1409** Test Method for Determination of Oxygen and Nitrogen in Titanium and Titanium Alloys by the Inert Gas Fusion Technique

**E1447** Test Method for Determination of Hydrogen in Titanium and Titanium Alloys by Inert Gas Fusion Thermal Conductivity/Infrared Detection Method

**E1941** Test Method for Determination of Carbon in Refractory and Reactive Metals and Their Alloys

**E2371** Test Method for Analysis of Titanium and Titanium Alloys by Atomic Emission Plasma Spectrometry

**F981** Practice for Assessment of Compatibility of Biomaterials for Surgical Implants with Respect to Effect of Materials on Muscle and Bone

### 2.2 ISO Standards:<sup>3</sup>

**ISO 6892** Metallic Materials Tensile Testing at Ambient Temperature

**ISO 9001** Quality Management Systems Requirements

### 2.3 ASQ Standard:

**ASQ C1** Specifications of General Requirements for a Quality Control Program<sup>4</sup>

### 2.4 Aerospace Material Specifications:

**AMS 2249** Chemical Check Analysis Limits, Titanium and Titanium Alloys<sup>5</sup>

## 3. Terminology

### 3.1 Definitions of Terms Specific to This Standard:

3.1.1 *beta transus, n*—the minimum temperature at which the alpha plus beta phase can transform to 100 % beta phase.

3.1.2 *lot, n*—the total number of mill products produced from one heat under the same conditions at essentially the same time.

## 4. Product Classification

4.1 *Strip*—Any product under 0.1875 in. (4.76 mm) in thickness and under 24 in. (610 mm) wide.

4.2 *Sheet*—Any product under 0.1875 in. (4.76 mm) in thickness and 24 in. (610 mm) or more in width.

4.3 *Plate*—Any product 0.1875 in. (4.76 mm) thick and over and 10 in. (254 mm) wide and over, with widths greater than five times thickness. Plate up to 4.00 in. (101.60 mm), thick inclusive is covered by this specification.

4.4 *Bar*—Round bars and flats from 0.1875 in. (4.76 mm) to 4.00 in. (101.60 mm) in diameter or thickness (other sizes and shapes by special order).

<sup>1</sup> This specification is under the jurisdiction of ASTM Committee F04 on Medical and Surgical Materials and Devices and is the direct responsibility of Subcommittee F04.12 on Metallurgical Materials.

Current edition approved Nov. 1, 2008. Published December 2008. Originally published in 1984. Last previous edition approved in 2002 as F136 – 02a. DOI: 10.1520/F0136-08E01.

<sup>2</sup> For referenced ASTM standards, visit the ASTM website, [www.astm.org](http://www.astm.org), or contact ASTM Customer Service at [service@astm.org](mailto:service@astm.org). For *Annual Book of ASTM Standards* volume information, refer to the standard's Document Summary page on the ASTM website.

<sup>3</sup> Available from American National Standards Institute (ANSI), 25 W. 43rd St., 4th Floor, New York, NY 10036, <http://www.ansi.org>.

<sup>4</sup> Available from American Society for Quality (ASQ), 600 N. Plankinton Ave., Milwaukee, WI 53203, <http://www.asq.org>.

<sup>5</sup> Available from Society of Automotive Engineers (SAE), 400 Commonwealth Dr., Warrendale, PA 15096-0001, <http://www.sae.org>.

\*A Summary of Changes section appears at the end of this standard.

4.5 *Forging Bar*—Bar as described in 4.4, used for production of forgings, may be furnished in the hot worked condition.

4.6 *Wire*—Rounds, flats, or other shapes less than 0.1875 in. (4.76 mm) in diameter.

## 5. Ordering Information

5.1 Include with inquiries and orders for material under this specification the following information:

- 5.1.1 Quantity,
- 5.1.2 ASTM designation and date of issue,
- 5.1.3 Form (sheet, strip, plate, bar, forging bar, or wire),
- 5.1.4 Condition (See Section 3 and 6.3),
- 5.1.5 Mechanical properties (if applicable, for special conditions),
- 5.1.6 Finish (See 6.2),
- 5.1.7 Applicable dimensions including size, thickness, width, length, or drawing number,
- 5.1.8 Special tests, if any, and
- 5.1.9 Other requirements.

## 6. Materials and Manufacture

6.1 The various titanium mill products covered in this specification normally are formed with the conventional forging and rolling equipment found in primary ferrous and nonferrous plants. The alloy is usually multiple melted in arc furnaces (including furnaces such as plasma arc and electron beam) of a type conventionally used for reactive metals.

6.2 *Finish*—The mill product may be furnished to the implant manufacturer as mechanically descaled or pickled, abrasively blasted, chemically milled, ground, machined, peeled, polished, combinations of these operations, or as specified by the purchaser. On billets, bars, plates, and forgings, it is permissible to remove minor surface imperfections by grinding if the resultant area meets the dimensional and surface finish requirements of this specification.

6.3 *Condition*—Material shall be furnished in the annealed or cold-worked condition. Mechanical properties for conditions other than those listed in Table 1 and Table 2 may be established by agreement between the supplier and the purchaser.

## 7. Chemical Requirements

7.1 The heat analysis shall conform to the chemical composition specified in Table 3. Ingot analysis may be used for

reporting all chemical requirements, except hydrogen. Samples for hydrogen shall be taken from the finished mill product. The supplier shall not ship material with chemistry outside the requirements specified in Table 3.

7.1.1 Requirements for the major and minor elemental constituents are listed in Table 3. Also listed are important residual elements. Analysis for elements not listed in Table 3 is not required to verify compliance with this specification.

### 7.2 Product Analysis:

7.2.1 Product analysis tolerances do not broaden the specified heat analysis requirements but cover variations between laboratories in the measurement of chemical content. The product analysis tolerances shall conform to the product tolerances in Table 4.

7.2.2 The product analysis is either for the purpose of verifying the composition of a heat or manufacturing lot or determining variations in the composition within the heat.

7.2.3 Acceptance or rejection of a heat or manufacturing lot of material may be made by the purchaser on the basis of this product analysis. Product analysis outside the tolerance limits allowed in Table 4 is cause for rejection of the product. A referee analysis may be used if agreed upon by the supplier and purchaser.

7.2.4 For referee purposes, use Test Methods E539, E1409, E1447, E1941, and E2371 or other analytical methods agreed upon between the purchaser and the supplier.

7.3 Samples for chemical analysis shall be representative of the material being tested. The utmost care must be used in sampling titanium for chemical analysis because of its affinity for elements such as oxygen, nitrogen, and hydrogen. In cutting samples for analysis, therefore, the operation should be carried out insofar as possible in a dust-free atmosphere. Cutting tools should be clean and sharp. Samples for analysis should be stored in suitable containers.

## 8. Mechanical Requirements

8.1 The material supplied under this specification shall conform to the mechanical property requirements in Table 1 and Table 2.

8.2 Specimens for tension tests shall be machined and tested in accordance with Test Methods E8/E8M. Tensile properties shall be determined using a strain rate of 0.003 to 0.007 in./in./min (mm/mm/min) through yield and then the crosshead

**TABLE 1 Annealed Mechanical Properties of Bar, Wire, and Forgings**

Nominal Diameter or Distance Between Parallel Sides, in. (mm)	Tensile Strength min, psi (MPa)	Yield Strength (0.2% offset) min, psi (MPa)	Elongation <sup>A</sup> in 4D or 4W min, %			Reduction of Area <sup>B</sup> min, %		
			L	LT	ST	L	LT	ST
Under 0.187 (4.75) thickness or diameter	125 000 (860)	115 000 (795)	10	...	...	...	...	...
0.187 (4.75) to under 1.75 (44.45), incl	125 000 (860)	115 000 (795)	10	...	...	25	...	...
1.75 (44.45) to under 2.50 (63.50), incl	120 000 (825)	110 000 (760)	8	...	...	20	...	...
2.50 (63.50) to 4.00 (101.60), incl	120 000 (825)	110 000 (760)	8	8 <sup>C</sup>	8 <sup>C</sup>	15	15 <sup>C</sup>	15 <sup>C</sup>

<sup>A</sup> Elongation of material 0.063 in. (1.6 mm) or greater in diameter (D) or width (W) shall be measured using a gage length of 2 in. or 4 D or 4 W. The gage length must be reported with the test results. The method for determining elongation of material under 0.063 in. (1.6 mm) in diameter or thickness may be negotiated. Alternatively, a gage length corresponding to ISO 6892 may be used when agreed upon between supplier and purchaser. (5.65 times the square root of So, where So is the original cross sectional area.) Gage length shall be reported with the elongation value. L = longitudinal; LT = long transverse; ST = short transverse.

<sup>B</sup> Applies to bar and forgings only. L = longitudinal; LT = long transverse; ST = short transverse. For round bar, the long and short transverse are identical tests, therefore only one transverse is required.

<sup>C</sup> Transverse requirements in Table 1 apply only to product from which a tensile specimen not less than 2.50 in. (63.5 mm) in length can be obtained.