This document is not an ASTM standard and is intended only to provide the user of an ASTM standard an indication of what changes have been made to the previous version. Because it may not be technically possible to adequately depict all changes accurately, ASTM recommends that users consult prior editions as appropriate. In all cases only the current version of the standard as published by ASTM is to be considered the official document.



Designation: D5436-99 Designation: D 5436 - 03 (Reapproved 2008)

# Standard Specification for Cast Poly(Methyl Methacrylate) Plastic Rods, Tubes, and Shapes<sup>1</sup>

This standard is issued under the fixed designation D 5436; the number immediately following the designation indicates the year of original adoption or, in the case of revision, the year of last revision. A number in parentheses indicates the year of last reapproval. A superscript epsilon ( $\varepsilon$ ) indicates an editorial change since the last revision or reapproval.

This standard has been approved for use by agencies of the Department of Defense.

### 1. Scope\*

1.1 This specification covers poly(methyl methacrylate) rods, tubes, and other shapes produced by casting or machining cast blanks. This specification does not apply to heat-formed and molded or extruded parts and shapes, or sections that are made by assembling or joining two or more pieces.

NOTE 1—The properties included in this specification are those required to identify the types and grades of materials covered. There may be other requirements necessary to identify particular characteristics.

1.2 This standard does not purport to address all of the safety concerns, if any, associated with its use. It is the responsibility of the user of this standard to establish appropriate safety and health practices and determine the applicability of regulatory limitations prior to use.

NOTE 2-There is no known ISO equivalent to this standard.

### 2. Referenced Documents

- 2.1 ASTM Standards:<sup>2</sup>
- D 542 Test Method for Index of Refraction of Transparent Organic Plastics
- D 570 Test Method for Water Absorption of Plastics
- D 618 Practice for Conditioning Plastics and Electrical Insulating Materials for Testing<sup>2</sup> Practice for Conditioning Plastics for Testing
- D 638 Test Method for Tensile Properties of Plastics
- D 648 Test Method for Deflection Temperature of Plastics Under Flexural Load in the Edgewise Position
- D 792 Test Methods for Density and Specific Gravity (Relative Density) and Density of Plastics by Displacement

D 883 Terminology Relating to Plastics

- D 1003 Test Method for Haze and Luminous Transmittance of Transparent Plastics 01eba5bf58/astm-d5436-032008
- D 1600 Terminology offor Abbreviated Terms Relating to Plastics
- D 3892 Practice for Packaging/Packing of Plastics
- E 29 Practice for Using Significant Digits in Test Data to Determine Conformance with Specifications

### 3. Terminology

3.1 The terminology used in this specification is in accordance with Terminology D 883 and Terminology D 1600.

## 4. Classification

- 4.1 Types—This specification covers two types of cast methacrylate plastics:
- 4.1.1 Type UVA—Material having ultraviolet-lightabsorbing properties as shown in Table 1.
- 4.1.2 Type UVT-Material not subject to the light-absorbing properties shown in Table 1.
- 4.2 Finish—Castings may be specified with the following finishes:

#### \*A Summary of Changes section appears at the end of this standard.

Copyright © ASTM International, 100 Barr Harbor Drive, PO Box C700, West Conshohocken, PA 19428-2959, United States.

<sup>&</sup>lt;sup>+</sup> This specification is under the jurisdiction of ASTM Committee D-20 on Plastics and is the direct responsibility of Subcommittee D20.15 on Thermoplastic Materials. Current edition approved Nov. 10, 1999. Published February 2000. Originally published as D5436–93. Last previous edition D5436–93.

<sup>&</sup>lt;sup>1</sup> This specification is under the jurisdiction of ASTM Committee D20 on Plastics and is the direct responsibility of Subcommittee D20.15 on Thermoplastic Materials

Current edition approved Nov. 1, 2008. Published December 2008. Originally approved in 1993. Last previous edition approved in 2003 as D 5436-03.

<sup>&</sup>lt;sup>2</sup> For referenced ASTM standards, visit the ASTM website, www.astm.org, or contact ASTM Customer Service at service@astm.org. For Annual Book of ASTM Standards , Vol 08.01.volume information, refer to the standard's Document Summary page on the ASTM website.

	D	5436 -	03	(2008)
--	---	--------	----	--------

 
 TABLE 1 Detail Requirements for Cast Methacrylate Rods, Tubes, and Shapes

	Type UVA	Type UVT
Index of refraction, n <sub>D</sub> , 23°C		
min:	1.48	1.48
max:	1.50	1.50
Specific gravity, 23/23°C (73.4/73.4°F)		
min:	1.18	1.18
max:	1.20	1.20
Spectral transmittance, %, max		
270 nm:	5	
280 nm:	5	
290 nm:	5	
310 nm:	5	
340 nm:	5	
Luminous transmittance, %, min		
up to 4.7 mm (0.187 in.) thickness:	91	91
25.4 mm (1.00 in.) thickness:	89	89
greater than 25.4 mm (1.00 in.) thickness:	87	87
Haze, %, max	3.0	3.0
Deflection temperature under load at 1820	see Fig. 1	<del>see F</del>
<del>── kPa (264 psi), °C</del>		
Deflection temperature under load at 1820		
kPa (264 psi), °C (°F) min.		
<del>ig.)</del>	<del>87 (188.6)</del>	<del>87 (188.6)</del>
<12.0 mm (0.472 in.)	<u>87 (188.6)</u>	87 (188.6)
>12.0 mm (0.472 in.)–24.0 mm (0.944 in.)	88 (190.4)	88 (190.4)
>24.0 mm (0.944 in.)–100 mm (3.937 in.)	93 (199.4)	93 (199.4)
Water absorption at 23°C		
Gain in weight, 3.2 mm (0.125 in.) thick, %,	0.8	0.8
max		
Tensile strength at 23°C (73.4°F), min, MPa	55 (8000)	55 (8000)
(psi)		
Elongation at break, %, min	2	2

# 4.2.1 *Finish 1*—Rods, tubes, and shapes having a smooth surface finish obtained either in the casting process or by highly polishing the surface.

4.2.2 Finish 2—Rods, tubes, and shapes having a rough, unfinished surface which may be frosted, abraded, sanded, machined, or as-cast.

NOTE 3-The sawed ends of Finish 1 and Finish 2 rods, tubes, and shapes are not polished.

https://standards.iteh.ai/catalog/standards/sist/eaeca3b3-412b-4fa7-9a46-6a01eba5bf58/astm-d5436-032008 5. General Requirements

#### 5. General Requirements

5.1 Finish 1 and Finish 2 cast tubes are subject to the following permissible variations from the specified dimensions:

5.1.1 Cast tubes may be specified with either Type A or Type B wall thickness tolerances as listed in Table 2. Type A tolerances are specified for applications where wall thickness is critical to performance, otherwise Type B is generally specified.

5.1.2 Cast tubes are subject to the outside-diameter tolerances listed in Table 3.

5.1.3 Cut-to-size lengths of cast tube are subject to the length tolerances listed in Table 4.

5.2 Finish 1 and Finish 2 cast rods are subject to the following dimensions and tolerances.

5.2.1 Cast rods are subject to the diameter tolerances listed in Table 5.

5.2.2 Cut-to-size lengths of cast rod are subject to the length tolerances listed in Table 4.

5.3 Tolerances for shapes other than simple rods and tubes depend upon the shapes themselves. Tolerances for these cast shapes are to be specified independently.

TABLE 2 Sizes and Permissible Tolerances for Wall Thickness of
Cast Tube

Nominal Wall Thickness,	Permissible Wall Thickness Tolerances, $\pm$ , mm (in.)		
mm (in.)	Туре А	Туре В	
up to 4.7 (0.187)	0.5 (0.020)	not applicable	
up to 6.4 (0.250)	0.6 (0.025)	1.1 (0.045)	
up to 9.5 (0.375)	0.9 (0.035)	1.4 (0.055)	
up to 12.7 (0.550)	1.1 (0.045)	1.5 (0.060)	
up to 19.0 (0.750)	1.5 (0.060)	2.3 (0.090)	
up to 25.4 (1.00)	3.8 (0.150)	not applicable	
greater than 25.4 (1.00)	6.4 (0.250)	not applicable	