



Designation: C693–93 (Reapproved 2003) Designation: C 693 – 93 (Reapproved 2008)

Standard Test Method for Density of Glass by Buoyancy¹

This standard is issued under the fixed designation C 693; the number immediately following the designation indicates the year of original adoption or, in the case of revision, the year of last revision. A number in parentheses indicates the year of last reapproval. A superscript epsilon (ϵ) indicates an editorial change since the last revision or reapproval.

1. Scope

1.1 This test method covers the determination of the density of glasses at or near 25°C, by buoyancy.

1.2 *This standard does not purport to address all of the safety concerns, if any, associated with its use. It is the responsibility of the user of this standard to establish appropriate safety and health practices and determine the applicability of regulatory limitations prior to use.*

2. Referenced Documents

2.1 *ASTM Standards:*²

E 12 [Terminology Relating to Density and Specific Gravity of Solids, Liquids, and Gases](#)

3. Terminology

3.1 *Definition:*

3.1.1 *density of solids*—the mass of a unit volume of a material at a specified temperature. The units shall be stated as grams per cubic centimetre (see Terminology E 12).

4. Significance and Use

4.1 Density as a fundamental property of glass has basic significance. It is useful in the physical description of the glass and as essential data for research, development, engineering, and production.

5. Apparatus

5.1 *Analytical Balance*, with sensitivity and accuracy of 0.1 mg.

5.2 *Beaker*, of convenient capacity (250 to 750 cm³) to fit inside the balance chamber and allow immersion of the basket or wire loop specimen holder in distilled water.

5.3 *Thermometers*, calibrated (20 to 30°C), sensitive to 0.1°C for determining air and water temperatures.

5.4 *Nickel-Chromium-Iron or Platinum-Alloy Wire*, less than 0.2-mm diameter for suspending the specimen either in a basket or a loop made of the same wire. The suspension wire shall be cleaned by degreasing or heating in a vacuum.³ An acceptable alternative method of cleaning the platinum-alloy wire is to heat in an oxidizing gas flame until there is no longer any color emitted from the gases passing around the wire.

5.5 *Weights*, with accuracy of 0.1 mg.

5.6 *Barometer*, with sensitivity of 1-mm Hg (optional, see Note 3).

6. Reagent

6.1 *Distilled Water*, fresh, boiled, and used within 24 h, allowed to stabilize at balance air temperature for at least 2 h in the beaker.

7. Test Specimen

7.1 Specimens weighing about 20 g, with a minimum of seeds or other inclusions (Note 1), shall be taken or cut from the sample object, preferably in cylindrical or rectangular bar form with smooth, slightly rounded surfaces having no cracks or sharp edges.

¹ This test method is under the jurisdiction of ASTM Committee C14 on Glass and Glass Products and is the direct responsibility of Subcommittee C14.04 on Physical and Mechanical Properties.

Current edition approved April 10, 2003. Published July 1993. Originally approved in 1971. Last previous edition approved in 1988 as C693–84 (1988)^{ε1}.

Current edition approved April 1, 2008. Published December 2008. Originally approved in 1971. Last previous edition approved in 2003 as C 693 – 93 (2003).

² Discontinued—Replaced by E1547, *Annual Book of ASTM Standards*, Vol 15.05.

³ Withdrawn. The last approved historical version of this standard is referenced on www.astm.org

³ Bowman, H. A., and Schoonover, R. M., "Procedure for High Precision Density Determinations by Hydrostatic Weighing." *Journal of Research*, National Bureau of Standards, Vol 71C, No. 3, July–August 1967, pp. 179–198.