
Primerjalna preskusna metoda za sproščanje niklja iz izdelkov, vstavljenih v prebodene dele človeškega telesa, in izdelkov, ki so v neposrednem in daljšem stiku s kožo

Reference test method for release of nickel from all post assemblies which are inserted into pierced parts of the human body and articles intended to come into direct and prolonged contact with the skin

Referenzprüfverfahren zur Bestimmung der Nickellässigkeit von sämtlichen Stäben, die in durchstochene Körperteile eingeführt werden und Erzeugnissen, die unmittelbar und länger mit der Haut in Berührung kommen

<https://standards.iteh.ai/catalog/standards/sist/73e03b5-89eb-4491-a444-3d5d74529b93/osist-pr-en-1811-2021>

Méthode d'essai de référence relative à la libération du nickel par les assemblages de tiges qui sont introduites dans les parties percées du corps humain et les produits destinés à entrer en contact direct et prolongé avec la peau

Ta slovenski standard je istoveten z: prEN 1811

ICS:

39.060 Nakit Jewellery

oSIST prEN 1811:2021

en,fr,de

iTeh STANDARD PREVIEW
(standards.iteh.ai)

[oSIST prEN 1811:2021](#)

<https://standards.iteh.ai/catalog/standards/sist/73e03b5-89eb-4491-a444-3d5d74529f93/osist-pren-1811-2021>

EUROPEAN STANDARD
NORME EUROPÉENNE
EUROPÄISCHE NORM

DRAFT
prEN 1811

November 2021

ICS 39.060

Will supersede EN 1811:2011+A1:2015

English Version

Reference test method for release of nickel from all post assemblies which are inserted into pierced parts of the human body and articles intended to come into direct and prolonged contact with the skin

Méthode d'essai de référence relative à la libération du nickel par les assemblages de tiges qui sont introduites dans les parties percées du corps humain et les produits destinés à entrer en contact direct et prolongé avec la peau

Referenzprüfverfahren zur Bestimmung der Nickellässigkeit von sämtlichen Stäben, die in durchstochene Körperteile eingeführt werden und Erzeugnissen, die unmittelbar und länger mit der Haut in Berührung kommen

This draft European Standard is submitted to CEN members for enquiry. It has been drawn up by the Technical Committee CEN/TC 347.

If this draft becomes a European Standard, CEN members are bound to comply with the CEN/CENELEC Internal Regulations which stipulate the conditions for giving this European Standard the status of a national standard without any alteration.

This draft European Standard was established by CEN in three official versions (English, French, German). A version in any other language made by translation under the responsibility of a CEN member into its own language and notified to the CEN-CENELEC Management Centre has the same status as the official versions.

CEN members are the national standards bodies of Austria, Belgium, Bulgaria, Croatia, Cyprus, Czech Republic, Denmark, Estonia, Finland, France, Germany, Greece, Hungary, Iceland, Ireland, Italy, Latvia, Lithuania, Luxembourg, Malta, Netherlands, Norway, Poland, Portugal, Republic of North Macedonia, Romania, Serbia, Slovakia, Slovenia, Spain, Sweden, Switzerland, Turkey and United Kingdom.

Recipients of this draft are invited to submit, with their comments, notification of any relevant patent rights of which they are aware and to provide supporting documentation.

Warning : This document is not a European Standard. It is distributed for review and comments. It is subject to change without notice and shall not be referred to as a European Standard.



EUROPEAN COMMITTEE FOR STANDARDIZATION
COMITÉ EUROPÉEN DE NORMALISATION
EUROPÄISCHES KOMITEE FÜR NORMUNG

CEN-CENELEC Management Centre: Rue de la Science 23, B-1040 Brussels

Contents	Page
European foreword	4
Introduction	5
1 Scope	6
2 Normative references	6
3 Terms and definitions	6
4 Principle of the procedure	7
5 Reagents	7
6 Apparatus	8
7 Samples	9
7.1 Number of test samples	9
7.2 Sample area	9
7.2.1 Definition of sample area	9
7.2.2 Determination of sample area	9
7.2.3 Masking of areas other than sample area	9
7.3 Sample degreasing before testing	10
8 Procedure	10
8.1 Preparation of test solution	10
8.2 Release procedure	10
8.3 Blank tests	11
8.4 Determination of nickel	11
8.4.1 General	11
8.4.2 Calibration solutions	11
8.4.3 Detection limit and quantification limit	11
8.4.4 Number of replicate measurements	11
9 Calculations	12
9.1 Nickel release	12
9.2 Interpretation of results	12
9.2.1 General	12
9.2.2 Conformity assessment	12
9.2.3 Uncertainty budget	13
10 Test report	13
Annex A (informative) Expanded measurement uncertainty of the test procedure and compliance assessment	14
Annex B (informative) Preparation of all post assemblies which are inserted into pierced parts of the human body and of articles intended to come into direct and prolonged contact with the skin prior to nickel testing	16
B.1 General	16
B.2 Principle	16
B.3 Determination of the nickel release test method	16

B.4	Determination of surfaces coming into direct and prolonged contact with the skin or pierced parts of the body	16
B.5	Methods of determining the surface areas.....	26
B.6	Vessel for nickel release testing.....	27
	Annex C (informative) Articles made from dissimilar materials	28
	Bibliography	29

iTeh STANDARD PREVIEW (standards.iteh.ai)

[oSIST prEN 1811:2021](https://standards.iteh.ai/catalog/standards/sist/73e03b5-89eb-4491-a444-3d5d74529f93/osist-pren-1811-2021)

<https://standards.iteh.ai/catalog/standards/sist/73e03b5-89eb-4491-a444-3d5d74529f93/osist-pren-1811-2021>

prEN 1811:2021 (E)

European foreword

This document (prEN 1811:2021) has been prepared by Technical Committee CEN/TC 347 “Methods for analysis of allergens”, the secretariat of which is held by SNV.

This document is currently submitted to the CEN Enquiry.

This document will supersede EN 1811:2011+A1:2015.

This document has been prepared under a Standardization Request given to CEN by the European Commission and the European Free Trade Association.

iTeh STANDARD PREVIEW
(standards.iteh.ai)

[oSIST prEN 1811:2021](https://standards.iteh.ai/catalog/standards/sist/73e03b5-89eb-4491-a444-3d5d74529f93/osist-pren-1811-2021)

<https://standards.iteh.ai/catalog/standards/sist/73e03b5-89eb-4491-a444-3d5d74529f93/osist-pren-1811-2021>

Introduction

Nickel is the most frequent cause of contact allergy in Europe and adverse skin reaction to nickel has been known for many decades.

Skin absorption of a sufficient amount of nickel ions, which are released from some nickel-containing materials which are inserted into pierced ears or other pierced parts of the human body or which are in direct and prolonged contact with the skin, is required to cause sensitization.

Once sensitized, further exposure to soluble nickel salts ions results in allergic contact dermatitis. It is known that sensitization to nickel requires higher exposure levels than does the elicitation in already sensitized individuals. There is a large variation in the degree of sensitivity to nickel between individuals. This widespread health problem has forced the introduction of a number of measures designed to reduce its prevalence. These measures include the requirements of this document which provides an *in vitro* chemical test that correlates as far as possible with the variable human biological reactions that occur when metallic or metallic coated articles containing nickel are in direct and prolonged contact with the skin or inserted into pierced parts of the body. This document provides a measure of the release of nickel from an article immersed for one week in artificial sweat. Clinical patch-testing of a small selection of nickel-containing alloys and coatings on nickel-sensitized persons indicates that high and low results achieved with the present analytical method correspond closely with patch-test reactivity. Moreover, a nickel migration limit of 0,5 $\mu\text{g}/\text{cm}^2/\text{week}$ for articles intended to come into direct and prolonged contact with the skin and a limit of less than 0,2 $\mu\text{g}/\text{cm}^2/\text{week}$ for all post piercing assemblies inserted into pierced ears and other pierced parts of the human body has been set in Commission Regulation (EC) No 1907/2006 of the European Parliament and the Council (in the current version).

(standards.iteh.ai)

[oSIST prEN 1811:2021](https://standards.iteh.ai/catalog/standards/sist/73e03b5-89eb-4491-a444-3d5d74529f93/osist-pren-1811-2021)

<https://standards.iteh.ai/catalog/standards/sist/73e03b5-89eb-4491-a444-3d5d74529f93/osist-pren-1811-2021>

1 Scope

This document specifies a method for simulating the release of nickel from all post assemblies which are inserted into pierced ears and other pierced parts of the human body and articles intended to come into direct and prolonged contact with the skin in order to determine whether such articles are in compliance with No. 27 Annex XVII of Regulation (EC) No 1907/2006 of the European Parliament and of the Council (REACH).

Spectacle frames and sunglasses are excluded from the scope of this document.

NOTE Spectacle frames and sunglasses are subject to the requirements of EN 16128.

2 Normative references

The following documents are referred to in the text in such a way that some or all of their content constitutes requirements of this document. For dated references, only the edition cited applies. For undated references, the latest edition of the referenced document (including any amendments) applies.

EN 12472, *Method for the simulation of accelerated wear and corrosion for the detection of nickel release from coated items*

EN ISO 3696, *Water for analytical laboratory use - Specification and test methods (ISO 3696)*

3 Terms and definitions

For the purposes of this document, the following terms and definitions apply.

ISO and IEC maintain terminological databases for use in standardization at the following addresses:

- IEC Electropedia: available at <https://www.electropedia.org/>
- ISO Online browsing platform: available at <https://www.iso.org/obp>

3.1

homogeneous

of uniform composition throughout that cannot be separated into different materials

Note 1 to entry: A coated material is not homogeneous.

3.2

representative

best estimate for the effective release rate of all surfaces which are in direct and prolonged contact with the skin or pierced parts of the body under normal and foreseeable conditions of use

3.3

surface finish

appearance and texture of a surface characterized by its smoothness or roughness

Note 1 to entry: In order of increasing smoothness, the surface finish can be typically described as machined finish, cut finish, brushed finish, matt finish, satin finish, mirror or polished finish.

3.4

sample area

a

surface(s) that is/are immersed in the test solution and not covered with a masking agent

3.5**disassemble**

separate into its constituent parts without damaging these parts or their surface condition

3.6**post assembly**

ear stud or body piercing article

3.7**test solution**

solution as prepared according to 8.1

3.8**release solution**

solution resulting from the release procedure according to 8.2

4 Principle of the procedure

The article to be tested for nickel release is placed in a solution of artificial sweat for one week. The concentration of dissolved nickel in the solution is determined by an appropriate analytical method, for example inductively-coupled plasma spectrometry. The nickel release is expressed in micrograms per square centimetre per week ($\mu\text{g}/\text{cm}^2/\text{week}$).

Articles with non-nickel-containing outer coatings that come into direct and prolonged contact with the skin shall be tested according to EN 12472, followed by this standard.

NOTE Information on the presence of nickel can be obtained by performing one of the tests specified in CEN/TR 12471 (under preparation).

[oSIST prEN 1811:2021](https://standards.iteh.ai/catalog/standards/sist/73e03b5-89eb-4491-a444-3d5d74529f93/osist-pren-1811-2021)

5 Reagents

<https://standards.iteh.ai/catalog/standards/sist/73e03b5-89eb-4491-a444-3d5d74529f93/osist-pren-1811-2021>

Except where indicated, all reagents, materials and apparatus that can come into contact with test parts or reagents shall be demonstrably free of nickel, and all reagents shall be of recognized analytical grade or better.

5.1 Deionised water according to EN ISO 3696, grade 2.

5.2 Sodium chloride, NaCl.

5.3 DL-lactic acid, $\text{CH}_3\text{CHOHCOOH}$, > 88 % (m/m).

5.4 Urea, $\text{CO}(\text{NH}_2)_2$.

5.5 Sodium hydroxide pellets, purity ≥ 98 %, anhydrous.

5.5.1 Preparation of 1 M sodium hydroxide solution.

Weigh $4 \text{ g} \pm 0,01 \text{ g}$ sodium hydroxide (5.5), transfer to a 100 ml beaker and add 50 ml deionised water (5.1). Stir and cool to room temperature. Transfer the solution to a 100 ml volumetric flask and make up to volume with deionised water (5.1).

Alternatively, it is possible to use 1 M ready-to-use solution.

prEN 1811:2021 (E)**5.5.2 Preparation of 0,1M sodium hydroxide solution.**

Transfer 25 ml of the 1 M sodium hydroxide solution (5.5.1) to a 250 ml volumetric flask and make up to volume with deionised water (5.1).

Alternatively, it is possible to use 0,1 M ready-to-use solution.

5.6 Hydrochloric acid, 32 % (m/m).**5.6.1 Preparation of 0,1 M hydrochloric acid solution.**

Transfer 1 ml of hydrochloric acid (5.6) into a 100 ml volumetric flask and make up to volume with deionised water (5.1).

Alternatively, it is possible to use 0,1 M ready-to-use solution.

5.7 Nitric acid, 65 % to 70 % (m/m).**5.7.1 Diluted nitric acid, approximately 5 % (m/m).**

Transfer 30 ml of nitric acid (5.7) into a 500-ml beaker containing about 350 ml of deionised water (5.1). Stir and cool to room temperature. Transfer the solution to a 500-ml volumetric flask and make up to volume with deionised water.

5.8 Degreasing solution.

Dissolve 5 g of an anionic surface-active agent such as sodium dodecylbenzene sulfate or sodium alkylaryl sulfate in 1 000 ml deionised water (5.1). An appropriately diluted, neutral, commercially available detergent may be used.

5.9 Wax or lacquer (e.g. suitable for electroplating purposes) capable of protecting a surface from nickel release.

<https://standards.itech.ai/catalog/standards/sist/73e03b5-89eb-4491-a444-3d5d74529f93/osist-pren-1811-2021>

The wax or lacquer shall be shown to prevent nickel release from a nickel-releasing surface when one or more coats are applied in the same manner as on a test sample and shall not affect the nickel content of the release solution. The wax/ lacquer shall be tested to demonstrate its suitability for the intended purpose.

NOTE 1 When using wax, the samples are dipped into the molten wax. To improve the adhesion of the wax, the article can be pre-warmed, provided that article properties are not changed.

NOTE 2 To cover cracks and fissures, it might be necessary to apply more than one coating of lacquer, 2 to 3 coats might be required to achieve the desired outcome. It can be helpful to inspect the quality of masking visually with a low-powered (e.g. 2x to 5x) magnifier.

6 Apparatus**6.1 Usual laboratory apparatus.****6.2 A pH-meter**, accurate to $\pm 0,05$ pH.

6.3 An analytical instrument capable of detecting a concentration of 0,01 mg nickel per litre in the final release solution.

It is recommended to use either an inductively-coupled plasma spectrometer (ICP-OES, optical emission, or ICP-MS, mass spectrometer) or an electro thermal excitation atomic absorption spectrometer (GFAAS).

6.4 Thermostatically controlled water-bath or oven with or without cooling option, capable of maintaining a temperature of (30 ± 2) °C.

6.5 A vessel with lid, both composed of a non-metallic, nickel-free and nitric-acid-resistant material, such as glass and/or polypropylene and/or polytetrafluoroethylene and/or polystyrene.

The sample shall be suspended in the liquid by a holder made from the same materials as listed above, so as to limit contact of the sample area (7.2.1) with the walls and base of the vessel. The size and shape of vessel and holder shall be chosen so as to minimize the volume of test solution required to completely cover the article to be tested.

NOTE A thread can be used to hang the samples in the liquid without touching the vessel.

In order to remove any trace of nickel, the vessel and holder shall be pre-treated by being stored in a solution of diluted nitric acid (5.7.1) for at least 4 h. After acid cleaning, rinse the vessel and holder with deionised water and dry.

6.6 Device for measuring length, for example a digital calliper accurate to at least 50 µm or a micrometer accurate to at least 5 µm.

7 Samples

7.1 Number of test samples

A minimum of three test samples of the same batch shall be tested wherever possible.

7.2 Sample area

(standards.iteh.ai)

7.2.1 Definition of sample area

Only the surface(s) that come(s) into direct and prolonged contact with the skin and/or that has/have contact with the pierced parts of the body shall be tested (i.e. the sample area).

The test laboratory shall refer to B.4 in order to determine which surfaces are to be tested.

For the calculation of the sample area for the nickel release determination, the areas of non-nickel-containing parts, shall not be included in the calculation.

7.2.2 Determination of sample area

Determination of the sample area (a) in square centimetres is achieved by marking the contour of the sample area assuming that the article is worn or used as intended (refer to Annex B) and measuring it by an appropriate measuring device (6.6).

In order to achieve the required degree of analytical sensitivity, a minimum sample area of 0,2 cm² shall be tested. If necessary, identical articles may be tested together to obtain this minimum area.

The closer the nickel release is to the limits specified in the REACH regulation, or the smaller the sample area is, the more precise the surface measurement needs to be.

7.2.3 Masking of areas other than sample area

In order to prevent release of nickel from areas other than the sample area, such areas shall be removed or protected from the test solution. This can be achieved after degreasing (see 7.3) by the application of one or more coatings of a wax or lacquer (5.9) that has been shown to protect from nickel release.

The test laboratory should see B.4 in order to determine which surfaces are to be tested.

NOTE If the contact zone with the skin is representative of the whole article, consider testing it without masking. See B.4 for guidance.

prEN 1811:2021 (E)**7.3 Sample degreasing before testing**

Gently swirl the sample for 2 min in degreasing solution (5.8) at room temperature. Rinse thoroughly with deionised water and dry using absorbing paper. After degreasing, articles shall be handled with plastic forceps or clean protective gloves.

NOTE This cleaning stage is intended to remove extraneous grease and skin secretions due to handling, but not any protective coatings.

8 Procedure**8.1 Preparation of test solution**

The test solution consists of deionised water (5.1) containing:

- 0,5 % (m/m) sodium chloride (5.2);
- 0,1 % (m/m) lactic acid (5.3);
- 0,1 % (m/m) urea (5.4); and
- 1 M (5.5.1) and 0,1 M (5.5.2) sodium hydroxide solution.

The test solution shall be prepared as follows:

Pour 900 ml of freshly prepared deionised water (5.1) into a 1 000 ml beaker. Add $1,00 \pm 0,01$ g of urea (5.4), $5,00 \pm 0,05$ g of sodium chloride (5.2) and $1,00 \pm 0,01$ g of lactic acid (5.3), and stir until dissolved.

Calibrate a pH meter in accordance with the manufacturer's instructions using freshly prepared buffer solutions.

Immerse the pH electrode into the test solution and measure the pH. Slowly and gently, add drop by drop a volume of 1 M sodium hydroxide (5.5.1) until a pH of 5,5 is reached and subsequently with continuous stirring, add slowly and gently drop by drop a volume of 0,1 M sodium hydroxide (5.5.2) until a pH $6,5 \pm 0,05$ is reached and remains stable.

Measure the pH after 10 min from the last addition of 0,1 M sodium hydroxide to ensure that the pH is in the range $6,5 \pm 0,05$.

Transfer the solution to a 1 000 ml volumetric flask and make up to volume with deionised water. Before use, ensure that the pH of the test solution is in the range of pH $6,5 \pm 0,05$.

If it is necessary to reduce the pH of the solution to $6,5 \pm 0,05$ before testing, this shall be done by adding slowly and gently with continuous stirring drop by drop a volume of 0,1 M hydrochloric acid (5.6.1).

For each test, the test solution shall have been prepared within the last 24 h.

8.2 Release procedure

NOTE 1 In the following text the term "test solution" represents the solution as prepared according to 8.1, the "release solution" is the solution resulting from the release procedure. See also definitions 3.8 and 3.7.

Place the degreased sample (7.3), suspended by its holder, in the test vessel (6.5). Add an amount of test solution corresponding to approximately 1 ml per cm^2 sample area (see B.5 and B.6). The suspended sample area shall be totally immersed. It is not necessary to immerse areas that are completely protected by wax or lacquer (see 7.2.3). The minimum volume of test solution shall be 0,5 ml irrespective of the surface area. Note the sample area and the amount of the test solution used. Close the