

---

**Žerjavi - Konstrukcija, splošno - 3-1. del: Mejna stanja in dokaz varnosti jeklene nosilne konstrukcije**

Cranes - General Design - Part 3-1: Limit States and proof competence of steel structure

Krane - Konstruktion allgemein - Teil 3-1: Grenzzustände und Sicherheitsnachweis von Stahltragwerken

Appareils de levage à charge suspendue - Conception générale - Partie 3-1 : Etats limites et vérification d'aptitude des charpentes en acier

**iTeh STANDARD PREVIEW**

<https://standards.itih.ai/catalog/standards/sist/07ce89e5-68e6-46af-a417-dd045187com/sist-en-13001-3-1-2012a2-2018>

**Ta slovenski standard je istoveten z: EN 13001-3-1:2012+A2:2018**

---

**ICS:**

53.020.20      Dvigala      Cranes

**SIST EN 13001-3-1:2012+A2:2018      en,fr,de**

## **iTeh STANDARD PREVIEW** **(standards.iteh.ai)**

SIST EN 13001-3-1:2012+A2:2018

<https://standards.iteh.ai/catalog/standards/sist/07ce89c5-68e6-46af-a417-dd643f87ebf1/sist-en-13001-3-1-2012a2-2018>

EUROPEAN STANDARD  
NORME EUROPÉENNE  
EUROPÄISCHE NORM

**EN 13001-3-1:2012+A2**

January 2018

ICS 53.020.20

Supersedes EN 13001-3-1:2012+A1:2013

English Version

**Cranes - General Design - Part 3-1: Limit States and proof  
competence of steel structure**

Appareils de levage à charge suspendue - Conception  
générale - Partie 3-1 : Etats limites et vérification  
d'aptitude des charpentes en acier

Krane - Konstruktion allgemein - Teil 3-1:  
Grenzzustände und Sicherheitsnachweis von  
Stahltragwerken

This European Standard was approved by CEN on and includes Amendment 2 approved by CEN on 30 October 2017.

CEN members are bound to comply with the CEN/CENELEC Internal Regulations which stipulate the conditions for giving this European Standard the status of a national standard without any alteration. Up-to-date lists and bibliographical references concerning such national standards may be obtained on application to the CEN-CENELEC Management Centre or to any CEN member.

This European Standard exists in three official versions (English, French, German). A version in any other language made by translation under the responsibility of a CEN member into its own language and notified to the CEN-CENELEC Management Centre has the same status as the official versions.

CEN members are the national standards bodies of Austria, Belgium, Bulgaria, Croatia, Cyprus, Czech Republic, Denmark, Estonia, Finland, Former Yugoslav Republic of Macedonia, France, Germany, Greece, Hungary, Iceland, Ireland, Italy, Latvia, Lithuania, Luxembourg, Malta, Netherlands, Norway, Poland, Portugal, Romania, Serbia, Slovakia, Slovenia, Spain, Sweden, Switzerland, Turkey and United Kingdom.



EUROPEAN COMMITTEE FOR STANDARDIZATION  
COMITÉ EUROPÉEN DE NORMALISATION  
EUROPÄISCHES KOMITEE FÜR NORMUNG

**CEN-CENELEC Management Centre: Rue de la Science 23, B-1040 Brussels**

Contents	Page
1 Scope .....	7
2 Normative references .....	7
3 Terms ,definitions, symbols and abbreviations.....	9
3.1 Terms and definitions .....	9
3.2 Symbols and abbreviations .....	9
4 General.....	12
4.1 Documentation.....	12
4.2 Materials for structural members.....	13
4.2.1 Grades and qualities.....	13
4.2.2 Impact toughness .....	16
4.3 Bolted connections .....	18
4.3.1 Bolt materials .....	18
4.3.2 General.....	18
4.3.3 Shear and bearing connections.....	19
4.3.4 Friction grip type (slip resistant) connections.....	19
4.3.5 Connections loaded in tension .....	19
4.4 Pinned connections .....	19
4.5 Welded connections.....	20
4.6 Proof of competence for structural members and connections.....	20
5 Proof of static strength.....	21
5.1 General.....	21
5.2 Limit design stresses and forces.....	21
5.2.1 General.....	21
5.2.2 Limit design stress in structural members.....	21
5.2.3 Limit design forces in bolted connections.....	23
5.2.4 Limit design forces in pinned connections .....	31
5.2.5 Limit design stresses in welded connections.....	35
5.3 Execution of the proof .....	38
5.3.1 Proof for structural members.....	38
5.3.2 Proof for bolted connections.....	38
5.3.3 Proof for pinned connections .....	39
5.3.4 Proof for welded connections.....	40
6 Proof of fatigue strength.....	40
6.1 General.....	40
6.2 Limit design stresses.....	42
6.2.1 Characteristic fatigue strength.....	42
6.2.2 Weld quality .....	44
6.2.3 Requirements for fatigue testing.....	45
6.3 Stress histories.....	45
6.3.1 General.....	45
6.3.2 Frequency of occurrence of stress cycles .....	45
6.3.3 Stress history parameter .....	46
6.3.4 Stress history classes S.....	47
6.4 Execution of the proof .....	48

6.5	Determination of the limit design stress range .....	49
6.5.1	Applicable methods .....	49
6.5.2	Direct use of stress history parameter .....	49
6.5.3	Use of class S .....	49
6.5.4	Combined effect of normal and shear stresses .....	51
7	Proof of static strength of hollow section girder joints .....	51
8	Proof of elastic stability .....	52
8.1	General .....	52
8.2	Lateral buckling of members loaded in compression .....	52
8.2.1	Critical buckling load .....	52
8.2.2	Limit compressive design force .....	54
8.3	Buckling of plate fields subjected to compressive and shear stresses .....	57
8.3.1	General .....	57
8.3.2	Limit design stress with respect to longitudinal stress $\sigma_x$ .....	59
8.3.3	Limit design stress with respect to transverse stress $\sigma_y$ .....	61
8.3.4	Limit design stress with respect to shear stress $\tau$ .....	63
8.4	Execution of the proof .....	64
8.4.1	Members loaded in compression .....	64
8.4.2	Plate fields .....	64
Annex A (informative)	Limit design shear force $F_{v,Rd}$ per bolt and per shear plane for multiple shear plane connections .....	66
Annex B (informative)	Preloaded bolts .....	67
Annex C (normative)	Design weld stresses $\sigma_{w,Sd}$ and $\tau_{w,Sd}$ .....	69
C.1	Butt joint .....	69
C.2	T-joint with fillet or partial penetration weld .....	70
C.3	Effective distribution length under concentrated load .....	71
C.4	Other types of welds .....	72
Annex D (normative)	Values of slope constant $m$ and characteristic fatigue strength $\Delta\sigma_c$ , $\Delta\tau_c$ .....	73
Annex E (normative)	Calculated values of limit design stress ranges $\Delta\sigma_{Rd}$ and $\Delta\sigma_{Rd,1}$ .....	94
Annex F (informative)	Evaluation of stress cycles (example) .....	96
Annex G (informative)	Calculation of stiffnesses for connections loaded in tension .....	98
Annex H (informative)	Hollow Sections .....	101
Annex I (informative)	Selection of a suitable set of crane standards for a given application ....	113
Annex ZA (informative)	Relationship between this European Standard and the Essential Requirements of EU Directive 2006/42/EC .....	114

## European foreword

This document (EN 13001-3-1:2012+A2:2018) has been prepared by Technical Committee CEN/TC 147 “Cranes - Safety”, the secretariat of which is held by BSI.

This European Standard shall be given the status of a national standard, either by publication of an identical text or by endorsement, at the latest by July 2018, and conflicting national standards shall be withdrawn at the latest by July 2018.

Attention is drawn to the possibility that some of the elements of this document may be the subject of patent rights. CEN [and/or CENELEC] shall not be held responsible for identifying any or all such patent rights.

This document includes Amendment 1 approved by CEN on 11 May 2013.

This document includes Amendment 2 approved by CEN on 30 October 2017.

This document supersedes A2 EN 13001-3-1:2012+A1:2013 A2.

The start and finish of text introduced or altered by amendment is indicated in the text by tags A1 A1 or A2 A2.

This document has been prepared under a mandate given to CEN by the European Commission and the European Free Trade Association, and supports essential requirements of EU Directive(s).

For relationship with EU Directive(s), see informative Annex ZA, which is an integral part of this document.

A1 CEN/TC 147/WG 2 has made a new edition of EN 13001-3-1 to adapt the standard as follows:

- Subclause 4.2.1 is changed in such a way that Table 2 is permanently valid and requirements for other materials are added, and
- editorial changes are done to improve the document. A1

A2 CEN/TC 147/WG 2 has made a new consolidation of EN 13001-3-1 to adapt the standard as follows:

- New steel qualities from EN 10149-2 and stainless steels from EN 10088-2 added to 4.2.1.
- Application of bolt preloading scatter in 5.2.3.3 was modified.
- Table 8 changed to exclude matching material for ultra-high strength steel.
- Fatigue strength specific resistance factors were adjusted in 6.1.
- Requirements for fatigue testing were modified.
- Formula for assessing combined effect of normal and shear stresses was changed in 6.5.4.
- Annex C improved for calculation of fillet welds.

- Characteristic fatigue strengths modified for notch cases D.1.1, D.1.2, D.3.29 and D.3.30.
- Number of minor changes for reasons of editorial and technical accuracy. <sup>(A2)</sup>

This European Standard is one Part of EN 13001, *Cranes — General design*. The other parts are as follows:

- *Part 1: General principles and requirements;*
- *Part 2: Load actions;*
- *Part 3-2: Limit states and proof of competence of wire ropes in reeving systems;*
- *Part 3-3: Limit states and proof of competence of wheel/rail contacts;*
- *Part 3-4: Limit states and proof of competence of machinery;*
- *Part 3-5: Limit states and proof of competence of forged hooks.*

According to the CEN-CENELEC Internal Regulations, the national standards organisations of the following countries are bound to implement this European Standard: Austria, Belgium, Bulgaria, Croatia, Cyprus, Czech Republic, Denmark, Estonia, Finland, Former Yugoslav Republic of Macedonia, France, Germany, Greece, Hungary, Iceland, Ireland, Italy, Latvia, Lithuania, Luxembourg, Malta, Netherlands, Norway, Poland, Portugal, Romania, Serbia, Slovakia, Slovenia, Spain, Sweden, Switzerland, Turkey and the United Kingdom.

## iTeh STANDARD PREVIEW (standards.iteh.ai)

[SIST EN 13001-3-1:2012+A2:2018](https://standards.iteh.ai/catalog/standards/sist/07ce89c5-68e6-46af-a417-dd643f87ebf1/sist-en-13001-3-1-2012a2-2018)

<https://standards.iteh.ai/catalog/standards/sist/07ce89c5-68e6-46af-a417-dd643f87ebf1/sist-en-13001-3-1-2012a2-2018>

**EN 13001-3-1:2012+A2:2018 (E)****Introduction**

This European Standard has been prepared to be a harmonized standard to provide one means for the mechanical design and theoretical verification of cranes to conform **EN** to **EN** the essential health and safety requirements of the Machinery Directive, as amended. This standard also establishes interfaces between the user (purchaser) and the designer, as well as between the designer and the component manufacturer, in order to form a basis for selecting cranes and components.

This European Standard is a type C standard as stated in EN ISO 12100.

The machinery concerned and the extent to which hazards, hazardous situations and events are covered are indicated in the scope of this standard.

When provisions of this type C standard are different from those which are stated in type A or B standards, the provisions of this type C standard take precedence over the provisions of the other standards, for machines that have been designed and built according to the provisions of this type C standard.

**iTeh STANDARD PREVIEW**  
**(standards.iteh.ai)**

SIST EN 13001-3-1:2012+A2:2018

<https://standards.iteh.ai/catalog/standards/sist/07ce89c5-68e6-46af-a417-dd643f87ebf1/sist-en-13001-3-1-2012a2-2018>



## 1 Scope

This European Standard is to be used together with EN 13001-1 and EN 13001-2 and as such they specify general conditions, requirements and methods to prevent mechanical hazards of cranes by design and theoretical verification.

NOTE Specific requirements for particular types of cranes are given in the appropriate European Standard for the particular crane type.

The following is a list of significant hazardous situations and hazardous events that could result in risks to persons during intended use and reasonably foreseeable misuse. Clauses 4 to 8 of this standard are necessary to reduce or eliminate risks associated with the following hazards:

- a) exceeding the limits of strength (yield, ultimate, fatigue);
- b) exceeding temperature limits of material or components;
- c) elastic instability of the crane or its parts (buckling, bulging).

This European Standard is not applicable to cranes which are manufactured before the date of its publication as EN and serves as reference base for the European Standards for particular crane types (see Annex I).

NOTE EN 13001-3-1 deals only with the limit state method in accordance with EN 13001-1.

## 2 Normative references

The following documents, in whole or in part, are normatively referenced in this document and are indispensable for its application. For dated references, only the edition cited applies. For undated references, the latest edition of the referenced document (including any amendments) applies.

☐A2☐ deleted reference ☐A2☐

EN 1993-1-8:2005, *Eurocode 3: Design of steel structures — Part 1-8: Design of joints*

EN 10025-2:2004, *Hot rolled products of structural steels — Part 2: Technical delivery conditions for non-alloy structural steels*

EN 10025-3:2004, *Hot rolled products of structural steels — Part 3: Technical delivery conditions for normalized/normalized rolled weldable fine grain structural steels*

EN 10025-4:2004, *Hot rolled products of structural steels — Part 4: Technical delivery conditions for thermomechanical rolled weldable fine grain structural steels*

EN 10025-6:2004, *Hot rolled products of structural steels — Part 6: Technical delivery conditions for flat products of high yield strength structural steels in the quenched and tempered condition*

EN 10029:2010, *Hot rolled steel plates 3 mm thick or above — Tolerances on dimensions and shape*

☐A2☐ deleted references ☐A2☐

**EN 13001-3-1:2012+A2:2018 (E)**

EN 10088-2:2014, *Stainless steels — Part 2: Technical delivery conditions for sheet/plate and strip of corrosion resisting steels for general purposes*

EN 10149-2:2013, *Hot-rolled flat products made of high yield strength steels for cold forming — Part 2: Delivery conditions for thermomechanically rolled steels*

EN 10149-3:2013, *Hot-rolled flat products made of high yield strength steels for cold forming — Part 3: Delivery conditions for normalized or normalized rolled steels* <sup>A2</sup>

EN 10160:1999, *Ultrasonic testing of steel flat product of thickness equal or greater than 6 mm (reflection method)*

EN 10163-1:2004, *Delivery requirements for surface conditions of hot-rolled steel plates, wide flats and sections — Part 1: General requirements*

EN 10163-2:2004, *Delivery requirements for surface conditions of hot-rolled steel plates, wide flats and sections — Part 2: Plate and wide flats*

EN 10163-3:2004, *Delivery requirements for surface conditions of hot-rolled steel plates, wide flats and sections — Part 3: Sections*

EN 10164:2004, *Steel products with improved deformation properties perpendicular to the surface of the product — Technical delivery conditions*

EN 13001-1, *Cranes — General design — Part 1: General principles and requirements*

EN 13001-2, *Crane safety — General design — Part 2: Load actions*

EN 20273:1991, *Fasteners — Clearance holes for bolts and screws (ISO 273:1979)*  
<https://standards.iteh.ai/catalog/standards/sist/07ce89c5-68e6-46af-a417-dd643f87ebf1/sist-en-13001-3-1-2012a2-2018>

EN ISO 148-1:2016 *Metallic materials — Charpy pendulum impact test — Part 1: test method* <sup>A2</sup>

EN ISO 286-2:2010, *Geometrical product specifications (GPS) — ISO code system for tolerances on linear sizes — Part 2: Tables of standard tolerance classes and limit deviations for holes and shafts (ISO 286-2:2010)*

EN ISO 898 1:2013, *Mechanical properties of fasteners made of carbon steel and alloy steel — Part 1: Bolts, screws and studs with specified property classes — Coarse thread and fine pitch thread (ISO 898 1:2013)* <sup>A2</sup>

EN ISO 5817:2014, *Welding — Fusion-welded joints in steel, nickel, titanium and their alloys (beam welding excluded) — Quality levels for imperfections (ISO 5817:2014)* <sup>A2</sup>

EN ISO 9013:2002, *Thermal cutting — Classification of thermal cuts — Geometrical product specification and quality tolerances (ISO 9013:2002)*

EN ISO 12100:2010, *Safety of machinery — General principles for design — Risk assessment and risk reduction (ISO 12100:2010)*

EN ISO 17659:2004, *Welding — Multilingual terms for welded joints with illustrations (ISO 17659:2002)*

ISO 4306-1:2007, *Cranes — Vocabulary — Part 1: General*

### 3 Terms, definitions, symbols and abbreviations

#### 3.1 Terms and definitions

For the purposes of this document, the terms and definitions given in EN ISO 12100:2010  $\square_{A2}$  *deleted text*  $\square_{A2}$  apply. For the definitions of loads, Clause 6 of ISO 4306-1:2007 applies.

#### 3.2 Symbols and abbreviations

The symbols and abbreviations used in this Part of the EN 13001 are given in Table 1.

**Table 1 — Symbols and abbreviations (1 of 4)**

Symbols, abbreviations	Description
$A$	cross section
$A_n$	net cross section
$A_S$	stress area of a bolt
$A_S$	shear area of the tear-out section (pinned connections)
$a$	length of plate in buckling
$a$	throat thickness of fillet welds
$a_r$	effective weld thickness
$b$	width of plate
$c$	edge stress ratio factor (buckling)
$D_o, D_i$	outer, inner diameter of hollow pin
$d$	diameter (shank of bolt, pin)
$d_o$	diameter of hole
$E$	modulus of elasticity
$F_b$	tensile force in bolt
$F_d$	limit force
$\square_{A1} F_k \square_{A1}$	characteristic value (force)
$F_p$	preloading force in bolt
$F_{Rd}$	limit design force
$F_e$	external force (on bolted connection)
$F_{b, Rd}$	limit design bearing force
$F_{b, Sd}, F_{bi, Sd}$	design bearing force
$F_{cs, Rd}$	limit design tensile force
$F_{p, d}$	design preloading force
$F_{cr}$	reduction in compression force due to external tension

Table 1 — Symbols and abbreviations (2 of 4)

Symbols, abbreviations	Description
$F_{t,Rd}$	limit design tensile force in bolt
$F_{t,Sd}$	external tensile force per bolt
$F_{v,Sd}$	design shear force per bolt and shear plane
$F_{vp,Rd}$	limit design shear force per pin and shear plane
$F_{vp,Sd}$	design shear force per pin and shear plane
$F_{s,Rd}$	limit design slip force per bolt and shear plane
$F_{vs,Rd}$	limit design shear force of the connected part
$F_{vd,Sd}$	design force in the connected part
$F_{vt,Rd}$	limit design tensile force of the connected part
$F_{\sigma,\tau}$	acting normal/shear force
$f$	maximum imperfection
$f_d$	limit stress
$f_k$	characteristic value (stress)
$f_{Rd}$	limit design stress
$f_u$	ultimate strength of material
$f_{ub}$	ultimate strength of bolts
$f_{w,Rd}$	limit design weld stress
$f_y$	yield stress of material, specified or measured
$f_{yb}$	yield stress of bolts
$f_{yp}$	yield stress of pins, specified or measured
$h_d$	distance between weld and contact level of acting load
$I, I_i$	moments of inertia of members
$k$	stress concentration factor (pinned connections)
$K_b$	stiffness of bolt
$K_c$	stiffness of connected parts
$k^*$	specific spectrum ratio factor
$k_m$	stress spectrum factor based on m of the detail under consideration
$k_3$	stress spectrum factor based on m = 3
$k_{ox}, k_{oy}, k_{\tau}$	buckling factors
$L$	element length (buckling)
$l_m$	gauge length
$l_r$	relevant weld length
$l_w$	weld length
$M_{Rd}$	limit design bending moment
$M_{Sd}$	design bending moment
$m$	slope constant of log $\Delta\sigma$ /log N-curve
$N$	compressive force (buckling)

Table 1 — Symbols and abbreviations (3 of 4)

Symbols, abbreviations	Description
$NC$	notch class
$N_k$	critical buckling load
$N_{ref}$	reference number of cycles
$min \sigma, max \sigma$	extreme values of stresses
$P_s$	probability of survival
$p$	penetration of weld
$Q$	shear (evaluation of stress cycles)
$q_i$	impact toughness parameter
$\alpha$	cross section parameter (lateral buckling)
$\alpha_b$	characteristic factor for bearing connection
$\alpha_L$	load introduction factor (bolted connection)
$\alpha_w$	characteristic factor for limit weld stress
$\gamma_m$	general resistance factor
$\gamma_{mf}$	fatigue strength specific resistance factor
$\gamma_p$	partial safety factor
$\gamma_R$	resulting resistance factor
$\gamma_S$	specific resistance factor
$\gamma_{Rb}$	resulting resistance factor of bolt
$\gamma_{sbb}, \gamma_{sbs}, \gamma_{sbt}$	specific resistance factors of bolted connections
$\gamma_{Rm}$	resulting resistance factor of members
$\gamma_{sm}$	specific resistance factor of members
$\gamma_{Rp}$	resulting resistance factor of pins
$\gamma_{spm}, \gamma_{sps}, \gamma_{spb}, \gamma_{spt}$	specific resistance factors of pins
$\gamma_{Rs}$	resulting resistance factor of slip-resistance connection
$\gamma_{ss}$	specific resistance factor of slip-resistance connection
$\gamma_{Rc}$	resulting resistance factor for tension on section with holes
$\gamma_{st}$	specific resistance factor for tension on section with holes
$\gamma_{Rw}$	resulting resistance factor of welding connection
$\gamma_{sw}$	specific resistance factor of welding connection
$\delta_p$	elongation from preloading
$\phi_2$	dynamic factor
$\kappa$	dispersion angle (wheel pressure)
$K, K_x, K_y, K_\tau$	reduction factors (buckling)
$\lambda$	width of contact area in weld direction

Table 1 — Symbols and abbreviations (4 of 4)

Symbols, abbreviations	Description
$\lambda_x, \lambda_y, \lambda_z$	non-dimensional plate slenderness (buckling)
$\psi$	edge stress ratio (buckling)
$\Delta F_b$	additional force
$\Delta \delta_t$	additional elongation
$\mu$	slip factor
$v$	relative total number of stress cycles <del><math>\overline{A_1}</math></del> deleted text $\overline{A_1}$
$v_D$	ratio of diameters
$\Delta \sigma_c$	characteristic value of stress range (normal stress)
$\Delta \tau_c$	characteristic value of stress range (shear stress)
$\sigma_e$	reference stress (buckling)
$\sigma_b$	lower extreme value of stress range
$\sigma_u$	upper extreme value of stress range
$\sigma_{Sd}$	design stress (normal)
$\tau_{Sd}$	design stress (shear)
$\sigma_{w, Sd}$	design weld stress (normal)
$\tau_{w, Sd}$	design weld stress (shear)
$\Delta \sigma_{Rd}$	limit design stress range (normal)
$\Delta \sigma_{Rd,1}$	limit design stress range for $k^* = 1$
$\Delta \tau_{Rd}$	limit design stress range (shear)
$\Delta \sigma_{Sd}$	design stress range (normal)
$\Delta \tau_{Sd}$	design stress range (shear)

## 4 General

### 4.1 Documentation

The documentation of the proof of competence shall include:

- design assumptions including calculation models,
- applicable loads and load combinations,
- material grades and qualities,
- weld quality levels, in accordance with EN ISO 5817,
- materials of connecting elements,
- relevant limit states,
- results of the proof of competence calculation. and tests when applicable.

## 4.2 Materials for structural members

### 4.2.1 Grades and qualities

European Standards specify materials and specific values. This standard gives a preferred selection.

For structural members, steel according to following European Standards should be used:

- a) Non-alloy structural steels EN 10025-2;
- b) Weldable fine grain structural steels in conditions:
  - 1) normalized (N) EN 10025-3;
  - 2) thermomechanical (M) EN 10025-4;
- c) High yield strength structural steels in the quenched and tempered condition EN 10025-6;
- d) High yield strength steels for cold forming in conditions:
  - 1) thermomechanical (M) EN 10149-2;
  - 2) normalized (N) EN 10149-3.

**[A2]** e) Austenitic stainless steels EN 10088-2.

Where stainless steels are welded, special attention should be given to the welding process and corrosion effects.

[SIST EN 13001-3-1:2012+A2:2018](https://standards.iteh.ai/catalog/standards/sist/07ce89c5-68e6-46af-a417-3110c33e90a8/en-13001-3-1:2012+A2:2018)

<https://standards.iteh.ai/catalog/standards/sist/07ce89c5-68e6-46af-a417-3110c33e90a8/en-13001-3-1:2012+A2:2018>

Table 2 shows specific values for the nominal value of strength  $f_u$ ,  $f_y$ . For limit design stresses  $f_{Rd}$  see 5.2. The values given are applicable for temperatures up to 100 °C for stainless steels and up to 150 °C for all other steels. For more information see the specific European Standard. **[A2]**

**[A1]** *deleted text* **[A1]**

To allow the use of nominal values of plate thicknesses in the proof calculations, the minus tolerance of the plate shall be equal or better than that of class A of EN 10029:2010. Otherwise the actual minimum value of plate thickness shall be used. To allow the use of nominal dimensions for other steel products than plates, their minus tolerances shall be within those of the relevant European standards for those products.

**[A1]** Grades and qualities other than those mentioned in the above standards and in Table 2 may be used if the mechanical properties and the chemical composition are specified in a manner corresponding to relevant European standard, and the following conditions are fulfilled:

- the design value of  $f_y$  is limited to  $f_u/1,05$  for materials with  $f_u/f_y < 1,05$ ;
- the percentage elongation at fracture  $A \geq 7\%$  on a gauge length  $L_0 = 5,65 \times \sqrt{S_0}$  (where  $S_0$  is the original cross-sectional area);
- the weldability or non-weldability of the material is specified and, if intended for welding, weldability is demonstrated;
- if the material is intended for cold forming, the pertinent parameters are specified. **[A1]**

NOTE Where it is deemed necessary to check for internal defects, classes of EN 10160 should be specified.