



Designation: F1304–03 ~~Designation: F 1304 – 08~~

Standard Test Method for Deflection of Resilient Floor Tile¹

This standard is issued under the fixed designation F 1304; the number immediately following the designation indicates the year of original adoption or, in the case of revision, the year of last revision. A number in parentheses indicates the year of last reappraisal. A superscript epsilon (ϵ) indicates an editorial change since the last revision or reappraisal.

1. Scope

1.1 This test method is used to determine the deflection of relatively rigid resilient floor tile such as vinyl composition tile.

1.2 *This standard does not purport to address all of the safety concerns, if any, associated with its use. It is the responsibility of the user of this standard to establish appropriate safety and health practices and determine the applicability of regulatory limitations prior to use.*

2. Referenced Documents

2.1 *ASTM Standards:*²

E 691 [Practice for Conducting an Interlaboratory Study to Determine the Precision of a Test Method](#)

F 141 [Terminology Relating to Resilient Floor Coverings](#)

2.2 *ANSI Standards:*

~~ANSI/ASQC Z1.4–1993~~ [ANSI/ASQC Z1.4 Sampling Procedures and Tables for Inspection by Attributes](#)³

3. Significance and Use

3.1 This test method measures a physical property associated with resilient floor tile's ability to conform to an uneven subfloor without breaking or cracking.

4. Apparatus

4.1 *Deflection Frame*, as shown in Fig. 1.

4.2 *Tensile Test Apparatus*, capable of holding the deflection frame and having a movement of at least 2.5 in. (64 mm) at a rate of 4 in. (100 mm)/min at a load of 10 lb (4.54 kg).

4.3 *Measuring Device*, for measuring the deflection of the specimen at break or pull out from between the support bars to a tolerance of 0.05 in. (1.3 mm).

4.4 *Cutting Device*, for cutting the samples to 2 by 9 in. (50 by 229 mm).

5. Sampling

~~5.1 For sampling, refer to ANSI/ASQC Z1.4–1993.~~

5.1 For sampling, refer to [ANSI/ASQC Z1.4–most recent version](#).

5.2 Specimens for test shall be $2 \pm \frac{1}{32}$ by $9 \pm \frac{1}{32}$ in. (50 ± 0.8 by 229 ± 0.8 mm).

5.3 Six samples shall be taken from each test unit, three cut with the long dimension in the machine direction, and three with the long dimension across the machine direction. These samples are tested for deflection.

6. Preparation of Apparatus

6.1 Install the deflection frame in the tensile tester. Check to see that the three bars are parallel, and that the center bar is accurately centered between the two outside bars. Position the frame so that the test sample can be placed with the wearing surface touching the center bar, and the back surface touching the two outer bars, without deflection of the sample. This is the zero point for measuring deflection. Check that the deflection speed of the tester is $4 \pm \frac{1}{8}$ in./min. (102 ± 3 mm/min.). Check the deflection

¹ This test method is under the jurisdiction of ASTM Committee F06 on Resilient Floor Coverings and is the direct responsibility of Subcommittee F06.20 on Test Methods - Products Construction/Materials .

Current edition approved March 10, 2003. Published May 2003. Originally approved in 1990. Last previous edition approved in 2001 as F1304–2001.

Current edition approved Dec. 1, 2008. Published January 2009. Originally approved in 1990. Last previous edition approved in 2003 as F1304–03.

² For referenced ASTM standards, visit the ASTM website, www.astm.org, or contact ASTM Customer Service at service@astm.org. For *Annual Book of ASTM Standards* - Vol 14.02, volume information, refer to the standard's Document Summary page on the ASTM website.

³ *Annual Book of ASTM Standards*, Vol 15.04.

³ Available from American National Standards Institute (ANSI), 25 W. 43rd St., 4th Floor, New York, NY 10036, <http://www.ansi.org>.