

**SLOVENSKI STANDARD**  
**kSIST-TS FprCEN ISO/TS 19590:2019**  
**01-januar-2019**

---

**Nanotehnologije - Granulometrijska sestava in koncentracija anorganskih nanodelcev v vodnih medijih z masno spektrometrijo z induktivno sklopljeno plazmo (ISO/TS 19590:2017)**

Nanotechnologies - Size distribution and concentration of inorganic nanoparticles in aqueous media via single particle inductively coupled plasma mass spectrometry (ISO/TS 19590:2017)

Nanotechnologien - Größenverteilung und Konzentration anorganischer Nanopartikel in wässrigen Medien durch Massenspektrometrie an Einzelpartikeln mit induktiv gekoppeltem Plasma (ISO/TS 19590:2017)

<https://standards.iteh.ai/catalog/standards/sist/fdd264a0-cd59-4e68-a6e4-41515e482dfc/sist-ts-cen-iso-ts-19590-2019>

Nanotechnologies - Distribution granulométrique et concentration de nanoparticules inorganiques en milieu aqueux par spectrométrie de masse à plasma induit en mode particule unique (ISO/TS 19590:2017)

**Ta slovenski standard je istoveten z: FprCEN ISO/TS 19590**

---

**ICS:**

07.120

Nanotehnologije

Nanotechnologies

**kSIST-TS FprCEN ISO/TS 19590:2019 en,fr,de**



# TECHNICAL SPECIFICATION

ISO/TS  
**19590**

First edition  
2017-03

---

---

---

## Nanotechnologies — Size distribution and concentration of inorganic nanoparticles in aqueous media via single particle inductively coupled plasma mass spectrometry

iTeh STA *Nanotechnologies - Distribution de taille et concentration de nanoparticules inorganiques en milieu aqueux par spectrométrie de masse à plasma induit en mode particule unique*  
(standards.iteh.ai)

[SIST-TS CEN ISO/TS 19590:2019](#)

<https://standards.iteh.ai/catalog/standards/sist/fdd264a0-cd59-4e68-a6e4-41515e482dfc/sist-ts-cen-iso-ts-19590-2019>



Reference number  
ISO/TS 19590:2017(E)

© ISO 2017

# iTeh STANDARD PREVIEW (standards.iteh.ai)

[SIST-TS CEN ISO/TS 19590:2019](#)

<https://standards.iteh.ai/catalog/standards/sist/fdd264a0-cd59-4e68-a6e4-41515e482dfc/sist-ts-cen-iso-ts-19590-2019>



## COPYRIGHT PROTECTED DOCUMENT

© ISO 2017, Published in Switzerland

All rights reserved. Unless otherwise specified, no part of this publication may be reproduced or utilized otherwise in any form or by any means, electronic or mechanical, including photocopying, or posting on the internet or an intranet, without prior written permission. Permission can be requested from either ISO at the address below or ISO's member body in the country of the requester.

ISO copyright office  
Ch. de Blandonnet 8 • CP 401  
CH-1214 Vernier, Geneva, Switzerland  
Tel. +41 22 749 01 11  
Fax +41 22 749 09 47  
copyright@iso.org  
www.iso.org

## Contents

|  | Page      |
|--|-----------|
| <b>Foreword</b>  | <b>iv</b> |
| <b>Introduction</b>  | <b>v</b>  |
| <b>1 Scope</b>   | <b>1</b>  |
| <b>2 Normative references</b>  | <b>1</b>  |
| <b>3 Terms and definitions</b>   | <b>1</b>  |
| <b>4 Abbreviated terms</b>   | <b>2</b>  |
| <b>5 Conformance</b>   | <b>2</b>  |
| <b>6 Procedure</b>   | <b>3</b>  |
| 6.1 Principle  | 3         |
| 6.2 Apparatus and equipment  | 3         |
| 6.3 Chemicals, reference materials and reagents                                  | 3         |
| 6.3.1 Chemicals  | 3         |
| 6.3.2 Reference materials  | 3         |
| 6.3.3 Reagents   | 4         |
| 6.4 Samples  | 4         |
| 6.4.1 Amount of sample   | 4         |
| 6.4.2 Sample dilution  | 5         |
| 6.5 Instrumental settings and performance check                                  | 5         |
| 6.5.1 Settings of the ICP-MS system  | 5         |
| 6.5.2 Checking the performance of the ICP-MS system                              | 5         |
| 6.6 Determination of the transport efficiency                                    | 6         |
| 6.6.1 Determination of transport efficiency based on measured particle frequency | 6         |
| 6.6.2 Determination of transport efficiency based on measured particle size      | 7         |
| 6.7 Determination of the linearity of response                                   | 8         |
| 6.8 Determination of the blank level   | 8         |
| 6.9 Analysis of aqueous suspension   | 8         |
| 6.10 Data conversion   | 9         |
| <b>7 Results</b>   | <b>9</b>  |
| 7.1 Calculations   | 9         |
| 7.1.1 Calculation of the transport efficiency                                    | 10        |
| 7.1.2 Calculation of the ICP-MS response   | 10        |
| 7.1.3 Calculation of particle concentration and size                             | 10        |
| 7.1.4 Calculation of the particle concentration detection limit                  | 11        |
| 7.1.5 Calculation of the particle size detection limit                           | 12        |
| 7.1.6 Calculation of ionic concentration   | 13        |
| 7.2 Performance criteria   | 13        |
| 7.2.1 Transport efficiency   | 13        |
| 7.2.2 Linearity of the calibration curve   | 13        |
| 7.2.3 Blank samples  | 13        |
| 7.2.4 Number of detected particles   | 13        |
| <b>8 Test report</b>   | <b>13</b> |
| <b>Annex A (informative) Calculation spreadsheet</b>                             | <b>15</b> |
| <b>Bibliography</b>  | <b>19</b> |

## Foreword

ISO (the International Organization for Standardization) is a worldwide federation of national standards bodies (ISO member bodies). The work of preparing International Standards is normally carried out through ISO technical committees. Each member body interested in a subject for which a technical committee has been established has the right to be represented on that committee. International organizations, governmental and non-governmental, in liaison with ISO, also take part in the work. ISO collaborates closely with the International Electrotechnical Commission (IEC) on all matters of electrotechnical standardization.

The procedures used to develop this document and those intended for its further maintenance are described in the ISO/IEC Directives, Part 1. In particular the different approval criteria needed for the different types of ISO documents should be noted. This document was drafted in accordance with the editorial rules of the ISO/IEC Directives, Part 2 (see [www.iso.org/directives](http://www.iso.org/directives)).

Attention is drawn to the possibility that some of the elements of this document may be the subject of patent rights. ISO shall not be held responsible for identifying any or all such patent rights. Details of any patent rights identified during the development of the document will be in the Introduction and/or on the ISO list of patent declarations received (see [www.iso.org/patents](http://www.iso.org/patents)).

Any trade name used in this document is information given for the convenience of users and does not constitute an endorsement.

For an explanation on the voluntary nature of standards, the meaning of ISO specific terms and expressions related to conformity assessment, as well as information about ISO's adherence to the World Trade Organization (WTO) principles in the Technical Barriers to Trade (TBT) see the following URL: [www.iso.org/iso/foreword.html](http://www.iso.org/iso/foreword.html).

This document was prepared by ISO/TC 229, *Nanotechnologies*.

[SIST-TS CEN ISO/TS 19590:2019](#)

<https://standards.iteh.ai/catalog/standards/sist/fdd264a0-cd59-4e68-a6e4-41515e482dfc/sist-ts-cen-iso-ts-19590-2019>

## Introduction

This document was developed in response to the worldwide demand of suitable methods for the detection and characterization of nanoparticles in food and consumer products. Products based on nanotechnology or containing engineered nanoparticles are already in use and beginning to impact the food-associated industries and markets. As a consequence, direct and indirect consumer exposure to engineered nanoparticles (in addition to natural nanoparticles) becomes more likely. The detection of engineered nanoparticles in food, in samples from toxicology and in exposure studies therefore becomes an essential part in understanding the potential benefits, as well as the potential risks, of the application of nanoparticles.

Single particle inductively coupled plasma mass spectrometry (spICP-MS) is a method capable of detecting single nanoparticles at very low concentrations. The aqueous sample is introduced continuously into a standard ICP-MS system that is set to acquire data with a high time resolution (i.e. a short dwell time). Following nebulization, a fraction of the nanoparticles enters the plasma where they are atomized and the individual atoms ionized. For every particle atomized, a cloud of ions results. This cloud of ions is sampled by the mass spectrometer and since the ion density in this cloud is high, the signal pulse is high compared to the background (or baseline) signal if a high time resolution is used. A typical run time is 30 s to 200 s and is called a “time scan.” The mass spectrometer can be tuned to measure any specific element, but due to the high time resolution, typically only one m/z value will be monitored during a run (with the current instruments).

The number of pulses detected per second is directly proportional to the number of nanoparticles in the aqueous suspension that is being measured. To calculate concentrations, the transport efficiency has to be determined first using a reference nanoparticle. The intensity of the pulse and the pulse area are directly proportional to the mass of the measured element in a nanoparticle, and thereby to the nanoparticle's diameter to the third power (i.e. assuming a spherical geometry for the nanoparticle). This means that for any increase of a particle's diameter, the response will increase to the third power and therefore a proper validation of the response for each size range of each composition of nanoparticle is required. Calibration is best performed using a reference nanoparticle material; however, such materials are often not available. Therefore, calibration in this procedure is performed using ionic standard solutions of the measured element under the same analytical condition.

The data can be processed by commercially available software or it can be imported in a custom spreadsheet program to calculate the number and mass concentration, the size (the spherical equivalent diameter) and the corresponding number-based size distribution of the nanoparticles. In addition, mass concentrations of ions present in the same sample can be determined from the same data.

The interested reader can consult References [1] to [4] for further information.



# Nanotechnologies — Size distribution and concentration of inorganic nanoparticles in aqueous media via single particle inductively coupled plasma mass spectrometry

## 1 Scope

This document specifies a method for the detection of nanoparticles in aqueous suspensions and characterization of the particle number and particle mass concentration and the number-based size distribution using ICP-MS in a time-resolved mode to determine the mass of individual nanoparticles and ionic concentrations.

The method is applicable for the determination of the size of inorganic nanoparticles (e.g. metal and metal oxides like Au, Ag, TiO<sub>2</sub>, BVO<sub>4</sub>, etc.), with size ranges of 10 nm to 100 nm (and larger particles up to 1 000 nm to 2 000 nm) in aqueous suspensions. Metal compounds other than oxides (e.g. sulfides, etc.), metal composites or coated particles with a metal core can be determined if the chemical composition and density are known. Particle number concentrations that can be determined in aqueous suspensions range from 10<sup>6</sup> particles/L to 10<sup>9</sup> particles/L which corresponds to mass concentrations in the range of approximately 1 ng/L to 1 000 ng/L (for 60 nm Au particles). Actual numbers depend on the type of mass spectrometer used and the type of nanoparticle analysed.

In addition to the particle concentrations, ionic concentrations in the suspension can also be determined. Limits of detection are comparable with standard ICP-MS measurements. Note that nanoparticles with sizes smaller than the particle size detection limit of the spICP-MS method may be quantified as ionic.

The method proposed in this document is not applicable for the detection and characterization of organic or carbon-based nanoparticles like encapsulates, fullerenes and carbon nanotubes (CNT). In addition, it is not applicable for elements other than carbon and that are difficult to determine with ICP-MS. Reference [5] gives an overview of elements that can be detected and the minimum particle sizes that can be determined with spICP-MS.

## 2 Normative references

The following documents are referred to in the text in such a way that some or all of their content constitutes requirements of this document. For dated references, only the edition cited applies. For undated references, the latest edition of the referenced document (including any amendments) applies.

ISO/TS 80004-1, *Nanotechnologies — Vocabulary — Part 1: Core terms*

## 3 Terms and definitions

For the purposes of this document, the terms and definitions given in ISO/TS 80004-1 and the following apply.

ISO and IEC maintain terminological databases for use in standardization at the following addresses:

- IEC Electropedia: available at <http://www.electropedia.org/>
- ISO Online browsing platform: available at <http://www.iso.org/obp>

### 3.1

#### **nanoparticle**

nano-object with all three external dimensions in the nanoscale

[SOURCE: ISO/TS 80004-2:2015, modified]

**ISO/TS 19590:2017(E)****3.2****aqueous suspension**

particle suspension whose suspending phase is composed of water

**3.3****inductively coupled plasma mass spectrometry****ICP-MS**

analytical technique comprising a sample introduction system, an inductively coupled plasma source for ionization of the analytes, a plasma/vacuum interface and a mass spectrometer comprising an ion focusing, separation and detection system

**3.4****dwell time**

time during which the ICP-MS detector collects and integrates pulses

Note 1 to entry: Following integration, the total count number per dwell time is registered as one data point, expressed in counts, or counts per second.

**3.5****transport efficiency****particle transport efficiency****nebulization efficiency**

ratio of the number of particles or mass of solution entering the plasma to the number of particles or mass of solution aspirated to the nebulizer

**3.6****particle number concentration**

number of particles divided by the volume of a suspension, e.g. particles/L

**iTeh STANDARD PREVIEW****(standards.iteh.ai)****3.7****particle mass concentration**

total mass of the particles divided by the volume of a sample, e.g. ng/L

<https://standards.iteh.ai/catalog/standards/sist/fdd264a0-cd59-4e68-a6e4-41515e482dfc/sist-ts-cen-iso-ts-19590-2019>**3.8****number-based particle size distribution**

list of values that defines the relative amount by numbers of particles present according to size

**4 Abbreviated terms**

|          |   |
|----------|---|
| spICP-MS | single particle inductively coupled plasma mass spectrometry (for the definition of ICP-MS, see <a href="#">3.3</a> or ISO/TS 80004-6:2013, 4.22) |
|----------|---|

**5 Conformance**

This method is restricted to aqueous suspensions of pure nanoparticles, aqueous extracts of materials or consumer products, aqueous digests of food or tissue samples, aqueous toxicological samples or environmental water samples. The applicability of the method for such samples should be evaluated by the user. Information about sample processing of non-aqueous samples can be found in the literature. Aqueous environmental samples are filtrated and diluted<sup>[6]</sup>, food and toxicological samples are chemically or enzymatically digested and diluted<sup>[7][8]</sup>. However, to relate particle number or mass concentrations in aqueous suspensions to the concentrations in the original sample information on extraction, efficiency and matrix effects are required. Additional validation by the user is required.

## 6 Procedure

### 6.1 Principle

When nanoparticles are introduced into an ICP-MS system, they produce a plume of analyte ions. The plumes corresponding to individual nanoparticles can be detected as a signal spike in the mass spectrometer if a high time resolution is used. Using dwell times of  $\leq 10$  ms and an appropriate dilution of the nanoparticle suspension allows the detection of individual nanoparticles, hence the name “single particle”-ICP-MS. Dilution is often required to avoid violation of the “single particle rule” (i.e. more than one particle arriving at the detector in one dwell time). As an example, using a dwell time of 3 ms, a maximum of 20 000 particles can be registered per minute. However, to satisfy the “single particle rule”, the number of pulses in the time scan should not exceed ca. 1 200 per minute<sup>[9]</sup> (as a guidance, a suspension of 60 nm gold particles with a mass concentration of 200 ng/L at an ICP-MS input flow of 0,5 mL/min and a transport efficiency of 3 % will result in this number of pulses).

### 6.2 Apparatus and equipment

6.2.1 **Inductively coupled plasma mass spectrometer**, capable of handling dwell times  $\leq 10$  ms.

6.2.2 **Vortex mixer**.

6.2.3 **Analytical balance**, capable of weighing to the nearest 1 mg.

6.2.4 **Ultrasonic bath**.

6.2.5 **Standard laboratory glassware**.

### 6.3 Chemicals, reference materials and reagents

<https://standards.iteh.ai/catalog/standards/sist-fdd264a0-cd59-4e68-a6e4-41515e482dfc/sist-ts-cen-iso-ts-19590-2019>

#### 6.3.1 Chemicals

6.3.1.1 **Sodium dodecyl sulfate (SDS)**; C<sub>12</sub>H<sub>25</sub>NaO<sub>4</sub>S.

6.3.1.2 **Sodium citrate**; C<sub>6</sub>H<sub>5</sub>Na<sub>3</sub>O<sub>7</sub>·2H<sub>2</sub>O.

6.3.1.3 **Nitric acid**, 70 %.

6.3.1.4 **Purified water**, typically, water with a  $>18$  MΩ·cm resistivity and  $<5$  µg/L of dissolved salts.

6.3.1.5 **Rinsing fluid for the ICP-MS sampling system**, consisting of 3 % nitric acid prepared by diluting 40 mL of concentrated nitric acid (6.3.1.3) to 760 mL purified water in a 1 L plastic container.

#### 6.3.2 Reference materials

6.3.2.1 For the determination of the transport efficiency, a nanoparticle reference material is used, for example a suspension of gold nanoparticles, nominal particle size 60 nm, with a nominal mass concentration of 50 mg/L stabilized in a citrate buffer. As an alternative, a suspension of silver nanoparticles, nominal particle size 60 nm stabilized in a citrate buffer can be used provided the materials are sufficiently homogeneous and stable<sup>[10]</sup>. Since the nanoparticle reference materials are used only to determine the transport efficiency, having the same chemical composition as the nanoparticle analyte is not required.