

SLOVENSKI STANDARD
oSIST prEN 14901-2:2018
01-november-2018

Cevi, fittingi in pribor iz duktilne železove litine - Zahteve in preskusne metode za zunanje organske prevleke fittingov in pribora iz duktilne železove litine - 2. del: Termoplastična prevleka iz kislinsko modificiranega poliolefina

Ductile iron pipes, fittings and accessories - Requirements and test methods for organic coatings of ductile iron fittings and accessories - Part 2: Thermoplastic acid modified polyolefin coating (EN14901-2)

Rohre, Formstücke und Zubehör aus duktilem Gusseisen - Anforderungen und Prüfverfahren für organische Beschichtungen von Formstücken und Zubehör aus duktilem Gusseisen - Teil 2: Thermoplastisch säuremodifizierte Polyolefin-Beschichtung

Tuyaux, raccords et accessoires en fonte ductile - Prescriptions et méthodes d'essai relatives aux revêtements organiques des raccords et accessoires en fonte ductile - Partie 2 : Revêtement thermoplastique en polyoléfine modifiée par un acide

Ta slovenski standard je istoveten z: prEN 14901-2

ICS:

23.040.10	Železne in jeklene cevi	Iron and steel pipes
23.040.40	Kovinski fittingi	Metal fittings
25.220.60	Organske prevleke	Organic coatings

oSIST prEN 14901-2:2018

en,fr,de

EUROPEAN STANDARD
NORME EUROPÉENNE
EUROPÄISCHE NORM

DRAFT
prEN 14901-2

October 2018

ICS 23.040.10; 23.040.40; 25.220.60

English Version

**Ductile iron pipes, fittings and accessories - Requirements
and test methods for organic coatings of ductile iron
fittings and accessories - Part 2: Thermoplastic acid
modified polyolefin coating (EN14901-2)**

Rohre, Formstücke und Zubehör aus duktilem
Gusseisen - Anforderungen und Prüfverfahren für
organische Beschichtungen von Formstücken und
Zubehör aus duktilem Gusseisen - Teil 2:
Thermoplastisch säuremodifizierte Polyolefin-
Beschichtung

This draft European Standard is submitted to CEN members for enquiry. It has been drawn up by the Technical Committee CEN/TC 203.

If this draft becomes a European Standard, CEN members are bound to comply with the CEN/CENELEC Internal Regulations which stipulate the conditions for giving this European Standard the status of a national standard without any alteration.

This draft European Standard was established by CEN in three official versions (English, French, German). A version in any other language made by translation under the responsibility of a CEN member into its own language and notified to the CEN-CENELEC Management Centre has the same status as the official versions.

CEN members are the national standards bodies of Austria, Belgium, Bulgaria, Croatia, Cyprus, Czech Republic, Denmark, Estonia, Finland, Former Yugoslav Republic of Macedonia, France, Germany, Greece, Hungary, Iceland, Ireland, Italy, Latvia, Lithuania, Luxembourg, Malta, Netherlands, Norway, Poland, Portugal, Romania, Serbia, Slovakia, Slovenia, Spain, Sweden, Switzerland, Turkey and United Kingdom.

Recipients of this draft are invited to submit, with their comments, notification of any relevant patent rights of which they are aware and to provide supporting documentation.

Warning : This document is not a European Standard. It is distributed for review and comments. It is subject to change without notice and shall not be referred to as a European Standard.



EUROPEAN COMMITTEE FOR STANDARDIZATION
COMITÉ EUROPÉEN DE NORMALISATION
EUROPÄISCHES KOMITEE FÜR NORMUNG

CEN-CENELEC Management Centre: Rue de la Science 23, B-1040 Brussels

Contents	Page
European foreword.....	4
Introduction	5
1 Scope.....	6
2 Normative references.....	6
3 Terms and definitions	7
4 Ordering information	9
5 Technical Requirements.....	9
5.1 General.....	9
5.2 Surface preparation	9
5.3 Appearance and continuity	9
5.4 Adhesion.....	9
5.5 Coating thickness	9
5.6 Non porosity.....	10
5.7 Repairs.....	10
5.8 Marking.....	10
6 Performance requirements.....	10
6.1 General.....	10
6.2 Impact resistance.....	10
6.3 Indentation resistance	10
6.4 Durability	10
6.4.1 Heat ageing resistance in water.....	10
6.5 Chemical resistance (only for waste water/sewage application)	10
6.6 Abrasion resistance (only for waste water/sewage application).....	11
6.7 Materials in contact with water intended for human consumption.....	11
7 Test methods	11
7.1 Routine tests.....	11
7.1.1 Surface preparation	11
7.1.2 Appearance.....	11
7.1.3 Adhesion.....	11
7.1.4 Coating thickness	11
7.2 Performance tests.....	11
7.2.1 General.....	11
7.2.2 Impact resistance.....	11
7.2.3 Indentation resistance	12
7.2.4 Non porosity.....	12
7.2.5 Durability	12
Annex A (informative) Quality assurance	13
A.1 General.....	13
A.2 Performance type test, component size grouping.....	14
A.3 Quality assessment system.....	14
Annex B (informative) Coating materials and application.....	15

B.1	General	15
B.2	Coating application	15
Annex C (informative)	Handling, transportation and storage.....	16
C.1	Handling.....	16
C.2	Transportation to storage areas	16
C.3	Storage.....	16
C.4	Loading of components for delivery	16
Bibliography	17

iTeh STANDARD PREVIEW
(standards.iteh.ai)

SIST EN 14901-2:2020

<https://standards.iteh.ai/catalog/standards/sist/270b479e-1816-4238-9e36-508fac74313f/sist-en-14901-2-2020>

prEN 14901-2:2018 (E)

European foreword

This document (prEN 14901-2:2018) has been prepared by Technical Committee CEN/TC 203 “Cast iron pipes, fittings and their joints”, the secretariat of which is held by AFNOR.

This document is currently submitted to the CEN Enquiry.

iTeh STANDARD PREVIEW
(standards.iteh.ai)

SIST EN 14901-2:2020

<https://standards.iteh.ai/catalog/standards/sist/270b479e-1816-4238-9e36-508fac74313f/sist-en-14901-2-2020>

Introduction

This document is in conformity with the general requirements already established by CEN/TC 164 in the field of water supply (e.g. potable water), CEN/TC 165 in the field of wastewater and CEN/TC 234 in the field of gas distribution.

In respect of potential adverse effects on the quality of water intended for human consumption, caused by the product covered by this document:

- 1) this document provides no information as to whether the product may be used without restriction in any of the member states of the EU or EFTA;
- 2) it should be noted that, while awaiting the adoption of verifiable European criteria, existing national regulations concerning the use and/or the characteristics of this product remain in force.

iTeh STANDARD PREVIEW
(standards.iteh.ai)

SIST EN 14901-2:2020

<https://standards.iteh.ai/catalog/standards/sist/270b479e-1816-4238-9e36-508fac74313f/sist-en-14901-2-2020>

prEN 14901-2:2018 (E)**1 Scope**

This document defines the requirements and test methods for factory applied thermoplastic acid modified polyolefin (TMPO) coatings used for the protection of ductile iron fittings and accessories conforming to EN 545, EN 598, EN 969, EN 12842 and EN 14525:

- conveying water (e.g. potable water, raw water, ...) at operating temperature up to 50 °C; or
- conveying waste water at operating temperature up to 45 °C; or
- conveying gas at operating temperature up to 50 °C;
- suitable for external environments, i.e. soils, waters and atmospheres of all common corrosion loads, characterized in D.2.3 of EN 545:2010.

2 Normative references

The following documents are referred to in the text in such a way that some or all of their content constitutes requirements of this document. For dated references, only the edition cited applies. For undated references, the latest edition of the referenced document (including any amendments) applies.

EN 545:2010, *Ductile iron pipes, fittings, accessories and their joints for water pipelines - Requirements and test methods*

EN 598, *Ductile iron pipes, fittings, accessories and their joints for sewerage application — Requirements and test methods*

EN 805, *Water supply - Requirements for systems and components outside buildings*

EN 969, *Ductile iron pipes, fittings, accessories and their joints for gas pipelines - Requirements and test methods*

EN 12842, *Ductile iron fittings for PVC-U or PE piping systems - Requirements and test methods*

EN 14525, *Ductile iron wide tolerance couplings and flange adaptors for use with pipes of different materials: ductile iron, Grey iron, Steel, PVC-U PE, Fibre-cement*

EN ISO 4624, *Paints and varnishes - Pull-off test for adhesion (ISO 4624)*

EN ISO 8501-1, *Preparation of steel substrates before application of paints and related products - Visual assessment of surface cleanliness - Part 1: Rust grades and preparation grades of uncoated steel substrates and of steel substrates after overall removal of previous coatings (ISO 8501-1)*

3 Terms and definitions

For the purposes of this document, the following terms and definitions apply

ISO and IEC maintain terminological databases for use in standardization at the following addresses:

- IEC Electropedia: available at <http://www.electropedia.org/>
- ISO Online browsing platform: available at <http://www.iso.org/obp>

3.1

ductile iron

type of cast iron used for pipes, fittings and accessories in which graphite is present primarily in spheroidal form

3.2

fitting

casting other than a pipe or accessory which allows pipe network deviation, change of direction or bore

Note 1 to entry: Flanged-socket pieces, flanged spigot pieces and collars are also classified as fittings.

3.3

accessory

any casting other than a pipe or fitting or valve which is used in a pipeline:

- glands and locking rings for restrained and/or mechanical flexible joints;
- pipe saddles for house connection;
- adjustable flanges;
- glands for mechanical flexible joints;
- inspection chambers;
- manholes

3.4

component

product defined in 3.2 to 3.3

3.5

adhesion

force per unit area, applied perpendicular to the surface, which is necessary to separate the coating from its substrate

3.6

impact strength

impact energy which a coating can withstand without damage under specific test conditions

3.7

indentation resistance

resistance of the coating to the penetration of a punch under defined test conditions

prEN 14901-2:2018 (E)**3.8****non porosity**

absence of electrical puncture in a high voltage test under defined test conditions

3.9**thermoplastic acid modified polyolefin powder material (TMPO powder)**

polyolefin resin in which a significant amount of carbon hydrogen chemical bonds are replaced by carboxylic acid functional groups

3.10**thermoplastic acid modified polyolefin coating (TMPO coating)**

factory applied coating with TMPO powder applied by sintering or flock spraying or dipping in fluidized bed on preheated parts or by electrostatic spraying and then heating the parts

3.11**performance test**

test which is done once and is repeated only after change of coating material supplier, coating material or relevant change in process application

3.12**routine test**

test carried out to control the manufacturing process with a frequency defined by the manufacturer of the coated ductile iron component

3.13**designated zones**

areas of a casting where because of jointing tolerance restrictions, testing difficulties, or shrouding by a gasket, etc. a lower standard of coating performance is unavoidable

Note 1 to entry: For the purpose of this standard these areas are defined as: 79e-1816-4238-9e36-508fac74313f/sist-en-14901-2-2020

- joint areas;
- bolt holes;
- permitted markings;
- ribs;
- edges.

Note 2 to entry: Where considered necessary, these zones may be protected by appropriate additional corrosion protection measures during or after installation. However, such measures are not part of this standard.

3.14**average thickness**

arithmetic mean of all thickness measurements taken on one coated item

3.15**localized thickness**

measured thickness at any one point of one coated item