



SLOVENSKI STANDARD
oSIST prEN ISO 439:2019
01-april-2019

Jeklo in železove litine - Določevanje silicija - Gravimetrijska metoda (ISO/DIS 439:2019)

Steel and cast irons - Determination of silicon content - Gravimetric method (ISO/DIS 439:2019)

Stahl und Eisen - Bestimmung des Gesamtsiliziumgehaltes- Gravimetrisches Verfahren (ISO/DIS 439:2019)

Aciers et fontes - Détermination de la teneur en silicium - Méthode gravimétrique (ISO/DIS 439:2019)

Ta slovenski standard je istoveten z: prEN ISO 439

ICS:

77.080.01 Železne kovine na splošno Ferrous metals in general

oSIST prEN ISO 439:2019

en,fr,de

DRAFT INTERNATIONAL STANDARD

ISO/DIS 439

ISO/TC 17/SC 1

Secretariat: JISC

Voting begins on:
2019-02-07Voting terminates on:
2019-05-02

Steel and cast irons — Determination of silicon content — Gravimetric method

Aciers et fontes — Dosage du silicium total — Méthode gravimétrique

ICS: 77.080.01

iTeh STANDARD PREVIEW
(standards.iteh.ai)

SIST EN ISO 439:2020

<https://standards.iteh.ai/catalog/standards/sist/1ab44617-795f-4029-8f98-0079a269fae4/sist-en-iso-439-2020>

THIS DOCUMENT IS A DRAFT CIRCULATED FOR COMMENT AND APPROVAL. IT IS THEREFORE SUBJECT TO CHANGE AND MAY NOT BE REFERRED TO AS AN INTERNATIONAL STANDARD UNTIL PUBLISHED AS SUCH.

IN ADDITION TO THEIR EVALUATION AS BEING ACCEPTABLE FOR INDUSTRIAL, TECHNOLOGICAL, COMMERCIAL AND USER PURPOSES, DRAFT INTERNATIONAL STANDARDS MAY ON OCCASION HAVE TO BE CONSIDERED IN THE LIGHT OF THEIR POTENTIAL TO BECOME STANDARDS TO WHICH REFERENCE MAY BE MADE IN NATIONAL REGULATIONS.

RECIPIENTS OF THIS DRAFT ARE INVITED TO SUBMIT, WITH THEIR COMMENTS, NOTIFICATION OF ANY RELEVANT PATENT RIGHTS OF WHICH THEY ARE AWARE AND TO PROVIDE SUPPORTING DOCUMENTATION.

This document is circulated as received from the committee secretariat.

ISO/CEN PARALLEL PROCESSING



Reference number
ISO/DIS 439:2019(E)

© ISO 2019

iTeh STANDARD PREVIEW (standards.iteh.ai)

SIST EN ISO 439:2020

<https://standards.iteh.ai/catalog/standards/sist/1ab44617-795f-4029-8f98-0079a269fae4/sist-en-iso-439-2020>



COPYRIGHT PROTECTED DOCUMENT

© ISO 2019

All rights reserved. Unless otherwise specified, or required in the context of its implementation, no part of this publication may be reproduced or utilized otherwise in any form or by any means, electronic or mechanical, including photocopying, or posting on the internet or an intranet, without prior written permission. Permission can be requested from either ISO at the address below or ISO's member body in the country of the requester.

ISO copyright office
CP 401 • Ch. de Blandonnet 8
CH-1214 Vernier, Geneva
Phone: +41 22 749 01 11
Fax: +41 22 749 09 47
Email: copyright@iso.org
Website: www.iso.org

Published in Switzerland

Contents

Page

Foreword.....	iv
1 Scope.....	1
2 Normative references.....	1
3 Terms and definitions.....	1
4 Principle.....	1
5 Reagents.....	1
6 Apparatus.....	2
7 Sampling.....	2
8 Procedure.....	2
8.1 Test portion.....	2
8.2 Blank test.....	3
8.3 Determination.....	3
8.3.1 Acid attack of the test portion and formation of hydrated silicon dioxide.....	3
8.3.2 Filtration and washing.....	3
8.3.3 Recovery of silicon compounds in the filtrate.....	4
8.3.4 Ignition, volatilization of silicon dioxide and weighing.....	4
9 Expression of results.....	4
9.1 Method of calculation.....	4
9.2 Precision.....	5
10 Test report.....	5
Annex A (informative) Additional information on the international interlaboratory test.....	6
Annex B (informative) Graphical representation of precision data.....	9
Bibliography.....	10

ISO/DIS 439:2019(E)

Foreword

ISO (the International Organization for Standardization) is a worldwide federation of national standards bodies (ISO member bodies). The work of preparing International Standards is normally carried out through ISO technical committees. Each member body interested in a subject for which a technical committee has been established has the right to be represented on that committee. International organizations, governmental and non-governmental, in liaison with ISO, also take part in the work. ISO collaborates closely with the International Electrotechnical Commission (IEC) on all matters of electrotechnical standardization.

The procedures used to develop this document and those intended for its further maintenance are described in the ISO/IEC Directives, Part 1. In particular, the different approval criteria needed for the different types of ISO documents should be noted. This document was drafted in accordance with the editorial rules of the ISO/IEC Directives, Part 2 (see www.iso.org/directives).

Attention is drawn to the possibility that some of the elements of this document may be the subject of patent rights. ISO shall not be held responsible for identifying any or all such patent rights. Details of any patent rights identified during the development of the document will be in the Introduction and/or on the ISO list of patent declarations received (see www.iso.org/patents).

Any trade name used in this document is information given for the convenience of users and does not constitute an endorsement.

For an explanation of the voluntary nature of standards, the meaning of ISO specific terms and expressions related to conformity assessment, as well as information about ISO's adherence to the World Trade Organization (WTO) principles in the Technical Barriers to Trade (TBT) see www.iso.org/iso/foreword.html.

This document was prepared by Technical Committee ISO/TC 17, *Steel*, Subcommittee SC 1, *Methods of determination of chemical composition*.

This third edition cancels and replaces the second edition (ISO 439:1994), which has been technically revised in order to re-assess the precision data.

Steel and cast irons — Determination of silicon content — Gravimetric method

1 Scope

This International Standard specifies a gravimetric method for the determination of the silicon content in steels and cast irons.

The method is applicable to silicon contents between 0,10 % (mass fraction) and 5,0 % (mass fraction).

NOTE For samples containing molybdenum, niobium, tantalum, titanium, tungsten, zirconium or high levels of chromium, the results are less precise than for unalloyed steels.

2 Normative references

The following documents, in whole or in part, are normatively referenced in this document and are indispensable for its application. For dated references, only the edition cited applies. For undated references, the latest edition of the referenced document (including any amendments) applies.

ISO 3696, *Water for analytical laboratory use — Specification and test methods*

EN ISO 14284, *Steel and iron - Sampling and preparation of samples for the determination of chemical composition*

3 Terms and definitions

No terms and definitions are listed in this document.

ISO and IEC maintain terminological databases for use in standardization at the following addresses:

- IEC Electropedia: available at <http://www.electropedia.org/>
- ISO Online browsing platform: available at <http://www.iso.org/obp>

4 Principle

Dissolution of a test portion with hydrochloric and nitric acids.

Conversion of acid-soluble silicon compounds to hydrated silicon dioxide by evaporation with perchloric acid until white fumes appear. Filtration of the hydrated silicon dioxide and acid-insoluble silicon compounds, ignition to form impure silicon dioxide and then weighing.

Treatment of the ignited residue with hydrofluoric and sulfuric acids, followed by ignition and weighing.

5 Reagents

During the analysis, unless otherwise stated, use only reagents of recognized analytical grade and grade 2 water as specified in ISO 3696.

5.1 Hydrochloric acid, $\rho = 1,19$ g/ml, approximately

ISO/DIS 439:2019(E)**5.2 Hydrochloric acid solution, 1 + 1**

Add 500 ml of hydrochloric acid (5.1) to 500 ml of water and mix.

5.3 Hydrochloric acid solution, 1 + 19

Add 10 ml of hydrochloric acid (5.1) to 190 ml of water and mix.

5.4 Nitric acid solution, 3 + 1

Add 150 ml of nitric acid, $\rho = 1,40$ g/ml, approximately to 50 ml of water and mix.

5.5 Hydrofluoric acid, $\rho = 1,14$ g/ml, approximately**5.6 Perchloric acid, $\rho = 1,67$ g/ml, approximately**

WARNING — Perchloric acid vapour may cause explosions in the presence of ammonia, nitrous fumes or organic material in general.

NOTE Perchloric acid ($\rho =$ about 1,54 g/ml, approximately) can also be used.

5.7 Sulphuric acid solution, 1 + 1

Cautiously add 50 ml of sulphuric acid, $\rho = 1,84$ g/ml, approximately, to 50 ml of water, allow to cool and mix.

6 Apparatus

Ordinary laboratory equipment and the following:

6.1 Platinum crucibles, of capacity approximately 30 ml**6.2 Muffle furnace, adjustable from 800 °C up to 1 100 °C****6.3 Filter paper, medium-texture, of known low ash content.****7 Sampling**

Carry out sampling in accordance with ISO 14284 or appropriate national standards for steels and cast irons.

8 Procedure**8.1 Test portion**

Use millings or drillings of a maximum thickness of 0,2 mm.

According to the presumed silicon content, weigh, to the nearest 1 mg, the following mass (m_0) of the test portion:

- a) for silicon contents between 0,10 % (mass fraction) and 0,50 % (mass fraction): m_0 approximately 5 g;
- b) for silicon contents between 0,50 % (mass fraction) and 2,5 % (mass fraction): m_0 approximately 2,5 g;
- c) for silicon contents between 2,5 % (mass fraction) and 5,0 % (mass fraction): m_0 approximately 1 g

8.2 Blank test

In parallel with the determination and following the same procedure, carry out a blank test using the same quantities of all reagents as used for the determination.

8.3 Determination

8.3.1 Acid attack of the test portion and formation of hydrated silicon dioxide

Place the test portion (8.1) in a beaker of acid-resistant glass of suitable capacity.

Add 30 ml of hydrochloric acid (5.1), and then gently heat the beaker covered with a watch glass until the reaction ceases. Oxidize by careful addition of 15 ml of nitric acid (5.4). When the fairly violent reaction ceases, rinse the watch glass with a little portion of hot water and collect the washings in the beaker. Add a volume of perchloric acid (5.6) as indicated in table 1.

Table 1 — Volume of perchloric acid (5.6)

Mass of test portion (8.1) g	Volume of perchloric acid (4.6) ml	
	$\rho = 1,67 \text{ g/ml}$	$\rho = 1,54 \text{ g/ml}$
5	60	75
2,5	40	50
1	25	35

WARNING — Perchloric acid (4.6) must be added cautiously in small portions, especially when a 5 g test portion has been taken, in order to avoid boiling over, due to a very violent reaction.

Heat the uncovered beaker slightly until the attack is complete and then, increase the rate of heating. As soon as the first white perchloric acid fumes appear, cover the beaker with the watch glass and continue fuming for about 20 min.

NOTE If the alloy contains chromium at contents greater than 1%, it's recommended to wait for the appearance of the characteristic red color of the chromic acid. At this stage, chromium can be removed as chromyl chloride: slowly pour down along the sides of the beaker 1 to 2 ml of hydrochloric acid (5.1). Continue heating, until abundant perchloric fumes appear and chromium re-oxidises. Repeat as many times as necessary until the perchloric fumes are no longer orange-colored, when hydrochloric acid is added.

Allow to cool, carefully moisten with 5 ml of hydrochloric acid (5.1), heat slightly, dilute with 100 ml of water at 70 °C to 80 °C and heat again until the salts are dissolved (taking care not to allow the solution to boil).

8.3.2 Filtration and washing

With a rubber-tipped glass rod, detach any hydrated silicon dioxide or acid-insoluble silicon compounds that may be adhering to the beaker and filter immediately through a filter paper (6.3) containing a little filter-paper pulp of the same quality.

Wash the beaker and the filter with hot hydrochloric acid (5.3), transferring the hydrated silicon dioxide and acid-insoluble silicon compounds to the filter, and complete the washing, first with hot hydrochloric acid (5.2) and then with cold water until the iron salts are completely eliminated.

NOTE The filter should be washed thoroughly in order to avoid popping and loss of residue due to perchloric acid during ignition.

ISO/DIS 439:2019(E)

8.3.3 Recovery of silicon compounds in the filtrate

Transfer the filtrate and the washings to the beaker previously used for the attack, evaporate them by heating until dense white fumes of perchloric acid are evolved, and maintain a steady refluxing of acid on the walls of the beaker for about 20 min. Moisten and dilute according to the procedure specified in 8.3.1, then filter through a second filter paper (6.3) and wash according to the procedure specified in 8.3.2.

8.3.4 Ignition, volatilization of silicon dioxide and weighing

Put the two filters and their contents together in a platinum crucible (6.1). Heat at between 500 °C and 600 °C until the filters are completely incinerated, then cover the crucible partially with a platinum cover and ignite in the muffle furnace (6.2) at 1 100 °C for 30 min to 45 min, depending on the quantity of silicon dioxide and, for samples containing molybdenum, until a constant mass is obtained.

Allow to cool, add approximately 2 ml of sulfuric acid (5.7) to the crucible, heat carefully and continue heating until the sulfuric acid fumes are completely eliminated. Then ignite in the muffle furnace at 800 °C to constant mass.

Allow to cool in a desiccator and weigh the crucible and its contents (mass in grams: m_1).

Then moisten the ignited silicon dioxide with a few drops of sulfuric acid (5.7), add approximately 5 ml of hydrofluoric acid (5.5), evaporate to dryness and continue heating until the sulfuric acid fumes are completely eliminated.

NOTE If molybdenum, niobium, tantalum, titanium, tungsten or zirconium are present, add 2 ml of sulfuric acid (5.7) in order to avoid any partial volatilization of the fluorides of these elements.

Complete the ignition in the muffle furnace at 800 °C for 10 min.

Allow to cool in a desiccator, then weigh the crucible and its contents (mass in grams: m_2).

9 Expression of results**9.1 Method of calculation**

The silicon content, w_{Si} , expressed as a percentage by mass, is given by the equation:

$$w_{Si} = 0,4674x \frac{(m_1 - m_2) - (m_3 - m_4)}{m_0} x 100$$

$$w_{Si} = 46,74x \frac{(m_1 - m_2) - (m_3 - m_4)}{m_0}$$

where

m_0 is the mass of the test portion, in grams;

m_1 is the mass of the crucible and the impure silicon dioxide, in grams;

m_2 is the mass of the crucible and residue after volatilization of the silicon dioxide, in grams;

m_3 is the mass of the crucible and the impure silicon dioxide in the blank test, in grams;

m_4 is the mass of the crucible and residue after volatilization of the silicon dioxide in the blank test, in grams;

0,4674 is the Si/SiO₂ coefficient