



Designation: ~~C1456-00~~ Designation: **C 1456 – 08**

Standard Test Method for ~~the Determination of Uranium or Gadolinium, or~~ **Both, Gadolinium (or both) in Gadolinium Oxide-Uranium Oxide Pellets or by X-Ray Fluorescence (XRF)¹**

This standard is issued under the fixed designation C 1456; the number immediately following the designation indicates the year of original adoption or, in the case of revision, the year of last revision. A number in parentheses indicates the year of last reapproval. A superscript epsilon (ϵ) indicates an editorial change since the last revision or reapproval.

1. Scope

~~1.1 This standard describes the steps necessary for the preparation and analysis by X-ray fluorescence (XRF) of gadolinium and/or uranium in gadolinium oxide-uranium oxide pellets or powders.~~

~~1.2 This method requires the use of appropriate internal standard(s). Care must be taken to ascertain that samples analyzed by this method do not contain the internal standard element(s) or that this contamination has been corrected for mathematically whenever present. Such corrections are not addressed in this standard.~~

~~1.3~~

~~1.1 This test method describes the steps necessary for the preparation and analysis by X-ray fluorescence (XRF) of gadolinium or uranium (or both) in gadolinium oxide-uranium oxide pellets or powders.~~

~~1.2 This test method requires the use of appropriate internal standard(s). Care must be taken to ascertain that samples analyzed by this method do not contain the internal standard element(s) or that this contamination has been corrected for mathematically whenever present. Such corrections are not addressed in this test method.~~

~~1.3 This standard contains notes that are explanatory and are not part of the mandatory requirements of the standard.~~

~~1.4 The values stated in SI units are to be regarded as standard. No other units of measurement are included in this standard.~~

~~1.5 This standard does not purport to address all of the safety concerns, if any, associated with its use. It is the responsibility of the user of this standard to establish appropriate safety and health practices and determine the applicability of regulatory limitations prior to use. Specific precautions are given in Section 8 and various notes throughout the method.~~

2. Referenced Documents

~~2.1 ASTM Standards: C982 *Guide for Selecting Components for Generic Energy Dispersive X-Ray Fluorescence (XRF) Systems*~~²

C 1118 *Guide for Selecting Components for Wavelength-Dispersive X-Ray Fluorescence (XRF) Systems*

D 1193 *Specification for Reagent Water*

E 135 *Terminology Relating to Analytical Chemistry for Metals, Ores, and Related Materials*—*Terminology Relating to Analytical Chemistry for Metals, Ores, and Related Materials*

~~2.2 Other Document~~

~~ANSI/HPS N43.2-2001 *Radiation Safety for X-ray Diffraction and X-ray Fluorescence Analysis Equipment*~~³

3. Terminology

3.1 *Definitions*— For definitions of terms used in this guide, see Terminology E 135.

3.2 *Symbol:*

LiTB = lithium tetraborate (see 7.4).

4. Summary of Test Method

4.1 Solution or pellet standards containing the equivalent of 1–10 % gadolinium oxide and 90–99 % uranium oxide and appropriate internal standards are placed in the sample holder of a ~~x-ray~~ X-ray spectrometer and exposed to an ~~x-ray~~ X-ray beam

¹ This guide is under the jurisdiction of ASTM Committee C-26 on Nuclear Fuel Cycle and is the direct responsibility of Subcommittee C-26.05 on Methods of Test. Current edition approved Feb. 10, 2000. Published March 2000.

² This test method is under the jurisdiction of ASTM Committee C26 on Nuclear Fuel Cycle and is the direct responsibility of Subcommittee C26.05 on Methods of Test. Current edition approved Dec. 1, 2008. Published January 2009. Originally approved in 2000. Last previous edition approved in 2000 as C 1456 – 00.

³ For referenced ASTM standards, visit the ASTM website, www.astm.org, or contact ASTM Customer Service at service@astm.org. For *Annual Book of ASTM Standards* Vol 12.01, volume information, refer to the standard's Document Summary page on the ASTM website.

⁴ *Annual Book of ASTM Standards*, Vol 11.01.

⁵ Available from American National Standards Institute (ANSI), 25 W. 43rd St., 4th Floor, New York, NY 10036, <http://www.ansi.org>.

capable of exciting the uranium and gadolinium L- α emission lines and the appropriate emission line for the internal standard. The intensities generated are measured by an appropriate detector. The intensity ratio values obtained from this data are used to calibrate the ~~x-ray~~X-ray analyzer.

4.2 Samples are prepared in the same manner as the standards and analyzed using conditions and curves generated from those standards.

NOTE 1—Yttrium and strontium have been used successfully as internal standards for uranium and samarium for gadolinium. Scatter lines also have been used as internal standard ~~lines (1)-lines.~~⁴ An explanation of internal standard method is found in several ~~sources (2sources.~~^{5,7)-6}

5. Significance and Use

5.1 This ~~guide-test method~~ is applicable to samples containing 2 to 10 % gadolinium oxide and 90 to 98 % uranium oxide on the “as received” basis. The method may be used to determine concentration of either uranium, gadolinium, or both.

5.2 Either wavelength-dispersive or energy-dispersive ~~x-ray~~X-ray fluorescence systems may be used provided the software accompanying the system is able to accommodate the use of internal standards.

6. Apparatus

6.1 *X-Ray Spectrometer*—See Guide ~~E982 or Guide~~C 1118 or the manufacturer’s operating manuals for the selection of the X-ray spectrometer. The method is valid for either energy-dispersive or wavelength-dispersive systems.

6.2 *Sample Cups/holders*—Prepare liquid sample cups for the ~~x-ray~~X-ray spectrometer as described by the manufacturer. Vented, disposable sample cups with snap-on caps are satisfactory for most such ~~analyses. Such~~analyses; such cups decrease the likelihood of contamination between samples. Sample holders for fused pellets should keep any pellet chips from getting into the moving parts of the instrument.

6.3 *Window Film*—Polyester, polyethylene, and polypropylene films have been used successfully as the film window for cups or holders, or both. Tests should be performed to determine the serviceability of any film chosen before insertion into the instrument.

6.4 *Solution Dispenser (optional)* —The dispenser for the internal standard solution, if used, should be capable of ~~reproducibility~~reproducibly dispensing the internal standard solution to a level of 0.1 % relative standard deviation of the volume dispensed.

6.5 *Muffle Furnace*, 1100°C capacity.

7. Reagents and Materials

7.1 *Purity of Materials*—Reagent grade chemicals shall be used in all tests. Unless otherwise indicated, it is intended that all reagents conform to the specifications of the Committee of Analytical Reagents of the American Chemical Society where such specifications are available.⁷ Other grades may be used provided it is first ascertained that the reagent is of sufficiently high purity to permit its use without lessening the accuracy of the determination.

7.2 *Purity of Water*—Unless otherwise indicated, references to water shall mean reagent water conforming to Specification D 1193.

7.3 *Gadolinium Oxide, Gd₂O₃*—It is recommended that the standards be prepared using same batch as in pellets/powder.

7.4 *Lithium Tetraborate, Li₂B₄O₇*, fusion grade.

7.5 *Nitric Acid, HNO₃*, concentrated (70 %).

7.6 *Samarium Oxide, Sm₂O₃*, or other suitable internal standard for gadolinium (see Note 1).

7.7 *Uranium Oxide, U₃O₈*, ~~NBL CRM-129 (or equivalent) (4)-~~, NBL CRM-129 (or equivalent).⁸

NOTE 2—High purity UO₂ may be used if certification of uranium analysis is not required.

7.8 *Yttrium Oxide, Y₂O₃*, or other suitable internal standard for uranium (see Note 1).

8. Technical Precautions

8.1 XRF equipment analyzes by the interaction of ionizing radiation with the sample. Applicable safety regulations and standard

⁴ Annual Book of ASTM Standards, Vol 03.05.

⁴ Andermann, G. and Kemp, J.W., “Scattered X-Rays as Internal Standards in X-Ray Spectroscopy,” *Analytical Chemistry*, Vol 20 (8), 1958.

⁶ The boldface numbers in parentheses refer to the list of references at the end of this standard.

⁵ Bertin, E.P., *Introduction to X-Ray Spectrometric Analysis*, Plenum Press, New York and London, 1978.

⁶ Reagent Chemicals, American Chemical Society Specifications, American Chemical Society, Washington, DC. For suggestions on the testing of reagents not listed by the American Chemical Society, see *Analar Standards for Laboratory Chemicals*, BDH Ltd., Poole, Dorset, U.K., and the *United States Pharmacopeia and National Formulary*, U.S. Pharmacopeial Convention, Inc. (USPC), Rockville, MD.

⁶ Tertian, R. and Claisse, F., *Principles of Quantitative X-Ray Fluorescence Analysis*, Heyden and Son, London, Philadelphia and Rheine, 1982.

⁷ *Reagent Chemicals, American Chemical Society Specifications*, American Chemical Society, Washington, DC. For Suggestions on the testing of reagents not listed by the American Chemical Society, see *Annual Standards for Laboratory Chemicals*, BDH Ltd., Poole, Dorset, U.K., and the *United States Pharmacopeia and National Formulary*, U.S. Pharmacopeial Convention, Inc. (USPC), Rockville, MD.

⁸ The sole source of supply of the apparatus known to the committee at this time is U.S. Department of Energy, New Brunswick Laboratory, D 350, 9800 South Cass Avenue, Argonne, IL 60439, ATTN: Reference Material Sales. If you are aware of alternative suppliers, please provide this information to ASTM International Headquarters. Your comments will receive careful consideration at a meeting of the responsible technical committee, which you may attend.