DRAFT INTERNATIONAL STANDARD

ISO/DIS 4034

ISO/TC **2**/SC **12**

Secretariat: **DIN**

Voting begins on:
2016-03-31

Voting terminates on:
2016-06-29

Hexagon regular nuts (style 1) — Product grade C

Écrous hexagonaux normaux (style 1) — Grade C

ICS: 21.060.20

ISO/CEN PARALLEL PROCESSING

This draft has been developed within the International Organization for Standardization (ISO), and processed under the **ISO lead** mode of collaboration as defined in the Vienna Agreement.

This draft is hereby submitted to the ISO member bodies and to the CEN member bodies for a parallel three month enquiry.

To expedite distribution, this document is circulated as received from the committee secretariat. ISO Central Secretariat work of editing and text composition will be undertaken at publication stage.

Reference number
ISO/DIS 4034:2016(E)

ISO copyright office
Ch. de Blandonnet 8 • CP 401
CH-1214 Vernier, Geneva, Switzerland
Tel. +41 22 749 01 11
Fax +41 22 749 09 47
copyright@iso.org
www.iso.org

Foreword

ISO (the International Organization for Standardization) is a worldwide federation of national standards bodies (ISO member bodies). The work of preparing International Standards is normally carried out through ISO technical committees. Each member body interested in a subject for which a technical committee has been established has the right to be represented on that committee. International organizations, governmental and non-governmental, in liaison with ISO, also take part in the work. ISO collaborates closely with the International Electrotechnical Commission (IEC) on all matters of electrotechnical standardization.

The procedures used to develop this document and those intended for its further maintenance are described in the ISO/IEC Directives, Part 1. In particular the different approval criteria needed for the different types of ISO documents should be noted. This document was drafted in accordance with the editorial rules of the ISO/IEC Directives, Part 2 (see www.iso.org/directives).

Attention is drawn to the possibility that some of the elements of this document may be the subject of patent rights. ISO shall not be held responsible for identifying any or all such patent rights. Details of any patent rights identified during the development of the document will be in the Introduction and/or on the ISO list of patent declarations received (see www.iso.org/patents).

Any trade name used in this document is information given for the convenience of users and does not constitute an endorsement.

For an explanation on the meaning of ISO specific terms and expressions related to conformity assessment, as well as information about ISO's adherence to the WTO principles in the Technical Barriers to Trade (TBT) see the following URL: Foreword - Supplementary information

The committee responsible for this document is ISO/TC 2, *Fasteners*, Subcommittee SC 12, *Fasteners with metric internal thread*.

This fifth edition cancels and replaces the fourth edition (ISO 4034:2012).

This standard differs from ISO 4034:2012 as follows:

— the Scope has been updated;

— the thread M7 has been added;

— errors for $m_{,\,min}$ have been corrected for M27 (22,5 instead of 22,6) and M64 (49,1 instead of 49,4);

— errors in calculation of $m_{w,\,min}$ values have been corrected for M6 (3,9 instead of 3,7) , M27 (18,0 instead of 18,1), M36 (23,5 instead of 23,2) and M64 (39,3 instead of 39,5);

— the property class 6 has been added;

— the reference to ISO/TR 16224 for nut design has been added.

Hexagon regular nuts (style 1) — Product grade C

1 Scope

This International Standard specifies the characteristics of hexagon regular nuts (style 1) with coarse pitch thread from nominal diameters M5 through M64, with product grade C.

2 Normative references

The following documents, in whole or in part, are normatively referenced in this document and are indispensable for its application. For dated references, only the edition cited applies. For undated references, the latest edition of the referenced document (including any amendments) applies.

ISO 225, *Fasteners — Bolts, screws, studs and nuts — Symbols and descriptions of dimensions*

ISO 262, *ISO general purpose metric screw threads — Selected sizes for screws, bolts and nuts*

ISO 724, *ISO general-purpose metric screw threads — Basic dimensions*

ISO 898-2, *Mechanical properties of fasteners made of carbon steel and alloy steel — Part 2: Nuts with specified property classes — Coarse thread and fine pitch thread*

ISO 965-2, *ISO general purpose metric screw threads — Tolerances — Part 2: Limits of sizes for general purpose external and internal screw threads — Medium quality*

ISO 965-5, *ISO general-purpose metric screw threads — Tolerances — Part 5: Limits of sizes for internal screw threads to mate with hot-dip galvanized external screw threads with maximum size of tolerance position h before galvanizing*

ISO 3269, *Fasteners — Acceptance inspection*

ISO 4042, *Fasteners — Electroplated coatings*

ISO 4759-1, *Tolerances for fasteners — Part 1: Bolts, screws, studs and nuts — Product grades A, B and C*

ISO 6157-2, *Fasteners — Surface discontinuities — Part 2: Nuts*

ISO 8992, *Fasteners — General requirements for bolts, screws, studs and nuts*

ISO 10683, *Fasteners — Non-electrolytically applied zinc flake coatings*

ISO 10684, *Fasteners — Hot dip galvanized coatings*

3 Dimensions

See Figure 1 and Tables 1 and 2.

Symbols and descriptions of dimensions are specified in ISO 225.



a $\beta = 15°$ to $30°$

b $\theta = 90°$ to $120°$

Figure 1 - Dimensions

Table 1 — Preferred threads

Dimensions in millimetres

Thread, D		M5	M6	M8	M10	M12	M16	M20
P[a]		0,8	1	1,25	1,5	1,75	2	2,5
d_w	min.	6,7	8,7	11,5	14,5	16,5	22,0	27,7
e	min.	8,63	10,89	14,20	17,59	19,85	26,17	32,95
m	max.	5,6	6,4	7,9	9,5	12,2	15,9	19,0
	min.	4,4	4,9	6,4	8,0	10,4	14,1	16,9
m_w	min.	3,5	3,9	5,1	6,4	8,3	11,3	13,5
s	nom. = max.	8,00	10,00	13,00	16,00	18,00	24,00	30,00
	min.	7,64	9,64	12,57	15,57	17,57	23,16	29,16
Thread, D		**M24**	**M30**	**M36**	**M42**	**M48**	**M56**	**M64**
P[a]		3	3,5	4	4,5	5	5,5	6
d_w	min.	33,3	42,8	51,1	60,0	69,5	78,7	88,2
e	min.	39,55	50,85	60,79	71,30	82,60	93,56	104,86
m	max.	22,3	26,4	31,9	34,9	38,9	45,9	52,4
	min.	20,2	24,3	29,4	32,4	36,4	43,4	49,1
m_w	min.	16,2	19,4	23,5	25,9	29,1	34,7	39,3
s	nom. = max.	36,00	46,00	55,00	65,00	75,00	85,00	95,00
	min.	35,00	45,00	53,80	63,10	73,10	82,80	92,80

a P is the pitch of the thread.

Table 2 — Non-preferred threads

Dimensions in millimetres

Thread, D		M7	M14	M18	M22	M27	M33	M39	M45	M52	M60
P[a]		1	2	2,5	2,5	3	3,5	4	4,5	5	5,5
d_w	min.	9,5	19,2	24,9	31,4	38,0	46,6	55,9	64,7	74,2	83,4
e	min.	11,94	22,78	29,56	37,29	45,20	55,37	66,44	76,95	88,25	99,21
m	max.	8,30	13,9	16,9	20,2	24,7	29,5	34,3	36,9	42,9	48,9
	min.	6,10	12,1	15,1	18,1	22,5	27,4	31,8	34,4	40,4	46,4
m_w	min.	5,50	9,7	12,1	14,5	18,0	21,9	25,4	27,5	32,3	37,1
s	nom. = max.	11,00	21,00	27,00	34,00	41,00	50,00	60,00	70,00	80,00	90,00
	min.	10,57	20,16	26,16	33,00	40,00	49,00	58,80	68,10	78,10	87,80

[a] P is the pitch of the thread.

4 Requirements and reference International Standards

See Table 3.

Table 3 — Requirements and reference International Standards

Material		Steel	
General requirements	International Standard	ISO 8992	
Thread	Tolerance class	7H[a]	
	International Standards	ISO 262, ISO 724, ISO 965-2, ISO 965-5	
Mechanical properties	Property class	$M5 \leq D \leq M39$	5, 6
		$D < M5$ and $D > M39$	Mechanical properties as agreed[b]
	International Standard	ISO 898-2	
Tolerance	Product grade	C	
	International Standard	ISO 4759-1	
Finish — Coating		As processed Requirements for electroplating are specified in ISO 4042. Requirements for non-electrolytically applied zinc flake coatings are specified in ISO 10683. Requirements for hot dip galvanized coatings are specified in ISO 10684. Additional requirements or other finishes or coatings shall be agreed between the supplier and the purchaser.	
Surface integrity		Limits for surface discontinuities are specified in ISO 6157-2.	
Acceptability		Acceptance inspection is specified in ISO 3269.	

[a] Other tolerance classes may be specified prior to coating, depending on the type of coating to be applied. For coated nuts, see relevant coating standards, e.g. ISO 4042, ISO 10683 and ISO 10684.
[b] See ISO/TR 16224 for information.

5 Designation

EXAMPLE A hexagon regular nut (style 1) with nominal diameter M12 and property class 5 is designated as follows:

Hexagon regular nut ISO 4034 – M12 – 5

Bibliography

ISO/TR 16224, *Technical aspects of nut design*

