

---

---

**Aerospace — Separable tube fittings  
for fluid systems, for 24° cones, for  
pressures up to 3 000 psi or 21 000  
kPa — Procurement specification,  
inch/metric**

*Aéronautique et espace — Raccordements séparables de tubes à cône  
de 24° pour circuits de fluides jusqu'à 3 000 psi ou 21 000 kPa —  
Spécification d'approvisionnement, inch/métrique*

iTeh STANDARD PREVIEW  
(standards.iteh.ai)

ISO 7169:2014

<https://standards.iteh.ai/catalog/standards/sist/a9987049-83dc-4710-a514-4a44927d841a/iso-7169-2014>



**iTeh STANDARD PREVIEW**  
**(standards.iteh.ai)**

[ISO 7169:2014](https://standards.iteh.ai/catalog/standards/sist/a9987049-83dc-4710-a514-4a44927d841a/iso-7169-2014)

<https://standards.iteh.ai/catalog/standards/sist/a9987049-83dc-4710-a514-4a44927d841a/iso-7169-2014>



**COPYRIGHT PROTECTED DOCUMENT**

© ISO 2014

All rights reserved. Unless otherwise specified, no part of this publication may be reproduced or utilized otherwise in any form or by any means, electronic or mechanical, including photocopying, or posting on the internet or an intranet, without prior written permission. Permission can be requested from either ISO at the address below or ISO's member body in the country of the requester.

ISO copyright office  
Case postale 56 • CH-1211 Geneva 20  
Tel. + 41 22 749 01 11  
Fax + 41 22 749 09 47  
E-mail [copyright@iso.org](mailto:copyright@iso.org)  
Web [www.iso.org](http://www.iso.org)

Published in Switzerland

# Contents

	Page
<b>Foreword</b> .....	<b>iv</b>
<b>Introduction</b> .....	<b>v</b>
<b>1 Scope</b> .....	<b>1</b>
<b>2 Normative references</b> .....	<b>1</b>
<b>3 Classification</b> .....	<b>1</b>
<b>4 Requirements</b> .....	<b>2</b>
4.1 Qualification.....	2
4.2 Materials.....	2
4.3 Design and manufacture.....	5
4.4 Surface protection and colour identification.....	6
4.5 Marking.....	7
4.6 Performance.....	7
4.7 Workmanship.....	9
<b>5 Quality assurance provisions</b> .....	<b>10</b>
5.1 Responsibility for inspection.....	10
5.2 Inspection lot.....	10
5.3 Classification of inspections and tests.....	10
5.4 Quality control records.....	11
5.5 Quality conformance inspection procedures.....	12
5.6 Test conditions.....	12
<b>6 Preparation for delivery</b> .....	<b>16</b>
6.1 Cleaning.....	16
6.2 Preservative material.....	16
6.3 Packaging.....	16
6.4 Package identification.....	16
6.5 Packing for shipment.....	16
6.6 Inspection.....	16
<b>Annex A (informative) Equivalent materials and processes</b> .....	<b>17</b>
<b>Bibliography</b> .....	<b>20</b>

## Foreword

ISO (the International Organization for Standardization) is a worldwide federation of national standards bodies (ISO member bodies). The work of preparing International Standards is normally carried out through ISO technical committees. Each member body interested in a subject for which a technical committee has been established has the right to be represented on that committee. International organizations, governmental and non-governmental, in liaison with ISO, also take part in the work. ISO collaborates closely with the International Electrotechnical Commission (IEC) on all matters of electrotechnical standardization.

The procedures used to develop this document and those intended for its further maintenance are described in the ISO/IEC Directives, Part 1. In particular the different approval criteria needed for the different types of ISO documents should be noted. This document was drafted in accordance with the editorial rules of the ISO/IEC Directives, Part 2 (see [www.iso.org/directives](http://www.iso.org/directives)).

Attention is drawn to the possibility that some of the elements of this document may be the subject of patent rights. ISO shall not be held responsible for identifying any or all such patent rights. Details of any patent rights identified during the development of the document will be in the Introduction and/or on the ISO list of patent declarations received (see [www.iso.org/patents](http://www.iso.org/patents)).

Any trade name used in this document is information given for the convenience of users and does not constitute an endorsement.

For an explanation on the meaning of ISO specific terms and expressions related to conformity assessment, as well as information about ISO's adherence to the WTO principles in the Technical Barriers to Trade (TBT) see the following URL: [Foreword - Supplementary information](http://www.iso.org/foreword)

The committee responsible for this document is ISO/TC 20, *Aircraft and space vehicles*, Subcommittee SC 10, *Aerospace fluid systems and components*.

This fifth edition cancels and replaces the fourth edition (ISO 7169:2007), of which it constitutes a minor revision.

## Introduction

This International Standard establishes the basic performance and quality criteria for threaded tube fitting assemblies and port connectors used in aerospace fluid systems.

The test requirements are intended to satisfy the most strenuous demands encountered in a high-performance aircraft hydraulic system. The procurement requirements are intended to ensure that fittings, which are procured in accordance with this specification, are of the same quality as the fittings used during the original qualification testing. Compliance with these test and procurement requirements is necessary for fittings that are used in control systems where a malfunction would affect the safety of flight.

## iTeh STANDARD PREVIEW (standards.iteh.ai)

[ISO 7169:2014](https://standards.iteh.ai/catalog/standards/sist/a9987049-83dc-4710-a514-4a44927d841a/iso-7169-2014)

<https://standards.iteh.ai/catalog/standards/sist/a9987049-83dc-4710-a514-4a44927d841a/iso-7169-2014>

**iTeh STANDARD PREVIEW**  
**(standards.iteh.ai)**

[ISO 7169:2014](https://standards.iteh.ai/catalog/standards/sist/a9987049-83dc-4710-a514-4a44927d841a/iso-7169-2014)

<https://standards.iteh.ai/catalog/standards/sist/a9987049-83dc-4710-a514-4a44927d841a/iso-7169-2014>

# Aerospace — Separable tube fittings for fluid systems, for 24° cones, for pressures up to 3 000 psi or 21 000 kPa — Procurement specification, inch/metric

## 1 Scope

This International Standard specifies performance and quality requirements for the qualification and manufacture of standard 24° cone fittings and manufacture of 24° cone fittings to ensure reliable performance or equivalent inch-dimensioned fitting ends to ensure reliable performance in aircraft hydraulic systems.

This International Standard specifies baseline criteria for the design and manufacture of system fittings that are qualification-tested on engines.

This International Standard covers fittings of the temperature types and pressure classes specified in ISO 6771.

## 2 Normative references

The following documents, in whole or in part, are normatively referenced in this document and are indispensable for its application. For dated references, only the edition cited applies. For undated references, the latest edition of the referenced document (including any amendments) applies.

ISO 2859-1, *Sampling procedures for inspection by attributes — Part 1: Sampling schemes indexed by acceptance quality limit (AQL) for lot-by-lot inspection*

ISO 3161, *Aerospace — UNJ threads — General requirements and limit dimensions*

ISO 5855-3, *Aerospace — MJ threads — Part 3: Limit dimensions for fittings for fluid systems*

ISO 6771, *Aerospace — Fluid systems and components — Pressure and temperature classifications*

ISO 6772, *Aerospace — Fluid systems — Impulse testing of hydraulic hose, tubing and fitting assemblies*

ISO 7257, *Aircraft — Hydraulic tubing joints and fittings — Rotary flexure test*

ISO 8574, *Aerospace — Hydraulic system tubing — Qualification tests for bent tubes*

ISO 9538, *Aerospace — Hydraulic tubing joints and fittings — Planar flexure test*

ISO 10583:1993, *Aerospace fluid systems — Test methods for tube/fitting assemblies*

## 3 Classification

Fittings furnished under this International Standard shall be classified as follows:

Type A — 3 000 psi (20 684 kPa) Pressure System

Type B — 21 000 kPa (3046 psi) Pressure System

When no classification is specified, Type B shall apply.

## 4 Requirements

### 4.1 Qualification

Fittings claiming conformity with this International Standard shall be representative of products which have successfully met the requirements and have passed the tests in this International Standard.

#### 4.1.1 Manufacturer qualification

Manufacturer approval shall be granted by an outside agency procedure (see [Table A.2](#), procedure No. 1).

#### 4.1.2 Product qualification

Product approval shall be granted by an outside agency procedure (see [Table A.2](#), procedure No. 2).

### 4.2 Materials

#### 4.2.1 Fittings

The fitting parts shall be manufactured from materials as given in [Table 1](#) or equivalents passing the specified tests. The various materials shall be used according to the pressure and temperature requirements of the system, as shown in [Tables 2](#) to [5](#).

#### 4.2.2 Tubing

The tubing used with the fittings shall be in accordance with the relevant specification or equivalent tubing passing the specified qualification tests.

iTeh STANDARD PREVIEW

(standards.iteh.ai)

ISO 7169:2014  
<https://standards.iteh.ai/catalog/standards/sist/83dc-4710-a514-4a44927d841a/iso-7169-2014>  
**Table 1 — Materials for fittings**

Part	Material	Type <sup>a</sup>	Material code <sup>b</sup>	Starting stock	Material No. <sup>c</sup>
Straight fittings and nuts	Aluminium alloy	I	D <sup>d</sup>	Bar, rod	1
			W		2
Shape fittings	Aluminium alloy	I	D <sup>d</sup>	Bar and forgings	3
			W		2
Straight and shape fittings	Carbon steel	II	F <sup>f</sup>	Bar, rod, forgings	4
	Corrosion-resistant steel	I, II, III	J	Bar and forgings	5
		I, II, III	K		7
		I, II, III, IV	R		6
		I, II, III I, II, II, IV	P V		11 11
	Titanium alloy	I, II, III	T	Bar and forgings	8
Sleeves (bite type)	Carbon steel	II	F <sup>e</sup>	Bar	9
Sleeves (swaged, brazed)	Corrosion-resistant steel	I, II, II I, II, II, IV	P	Bar	11
			V		11

<sup>a</sup> Temperature types and system pressure classes are defined in ISO 6771.

<sup>b</sup> See [Table 7](#).

<sup>c</sup> See [Table A.1](#).

<sup>d</sup> Inactive for new design, superseded by W.

<sup>e</sup> Inactive for new design, no replacement.

<sup>f</sup> Inactive for new design, superseded by V.



Table 1 (continued)

Part	Material	Type <sup>a</sup>	Material code <sup>b</sup>	Starting stock	Material No. <sup>c</sup>
Sleeves (welded)	Corrosion-resistant steel	I, II, III, IV	V	Bar	11
	Titanium alloy	I, II, III, IV	T		8

<sup>a</sup> Temperature types and system pressure classes are defined in ISO 6771.  
<sup>b</sup> See Table 7.  
<sup>c</sup> See Table A.1.  
<sup>d</sup> Inactive for new design, superseded by W.  
<sup>e</sup> Inactive for new design, no replacement.  
<sup>f</sup> Inactive for new design, superseded by V.

Table 2 — Test requirements, 3 000 psi steel or titanium fittings on steel or titanium tubing

Fitting and tube		Nominal pressure		Proof pressure		Burst pressure		Flexure test, bending stress 0 % to 10 %	
Metric	Inch	kPa	(psi)	kPa	(psi)	kPa	(psi)	kPa	(psi)
Size <sup>a</sup>	Size <sup>a</sup>								
—	-02	20 684	(3 000)	41 368	(6 000)	82 740	(12 000)	135 000	(20 000)
DN05	-03								
DN06	-04								
DN08	-05								
DN10	-06								
DN12	-08								
DN14	—							108 000	(16 000)
DN16	-10								
DN20	-12								
DN25	-16								
DN32	-20								
DN40	-24								
—	-32	108 000 <sup>b</sup>	(16 000 <sup>b</sup> )						

<sup>a</sup> Dash size in 1/16 in, example: -05 = 5/16 in diameter; DN size in millimetres, example: DN05: 5 mm.  
<sup>b</sup> No data available to support this value.

**Table 3 — Test requirements, 21 000 kPa steel or titanium fittings on steel or titanium tubing**

Fitting and tube		Nominal pressure		Proof pressure		Burst pressure		Flexure test, bending stress 0 % to 10 %	
Metric	Inch								
Size	Size <sup>a</sup>	kPa	(psi)	kPa	(psi)	kPa	(psi)	kPa	(psi)
—	-02	21 000	(3 046)	42 000	(6 091)	84 000	(12 183)	135 000	(20 000)
DN05	-03								
DN06	-04								
DN08	-05								
DN10	-06								
DN12	-08								
DN14	—								
DN16	-10								
DN20	-12								
DN25	-16								
DN32	-20								
DN40	-24								
—	-32							108 000 <sup>b</sup>	(16 000 <sup>b</sup> )

<sup>a</sup> Dash size in 1/16 in, example: -05 = 5/16 in diameter; DN size in millimetres, example: DN05: 5 mm.

<sup>b</sup> No data available to support this value.

**Table 4 — Test requirements, return line aluminium fittings, up to 1 500 psi, on aluminium**

Fitting and tube		Nominal pressure		Proof pressure		Burst pressure		Flexure test, bending stress 0 % to 10 %	
Metric	Inch								
Size <sup>a</sup>	Size <sup>a</sup>	kPa	(psi)	kPa	(psi)	kPa	(psi)	kPa	(psi)
—	-02	10 342	(1 500)	20 684	(3 000)	41 368	(6 000)	41 368	(6 000)
DN05	-03								
DN06	-04								
DN08	-05								
DN10	-06								
DN12	-08								
DN14	—								
DN16	-10								
DN20	-12								
DN25	-16								
DN32	-20								
DN40	-24								
—	-32							27 579 <sup>b</sup>	(4 000 <sup>b</sup> )

<sup>a</sup> Dash size in 1/16 in, example: -05 = 5/16 in diameter; DN size in millimetres, example: DN05: 5 mm.

<sup>b</sup> No data available to support this value.

**Table 5 — Test requirements, return line aluminium fittings, 10 500 kPa, on aluminium tubing**

Fitting and tube		Nominal pressure		Proof pressure		Burst pressure		Flexure test, bending stress 0 % to 10 %			
Metric	Inch	kPa	(psi)	kPa	(psi)	kPa	(psi)	kPa	(psi)		
Size <sup>a</sup>	Size <sup>a</sup>										
—	-02	10 500	(1 522)	21 000	(3 046)	42 000	(6 091)	41 368	(6 000)		
DN05	-03										
DN06	-04										
DN08	-05										
DN10	-06							37 922	(5 500)		
DN12	-08										
DN14	—										
DN16	-10										
DN20	-12									34 474	(5 000)
DN25	-16									27 579	(4 000)
DN32	-20	27 579 <sup>b</sup>	(4 000 <sup>b</sup> )								
DN40	-24										
—	-32										

<sup>a</sup> Dash size in 1/16 in, example: -05 = 5/16 in diameter; DN size in millimetres, example: DN05: 5 mm.

<sup>b</sup> No data available to support this value.

### 4.3 Design and manufacture [standards.iteh.ai](https://standards.iteh.ai)

#### 4.3.1 Threads

ISO 7169:2014

<https://standards.iteh.ai/catalog/standards/sist/a9987049-83dc-4710-a514-4a44927db11a/iso-7169-2014>

All threads shall be in accordance with ISO 3161 for inch-size tube fittings, and with ISO 5855-3 for SI-metric tube fittings.

Threads can be cut, rolled, or, except for titanium, ground. The external threads of fittings should be rolled and, if machined, shall have an arithmetical mean deviation,  $R_a$ , of the profile of 3,2 µm (0,125 µin) or smoother.

Rolled threads shall be free of laps, cracks, surface irregularities, and seams on any part of the pressure thread flank, in the thread-root, or on the non-pressure thread flank. Laps and seams whose depths are within the limits of Table 6 are acceptable on the crest and the non-pressure thread flank above the pitch diameter.

**Table 6 — Maximum depth of laps, seams and surface irregularities in rolled threads**

Fitting size		Depth	
Metric	Inch	mm	(in)
Size	Size <sup>a</sup>		
—	-02	0,15	(0,006)
DN05	-03	0,15	(0,006)
DN06	-04	0,18	(0,007)
DN08	-05	0,18	(0,007)
DN10	-06	0,20	(0,008)
DN12	-08	0,22	(0,009)
DN14	—	0,25	(0,01)

<sup>a</sup> Dash size in 1/16 in, example: -05 = 5/16 in diameter; DN size in millimetres, example: DN05 = 5 mm.