
**Watch-cases and accessories — Gold
alloy coverings —**

**Part 2:
Determination of fineness, thickness,
corrosion resistance and adhesion**

Boîtes de montres et leurs accessoires — Revêtements d'alliage d'or —
Partie 2: Détermination du titre, de l'épaisseur, de la résistance à la
corrosion et de l'adhérence

ISO 3160-2:2015

<https://standards.iteh.ai/catalog/standards/sist/07c10196-b43f-4372-8375-578622b22818/iso-3160-2-2015>



iTeh STANDARD PREVIEW
(standards.iteh.ai)

ISO 3160-2:2015
<https://standards.iteh.ai/catalog/standards/sist/07c10196-b43f-4372-8375-578622b22818/iso-3160-2-2015>



COPYRIGHT PROTECTED DOCUMENT

© ISO 2015, Published in Switzerland

All rights reserved. Unless otherwise specified, no part of this publication may be reproduced or utilized otherwise in any form or by any means, electronic or mechanical, including photocopying, or posting on the internet or an intranet, without prior written permission. Permission can be requested from either ISO at the address below or ISO's member body in the country of the requester.

ISO copyright office
Ch. de Blandonnet 8 • CP 401
CH-1214 Vernier, Geneva, Switzerland
Tel. +41 22 749 01 11
Fax +41 22 749 09 47
copyright@iso.org
www.iso.org

Contents

	Page
Foreword.....	iv
Introduction.....	v
1 Scope.....	1
2 Normative references.....	1
3 Terms and definitions.....	1
4 General.....	2
5 Determination of gold fineness.....	2
5.1 General.....	2
5.2 Methods of gold fineness determination.....	2
6 Determination of thickness.....	3
7 Determination of the corrosion resistance.....	3
7.1 Forms of corrosion.....	3
7.2 Sampling and preparation.....	4
7.2.1 General.....	4
7.2.2 Test of finished items (ready-for-use condition).....	4
7.2.3 Test of coating process (without passivation treatment).....	4
7.2.4 Non-significant surfaces.....	4
7.3 Continuity of the covering (porosity test).....	4
7.3.1 General.....	4
7.3.2 Test for a copper-containing base metal with or without nickel, and die- cast zinc-based alloys.....	4
7.3.3 Test a ferrous base metal.....	5
7.3.4 Non-determination of base metal.....	6
7.3.5 Testing with nitric acid vapour.....	6
7.4 Synthetic perspiration test.....	6
7.4.1 Test vessel.....	6
7.4.2 Test solution.....	6
7.4.3 Position of the sample.....	6
7.4.4 Temperature during the test.....	6
7.4.5 Duration of the test.....	6
7.5 Neutral saline mist test.....	7
7.5.1 General.....	7
7.5.2 Criteria.....	7
7.6 Test of the effects of agents containing sulfur.....	7
7.6.1 Thioacetamide test.....	7
7.6.2 Flowers of sulfur test in a moist atmosphere.....	7
8 Adhesion test.....	7
Annex A (normative) Method of obtaining a sample of gold alloy covering.....	8
Annex B (normative) Implementation of the reference methods for the determination of gold alloy coating fineness.....	10
Annex C (normative) Description of the main tests for determination of the thickness of gold alloy coverings.....	12
Bibliography.....	14

Foreword

ISO (the International Organization for Standardization) is a worldwide federation of national standards bodies (ISO member bodies). The work of preparing International Standards is normally carried out through ISO technical committees. Each member body interested in a subject for which a technical committee has been established has the right to be represented on that committee. International organizations, governmental and non-governmental, in liaison with ISO, also take part in the work. ISO collaborates closely with the International Electrotechnical Commission (IEC) on all matters of electrotechnical standardization.

The procedures used to develop this document and those intended for its further maintenance are described in the ISO/IEC Directives, Part 1. In particular the different approval criteria needed for the different types of ISO documents should be noted. This document was drafted in accordance with the editorial rules of the ISO/IEC Directives, Part 2 (see www.iso.org/directives).

Attention is drawn to the possibility that some of the elements of this document may be the subject of patent rights. ISO shall not be held responsible for identifying any or all such patent rights. Details of any patent rights identified during the development of the document will be in the Introduction and/or on the ISO list of patent declarations received (see www.iso.org/patents).

Any trade name used in this document is information given for the convenience of users and does not constitute an endorsement.

For an explanation on the meaning of ISO specific terms and expressions related to conformity assessment, as well as information about ISO's adherence to the WTO principles in the Technical Barriers to Trade (TBT) see the following URL: Foreword - Supplementary information

The committee responsible for this document is ISO/TC 114, *Horology*, Subcommittee SC 6, *Precious metal coverings*.

This fourth edition cancels and replaces the third edition (ISO 3160-2:2003), of which it constitutes a technical revision.

ISO 3160 consists of the following parts, under the general title *Watch-cases and accessories — Gold alloy coverings*:

- *Part 1: General requirements*
- *Part 2: Determination of fineness, thickness, corrosion resistance and adhesion*

Introduction

Gold alloy coatings deposited on watch-cases and their accessories have to comply with technical, decorative requirements and have to also satisfy national rules about precious metals.

This part of ISO 3160 aims to specify coating characterization methods to qualify their corrosion resistance and their adhesion to the substrate concerning esthetical and technical aspects, and to specify methods to determine thickness and gold fineness of these coatings to check that they satisfy the requirements of ISO 3160-1.

iTeh STANDARD PREVIEW
(standards.iteh.ai)

ISO 3160-2:2015

<https://standards.iteh.ai/catalog/standards/sist/07c10196-b43f-4372-8375-578622b22818/iso-3160-2-2015>

iTeh STANDARD PREVIEW **(standards.iteh.ai)**

ISO 3160-2:2015

<https://standards.iteh.ai/catalog/standards/sist/07c10196-b43f-4372-8375-578622b22818/iso-3160-2-2015>

Watch-cases and accessories — Gold alloy coverings —

Part 2:

Determination of fineness, thickness, corrosion resistance and adhesion

1 Scope

This part of ISO 3160 specifies methods to determine fineness, thickness, corrosion resistance and adhesion for gold alloy coverings on watch-cases and accessories, including bracelets when they are permanently attached to the case.

The tests apply only to significant surfaces.

This part of ISO 3160 applies to all gold alloy coverings specified in ISO 3160-1.

2 Normative references

The following documents, in whole or in part, are normatively referenced in this document and are indispensable for its application. For dated references, only the edition cited applies. For undated references, the latest edition of the referenced document (including any amendments) applies.

ISO 1463, *Metallic and oxide coatings — Measurement of coating thickness — Microscopical method*

ISO 2177, *Metallic coatings — Measurement of coating thickness — Coulometric method by anodic dissolution*

ISO 3160-1, *Watch-cases and accessories — Gold alloy coverings — Part 1: General requirements*

ISO 3497, *Metallic coatings — Measurement of coating thickness — X-ray spectrometric methods*

ISO 3543, *Metallic and non-metallic coatings — Measurement of thickness — Beta backscatter method*

ISO 3868, *Metallic and other non-organic coatings — Measurement of coating thicknesses — Fizeau multiple-beam interferometry method*

ISO 4538, *Metallic coatings — Thioacetamide corrosion test (TAA test)*

ISO 9220, *Metallic coatings — Measurement of coating thickness — Scanning electron microscope method*

ISO 9227, *Corrosion tests in artificial atmospheres — Salt spray tests*

ISO 11426, *Jewellery — Determination of gold in gold jewellery alloys — Cupellation method (fire assay)*

ISO 12687, *Metallic coatings — Porosity tests — Humid sulfur (flowers of sulfur) test*

ISO 14647, *Metallic coatings — Determination of porosity in gold coatings on metal substrates — Nitric acid vapour test*

ISO 27874, *Metallic and other inorganic coatings — Electrodeposited gold and gold alloy coatings for electrical, electronic and engineering purposes — Specification and test methods*

3 Terms and definitions

For the purposes of this document, the following terms and definitions apply.

3.1 significant surface

part of the surface which is to receive the gold alloy covering and which is essential to the appearance and serviceability of the component

Note 1 to entry: When there is no agreement between the supplier and customer, a significant surface is considered to be any surface which can be touched by a 5 mm diameter ball.

4 General

In the context of this part of ISO 3160, the term “corrosion” includes tarnishing and oxidation, as well as surface penetration and the effects of the penetration of corrosive agents into porosity and micro-discontinuities of the protection.

It is generally required that, except where specified to the contrary, gold-alloy-covered surfaces should not have suffered any damage after each of the proposed tests. In practice, however, this condition is never strictly fulfilled and certain minor changes are observed, especially at the edges of the gold-covered parts. Consequently, interpretation of the results requires a certain amount of common sense and, if necessary, agreement between the supplier and customer. The presence of such almost inevitable faults makes it impossible to sell the tested item as new. In this respect, the tests are therefore to be considered to be destructive.

The test methods apply to all gold alloy coverings specified in ISO 3160-1.

5 Determination of gold fineness

5.1 General

If the fineness is measured on a gold alloy covering which is separated from the base metal, the method used to separate the gold alloy covering from the base metal shall not affect the fineness of the gold covering to a significant extent.

For multilayer coverings, the covering content measured is the mean content, which shall be a minimum of 585 parts per thousand, in accordance with ISO 3160-1.

The method of separation of the sample is specified in [Annex A](#).

5.2 Methods of gold fineness determination

Any of the following methods shall be used for the determination of contents:

- a) chemical analysis by reduction in an aqueous solution of, for example, sulfur dioxide or any other suitable reducing agent;
- b) analysis by
 - 1) cupellation (fire test) as specified in ISO 11426,
 - 2) Energy Dispersive Spectroscopy on Scanning Electron Microscopy (SEM/EDS),
 - 3) atomic absorption spectrometry,
 - 4) spectrophotometry,
 - 5) X-ray spectrometry as specified in ISO 3497,
 - 6) plasma emission spectrometry (ICP method);
- c) touchstone method (only to be used to evaluate the approximate fineness);

d) any other physico-chemical method.

Any method used shall be capable of giving an indication of fineness to within an accuracy of 50 parts per thousand.

In the event of arbitration, cupellation and SEM/EDS are the reference methods.

The implementation of the two reference methods is described in [Annex B](#).

6 Determination of thickness

Any of the following test methods for the determination of the thickness of gold alloy coatings shall be used, provided a measuring accuracy of $\pm 10\%$ is guaranteed:

- a) the microsection method specified in ISO 1463 for a thickness of 5 μm (-20%) and above (local thickness);
- b) the dissolution method and chemical analysis for any thickness of gold alloy covering (average thickness) specified in ISO 27874;
- c) dissolution and measurement by the micrometer method specified in ISO 1463;
- d) the beta-ray backscatter method specified in ISO 3543;
- e) the X-ray spectrometric method (fluorescence) specified in ISO 3497;
- f) the coulometric method (coulometric method by anodic dissolution) specified in ISO 2177;
- g) the fizeau multiple-beam interferometry method specified in ISO 3868;
- h) the scanning electron microscope method specified in ISO 9220;
- i) any other physical-chemical method which can guarantee accuracy.

In the event of arbitration, the microsection method specified in ISO 1463 shall be used (local thickness).

7 Determination of the corrosion resistance

7.1 Forms of corrosion

The various forms of corrosion which appear on a gold-alloy-covered article may be divided into three groups.

- a) Corrosion of the base metal at points where there are gaps in the covering: electrochemical cells may act at these points and accelerate penetration, and also at the boundary between the covering and the base metal.
- b) Attack caused by saline agents or possibly by mildly acidic agents (contact with perspiration, packaging, leathers or certain plastics): the products of corrosion may be of various colours, i.e. orange, violet, blue, green or brown.
- c) Attack caused by sulfur-containing agents (atmospheric hydrogen sulfide, vulcanized rubber, etc.): such agents may also attack the base metal at points where there are gaps in the protective covering. In addition, they cause changes in the surface colouring, which may even turn matt and black.

The proposed tests make it possible for these various effects to be distinguished to a certain extent. Gold alloy coverings shall be resistant in all the environments described below. According to the nature of the article, the supplier may, with the agreement of the customer, determine the number of items to be submitted to each test.

The development of corrosion is closely allied to the relative humidity of the ambient environment.

7.2 Sampling and preparation

7.2.1 General

According to the nature of the article, the supplier may, with the agreement of the customer, determine the number of items to be submitted to each test and the test conditions. The test conditions shall be stated in the test report.

The tests for determination of the corrosion resistance are applicable to finished items in the condition in which they are supplied to customers. They can also be applied during manufacture, but any interpretation of results shall take into account the form which the item will take when in its final condition.

7.2.2 Test of finished items (ready-for-use condition)

If the item to be tested is delivered in the ready-for-use condition, no cleaning operation shall be carried out. It is well known that residues remaining after insufficient rinsing have a considerable effect on tarnishing. It is necessary for the item to be tested in the condition in which it will be received by the customer.

7.2.3 Test of coating process (without passivation treatment)

When testing the quality of the coating on significant surfaces, care shall be taken to avoid any unusual influence. The sample shall be completely cleaned, first by the use of a water-based detergent with ultrasonic agitation, then in a solution of distilled water and ethanol or isopropanol. Degreasing in a chlorinated solvent is insufficient.

7.2.4 Non-significant surfaces

The non-significant surfaces of the object shall be coated with a lacquer or a covering which is sufficiently resistant to prevent any attack on the protected metal throughout the duration of the test.

7.3 Continuity of the covering (porosity test)

7.3.1 General

In practice, for the porosity test, it is recommended that account can be taken of the tests given in ISO 10308^[4].

7.3.2 Test for a copper-containing base metal with or without nickel, and die-cast zinc-based alloys

7.3.2.1 Test vessel

Use a suitable closed vessel, made of glass or acid-resistant plastic, and expose the sample to the corrosive atmosphere on all sides.

7.3.2.2 Test solution

The solution shall be of the following composition:

- acetic acid: (CH_3COOH , $\rho_{20} = 1,048 \text{ g/cm}^3$ to $1,052 \text{ g/cm}^3$, \geq a mass fraction of 99,0 %): a mass fraction of 50 %;
- deionized water: a mass fraction of 50 %.

The vessel shall be filled with this solution to a height of about 10 mm. The walls of the vessel shall be lined with thick white blotting paper which dips into the liquid.

7.3.2.3 Position of the sample

The sample shall be suspended on a glass hook at a distance of at least 30 mm from the liquid and the walls of the vessel.

7.3.2.4 Temperature during the test

The temperature during the test shall be $(23 \pm 2) ^\circ\text{C}$.

7.3.2.5 Duration of the test

The duration of the test shall be 24 h.

7.3.2.6 Criteria

When observed, the sample shall not reveal to the naked eye either green droplets or accumulations of green deposits anywhere on the significant surface. On die-cast zinc-based alloys, no white deposit shall appear.

7.3.3 Test a ferrous base metal**7.3.3.1 Test vessel**

The test shall be carried out in a suitable closed vessel made of glass or acid-resistant plastic, in which the sample is exposed to a corrosive atmosphere on all sides.

7.3.3.2 Test solution

The solution shall have the following composition:

- crystalline sodium metabisulfite ($\text{Na}_2\text{S}_2\text{O}_5$ p.a. ACS, synonyms: sodium pyrosulfite, sodium disulfite); a mass fraction of 45 %;
- deionized water: a mass fraction of 55 %.

The vessel shall be filled with this solution to a height of about 10 mm. The walls of the vessel shall be lined with thick white blotting paper which dips into the liquid.

7.3.3.3 Position of the sample

The sample shall be suspended on a glass hook at a distance of at least 30 mm from the liquid and the walls of the vessel.

7.3.3.4 Temperature during the test

The temperature during the test shall be $(23 \pm 2) ^\circ\text{C}$.

7.3.3.5 Duration of the test

The duration of the test shall be 24 h.

7.3.3.6 Criteria

When observed, the sample shall not reveal to the naked eye any traces of corrosion anywhere on the significant surface. Slight general tarnishing of low-carat coatings is admissible.