



Designation: D6506 – 01 (Reapproved 2009)

# Standard Specification for Asphalt Based Protection Board for Below-Grade Waterproofing<sup>1</sup>

This standard is issued under the fixed designation D6506; the number immediately following the designation indicates the year of original adoption or, in the case of revision, the year of last revision. A number in parentheses indicates the year of last reapproval. A superscript epsilon ( $\epsilon$ ) indicates an editorial change since the last revision or reapproval.

## 1. Scope

1.1 This specification covers an asphalt based protection board used for protecting the integrity of below grade or below wearing surface waterproofing. The protection board protects the waterproofing system from backfill, surfacing, construction activities, and weathering conditions prior to backfilling or applying surfacing.

1.2 The values stated in SI units are to be regarded as the standard. The values given in parentheses are for information only.

1.3 *This standard does not purport to address all of the safety concerns, if any, associated with its use. It is the responsibility of the user of this standard to establish appropriate safety and health practices and determine the applicability of regulatory limitations prior to use.*

## 2. Referenced Documents

2.1 *ASTM Standards:*<sup>2</sup>

[D545 Test Methods for Preformed Expansion Joint Fillers for Concrete Construction \(Nonextruding and Resilient Types\)](#)

[D994 Specification for Preformed Expansion Joint Filler for Concrete \(Bituminous Type\)](#)

[D5147 Test Methods for Sampling and Testing Modified Bituminous Sheet Material](#)

[E154 Test Methods for Water Vapor Retarders Used in Contact with Earth Under Concrete Slabs, on Walls, or as Ground Cover](#)

## 3. Classification

3.1 *Two Classes of Product are Covered in This Specification:*

<sup>1</sup> This specification is under the jurisdiction of ASTM Committee D08 on Roofing and Waterproofing and is the direct responsibility of Subcommittee D08.22 on Waterproofing and Dampproofing Systems.

Current edition approved Jan. 1, 2009. Published January 2009. Originally approved in 2001. Last previous edition approved in 2001 as D6506 – 01. DOI: 10.1520/D6506-01R09.

<sup>2</sup> For referenced ASTM standards, visit the ASTM website, www.astm.org, or contact ASTM Customer Service at service@astm.org. For *Annual Book of ASTM Standards* volume information, refer to the standard's Document Summary page on the ASTM website.

3.1.1 *Class A*, is made with asphalt saturated organic felt on the bottom and a coated or saturated non-woven glass felt on top.

3.1.2 *Class B*, is made with glass fabrics both top and bottom.

3.1.3 *Classes A and B*, each include three thicknesses of board. If desired, one side of each of these classes may be covered with a thin plastic antistick sheet.

## 4. Materials and Manufacture

4.1 The protection board shall be comprised of layers of asphalt and reinforcing mat. One surface of the board will be uniformly coated with a bituminous material for limited weather protection.

4.2 The length and width measurements shall be as specified by the manufacturer. The tolerances of these dimensions (length and width) shall be  $\pm 6$  mm ( $\frac{1}{4}$  in.)

4.3 The surfaces of the protection board shall be uniform and free from defects such as cracks and indentations. The edges shall be uniform.

## 5. Sampling

5.1 Each sample shall consist of sufficient material to provide at least five specimens for the tests listed in Section 7. One representative sample shall be selected for each shipment of 10 000 ft<sup>2</sup> or fraction thereof.

## 6. Physical Requirements

6.1 Nominal thicknesses of protection board are as follows:

6.1.1 *Type 1*, board is  $\frac{1}{16}$  in.

6.1.2 *Type 2*, board is  $\frac{1}{8}$  in.

6.1.3 *Type 3*, board is  $\frac{1}{4}$  in.

6.2 *Class A* protection board shall conform to the requirements in [Table 1](#).

6.3 *Class B* protection board shall conform to the requirements in [Table 2](#).

## 7. Test Methods

7.1 *Thickness*—Determine the thickness of the specimen using vernier calipers in accordance with Test Methods [D5147](#), Section 5.