



**SLOVENSKI STANDARD**  
**oSIST prEN ISO 12460-3:2019**  
**01-september-2019**

---

**Lesne plošče - Ugotavljanje sproščanja formaldehida - 3. del: Metoda plinske analize (ISO/DIS 12460-3:2019)**

Wood-based panels - Determination of formaldehyde release - Part 3: Gas analysis method (ISO/DIS 12460-3:2019)

Holzwerkstoffe - Bestimmung der Formaldehydabgabe - Teil 3: Gasanalyse-Verfahren (ISO/DIS 12460-3:2019)

Panneaux à base de bois - Détermination du dégagement de formaldéhyde - Partie 3: Méthode d'analyse de gaz (ISO/DIS 12460-3:2019)

**Ta slovenski standard je istoveten z: prEN ISO 12460-3**

[SIST EN ISO 12460-3:2020](https://standards.metat/catalog/standards/sist/61545777-c2ba-4c79-b006-212801961e0/sist-en-iso-12460-3-2020)

<https://standards.metat/catalog/standards/sist/61545777-c2ba-4c79-b006-212801961e0/sist-en-iso-12460-3-2020>

**ICS:**

79.060.01	Lesne plošče na splošno	Wood-based panels in general
-----------	-------------------------	------------------------------

**oSIST prEN ISO 12460-3:2019**

**en**



# DRAFT INTERNATIONAL STANDARD

## ISO/DIS 12460-3

ISO/TC 89

Secretariat: DIN

Voting begins on:  
2019-05-20Voting terminates on:  
2019-08-12

---

---

## Wood-based panels — Determination of formaldehyde release —

### Part 3: Gas analysis method

*Panneaux à base de bois — Détermination du dégagement de formaldéhyde —  
Partie 3: Méthode d'analyse de gaz*

ICS: 79.060.01

iTeh Standards  
(<https://standards.iteh.ai>)  
Document Preview

[SIST EN ISO 12460-3:2020](https://standards.iteh.ai/catalog/standards/sist/81515777-e2ba-4c79-888b-242b8f1984e8/sist-en-iso-12460-3-2020)<https://standards.iteh.ai/catalog/standards/sist/81515777-e2ba-4c79-888b-242b8f1984e8/sist-en-iso-12460-3-2020>

THIS DOCUMENT IS A DRAFT CIRCULATED FOR COMMENT AND APPROVAL. IT IS THEREFORE SUBJECT TO CHANGE AND MAY NOT BE REFERRED TO AS AN INTERNATIONAL STANDARD UNTIL PUBLISHED AS SUCH.

IN ADDITION TO THEIR EVALUATION AS BEING ACCEPTABLE FOR INDUSTRIAL, TECHNOLOGICAL, COMMERCIAL AND USER PURPOSES, DRAFT INTERNATIONAL STANDARDS MAY ON OCCASION HAVE TO BE CONSIDERED IN THE LIGHT OF THEIR POTENTIAL TO BECOME STANDARDS TO WHICH REFERENCE MAY BE MADE IN NATIONAL REGULATIONS.

RECIPIENTS OF THIS DRAFT ARE INVITED TO SUBMIT, WITH THEIR COMMENTS, NOTIFICATION OF ANY RELEVANT PATENT RIGHTS OF WHICH THEY ARE AWARE AND TO PROVIDE SUPPORTING DOCUMENTATION.

This document is circulated as received from the committee secretariat.

**ISO/CEN PARALLEL PROCESSING**



Reference number  
ISO/DIS 12460-3:2019(E)

© ISO 2019

iTeh Standards  
(<https://standards.iteh.ai>)  
Document Preview

[SIST EN ISO 12460-3:2020](https://standards.iteh.ai/catalog/standards/sist/81515777-e2ba-4c79-888b-242b8f1984e8/sist-cn-iso-12460-3-2020)

<https://standards.iteh.ai/catalog/standards/sist/81515777-e2ba-4c79-888b-242b8f1984e8/sist-cn-iso-12460-3-2020>



**COPYRIGHT PROTECTED DOCUMENT**

© ISO 2019

All rights reserved. Unless otherwise specified, or required in the context of its implementation, no part of this publication may be reproduced or utilized otherwise in any form or by any means, electronic or mechanical, including photocopying, or posting on the internet or an intranet, without prior written permission. Permission can be requested from either ISO at the address below or ISO's member body in the country of the requester.

ISO copyright office  
CP 401 • Ch. de Blandonnet 8  
CH-1214 Vernier, Geneva  
Phone: +41 22 749 01 11  
Fax: +41 22 749 09 47  
Email: [copyright@iso.org](mailto:copyright@iso.org)  
Website: [www.iso.org](http://www.iso.org)

Published in Switzerland

# Contents

	Page
<b>Foreword</b> .....	<b>iv</b>
<b>1 Scope</b> .....	<b>1</b>
<b>2 Normative references</b> .....	<b>1</b>
<b>3 Terms and definitions</b> .....	<b>1</b>
<b>4 Principle</b> .....	<b>1</b>
<b>5 Reagents</b> .....	<b>1</b>
<b>6 Apparatus</b> .....	<b>2</b>
6.1 Main composites of test apparatus (see <a href="#">Figure 1</a> ).....	2
6.2 Laboratory equipment.....	3
<b>7 Sampling and preparation of test pieces</b> .....	<b>3</b>
7.1 Preparation of test pieces.....	3
7.2 Selection of test pieces for factory production control.....	4
7.3 Selection of test pieces for other purposes.....	4
7.4 Preparation of test pieces in case of dispute.....	4
<b>8 Procedure</b> .....	<b>4</b>
8.1 Number of determinations.....	4
8.2 Determination of moisture content.....	4
8.3 Determination of formaldehyde release.....	5
8.3.1 General.....	5
8.3.2 Determination of formaldehyde release - Option 1.....	6
8.3.3 Determination of formaldehyde release - Option 2.....	6
8.3.4 Determination of formaldehyde release - Option 3.....	6
8.3.5 Determination of formaldehyde release - Option 4.....	6
8.4 Determination of formaldehyde content of the absorber solutions.....	7
8.4.1 General.....	7
8.4.2 Principle.....	7
8.4.3 Analytical Procedure.....	7
8.4.4 Calibration curve.....	7
<b>9 Expression of results</b> .....	<b>9</b>
9.1 Gas analysis value.....	9
9.2 Calculation of results.....	9
9.2.1 Calculation of results of test pieces.....	9
9.2.2 Calculation of emission report value.....	10
9.3 Moisture content.....	10
<b>10 Test report</b> .....	<b>10</b>
<b>Bibliography</b> .....	<b>14</b>

## ISO/DIS 12460-3:2019(E)

### Foreword

ISO (the International Organization for Standardization) is a worldwide federation of national standards bodies (ISO member bodies). The work of preparing International Standards is normally carried out through ISO technical committees. Each member body interested in a subject for which a technical committee has been established has the right to be represented on that committee. International organizations, governmental and non-governmental, in liaison with ISO, also take part in the work. ISO collaborates closely with the International Electrotechnical Commission (IEC) on all matters of electrotechnical standardization.

The procedures used to develop this document and those intended for its further maintenance are described in the ISO/IEC Directives, Part 1. In particular, the different approval criteria needed for the different types of ISO documents should be noted. This document was drafted in accordance with the editorial rules of the ISO/IEC Directives, Part 2 (see [www.iso.org/directives](http://www.iso.org/directives)).

Attention is drawn to the possibility that some of the elements of this document may be the subject of patent rights. ISO shall not be held responsible for identifying any or all such patent rights. Details of any patent rights identified during the development of the document will be in the Introduction and/or on the ISO list of patent declarations received (see [www.iso.org/patents](http://www.iso.org/patents)).

Any trade name used in this document is information given for the convenience of users and does not constitute an endorsement.

For an explanation of the voluntary nature of standards, the meaning of ISO specific terms and expressions related to conformity assessment, as well as information about ISO's adherence to the World Trade Organization (WTO) principles in the Technical Barriers to Trade (TBT), see [www.iso.org/iso/foreword.html](http://www.iso.org/iso/foreword.html).

The committee responsible for this document is ISO/TC 89, *Wood-based panels*.

The objective of the revision was to improve the detection limit and the reproducibility of the method with regard to boards with low formaldehyde content.

This second edition cancels and replaces the first edition (ISO 12460-3:2015), which has been technically revised.

The main changes compared to the previous edition are as follows: [888b-242b8f1984e8/sist-en-iso-12460-3-2020](https://standards.iteh.ai/SIST-EN-ISO-12460-3-2020)

- test period can be reduced from 4 h to 3 h;
- in [7.3](#) four different options to determine the formaldehyde release are introduced;
- conditioning procedure for decor finish foils specified in [6.1](#).

A list of all parts in the ISO 12460 series can be found on the ISO website.

Any feedback or questions on this document should be directed to the user's national standards body. A complete listing of these bodies can be found at [www.iso.org/members.html](http://www.iso.org/members.html).

# Wood-based panels — Determination of formaldehyde release —

## Part 3: Gas analysis method

### 1 Scope

This part of ISO 12460 specifies a procedure for determination of accelerated formaldehyde release from uncoated and coated wood-based panels using the gas analysis method. The procedure is also suitable for the testing of other materials (e.g. edge bands, floor coverings, foams, foils, laminated wood products, veneered wood products, coated wood products).

### 2 Normative references

The following documents are referred to in the text in such a way that some or all of their content constitutes requirements of this document. For dated references, only the edition cited applies. For undated references, the latest edition of the referenced document (including any amendments) applies.

ISO 16979, *Wood-based panels — Determination of moisture content*

ISO 16999, *Wood-based panels — Sampling and cutting of test pieces*

### 3 Terms and definitions

No terms and definitions are listed in this document.

ISO and IEC maintain terminological databases for use in standardization at the following addresses:

— ISO Online browsing platform: available at <http://www.iso.org/obp>

— IEC Electropedia: available at <http://www.electropedia.org/>

### 4 Principle

A test piece of known surface area is placed in a closed chamber in which the temperature, humidity, airflow, and pressure are controlled to defined values. Formaldehyde released from the test pieces mixes with the air in the chamber. This air is continually drawn from the chamber and passes through gas wash bottles, containing water, which absorbs the released formaldehyde. At the end of the test, the formaldehyde concentration is determined photometrically or fluorimetrically. The formaldehyde release is calculated from this concentration, the sampling time, and the exposed area of the test pieces and is expressed in milligrams per square meter and hour (mg/m<sup>2</sup>h).

### 5 Reagents

Reagents of recognized analytical purity and distilled or demineralised water (referred throughout the following text as distilled water) shall be used for the analysis.

**5.1 4 ml Acetylacetone solution** are added to a 1 000 ml volumetric flask and made up to the mark with distilled water.

## ISO/DIS 12460-3:2019(E)

**5.2 200 g ammonium acetate solution** are dissolved with distilled water in a 1 000 ml volumetric flask and made up to the mark.

Optionally, a premixed reagent of acetylacetone and ammonium acetate as described in ISO 12460-4 can be used.

**5.3 Formaldehyde solution** commercially available (concentration typically between 35 % mass fraction to 40 % mass fraction).

**5.4 Standard iodine solution**  $c(I_2) = 0,05 \text{ mol/l}$ .

**5.5 Standard sodium thiosulphate solution**  $c(Na_2S_2O_3) = 0,1 \text{ mol/l}$ .

**5.6 Standard sodium hydroxide solution**  $c(NaOH) = 1 \text{ mol/l}$ .

**5.7 Standard sulphuric acid solution**  $c(H_2SO_4) = 1 \text{ mol/l}$ .

**5.8 Starch solution** 1 % by mass.

## 6 Apparatus

### 6.1 Main composites of test apparatus (see [Figure 1](#))

**6.1.1 Air filter** (1).

**6.1.2 Wash bottle**, 500 ml, containing ca. 400 ml distilled water (2).

**6.1.3 Desiccator**, 500 ml, containing silica gel (3).

**6.1.4 Air pump** (4).

**6.1.5 Needle valve** (5).

**6.1.6 Equipment for measuring rate of air flow through apparatus** (6).

**6.1.7 Test chamber** (diameter: 90 mm to 100 mm with a length which gives an internal volume of  $(4\ 000 \pm 200)$  ml with double casing of stainless steel or glass (7).

**6.1.8 Heating equipment for air** (e.g. copper coil inside the double casing) (8).

**6.1.9 Thermostat** (9).

**6.1.10 Magnetic valves** (10).

**6.1.11 4 pairs of gas wash bottles**, 100 ml or optionally, 4 pairs of gas wash bottles, 30 ml (21).

**6.1.12 Pressure monitor** (22).

**6.1.13 Temperature monitor** (23).



**6.1.14 Test piece holder**, constructed as a shelf with three rods made from stainless steel or another inert material (24).

NOTE The test apparatus described in [Figure 1](#) is based on a waterborne heating system. A test apparatus with an electrical heating system can be used optionally.

## 6.2 Laboratory equipment

**6.2.1 Ventilated oven**, as described in ISO 16979 for determination of moisture content (if requested).

**6.2.2 Spectrophotometer**, with cells of 50 mm optical path length and capable of measuring absorbance at 412 nm.

**6.2.3 Water bath**, capable of maintaining a temperature of  $(60 \pm 1) ^\circ\text{C}$ .

**6.2.4 Water bath**, capable of maintaining a temperature in the range of  $20 ^\circ\text{C}$  to  $25 ^\circ\text{C}$ .

**6.2.5 Six volumetric flasks**, 100 ml (calibrated at  $20 ^\circ\text{C}$ ).

**6.2.6 Four volumetric flasks**, 250 ml or optionally, four volumetric flasks, 100 ml (calibrated at  $20 ^\circ\text{C}$ ).

**6.2.7 Two volumetric flasks**, 1 000 ml (calibrated at  $20 ^\circ\text{C}$ ).

**6.2.8 Volumetric pipettes** (calibrated at  $20 ^\circ\text{C}$ ), 1 ml, 2 ml, 5 ml, 10 ml, 15 ml, 20 ml, 25 ml, 30 ml, 50 ml, 100 ml.

**6.2.9 Six flasks**, 50 ml (with stoppers).

**6.2.10 Microburette**.

**6.2.11 Burette**, 50 ml, graduated (calibrated at  $20 ^\circ\text{C}$ ).

**6.2.12 Balance**, capable of measuring to 0,00 1 g.

## 7 Sampling and preparation of test pieces

### 7.1 Preparation of test pieces

Three test pieces, each with the dimensions of  $(400 \pm 1) \text{ mm} \times (50 \pm 1) \text{ mm} \times$  board thickness, shall be prepared for the determination of formaldehyde release giving a total emitting surface area of  $0,04 \text{ m}^2$ .

If the sample available does not allow the preparation of test pieces of the specified dimension, then the combined emitting surface area of the test pieces(s) should be as close as possible to  $0,04 \text{ m}^2$ .

For testing layer glued materials (e.g. plywood, veneered particleboard), specimens shall be cut from the respective panel with the fibre direction of the faces perpendicular to the longitudinal axis of the specimen.

Each test piece has to be hermetically wrapped immediately after cutting and stored at ambient temperature.

Before testing, each test piece shall be stored hermetically wrapped at least one day at ambient temperature in order to improve the repeatability. For factory production control with hot test pieces, a valid correlation has to be established.

## ISO/DIS 12460-3:2019(E)

Test pieces shall be representative for the tested boards.

For testing, the test pieces shall be edge sealed with temperature resistant (i.e.  $\geq 60$  °C) self-adhesive aluminium tape or an alternative sealing method if equivalence has been demonstrated. The emitting (unsealed) surface area of the sealed test piece has to be measured and calculated in square metres (m<sup>2</sup>).

For decor finish foils it is recommended to pre-condition the material as follows in order to take into account inhomogeneity as to improve precision: 7 days at  $(20 \pm 2)$  °C and  $(65 \pm 5)$  % relative humidity.

### 7.2 Selection of test pieces for factory production control

Sampling and cutting of the test pieces shall be performed according to the principles of ISO 16999.

Test pieces are taken, uniformly distributed over the width of the (cooled) board, but excluding a 250 mm wide strip from the end of each board.

The formaldehyde determination should be carried out not more than 72 h after sampling.

### 7.3 Selection of test pieces for other purposes

The procedure of sampling, preparation of the test pieces, and conditioning (e.g. from boards already installed) shall be noted and described in the test report. The number and dimensions of the test pieces shall be as given in [7.1](#).

### 7.4 Preparation of test pieces in case of dispute

If this method is used in case of dispute, e.g. linked to disagreement about compliance and not otherwise agreed upon, the conditioning of the test pieces shall be carried out according to the following reference conditions.

The test pieces shall be conditioned to constant mass at a temperature of  $(20 \pm 2)$  °C and a relative humidity of  $(65 \pm 5)$  %.

Constant mass is considered to have been reached when the results of two successive weighings, carried out at intervals of not less than 24 h, do not differ by more than 0,1 % of the mass of the test pieces. Alternative two weeks of conditioning can be used.

Contamination of test pieces from other sources of formaldehyde during conditioning shall be avoided.

## 8 Procedure

### 8.1 Number of determinations

Determination shall always be made in duplicate using two different test pieces prepared according to [6.1](#). A third determination shall be carried out

- if the average emission value of the two determinations is  $>1,0$  mg/m<sup>2</sup>h and the two replicates deviate more than 20 % of the average value, or
- if the average emission value of the determinations is  $\leq 1,0$  mg/m<sup>2</sup>h and the two replicates deviate more than 0,2 mg/m<sup>2</sup>h from the average value.

For factory production control, a single determination can be sufficient.

### 8.2 Determination of moisture content

Moisture content shall be determined according to ISO 16979 using a separate sample (see [7.1](#)).