# INTERNATIONAL STANDARD

ISO 19642-3

First edition 2019-01

### Road vehicles — Automotive cables —

### Part 3:

Dimensions and requirements for 30 V a.c. or 60 V d.c. single core copper conductor cables

Teh ST Véhicules routiers — Cables automobiles —

Partie 3: Dimensions et exigences des câbles en cuivre mono conducteurs de 30 V a.c. ou 60 V c.c.

ISO 19642-3:2019 https://standards.iteh.ai/catalog/standards/sist/03f29bae-adfe-471d-9f2a-18c23f96c517/iso-19642-3-2019



## iTeh STANDARD PREVIEW (standards.iteh.ai)

ISO 19642-3:2019 https://standards.iteh.ai/catalog/standards/sist/03f29bae-adfe-471d-9f2a-18c23f96c517/iso-19642-3-2019



#### **COPYRIGHT PROTECTED DOCUMENT**

© ISO 2019

All rights reserved. Unless otherwise specified, or required in the context of its implementation, no part of this publication may be reproduced or utilized otherwise in any form or by any means, electronic or mechanical, including photocopying, or posting on the internet or an intranet, without prior written permission. Permission can be requested from either ISO at the address below or ISO's member body in the country of the requester.

ISO copyright office CP 401 • Ch. de Blandonnet 8 CH-1214 Vernier, Geneva Phone: +41 22 749 01 11 Fax: +41 22 749 09 47 Email: copyright@iso.org Website: www.iso.org

Published in Switzerland

Contents				Page		
Fore	eword			<b>v</b>		
Intr	oductio	n		vi		
1						
	•					
2	Norn	native re	ferences	1		
3	Term	Terms and definitions				
4	Specifications					
	4.1	Genera	l test conditions	2		
	4.2		concerns			
	4.3	Voltage	erating	2		
	4.4		rature classes			
	4.5		ctor material			
	4.6 4.7		ctorsion thickness			
	4.7		outside diameter			
	4.9		entative conductor sizes for testing			
	4.10		nce and requirements for the tests according to ISO 19642-2			
5	Dogu		s			
3	5.1		]			
	5.2					
		5.2.1	cable outside diameter	5		
		5.2.2	Insulation thickness and sitch ai) Conductor diameter	5		
		5.2.3	Conductor diameter	5		
		5.2.4	Cross-sectional area (CSA)	5		
	<b>F</b> 0	5.2.5	In-process cable outside diameter  In-process cable	6		
	5.3	Electric	Cross-sectional area (CSA) In-process cable outside diameter Tal tests ards itch ai/catalog/standards/sist/03f29bae-adfe-471d-9f2a- Conductor resistance 17/iso-19642-3-2019	6		
		5.3.1	Requirement for determination of temperature coefficients	6		
		5.3.3	Withstand voltage			
		5.3.4	Withstand voltage after environmental testing			
		5.3.5	Insulation faults			
		5.3.6	Insulation volume resistivity	6		
	5.4		nical tests			
		5.4.1	Strip force			
		5.4.2	Abrasion			
		5.4.3 5.4.4	Breaking force of the finished cable			
		5.4.5	Cyclic bendingFlexibility test			
	5.5		nmental tests			
	0.0	5.5.1	Test specimen preparation and winding tests			
		5.5.2	Long term heat ageing, 3 000 h at temperature class rating			
		5.5.3	Short term heat ageing, 240 h at temperature class rating +25 °C			
		5.5.4	Thermal overload, 6 h at temperature class rating +50 °C			
		5.5.5	Pressure test at high temperature			
		5.5.6	Shrinkage by heat			
		5.5.7 5.5.8	Low temperature winding			
		5.5.9	Temperature and humidity cycling			
		5.5.10	Resistance to hot water			
		5.5.11	Resistance to liquid chemicals			
		5.5.12	Durability of cable marking			
		5.5.13	Stress cracking resistance			
		5.5.14	Resistance to ozone	10		

#### ISO 19642-3:2019(E)

5.5.15	Resistance to flame propagation	10
Annex A (informative)	ISO conductor sizes, number of strands and strand diameters	13
Bibliography		16

# iTeh STANDARD PREVIEW (standards.iteh.ai)

ISO 19642-3:2019 https://standards.iteh.ai/catalog/standards/sist/03f29bae-adfe-471d-9f2a-18c23f96c517/iso-19642-3-2019

#### **Foreword**

ISO (the International Organization for Standardization) is a worldwide federation of national standards bodies (ISO member bodies). The work of preparing International Standards is normally carried out through ISO technical committees. Each member body interested in a subject for which a technical committee has been established has the right to be represented on that committee. International organizations, governmental and non-governmental, in liaison with ISO, also take part in the work. ISO collaborates closely with the International Electrotechnical Commission (IEC) on all matters of electrotechnical standardization.

The procedures used to develop this document and those intended for its further maintenance are described in the ISO/IEC Directives, Part 1. In particular, the different approval criteria needed for the different types of ISO documents should be noted. This document was drafted in accordance with the editorial rules of the ISO/IEC Directives, Part 2 (see <a href="www.iso.org/directives">www.iso.org/directives</a>).

Attention is drawn to the possibility that some of the elements of this document may be the subject of patent rights. ISO shall not be held responsible for identifying any or all such patent rights. Details of any patent rights identified during the development of the document will be in the Introduction and/or on the ISO list of patent declarations received (see <a href="https://www.iso.org/patents">www.iso.org/patents</a>).

Any trade name used in this document is information given for the convenience of users and does not constitute an endorsement.

For an explanation of the voluntary nature of standards, the meaning of ISO specific terms and expressions related to conformity assessment, as well as information about ISO's adherence to the World Trade Organization (WTO) principles in the Technical Barriers to Trade (TBT), see <a href="https://www.iso.org/iso/foreword.html">www.iso.org/iso/foreword.html</a>. (Standards.iteh.ai)

This document was prepared by Technical Committee ISO/TC 22, *Road vehicles*, Subcommittee SC 32, *Electrical and electronic components and general system aspects*.

A list of all parts in the ISO 19642 series can be found on the ISO website.

Any feedback or questions on this document should be directed to the user's national standards body. A complete listing of these bodies can be found at <a href="https://www.iso.org/members.html">www.iso.org/members.html</a>.

#### Introduction

This document was prepared following a joint resolution to improve the general structure of the ISO Automotive Electric Cable standards. This new structure adds more clarity and, by defining a new standard family, opens up the standard for future amendments.

Many other standards currently refer to ISO 6722-1, ISO 6722-2 and ISO 14572. So these standards will stay valid at least until the next scheduled systematic review and will be replaced later on by the ISO 19642 series.

For new Automotive Cable Projects customers and suppliers are advised on using the ISO 19642 series.

## iTeh STANDARD PREVIEW (standards.iteh.ai)

ISO 19642-3:2019 https://standards.iteh.ai/catalog/standards/sist/03f29bae-adfe-471d-9f2a-18c23f96c517/iso-19642-3-2019

### Road vehicles — Automotive cables —

#### Part 3:

## Dimensions and requirements for 30 V a.c. or 60 V d.c. single core copper conductor cables

WARNING — The use of this document can involve hazardous materials, operations and equipment. This document does not purport to address all of the safety concerns, if any, associated with its use. It is the responsibility of the user of this document to establish appropriate safety practices and determine the applicability of regulatory limitations prior to use.

#### Scope 1

This document specifies the dimensions and requirements for single-core cables intended for general purpose vehicle applications where the nominal system voltage is less than or equal to 30 V a.c. or less than or equal to 60 V d.c.. It also applies to individual cores in multi-core cables.

This document specifies requirements for copper conductor cables.

### iTeh STANDARD PREVIEW

## Normative references (standards.iteh.ai)

The following documents are referred to in the text in such a way that some or all of their content constitutes requirements of this document. For dated references, only the edition cited applies. For undated references, the latest edition of the referenced document (including any amendments) applies.

ISO 19642-1, Road vehicles — Automotive cables — Vocabulary and design guidelines

ISO 19642-2, Road vehicles — Automotive cables — Test methods

EN 13602, Copper and copper alloys — Drawn, round copper wire for the manufacture of electrical conductors

ASTM B1, Standard Specification for Hard-Drawn Copper Wire

ASTM B3, Standard Specification for Soft or Annealed Copper Wire

ASTM B33, Standard Specification for Tinned Soft or Annealed Copper Wire for Electrical Purposes

ASTM B298, Standard Specification for Silver-Coated Soft or Annealed Copper Wire

ASTM B355, Standard Specification for Nickel-Coated Soft or Annealed Copper Wire

#### Terms and definitions

For the purposes of this document, the terms and definitions given in ISO 19642-1 apply.

ISO and IEC maintain terminological databases for use in standardization at the following addresses:

- ISO Online browsing platform: available at <a href="https://www.iso.org/obp">https://www.iso.org/obp</a>
- IEC Electropedia: available at <a href="http://www.electropedia.org/">http://www.electropedia.org/</a>

#### **Specifications**

#### 4.1 General test conditions

The test conditions of ISO 19642-2 shall apply.

The cables shall be tested as specified in Table 2.

If suppliers and customers agree on modifications or changes to the methods and requirements, all the changes and modifications shall be clearly documented.

#### 4.2 Safety concerns

The precautions as described in the WARNING at the beginning of this document shall be followed.

#### 4.3 Voltage rating

The cable described in this document is limited to 30 V a.c. and 60 V d.c. maximum.

#### **Temperature classes**

All temperature classes in ISO 19642-1 are suitable for copper conductor cables.

## Conductor material iTeh STANDARD PREVIEW

The conductors shall consist of plain or coated copper strands as shown in Table 1.

ISO conductor sizes greater than or equal to 0,5 mm<sup>2</sup> shall consist of soft annealed copper or annealed compressed wires. ISO 19642-3:2019

https://standards.iteh.ai/catalog/standards/sist/03f29bae-adfe-471d-9f2a-ISO conductor sizes less than 0,5 mm² shall consist of soft annealed compressed copper, hard un-annealed copper or a copper alloy.

The specifications for the conductors shall be completed by material specifications. Elongation requirements shall be established by agreement between the customer and the supplier.

The finished cable shall meet the resistance and cross-sectional area (CSA) requirements of Table 6 for all conductors except alloys. When an alloy is used, the resistance requirement shall be established by agreement between the customer and the supplier.

NOTE Examples for strands are shown in Annex A.

Table 1 — Conductor specifications

Description	Specification number				
Hard-drawn copper wire	ASTM B1				
Soft or annealed copper wire	ASTM B3 or EN 13602				
Tinned soft or annealed copper wire	ASTM B33 or EN 13602				
Silver-coated soft or annealed copper wire	ASTM B298				
Nickel-coated soft or annealed copper wire	ASTM B355				
NOTE Silver and Nickel coated conductors are intended for use with high "temperature class ratings"					

#### 4.6 Conductors

The conductors in the finished cable shall meet the CSA and resistance requirements of Table 6.

The maximum diameter of the conductors is standardized and presented in <u>Table 7</u>.

The configuration of the stranded conductor is not standardized.

NOTE 1 Existing stranding configurations for copper conductors are presented in Table A.1.

NOTE 2 Preferred stranding configurations for copper conductors are presented in <u>Table A.2</u>.

Other stranding configurations may be used for copper conductors provided they meet the above requirements and are agreed between the customer and the supplier.

#### 4.7 Insulation thickness

The following three different insulation thicknesses are allowed in this document:

- 1. thick wall insulation;
- 2. thin wall insulation;
- 3. ultra-thin wall insulation.

The minimum wall thickness requirements for the different ISO conductor sizes are standardized and specified in <u>Table 7</u>.

The nominal wall thickness is derived from the minimum wall thickness in  $\underline{\text{Table 7}}$  by the following formulae:

$$w_{\text{nom}} = 1,25 \times w_{\text{min}}$$
 or  $w_{\text{nom}} = w_{\text{min}} / 0,8$  (standards.iteh.ai)

where

ISO 19642-3:2019

 $w_{\min}$  is the minimum wall thickness, og/standards/sist/03f29bae-adfe-471d-9f2a-18c23f96c517/iso-19642-3-2019

 $w_{\text{nom}}$  is the nominal wall thickness.

#### 4.8 Cable outside diameter

The cable outside diameter for each ISO conductor size and insulation thickness is standardized and specified in Table 7.

#### 4.9 Representative conductor sizes for testing

When a test is required, all combinations of conductor size, insulation thickness and insulation formulation shall meet the specified requirements.

However, if testing of representative conductor sizes is permitted by agreement between the customer and the supplier, compliance for a cable family may be demonstrated by testing examples of large and small conductor sizes only.

#### 4.10 Reference and requirements for the tests according to ISO 19642-2

Table 2 provides a list of all relevant tests in ISO 19642-2:2019 for single core cables.

Table 2 — Tests

	Mandatory			If required <sup>c</sup>	
Test description	In processa	Initial certification	Periodicb	Initial certifica- tion	<b>Periodic</b> b
5.1 Dimensional tests					
5.1.2 Cable outside diameter	_	X	X	_	_
5.1.3 Insulation thickness	_	X	X	_	_
5.1.4 Conductor diameter	_	_	_	X	X
5.1.5 Cross sectional area	_	_	_	X	X
5.1.6 In-process cable outside diameter	X	_	_	_	_
5.2 Electrical tests					
5.2.1 Conductor resistance	_	X	X	_	_
5.2.2 Determination of temperature coefficients	_	X	_	_	_
5.2.3 Withstand voltage	_	X	X	_	_
5.2.4 Withstand voltage after environmental testingd	_	_	_	_	_
5.2.5 Insulation faults	X	_	_	_	_
5.2.6 Insulation volume resistivity	_	_	_	X	X
5.3 Mechanical tests					
5.3.1 Strip force TAND	ARD	PREV	TF <del>'</del> W	X	X
5.3.2 Abrasion <sup>e</sup>		1 1 1			
5.3.2.4 Sandpaper abrasion test (Standa	ards.it	eh.ai)	X	_	_
5.3.2.5 Scrape abrasion test	_	X	X	_	_
5.3.3 Breaking force of the finished cable	19642-3;201	9 (03£20baa ad	6 4714 0f0	X	_
5.3.4 Cyclic bending 18c23f96c5	17/iso-19642	031290ac-ad 2-3-2019	<del></del>	X	_
5.3.5 Flexibility	_	_	_	X	_
5.4 Environmental tests					
5.4.1 Specimen preparation and winding tests <sup>d</sup>					
5.4.2 Long term heat ageing, 3 000 h at temperature class rating	_	X	_	_	_
5.4.3 Short term heat ageing, 240 h at temperature class rating +25 °C	_	X	X	_	_
5.4.4 Thermal overload, 6 h at temperature class rating +50 °C	_	_	_	X	Х
5.4.5 Pressure test at high temperature	_	X	X	_	_
5.4.6 Shrinkage by heat	_	X	X	_	_
5.4.7 Low temperature winding	_	X	X	_	_
Kev					

#### Key

- X: Test shall be performed according to ISO 19642-2
- Test is not required
- a A test made on the entire cable lot during or after manufacture.
- b The frequency of periodic testing shall be established by agreement between the customer and the supplier.
- The usage of "If required" tests shall be established by agreement between the customer and the supplier.
- d These tests are only used in preparation and after environmental endurance tests.
- e Only one of the abrasion tests has to be performed by agreement between the customer and the supplier.
- f Compliance for a cable family may be demonstrated by testing examples of large and small conductor sizes only.
- Some fluids are for "Initial certification" and others are "If required".

**Table 2** (continued)

	Mandatory			If required <sup>c</sup>	
Test description	In processa	Initial certifica- tion	Periodicb	Initial certifica- tion	<b>Periodic</b> b
5.4.8 Cold impact	_	_	_	X	X
5.4.9 Temperature and humidity cycling <sup>f</sup>	_	_	_	X	_
5.4.10 Resistance to hot water <sup>f</sup>	_	X	_	_	_
5.4.11 Resistance to liquid chemicals <sup>f, g</sup>	_	X	_	X	_
5.4.12 Durability of cable marking <sup>f</sup>	_	_	_	X	X
5.4.13 Stress cracking resistance <sup>f</sup>	_	_	_	X	_
5.4.14 Resistance to ozone <sup>f</sup>	_	_	_	X	_
5.4.15 Resistance to flame propagation	_	X	X	_	_

#### Key

- X: Test shall be performed according to ISO 19642-2
- —: Test is not required
- a A test made on the entire cable lot during or after manufacture.
- b The frequency of periodic testing shall be established by agreement between the customer and the supplier.
- The usage of "If required" tests shall be established by agreement between the customer and the supplier.
- d These tests are only used in preparation and after environmental endurance tests./
- Only one of the abrasion tests has to be performed by agreement between the customer and the supplier.
- f Compliance for a cable family may be demonstrated by testing examples of large and small conductor sizes only.
- Some fluids are for "Initial certification" and others are "If required".

https://standards.iteh.ai/catalog/standards/sist/03f29bae-adfe-471d-9f2a-

#### 5 Requirements

s 18c23f96c517/iso-19642-3-2019

#### 5.1 General

The cables shall be tested per ISO 19642-2 according to their temperature class rating.

The cables shall be tested as specified in <u>Table 2</u>.

#### 5.2 Dimensional tests

#### 5.2.1 Cable outside diameter

No single value shall be greater or less than the standardized values in <u>Table 7</u>.

#### 5.2.2 Insulation thickness

No single value shall be less than the standardized minimum value in <u>Table 7</u>.

#### 5.2.3 Conductor diameter

No single value shall be greater than the maximum value in <u>Table 7</u>.

#### 5.2.4 Cross-sectional area (CSA)

No single value shall be greater or less than the standardized values in <u>Table 6</u>.