

---

---

**Road vehicles — Automotive cables —  
Part 6:  
Dimensions and requirements for 600  
V a.c. or 900 V d.c. and 1 000 V a.c. or  
1 500 V d.c. single core aluminium  
conductor cables**

iTeh STANDARD PREVIEW  
(standards.iteh.ai)

*Véhicules routiers — Câbles automobiles —*

*Partie 6: Dimensions et exigences des câbles en aluminium mono  
conducteurs de 600 V a.c. ou 900 V c.c. et 1 000 V a.c. ou 1 500 V c.c.*

[https://standards.iteh.ai/catalog/standards/sist/783b2355-2754-48f7-86f4-  
e0a2158854b1/iso-19642-6-2019](https://standards.iteh.ai/catalog/standards/sist/783b2355-2754-48f7-86f4-e0a2158854b1/iso-19642-6-2019)



## iTeh STANDARD PREVIEW (standards.iteh.ai)

ISO 19642-6:2019

<https://standards.iteh.ai/catalog/standards/sist/783b2355-2754-48f7-86f4-e0a2158854b1/iso-19642-6-2019>



### **COPYRIGHT PROTECTED DOCUMENT**

© ISO 2019

All rights reserved. Unless otherwise specified, or required in the context of its implementation, no part of this publication may be reproduced or utilized otherwise in any form or by any means, electronic or mechanical, including photocopying, or posting on the internet or an intranet, without prior written permission. Permission can be requested from either ISO at the address below or ISO's member body in the country of the requester.

ISO copyright office  
CP 401 • Ch. de Blandonnet 8  
CH-1214 Vernier, Geneva  
Phone: +41 22 749 01 11  
Fax: +41 22 749 09 47  
Email: [copyright@iso.org](mailto:copyright@iso.org)  
Website: [www.iso.org](http://www.iso.org)

Published in Switzerland

# Contents

	Page
<b>Foreword</b> .....	<b>v</b>
<b>Introduction</b> .....	<b>vi</b>
<b>1 Scope</b> .....	<b>1</b>
<b>2 Normative references</b> .....	<b>1</b>
<b>3 Terms and definitions</b> .....	<b>1</b>
<b>4 Specifications</b> .....	<b>2</b>
4.1 General test conditions.....	2
4.2 Safety concerns.....	2
4.3 Voltage ratings.....	2
4.4 Temperature classes.....	2
4.5 Conductor material.....	2
4.6 Conductors.....	3
4.7 Insulation thickness.....	3
4.8 Cable outside diameter.....	4
4.9 Representative conductor sizes for testing.....	4
4.10 Reference and requirements for the tests according to ISO 19642-2.....	4
<b>5 Requirements</b> .....	<b>5</b>
5.1 General.....	5
5.2 Dimensional tests.....	6
5.2.1 Cable outside diameter.....	6
5.2.2 Insulation thickness.....	6
5.2.3 Conductor diameter.....	6
5.2.4 Cross sectional area.....	6
5.2.5 In-process cable outside diameter.....	6
5.3 Electrical tests.....	6
5.3.1 Conductor resistance.....	6
5.3.2 Determination of temperature coefficients.....	6
5.3.3 Withstand voltage.....	6
5.3.4 Withstand voltage after environmental testing.....	6
5.3.5 Insulation faults.....	7
5.3.6 Insulation volume resistivity.....	7
5.4 Mechanical tests.....	7
5.4.1 Strip force.....	7
5.4.2 Abrasion.....	7
5.4.3 Breaking force of the finished cable.....	8
5.4.4 Cyclic bending.....	8
5.4.5 Flexibility.....	8
5.5 Environmental tests.....	9
5.5.1 Test specimen preparation and winding tests.....	9
5.5.2 Long term heat ageing, 3 000 h at temperature class rating.....	9
5.5.3 Short term heat ageing, 240 h at temperature class rating +25 °C.....	9
5.5.4 Thermal overload, 6 h at temperature class rating +50 °C.....	9
5.5.5 Pressure test at high temperature.....	9
5.5.6 Shrinkage by heat.....	9
5.5.7 Low temperature winding.....	9
5.5.8 Cold impact.....	9
5.5.9 Temperature and humidity cycling.....	10
5.5.10 Resistance to hot water.....	10
5.5.11 Resistance to liquid chemicals.....	10
5.5.12 Durability of cable marking.....	10
5.5.13 Stress cracking resistance.....	10
5.5.14 Resistance to ozone.....	10

5.5.15 Resistance to flame propagation.....	11
<b>Annex A (informative) ISO conductor sizes, number of strands and strand diameter.....</b>	<b>14</b>
<b>Annex B (informative) Harness and cable colours.....</b>	<b>17</b>
<b>Bibliography.....</b>	<b>18</b>

**iTeh STANDARD PREVIEW**  
**(standards.iteh.ai)**

ISO 19642-6:2019

<https://standards.iteh.ai/catalog/standards/sist/783b2355-2754-48f7-86f4-e0a2158854b1/iso-19642-6-2019>

## Foreword

ISO (the International Organization for Standardization) is a worldwide federation of national standards bodies (ISO member bodies). The work of preparing International Standards is normally carried out through ISO technical committees. Each member body interested in a subject for which a technical committee has been established has the right to be represented on that committee. International organizations, governmental and non-governmental, in liaison with ISO, also take part in the work. ISO collaborates closely with the International Electrotechnical Commission (IEC) on all matters of electrotechnical standardization.

The procedures used to develop this document and those intended for its further maintenance are described in the ISO/IEC Directives, Part 1. In particular, the different approval criteria needed for the different types of ISO documents should be noted. This document was drafted in accordance with the editorial rules of the ISO/IEC Directives, Part 2 (see [www.iso.org/directives](http://www.iso.org/directives)).

Attention is drawn to the possibility that some of the elements of this document may be the subject of patent rights. ISO shall not be held responsible for identifying any or all such patent rights. Details of any patent rights identified during the development of the document will be in the Introduction and/or on the ISO list of patent declarations received (see [www.iso.org/patents](http://www.iso.org/patents)).

Any trade name used in this document is information given for the convenience of users and does not constitute an endorsement.

For an explanation of the voluntary nature of standards, the meaning of ISO specific terms and expressions related to conformity assessment, as well as information about ISO's adherence to the World Trade Organization (WTO) principles in the Technical Barriers to Trade (TBT), see [www.iso.org/iso/foreword.html](http://www.iso.org/iso/foreword.html).

This document was prepared by Technical Committee ISO/TC 22, *Road vehicles*, Subcommittee SC 32, *Electrical and electronic components and general system aspects*.

A list of all parts in the ISO 19642 series can be found on the ISO website.

Any feedback or questions on this document should be directed to the user's national standards body. A complete listing of these bodies can be found at [www.iso.org/members.html](http://www.iso.org/members.html).

## Introduction

This document was prepared following a joint resolution to improve the general structure of the ISO Automotive Electric Cable standards. This new structure adds more clarity and, by defining a new standard family, opens up the standard for future amendments.

Many other standards currently refer to ISO 6722-1, ISO 6722-2 and ISO 14572. So these standards will stay valid at least until the next scheduled systematic review and will be replaced later on by the ISO 19642 series.

For new Automotive Cable Projects customers and suppliers are advised on using the ISO 19642 series.

## iTeh STANDARD PREVIEW (standards.iteh.ai)

ISO 19642-6:2019

<https://standards.iteh.ai/catalog/standards/sist/783b2355-2754-48f7-86f4-e0a2158854b1/iso-19642-6-2019>

# Road vehicles — Automotive cables —

Part 6:

## Dimensions and requirements for 600 V a.c. or 900 V d.c. and 1 000 V a.c. or 1 500 V d.c. single core aluminium conductor cables

**WARNING** — The use of this document can involve hazardous materials, operations and equipment. This document does not purport to address all of the safety concerns, if any, associated with its use. It is the responsibility of the user of this document to establish appropriate safety practices and determine the applicability of regulatory limitations prior to use.

### 1 Scope

This document specifies the dimensions and requirements for single core cables intended for use in general purpose road vehicle applications where the nominal system voltage is 600 V a.c. or 900 V d.c. and 1 000 V a.c. or 1 500 V d.c. It also applies to the individual conductor cores used in multi core cables.

This document specifies requirements for aluminium conductor cables.

### 2 Normative references

The following documents are referred to in the text in such a way that some or all of their content constitutes requirements of this document. For dated references, only the edition cited applies. For undated references, the latest edition of the referenced document (including any amendments) applies.

ISO 6892-1, *Metallic materials — Tensile testing — Part 1: Method of test at room temperature*

ISO 19642-1, *Road vehicles — Automotive cables — Vocabulary and design guidelines*

ISO 19642-2, *Road vehicles — Automotive cables — Test methods*

EN 573-1, *Aluminium and aluminium alloys — Chemical composition and form of wrought products — Part 1: Numerical designation system*

EN 573-3:2013, *Aluminium and aluminium alloys — Chemical composition and form of wrought product — Part 3: Chemical composition and form of products*

EN 1715-2, *Aluminium and aluminium alloy — Drawing stock — Specific requirements for electrical applications*

ASTM B 231, *Standard Specification for Concentric-Lay-Standard Aluminium 1350 Conductors*

### 3 Terms and definitions

For the purposes of this document, the terms and definitions given in ISO 19642-1 apply.

ISO and IEC maintain terminological databases for use in standardization at the following addresses:

- ISO Online browsing platform: available at <https://www.iso.org/obp>
- IEC Electropedia: available at <http://www.electropedia.org/>

## 4 Specifications

### 4.1 General test conditions

The test conditions of ISO 19642-2 shall apply.

The cables shall be submitted to the tests as specified in [Table 3](#).

If suppliers and customers agree upon modifications or changes to the methods and requirements, all the changes and modifications shall be clearly documented.

### 4.2 Safety concerns

The precautions as described in the WARNING at the beginning of this document shall be followed.

### 4.3 Voltage ratings

The cables described in this document are limited to the voltage ratings shown below.

1. 600 V a.c. or 900 V d.c. maximum
2. 1 000 V a.c. or 1 500 V d.c. maximum

NOTE [Annex B](#) contains information regarding colouring for cables identified for the voltage ratings in this document.

**iTeh STANDARD PREVIEW**  
(standards.iteh.ai)

### 4.4 Temperature classes

Temperature classes suitable for aluminium conductor cables are defined in [Table 1](#).

ISO 19642-6:2019  
<https://standards.iteh.ai/catalog/standards/sist/783b2355-2754-48f7-86f4-e0a2158854b1/iso-19642-6-2019>  
**Table 1 — Temperature class rating**

Class	Equivalent class	Temperature °C
A	T1	-40 to 85
B	T2	-40 to 100
C	T3	-40 to 125
D	T4	-40 to 150
E	T5	-40 to 175
F	T6	-40 to 200

### 4.5 Conductor material

The conductors shall consist of annealed or annealed compressed aluminium or aluminium alloy strands. The specifications for the single strand wires of the conductors shall be according to [Table 2](#) and completed by material specifications. Elongation requirements shall be established by agreement between the customer and the supplier. The finished cable shall meet the resistance requirements of [Table 11](#) for all conductors.

The individual strands of the aluminium conductor shall be manufactured per 1 000 series aluminium or other alloys pursuant to EN 573-1. The chemical composition shall follow EN 573-3:2013, Table 1.

NOTE Examples for strands are shown in [Annex A](#).



**Table 2 — Characteristics of individual single strand wire after annealing**

Tensile strength $R_m^{a,b}$ MPa	Reference conductor material	Elongation at break $A_{a,b}$ %	Conductivity $k_{20}$	
			%IACS	Sm/mm <sup>2</sup>
70 - 120	1000 series	≥16	≥61,2	≥35,5
Minimum 90	Other alloys	(Recommended) ≥8 <sup>c,d</sup>	≥57,8 <sup>d</sup>	≥33,5 <sup>d</sup>

<sup>a</sup> The tensile strength and elongation at break shall be determined according to ISO 6892-1 and ASTM B 231.

<sup>b</sup> The tensile strength and elongation at break shall be measured at clamping length of 200 mm.

<sup>c</sup> This is not applicable for compressed conductors. The tensile strength, elongation, and chemical composition characteristics shall be established by agreement between customer and supplier.

<sup>d</sup> Additional aluminium alloys may be used. The conductivity, tensile strength, elongation characteristics and chemical composition shall be established by agreement between customer and supplier.

NOTE 1 See also EN-1715-2.

NOTE 2 %IACS is the Percentage of International Annealed Copper Standard.

#### 4.6 Conductors

The conductors in the finished cable shall meet the cross-sectional area (CSA) and resistance requirements of [Table 11](#).

The maximum diameter of the conductors is standardized and presented in [Table 12](#).

The configuration of the stranded conductor is not standardized.

NOTE 1 Existing stranding configurations for aluminium conductors are presented in [Table A.1](#).

NOTE 2 Preferred stranding configurations for aluminium conductors are presented in [Table A.2](#).

Other stranding configurations may be used for aluminium conductors provided they meet the above requirements and are agreed between the customer and the supplier.

#### 4.7 Insulation thickness

Two different insulation thicknesses are allowed in this document:

1. thick wall insulation;
2. thin wall insulation.

The minimum wall thickness requirements for the different ISO conductor sizes are standardized and specified in [Table 12](#).

The nominal wall thickness is derived from the minimum wall thickness in [Table 12](#) document by the following formulae:

$$w_{\text{nom}} = 1,25 \times w_{\text{min}} \text{ or } w_{\text{nom}} = w_{\text{min}} / 0,8$$

where

$w_{\text{min}}$  is the minimum wall thickness;

$w_{\text{nom}}$  is the nominal wall thickness.

#### 4.8 Cable outside diameter

The cable outside diameter for each ISO conductor size and insulation thickness is standardized and specified in [Table 12](#).

#### 4.9 Representative conductor sizes for testing

When a test is required, all combinations of conductor size, insulation thickness and insulation formulation shall meet the specified requirements. However, if testing of representative conductor sizes is permitted by agreement between the customer and the supplier, compliance for a cable family may be demonstrated by testing examples of large and small conductor sizes only.

#### 4.10 Reference and requirements for the tests according to ISO 19642-2

[Table 3](#) provides a list of all relevant tests in ISO 19642-2:2019 for single core aluminium conductor cables.

**Table 3 — Tests**

Test description	Mandatory			If required <sup>c</sup>	
	In process <sup>a</sup>	Initial certification	Periodic <sup>b</sup>	Initial certification	Periodic <sup>b</sup>
<b>5.1 Dimensional tests</b>					
5.1.2 Cable outside diameter	—	X	X	—	—
5.1.3 Insulation thickness	—	X	X	—	—
5.1.4 Conductor diameter	—	—	—	X	X
5.1.5 Cross sectional area	—	—	—	X	X
5.1.6 In-process cable outside diameter	X	—	—	—	—
<b>5.2 Electrical tests</b>					
5.2.1 Conductor resistance	—	X	X	—	—
5.2.2 Determination of temperature coefficients	—	X	—	—	—
5.2.3 Withstand voltage	—	X	X	—	—
5.2.4 Withstand voltage after environmental testing <sup>d</sup>	—	—	—	—	—
5.2.5 Insulation faults	X	—	—	—	—
5.2.6 Insulation volume resistivity	—	—	—	X	X
<b>5.3 Mechanical tests</b>					
5.3.1 Strip force	—	—	—	X	X
5.3.2 Abrasion <sup>e</sup>					
5.3.2.4 Sandpaper abrasion test	—	X	X	—	—
5.3.2.5 Scrape abrasion test	—	X	X	—	—
<b>Key</b>	<p>X: Test shall be performed according to ISO 19642-2</p> <p>—: Test is not required</p> <p><sup>a</sup> A test made on the entire cable lot during or after manufacture.</p> <p><sup>b</sup> The frequency of periodic testing shall be established by agreement between the customer and the supplier.</p> <p><sup>c</sup> The usage of "If required" tests shall be established by agreement between the customer and the supplier.</p> <p><sup>d</sup> These tests are only used in preparation and after environmental endurance tests.</p> <p><sup>e</sup> Only one of the abrasion tests has to be performed by agreement between the customer and the supplier.</p> <p><sup>f</sup> Compliance for a cable family may be demonstrated by testing examples of large and small conductor sizes only.</p> <p><sup>g</sup> Some fluids are for "Initial certification" and others are "If required".</p>				

Table 3 (continued)

Test description	Mandatory			If required <sup>c</sup>	
	In process <sup>a</sup>	Initial certification	Periodic <sup>b</sup>	Initial certification	Periodic <sup>b</sup>
5.3.3 Breaking force of the finished cable	—	—	—	X	—
5.3.4 Cyclic bending	—	—	—	X	—
5.3.5 Flexibility	—	—	—	X	—
<b>5.4 Environmental tests</b>					
5.4.1 Specimen preparation and winding tests <sup>d</sup>	—	—	—	—	—
5.4.2 Long term heat ageing, 3 000 h at temperature class rating	—	X	—	—	—
5.4.3 Short term heat ageing, 240 h at temperature class rating +25 °C	—	X	X	—	—
5.4.4 Thermal overload, 6 h at temperature class rating +50 °C	—	—	—	X	X
5.4.5 Pressure test at high temperature	—	X	X	—	—
5.4.6 Shrinkage by heat	—	X	X	—	—
5.4.7 Low temperature winding	—	X	X	—	—
5.4.8 Cold impact	—	—	—	X	X
5.4.9 Temperature and humidity cycling <sup>f</sup>	—	—	—	X	—
5.4.10 Resistance to hot water <sup>f</sup>	—	X	—	—	—
5.4.11 Resistance to liquid chemicals <sup>f, g</sup>	—	X	—	X	—
5.4.12 Durability of cable marking <sup>f</sup>	—	—	—	X	X
5.4.13 Stress cracking resistance <sup>f</sup>	—	—	—	X	—
5.4.14 Resistance to ozone <sup>f</sup>	—	—	—	X	—
5.4.15 Resistance to flame propagation	—	X	X	—	—
<b>Key</b>					
X: Test shall be performed according to ISO 19642-2					
—: Test is not required					
<sup>a</sup> A test made on the entire cable lot during or after manufacture.					
<sup>b</sup> The frequency of periodic testing shall be established by agreement between the customer and the supplier.					
<sup>c</sup> The usage of "If required" tests shall be established by agreement between the customer and the supplier.					
<sup>d</sup> These tests are only used in preparation and after environmental endurance tests.					
<sup>e</sup> Only one of the abrasion tests has to be performed by agreement between the customer and the supplier.					
<sup>f</sup> Compliance for a cable family may be demonstrated by testing examples of large and small conductor sizes only.					
<sup>g</sup> Some fluids are for "Initial certification" and others are "If required".					

## 5 Requirements

### 5.1 General

The cables shall be tested per ISO 19642-2 according to their temperature class rating.

The cables shall be tested as specified in [Table 3](#).