
**Aerospace — Rivets, solid, in
corrosion-resisting steel —
Procurement specification**

*Aéronautique et espace — Rivets ordinaires, en acier résistant à la
corrosion — Spécification d'approvisionnement*

iTeh STANDARD PREVIEW
(standards.iteh.ai)

[ISO 12289:2016](https://standards.iteh.ai/catalog/standards/sist/9e6f6ad7-e9af-4b2f-b896-3c0c8999f760/iso-12289-2016)

[https://standards.iteh.ai/catalog/standards/sist/9e6f6ad7-e9af-4b2f-b896-
3c0c8999f760/iso-12289-2016](https://standards.iteh.ai/catalog/standards/sist/9e6f6ad7-e9af-4b2f-b896-3c0c8999f760/iso-12289-2016)



iTeh STANDARD PREVIEW
(standards.iteh.ai)

ISO 12289:2016

<https://standards.iteh.ai/catalog/standards/sist/9e6f6ad7-e9af-4b2f-b896-3c0c8999f760/iso-12289-2016>



COPYRIGHT PROTECTED DOCUMENT

© ISO 2016, Published in Switzerland

All rights reserved. Unless otherwise specified, no part of this publication may be reproduced or utilized otherwise in any form or by any means, electronic or mechanical, including photocopying, or posting on the internet or an intranet, without prior written permission. Permission can be requested from either ISO at the address below or ISO's member body in the country of the requester.

ISO copyright office
Ch. de Blandonnet 8 • CP 401
CH-1214 Vernier, Geneva, Switzerland
Tel. +41 22 749 01 11
Fax +41 22 749 09 47
copyright@iso.org
www.iso.org

Contents

	Page
Foreword	iv
1 Scope	1
2 Normative references	1
3 Terms and definitions	1
4 Quality assurance	3
4.1 General.....	3
4.2 Acceptance inspection and test conditions.....	3
4.3 Use of statistical process control (SPC).....	3
5 Requirements and test methods	4
6 Records and test reports	8
7 Certificate of compliance	8
Bibliography	9

iTeh STANDARD PREVIEW (standards.iteh.ai)

[ISO 12289:2016](https://standards.iteh.ai/catalog/standards/sist/9e6f6ad7-e9af-4b2f-b896-3c0c8999f760/iso-12289-2016)

<https://standards.iteh.ai/catalog/standards/sist/9e6f6ad7-e9af-4b2f-b896-3c0c8999f760/iso-12289-2016>

Foreword

ISO (the International Organization for Standardization) is a worldwide federation of national standards bodies (ISO member bodies). The work of preparing International Standards is normally carried out through ISO technical committees. Each member body interested in a subject for which a technical committee has been established has the right to be represented on that committee. International organizations, governmental and non-governmental, in liaison with ISO, also take part in the work. ISO collaborates closely with the International Electrotechnical Commission (IEC) on all matters of electrotechnical standardization.

The procedures used to develop this document and those intended for its further maintenance are described in the ISO/IEC Directives, Part 1. In particular the different approval criteria needed for the different types of ISO documents should be noted. This document was drafted in accordance with the editorial rules of the ISO/IEC Directives, Part 2 (see www.iso.org/directives).

Attention is drawn to the possibility that some of the elements of this document may be the subject of patent rights. ISO shall not be held responsible for identifying any or all such patent rights. Details of any patent rights identified during the development of the document will be in the Introduction and/or on the ISO list of patent declarations received (see www.iso.org/patents).

Any trade name used in this document is information given for the convenience of users and does not constitute an endorsement.

For an explanation on the meaning of ISO specific terms and expressions related to conformity assessment, as well as information about ISO's adherence to the WTO principles in the Technical Barriers to Trade (TBT) see the following URL: [Foreword - Supplementary information](#).

The committee responsible for this document is ISO/TC 20, *Aircraft and space vehicles*, Subcommittee SC 4, *Aerospace fastener systems*.

This second edition cancels and replaces the first edition (ISO 12289:2003), of which it constitutes a minor revision.

Aerospace — Rivets, solid, in corrosion-resisting steel — Procurement specification

1 Scope

This International Standard specifies the characteristics and quality assurance requirements for solid rivets made in corrosion-resisting steel for aerospace construction.

It is applicable whenever it is referenced in a definition document.

2 Normative references

The following documents, in whole or in part, are normatively referenced in this document and are indispensable for its application. For dated references, only the edition cited applies. For undated references, the latest edition of the referenced document (including any amendments) applies.

ISO 2859-1, *Sampling procedures for inspection by attributes — Part 1: Sampling schemes indexed by acceptance quality limit (AQL) for lot-by-lot inspection*

ISO 7870-1, *Control charts — Part 1: General guidelines*

ISO 7870-2, *Control charts — Part 2: Shewhart control charts*

ISO 7870-3, *Control charts — Part 3: Acceptance control charts*

ISO 17057, *Aerospace — Rivets, solid — Test method*

ASTM E112¹⁾, *Standard test methods for determining average grain size*

3 Terms and definitions

For the purposes of this document, the following terms and definitions apply.

3.1

batch

quantity of finished products, manufactured using the same processes, from a single material cast (single heat of alloy) having the same *definition document* (3.4) number, diameter and length code, heat treated together to the same specified condition and produced as one continuous run

3.2

rivet wire sample

length of wire, sampled at one end of the coil used for the manufacture of rivets of the *batch* (3.1)

Note 1 to entry: The rivet wire samples should undergo the same heat treatments as the rivets of the batch, at the same time.

3.3

rivet sample

rivet sampled at random from the *batch* (3.1)

1) Published by the American Society for Testing and Materials (ASTM), 1916, Race street, Philadelphia, PA 19103, USA.

3.4

definition document

document specifying directly or indirectly all the requirements for products

Note 1 to entry: The definition document may be an International Standard, an in-house standard or a drawing.

3.5

crack

rupture in the material, which can extend in any direction and which can be intercrystalline or transcrystalline in character

3.6

seam

longitudinal open surface defect

3.7

lap

surface defect caused by folding over metal fins or sharp corners and then forming them into the surface

3.8

cold shut

doubling over of metal which can occur during the cold heading operation

3.9

blistering

defect in the metal on or near the surface, resulting from expansion of gas in a sub-surface zone

3.10

pit

small, sharp cavity in a metal surface caused by non-uniform electrodeposition or by corrosion

3.11

critical defect

defect that, according to judgement and experience, is likely to result in hazardous or unsafe conditions for individuals using, maintaining, or depending upon the considered product, or that is likely to prevent performance of the function of a major end item

ITEH STANDARD PREVIEW
(standards.iteh.ai)
ISO 12289:2016
<https://standards.iteh.ai/catalog/standards/sist/9e6f6ad7-e9af-4b2f-b896-3c0c8999f760/iso-12289-2016>

3.12

major defect

defect, other than critical, that is likely to result in a failure or to reduce materially the usability of the considered product for its intended purpose

3.13

minor defect

defect that is not likely to reduce materially the usability of the considered product for its intended purpose, or that is a departure from established specifications having little bearing on the effective use or operation of this product

3.14

sampling plan

plan according to which one or more samples are taken in order to obtain information and to reach a decision, if possible

3.15

acceptable quality limit

AQL

maximum percent defective (or the maximum number of defects per hundred units) that, for purposes of sampling inspection, can be considered satisfactory as a process average

Note 1 to entry: Variant: quality level, which in a *sampling plan* (3.14), corresponds to a specified but relatively high probability of acceptance.

4 Quality assurance

4.1 General

The manufacturer shall be capable of continuous production of solid rivets complying with the quality requirements specified in this International Standard. It is recommended that the manufacturer be certified to a recognized quality management system. The certification authority may be the prime contractor.

The purpose of acceptance inspection and tests of a solid rivet is to check, as simply as possible, using a method which is inexpensive but the most representative of the actual conditions of use, with the uncertainty inherent in statistical sampling, that the solid rivets satisfy the requirements of this International Standard.

Acceptance inspections and tests shall be carried out by the manufacturer, or under his responsibility.

4.2 Acceptance inspection and test conditions

Acceptance inspections and tests (requirements, methods, and numbers of solid rivets) are specified in [Table 1](#). They shall be carried out on each batch. Solid rivets shall be selected from the batch to be tested by simple random sampling.

Each solid rivet may be submitted to several inspections or tests, provided that none of characteristics to be verified has been previously altered during any of these inspections or tests.

The solid rivets to be subjected to destructive inspections or tests may be those on which non-destructive inspections or tests have been carried out.

A batch declared unacceptable after the acceptance inspection shall be resubmitted for acceptance only after all the defective units have been removed and/or defects have been corrected.

In this case, the attribute(s) which caused the rejection shall be verified using a sample of twice the normal size with the same acceptable limit.

If the reason for rejection results from the method, the test apparatus or from faulty heat treatment which can be rectified in a satisfactory manner, the tests may be repeated after elimination of the cause, provided that any surface treatment be removed prior to heat treatment, without being detrimental to rivet final use. A note to this effect shall be added to the corresponding inspection documents.

Unless otherwise specified, the test temperature shall be the ambient temperature.

4.3 Use of statistical process control (SPC)

When a characteristic is obtained by a controlled statistical process, the manufacturer has the possibility, in order to declare conformity of the characteristic, of refraining from making the final systematic sampling provided for in this International Standard, if he is capable of **formally justifying** this choice by using ISO/TR 13425 and the standards quoted in it as a basis.

This justification will include the following phases:

- analysis of the product's key characteristics;
- analysis of the risks for each implemented process;
- determination of the parameters and/or characteristics to be respected under SPC;
- determination of the capabilities of each process;
- drawing up an inspection plan and integration in the manufacturing process;
- drawing up of routes and control charts (ISO 7870-1, ISO 7870-2, and ISO 7870-3);

- use of control charts for data consolidation;
- determination of the audits to be run and the control to be carried out to ensure reliability of the device.

To be usable in production, this process shall be or should be validated beforehand by the qualifying body, either during the qualification phase or a posteriori according to the case, by analysing the justificatory file and the results of the qualification inspections such as provided for in [Clause 5](#).

5 Requirements and test methods

See [Table 1](#).

Table 1 — Requirements and test methods

Number	Characteristic	Requirement	Inspection and test method	Classification of defects and sampling
5.1	Material	In accordance with the product standard or definition document	See material standard.	
5.2	Dimensions	In accordance with the product standard or definition document	Usual instruments In case of dispute, the projection method at a magnification of ×25 for diameters ≤ 6 mm and ×10 for diameters > 6 mm, shall be used as the reference method. Checks shall be made at three equidistant points around the rivet.	Table 2
5.3	Manufacturing			
5.3.1	Heat treatment	Rivet wire samples shall undergo the same heat treatments as the rivets of the batch, at the same time. As specified in the material standard or definition document.		
5.3.2	Workmanship	No cracks, blistering or burrs	Visual examination with or without magnification. The magnification shall be limited to ×6.	Table 2
		Localized, non-continuous seams, laps, cold shuts, tool marks and pits having a maximum depth of 0,07 mm are permissible.	Defect depth shall be measured perpendicular to a line tangent with the surface.	
5.3.3	Surface treatment	Treatment in accordance with the product standard or definition document	See applicable surface treatment standard.	
5.4	Mechanical properties			
5.4.1	Double shear strength	See Table 3 .	ISO 17057	Table 4
5.5	Metallurgical properties			

Table 1 (continued)

Number	Characteristic	Requirement	Inspection and test method	Classification of defects and sampling
5.5.1	Grain size	Grain size shall be equal to or finer than four in accordance with ASTM E112.	Longitudinal cutting through the shank, polishing and etching using the appropriate reagents and then macroscopic examination	One test per heat of material per diameter
5.6	Product identification marking	In accordance with the product standard or definition document	Visual examination	Table 2
5.7	Delivery			
5.7.1	Packaging	<p>The packaging shall</p> <ul style="list-style-type: none"> — prevent any damage or corrosion occurring during handling, transport and storage, — only contain rivets from the same batch, the number of which is left to the manufacturer's discretion; however, the maximum mass is 25 kg, and — contain a copy of the manufacturer's delivery note relating to the batch. Furthermore, this note may be sent separately upon request. <p>Any particular or additional packaging requirements shall be specified with the order.</p>	Visual examination	
5.7.2	Labelling	<p>Durable labels, secured to the packaging, bearing the following information:</p> <ul style="list-style-type: none"> — designation; — quantity (mass or number); — manufacturer's name; — batch number. 	Visual examination	