INTERNATIONAL STANDARD

First edition 2018-05

Non-destructive testing — Acoustic emission testing — Steel structures of overhead travelling cranes and portal bridge cranes

Essais non destructifs — Essais d'émission acoustique — Structures en acier des ponts roulants et des portiques

iTeh STANDARD PREVIEW (standards.iteh.ai)

<u>ISO 19835:2018</u> https://standards.iteh.ai/catalog/standards/sist/cf24fde3-eb43-481a-813d-7016991a032c/iso-19835-2018



Reference number ISO 19835:2018(E)

iTeh STANDARD PREVIEW (standards.iteh.ai)

<u>ISO 19835:2018</u> https://standards.iteh.ai/catalog/standards/sist/cf24fde3-eb43-481a-813d-7016991a032c/iso-19835-2018



COPYRIGHT PROTECTED DOCUMENT

© ISO 2018

All rights reserved. Unless otherwise specified, or required in the context of its implementation, no part of this publication may be reproduced or utilized otherwise in any form or by any means, electronic or mechanical, including photocopying, or posting on the internet or an intranet, without prior written permission. Permission can be requested from either ISO at the address below or ISO's member body in the country of the requester.

ISO copyright office CP 401 • Ch. de Blandonnet 8 CH-1214 Vernier, Geneva Phone: +41 22 749 01 11 Fax: +41 22 749 09 47 Email: copyright@iso.org Website: www.iso.org

Published in Switzerland

Contents

Page

Foreword				
1	Scope			
2	Norma	ormative references		
3	Terms	Ferms and definitions		
4	Genera	al principles	2	
5		ualification of personnel		
6	Equipment			
		AE testing system		
		AE sensors		
	6.3	Signal cables		
	6.4	Couplant		
	6.5	Preamplifiers		
	6.6	Power-signal cables		
	6.7	Filters		
	6.8	AE instrument		
	6.9	Maintenance and verification of test equipment		
7	On-site operation			
7	Un-site operation			
	7.1	Preparation of documentation 7.1.1 Preliminary information RD PREVIEW		
		7.1.1 Prehminary information		
		7.1.2 Site investigation		
		7.1.3 Preparation of testing procedure and record sheets		
		 7.1.4 Sensor array 7.1.5 Loading procedures 108252018 		
	7.2	OF 1100 19033.2010	0	
	7.2	Mounting of sensoreh ai/catalog/standards/sist/cf24fde3-eb43-481a-813d-	0	
	7.5	Settings of the AE instrumento32e/iso-19835-2018 7.3.1 General requirements		
		1		
		7.3.2 Simulating of AE sources7.3.3 Sensitivity setting		
		7.3.5 Sensitivity setting		
		7.3.5 Calibration of the positioning system7.3.6 Determination of background noise		
	7.4	Performing the test		
	7.4	7.4.1 Loading procedure		
		7.4.1 Loading procedure 7.4.2 Noise during testing		
		7.4.3 Data acquisition and observations during testing		
		7.4.4 Data processing		
8	Intern	pretation and evaluation of test results		
9	_	tance criteria		
) 10	-	nentation		
10		General		
	10.1 10.2 10.3	Written testing procedure		
		Test records		
		Test report		
_				
Annex A (informative) Guidelines for sensor placement				
	Annex B (informative) Evaluation of test results			
Biblio	Bibliography 1			

Foreword

ISO (the International Organization for Standardization) is a worldwide federation of national standards bodies (ISO member bodies). The work of preparing International Standards is normally carried out through ISO technical committees. Each member body interested in a subject for which a technical committee has been established has the right to be represented on that committee. International organizations, governmental and non-governmental, in liaison with ISO, also take part in the work. ISO collaborates closely with the International Electrotechnical Commission (IEC) on all matters of electrotechnical standardization.

The procedures used to develop this document and those intended for its further maintenance are described in the ISO/IEC Directives, Part 1. In particular the different approval criteria needed for the different types of ISO documents should be noted. This document was drafted in accordance with the editorial rules of the ISO/IEC Directives, Part 2 (see www.iso.org/directives).

Attention is drawn to the possibility that some of the elements of this document may be the subject of patent rights. ISO shall not be held responsible for identifying any or all such patent rights. Details of any patent rights identified during the development of the document will be in the Introduction and/or on the ISO list of patent declarations received (see www.iso.org/patents).

Any trade name used in this document is information given for the convenience of users and does not constitute an endorsement.

For an explanation on the voluntary nature of standards, the meaning of ISO specific terms and expressions related to conformity assessment, as well as information about ISO's adherence to the World Trade Organization (WTO) principles in the Technical Barriers to Trade (TBT) see the following URL: www.iso.org/iso/foreword.html. (standards.iteh.ai)

This document was prepared by Technical Committee ISO/TC 135, *Non-destructive testing*, Subcommittee SC 9, *Acoustic emission testing*. https://standards.iteh.ai/catalog/standards/sist/cf24fde3-eb43-481a-813d-

7016991a032c/iso-19835-2018

Non-destructive testing — Acoustic emission testing — Steel structures of overhead travelling cranes and portal bridge cranes

1 Scope

This document describes the acoustic emission (AE) testing technique used to perform structural integrity evaluation on steel structures of overhead travelling cranes and portal bridge cranes.

This document applies to the testing of steel structures of in-service overhead travelling cranes and portal bridge cranes. Testing of other kinds of cranes can refer this document.

This testing method is not intended to be an alone NDT standard method for the evaluation of the structural integrity of overhead travelling cranes and portal bridge cranes. Other NDT methods are used to verify and supplement the AT results.

This document does not establish evaluation criteria.

2 Normative references TANDARD PREVIEW

The following documents are referred to in the text in such a way that some or all of their content constitutes requirements of this document. For dated references, only the edition cited applies. For undated references, the latest edition of the referenced document (including any amendments) applies.

ISO 4310, Cranes — Test code and procedure standards/sist/cf24fde3-eb43-481a-813d-

ISO 12714, Non-destructive testing $\frac{701}{2}$ Acoustic emission inspection — Secondary calibration of acoustic emission sensors

ISO 12716, Non-destructive testing — Acoustic emission inspection — Vocabulary

ISO/TR 13115, Non-destructive testing — Methods for absolute calibration of acoustic emission transducers by the reciprocity technique

3 Terms and definitions

For the purposes of this document, the terms and definitions given in ISO 12716 and the following apply.

ISO and IEC maintain terminological databases for use in standardization at the following addresses:

- ISO Online browsing platform: available at https://www.iso.org/obp
- IEC Electropedia: available at <u>http://www.electropedia.org/</u>

3.1

acoustic emission source AE source

AE source

source point or spatial position in the material where transient elastic waves are generated by the release of energy

3.2

acoustic emission location source AE location source

spatial area comprising one or more clusters associated with an *AE source* (3.1) and encompassing the true physical location of the AE events giving rise to the AE source

Note 1 to entry: Common location methods include zone location, computed location and continuous AE signal location.

3.3

activity

<of acoustic emission source> increasing total number of AE events in *AE location source (3.2)* with loading process or loading time

3.4

intensity

<of acoustic emission source> average elastic energy released by the AE events in the AE location
source (3.2)

Note 1 to entry: Burst AE source intensity related parameters are, e.g. maximum amplitude, energy, signal strength and, to a certain extent, ring down counts. Continuous AE source intensity related parameters are, e.g. root mean square (RMS AE) signal voltage, average rectified signal voltage and average signal level (ASL).

3.5

maximum operating load

maximum operation load is the maximum load of the crane bearing in the last 6 months before the AE testing

(standards.iteh.ai)

4 General principles

<u>ISO 19835:2018</u>

The main purpose of acoustic emission testing (AT) is to detect the acoustic emission source generated in the parent metal of steel structures, weld surface and internally, and locate the acoustic emission source.

The acoustic emission testing shall be done during the loading process, which includes the loading, load holding and unloading. The acoustic emission sensors should be arranged on the surface of steel structure being detected, to receive the signals generated by the active source and transfer it into electric signals. The AE instrument is used to collect, handle, display, record and analyse the signals, and then provides the parameters and location of the acoustic emission source.

5 Qualification of personnel

It is assumed that AE testing is performed by competent personnel. In order to ensure that this is the case, it is recommended that the personnel meet the requirements of ISO 9712 or equivalent.

6 Equipment

6.1 AE testing system

AE testing employs an AE instrument, AE sensors, preamplifiers, and interconnecting cables.

This combination together with some mechanical equipment holding the sensors forms the AE testing system.

All essential parts of the system shall be defined in a written procedure agreed at the time of enquiry or order (see 10.2).

6.2 AE sensors

It is recommended to use sensors in the frequency range between 100 kHz and 400 kHz.

The minimum sensitivity shall be equivalent or greater than 60 dB referred to 1 V/($m\cdot s-1$) in surface wave sound field calibration, or in longitudinal wave calibration.

When sensors with other response frequencies are used, they shall provide enough sensitivity within its frequency band.

Sensors shall be shielded against radio frequency and electromagnetic noise interference by proper shielding practice or by differential element design, or both. The metallic case of each AE sensor shall be electrically isolated from a metallic test object.

The AE sensors shall be stable over the response frequency and temperature range of use, and shall not exhibit sensitivity changes greater than 3 dB over this range.

AE sensors mounted on the surface of a steel structure shall be insulation from each other.

For sufficient sensitivity, a pencil lead break of 0,5 mm diameter, hardness 2H, in 50 mm distance from the sensor, shall generate an amplitude of at least 95 d B_{AE} .

The calibration of the sensors shall be performed according to ISO 12714 or with ISO/TR 13115.

6.3 Signal cables

The signal cables connecting sensors and preamplifiers shall be shielded against electromagnetic interference. Its length shall not exceed 1 m, unless the length-depending signal loss is considered and acceptable.

This requirement may be omitted where the preamplifier is mounted in the shielded sensor housing.

https://standards.iteh.ai/catalog/standards/sist/cf24fde3-eb43-481a-813d-7016991a032c/iso-19835-2018

6.4 Couplant

The used couplant should keep good sound transfer effect during testing.

6.5 Preamplifiers

The preamplifiers may be separate or may be mounted in the sensor housing.

The RMS voltage of preamplifiers circuit noise shall be less than 7 μ V.

The preamplifiers shall be stable over the response frequency and temperature range of use, and shall not exhibit sensitivity changes greater than 3 dB over this range.

The preamplifiers response frequency shall match with that of the sensors, and the gain of the preamplifiers, usually 40 dB or 34 dB, shall not cause saturation of the measurement chain up to a 100 dB_{AE} signal amplitude.

If the preamplifiers are of differential design, a minimum of 40 dB of common-mode rejection shall be provided.

6.6 Power-signal cables

The cable providing power to the preamplifier and conducting the amplified signal to the main processor shall be shielded against electromagnetic noise. Signal loss shall be no more than 1 dB per 30 m of cable length. 150 m is the recommended maximum cable length to avoid excessive signal attenuation.

The cables providing power to the preamplifier and conducting the amplified signal to the main processor shall be shielded against electromagnetic noise.

The signal loss of cables depends on type of cable, frequency and length. With cable length above 10 m, the resulting attenuation and the voltage drop off the DC-supply shall be evaluated and considered in the data analysis. The signal loss shall be no more than 1 dB per 30 m of cable length.

To avoid excessive signal attenuation, the recommended maximum cable length is 150 m.

6.7 Filters

The response frequency of filters in the preamplifiers and the AE instrument shall match with that of the AE sensors.

6.8 AE instrument

The AE instrument shall have enough AE channels to cover the testing area. For each channel, the instrument shall provide as a minimum the following features: displaying and recording of arrival time, threshold, amplitude, count, energy, rise time, duration time, and hits. It is preferred that the instrument is able to receive and record also external electric signals, such as pressure, temperature.

The individual sampling frequency of each channel shall be not less than 10 times the sensors' centre response frequency.

The measurement inaccuracy for threshold above 40 dB_{AE} shall be better than ±1 dB.

The measurement inaccuracy for counts shall be better than ± 5 %.

The instrument shall be capable to process, store and display at least 20 hits per second at all channels. The delay and display from the arrival of the AE hits shall not exceed 10 seconds. An alarm shall occur if the hit rate exceeds the capability of the instrument. A warning shall occur when the storage space runs short.

The measurement inaccuracy for peak amplitudes above 40 dB_{AE3}shall be better than ±1 dB. Usable dynamic range shall be a minimum of 65 dB_{016991a032c/iso-19835-2018}

The measurement inaccuracy for energy above 40 dB_{AE} shall be better than ± 5 %.

If delta-t source location is used, the resolution of rise time, duration and arrival time for each channel shall be better than $0,25 \ \mu$ s. The error of arrival time between each channel shall be better than $\pm 3 \ \mu$ s.

The measurement inaccuracy for the external parametric inputs shall be better than 2 % of the full range.

During data acquisition, AE software shall be capable to display the following diagrams: any AE parameter versus time or load, one AE parameter versus another AE parameter, linear and planar locations. The real-time update time for all diagrams shall be not more than 5 s.

The AE analysis software shall provide functions to replay and to analyse the recorded AE testing data.

6.9 Maintenance and verification of test equipment

The performance of the testing system shall be verified at specified intervals in conformity with the methods provided by the manufacturer of the AE instrument, or refer to EN 13477-1 and EN 13477-2.

7 On-site operation

7.1 Preparation of documentation

7.1.1 Preliminary information

Prior to the definition of the testing, some or all of the following information is necessary:

- the purpose of the test;
- details of the crane to be tested;
- the physical location of the area where the test shall be performed;
- the requirements for surface preparation;
- the sensitivity of the test;
- the method used to verify the sensitivity;
- the acceptance criteria, if specified;
- other requirements in relation to the test report;
- details of qualification of personnel.

The following documents for the tested crane are required as a minimum before performing an AE test:

- a) manufacturing documents of the crane to be tested, e.g. product certification, quality qualification document, as-built drawing;
- b) operation recording documents of the crane e.g. operating conditions and parameters, loading fluctuations, abnormal situation in operation; on the crane of the crane e.g. operating conditions and parameters, loading fluctuations, abnormal situation in operation; on the crane e.g. operating conditions and parameters, loading fluctuations, abnormal situation in operation; operation
- c) previous inspection and testing report;
- d) other documents, e.g. drawing and record showing repairs or modifications.

7.1.2 Site investigation

Prior to testing, it is necessary to carry out a site investigation to find all interference factors, such as friction of scaffold, electromagnetic interference, vibration. The interference of these factors shall be avoided during on-site testing.

7.1.3 Preparation of testing procedure and record sheets

The testing procedure and record sheets shall be prepared in accordance with the general testing procedure (see 10.2), crane and site conditions. The instrument, applicable sensors, testing place and surface conditions of the crane need to be specified.

7.1.4 Sensor array

A sufficient number of sensors shall be mounted on the steel structure of the crane to enable AE signal detection and source location, according to the dimension of the structure and the purpose of the testing. The allowed maximum sensor spacing can be determined by based on measured attenuation curve of AE amplitude. This can refer to EN 14584 and EN 15495. The spacing between sensors shall be the same as far as possible. All the sensors shall be numbered and indicated in the schematic diagram of the structure. <u>Annex A</u> provides guidelines for sensor placement for some structures of cranes.

7.1.5 Loading procedure

A loading procedure should be established according to the purpose of AE testing and the real condition of the crane.

The communication of the AE operator with the loading operator shall be included in the test procedure.

7.2 Mounting of sensor

The mounting of sensors shall meet with the following requirements:

- a) The sensors shall be installed according to the specified sensor array. The sensors shall keep a distance to welding attachment such as supporting steel plate during the whole testing of the structure. For local testing, the testing area shall be in the centre of the sensor array.
- b) The place for the mounting of a sensor on the structure shall be smooth and showing the metallic luster. The coating can be kept when it is smooth and compacted and measured attenuation is acceptable.
- c) Efficient couplants such as vacuum grease, vaseline, are recommended.
- d) Firmly fixing of the sensors with the structure shall be performed by a magnetic holding device, by an adhesive tape or other stuff, keeping the insulation.

7.3 Settings of the AE instrument iTeh STANDARD PREVIEW

7.3.1 General requirements

(standards.iteh.ai)

Connects the sensors and preamplifiers with the main processor by cables, turn on the AE instrument and wait until the equipment is in proper working condition. Roughly set the instrument and then debug the AE system following/steps:7.3:2.to/7.3:6.ystandards/sist/cf24fde3-eb43-481a-813d-

7016991a032c/iso-19835-2018

7.3.2 Simulating of AE sources

Simulated AE sources are used to determine the sensitivity of each channel and to calibrate the localisation system of AE sources.

The simulated AE sources should be capable of producing a transient elastic wave having an amplitude representative of the AE signals.

The simulated AE source may be a breaking pencil lead or an electronically induced event or equivalent.

When using the pencil lead break technique, the simulated AE signals shall be generated by breaking 2H pencil leads (0,3 mm or 0,5 mm diameter) against the component surface at the prescribed points.

The pencil leads shall be broken at an angle of approximate 30° to the surface using about 2,5 mm pencil lead extension.

The detected peak amplitude of the simulated event should be at a fixed distance near the sensor, typically $100 \text{ mm} \pm 5 \text{ mm}$, and the responsive value shall be the average of more than 3 times.

7.3.3 Sensitivity setting

The sensitivity setting for all channels shall be done before and after the testing. The average peak amplitude of any sensor shall be within ± 4 dB of the average of all sensors.

7.3.4 Determination of attenuation curve

The attenuation of acoustic emission signals for different steel structures shall be determined.

This is necessary for determining the sensor spacing for effective detection of AE sources and recalculation of signal amplitude to source location.

If attenuation data from the same testing condition is already available, it is not necessary to determine the attenuation again, but the attenuation data shall be indicated in the record and test report.

7.3.5 Calibration of the positioning system

When using the computed localization, the simulated AE signal shall be received and be located solely within the sensor array on the component.

The error of positioning shall be no more than ± 5 % of the sensors spacing.

When using the zone location, the simulated AE signal shall be received by at least one sensor in that area.

7.3.6 Determination of background noise

The background noise of the testing environment shall be tested for at least 5 minutes before the testing by lowering the threshold voltage.

The testing threshold of each channel shall be higher than the background noise by at least 6 dB.

If the background noise is close to or larger than the AE signals caused by the active discontinuities in the steel structure, the background noise shall be eliminated, or it is not suitable to perform the AE testing.

iTeh STANDARD PREVIEW

(standards.iteh.ai)

7.4 Performing the test

7.4.1 Loading procedure

ISO 19835:2018

The loading procedure shall be performed in accordance with 1SO 4310, and the recommend testing load shall be 1,1 times to 1,25 times of the rated lifting capacity or the maximum operating load, given by the owner of the crane based on the operating condition.

The testing load should be lifted up in the centre of the beam to 100 mm to 200 mm above the ground, and holding for at least 10 minutes.

The test shall be repeated two times. The load in the second test shall not exceed that of the first test, and the recommend load shall be 97 % of the first load.

7.4.2 Noise during testing

Attention is to be paid to the following factors that can affect the testing results:

- a) external mechanical vibration;
- b) mechanical friction;
- c) electromagnetic interference;
- d) weather conditions, such as interference from wind, rain, hail.

The testing shall be suspended when there is strong noise, and it can be continued when this strong noise has been excluded.

7.4.3 Data acquisition and observations during testing

The data acquisition shall include the parameters given in <u>6.8</u>. The sequence of signals in each channel is required when using zone location.