
**Paints and varnishes — Evaluation
of degradation of coatings —
Designation of quantity and size of
defects, and of intensity of uniform
changes in appearance —**

**Part 3:
Assessment of degree of rusting**

iTeh STANDARD PREVIEW
(standards.iteh.ai)

*Peintures et vernis — Évaluation de la dégradation des revêtements
— Désignation de la quantité et de la dimension des défauts, et de
l'intensité des changements uniformes d'aspect —
Partie 3: Évaluation du degré d'enrouillement*



iTeh STANDARD PREVIEW
(standards.iteh.ai)

ISO 4628-3:2016

<https://standards.iteh.ai/catalog/standards/sist/d7c3aa71-8e7e-49fa-bbbd-a607b78d8c2f/iso-4628-3-2016>



COPYRIGHT PROTECTED DOCUMENT

© ISO 2016, Published in Switzerland

All rights reserved. Unless otherwise specified, no part of this publication may be reproduced or utilized otherwise in any form or by any means, electronic or mechanical, including photocopying, or posting on the internet or an intranet, without prior written permission. Permission can be requested from either ISO at the address below or ISO's member body in the country of the requester.

ISO copyright office
Ch. de Blandonnet 8 • CP 401
CH-1214 Vernier, Geneva, Switzerland
Tel. +41 22 749 01 11
Fax +41 22 749 09 47
copyright@iso.org
www.iso.org

Contents		Page
Foreword		iv
1 Scope		1
2 Normative references		1
3 Terms and definitions		1
4 Assessment		2
5 Expression of results		2
6 Test report		2
Annex A (normative) Calibration images		9
Annex B (informative) Correlation between the ISO rating system and other systems		14
Bibliography		15

iTeh STANDARD PREVIEW
(standards.iteh.ai)

ISO 4628-3:2016

<https://standards.iteh.ai/catalog/standards/sist/d7c3aa71-8e7e-49fa-bbbd-a607b78d8c2f/iso-4628-3-2016>

Foreword

ISO (the International Organization for Standardization) is a worldwide federation of national standards bodies (ISO member bodies). The work of preparing International Standards is normally carried out through ISO technical committees. Each member body interested in a subject for which a technical committee has been established has the right to be represented on that committee. International organizations, governmental and non-governmental, in liaison with ISO, also take part in the work. ISO collaborates closely with the International Electrotechnical Commission (IEC) on all matters of electrotechnical standardization.

The procedures used to develop this document and those intended for its further maintenance are described in the ISO/IEC Directives, Part 1. In particular the different approval criteria needed for the different types of ISO documents should be noted. This document was drafted in accordance with the editorial rules of the ISO/IEC Directives, Part 2 (see www.iso.org/directives).

Attention is drawn to the possibility that some of the elements of this document may be the subject of patent rights. ISO shall not be held responsible for identifying any or all such patent rights. Details of any patent rights identified during the development of the document will be in the Introduction and/or on the ISO list of patent declarations received (see www.iso.org/patents).

Any trade name used in this document is information given for the convenience of users and does not constitute an endorsement.

For an explanation on the meaning of ISO specific terms and expressions related to conformity assessment, as well as information about ISO's adherence to the WTO principles in the Technical Barriers to Trade (TBT) see the following URL: [Foreword - Supplementary information](#)

The committee responsible for this document is ISO/TC 35, *Paints and varnishes*, Subcommittee SC 9, *General test methods for paints and varnishes*.

This third edition cancels and replaces the second edition (ISO 4628-3:2003), which has been technically revised with the following changes:

- a) a normative reference to ISO 13076 for illumination for the assessment has been added;
- b) a note on the rusted area of the degree of rusting Ri 5 has been added.

ISO 4628 consists of the following parts, under the general title *Paints and varnishes — Evaluation of degradation of coatings — Designation of quantity and size of defects, and of intensity of uniform changes in appearance*:

- Part 1: General introduction and designation system
- Part 2: Assessment of degree of blistering
- Part 3: Assessment of degree of rusting
- Part 4: Assessment of degree of cracking
- Part 5: Assessment of degree of flaking
- Part 6: Assessment of degree of chalking by tape method
- Part 7: Assessment of degree of chalking by velvet method
- Part 8: Assessment of degree of delamination and corrosion around a scribe or other artificial defect
- Part 10: Assessment of degree of filiform corrosion

Paints and varnishes — Evaluation of degradation of coatings — Designation of quantity and size of defects, and of intensity of uniform changes in appearance —

Part 3: Assessment of degree of rusting

1 Scope

This part of ISO 4628 specifies a method for assessing the degree of rusting of coatings by comparison with pictorial standards.

The pictorial standards provided in this part of ISO 4628 show coated steel surfaces which have deteriorated to different degrees by a combination of rust broken through the coating and visible underrust.

NOTE 1 The pictorial standards have been selected from the “European rust scale” published by the European Confederation of Paint, Printing Ink and Artists’ Colours Manufacturers’ Associations (CEPE), Brussels. The correlation between the ISO scale and the “European rust scale” is given in [Annex B, Table B.1](#).

NOTE 2 The correlation between the ISO scale and the rating system of ASTM D 610 is given in [Annex B, Table B.2](#).

NOTE 3 The rust formation on uncoated steel surfaces is designated in accordance with ISO 8501-1 (rust grades A, B, C, and D).

ISO 4628-1 defines the system used for designating the quantity and size of defects and the intensity of changes in appearance of coatings and outlines the general principles of the system. This system is intended to be used, in particular, for defects caused by ageing and weathering, and for uniform changes such as colour changes, for example yellowing.

2 Normative references

The following documents, in whole or in part, are normatively referenced in this document and are indispensable for its application. For dated references, only the edition cited applies. For undated references, the latest edition of the referenced document (including any amendments) applies.

ISO 4628-1:2016, *Paints and varnishes — Evaluation of degradation of coatings — Designation of quantity and size of defects, and of intensity of uniform changes in appearance — Part 1: General introduction and designation system*

ISO 13076, *Paints and varnishes — Lighting and procedure for visual assessments of coatings*

3 Terms and definitions

For the purposes of this document, the following terms and definitions apply.

3.1

degree of rusting

R_i

rating characterizing the degree of rust formation (rust broken through and visible underrust) on a coating

4 Assessment

Assess the degree of rusting (Ri) on a coating by means of the pictorial standards given in [Figure 1](#) to [Figure 5](#). The approximate areas rusted (rust broken through plus visible underrust) shown on these standards are as indicated in [Table 1](#).

Procedures for assessing invisible underrust, if required, shall be agreed between the interested parties.

Where different degrees of rusting occur in different parts of the area being assessed, indicate these degrees of rusting together with the part where each occurs.

Carry out the assessment under good illumination, as specified in ISO 13076.

If the average size of the rust spots on the test area differs considerably from those shown in the pictorial standards, an indication of their size may be given by reference to ISO 4628-1:2015, Table 2.

NOTE The pictorial standards are basically intended for assessing the degree of rusting of coated steel. They can be used for designating the degree of corrosion of coated non-ferrous metals if the form of breakdown is comparable with that shown in the standards.

Table 1 — Degree of rusting and rusted area

Degree of rusting	Rusted area %
Ri 0	0
Ri 1	0,05
Ri 2	0,5
Ri 3	1
Ri 4	8
Ri 5	40 to 50 ^a

^a When measuring the rusted area in [Figure A.5](#), it is only about 35 %. If rust is assessed visually using [Figure 5](#), the impression of rusted area is 40 % to 50 %. One reason might be that partly delaminated rust flakes are not distinguished from other rusted areas. But this is negligible because Ri 5 normally is outside any specification.

If the assessment is to be done by an optical imaging system, calibrate the system using the images given in [Annex A](#).

5 Expression of results

Express the degree of rusting as Ri class as shown in [Figure 1](#) to [Figure 5](#).

If applicable, indicate the different degrees of rusting obtained, together with the parts of the test area concerned.

If applicable, indicate the degree of rusting Ri together with the numerical rating of the size of the rust spots.

For example, if the rusted area corresponds to [Figure 3](#), Ri 3, and the sizes of the individual rust spots are between 0,5 mm and 5 mm, report the result as

— rusting; degree of rusting Ri3 (S4).

6 Test report

The test report shall contain at least the following information:

a) all details necessary to identify the coating examined;

- b) a reference to this part of ISO 4628, i.e. ISO 4628-3;
- c) the type of surface examined, its size and, if appropriate, its location;
- d) result of the assessment in accordance with [Clause 5](#);
- e) an indication of the illumination under which the assessment was carried out;
- f) any unusual features (anomalies) observed during the assessment;
- g) the date of the examination.

iTeh STANDARD PREVIEW
(standards.iteh.ai)

[ISO 4628-3:2016](#)

<https://standards.iteh.ai/catalog/standards/sist/d7c3aa71-8e7e-49fa-bbbd-a607b78d8c2f/iso-4628-3-2016>




Figure 1 — Degree of rusting Ri 1




Figure 2 — Degree of rusting Ri 2




Figure 3 — Degree of rusting Ri 3




Figure 4 — Degree of rusting Ri 4