



Designation: A908 – 03 (Reapproved2008)<sup>e1</sup>

# Standard Specification for Stainless Steel Needle Tubing<sup>1</sup>

This standard is issued under the fixed designation A908; the number immediately following the designation indicates the year of original adoption or, in the case of revision, the year of last revision. A number in parentheses indicates the year of last reapproval. A superscript epsilon ( $\epsilon$ ) indicates an editorial change since the last revision or reapproval.

*This standard has been approved for use by agencies of the Department of Defense.*

<sup>e1</sup> NOTE—The units statement in 1.3 was corrected editorially in October 2008.

## 1. Scope

1.1 This specification covers austenitic, stainless steel, needle tubing in hard-drawn tempers for industrial applications.

1.2 In general, needle tubing describes small-diameter tubing with outside diameters (ODs) in the range of 0.008 to 0.203 in. (0.2 to 5.2 mm) with nominal wall thicknesses in the range of 0.002 to 0.015 in. (0.05 to 0.4 mm). Needle tubing gages are normally 6 through 33.

1.3 The values stated in inch-pound units are to be regarded as standard. The values given in parentheses are mathematical conversions to SI units that are provided for information only and are not considered standard.

## 2. Referenced Documents

2.1 *ASTM Standards*:<sup>2</sup>

A1016/A1016M Specification for General Requirements for Ferritic Alloy Steel, Austenitic Alloy Steel, and Stainless Steel Tubes

## 3. Ordering Information

3.1 Orders for material in accordance with this specification should include the following, as required, to describe the material adequately:

3.1.1 Quantity (feet, metres, or number of lengths),

3.1.2 Gauge or size (outside diameter and minimum wall thickness),

3.1.3 Length (specific or random), and

3.1.4 Test report required (see the section on certification in Specification A1016/A1016M).

<sup>1</sup> This specification is under the jurisdiction of ASTM Committee A01 on Steel, Stainless Steel and Related Alloys and is the direct responsibility of Subcommittee A01.10 on Stainless and Alloy Steel Tubular Products.

Current edition approved Oct. 1, 2008. Published January 2009. Originally approved in 1991. Last previous edition approved in 2003 as A908 – 03. DOI: 10.1520/A0908-03R08E01.

<sup>2</sup> For referenced ASTM standards, visit the ASTM website, www.astm.org, or contact ASTM Customer Service at service@astm.org. For *Annual Book of ASTM Standards* volume information, refer to the standard's Document Summary page on the ASTM website.

## 4. Process

4.1 An electric furnace or other similar primary melting process with or without degassing or refining may be used.

## 5. General Requirements

5.1 Material furnished in accordance with this specification shall conform to the applicable requirements of the current edition of Specification A1016/A1016M, unless otherwise provided herein.

## 6. Manufacture

6.1 Needle tubing shall be made by the seamless or welded and drawn process and shall be furnished in the hard-drawn temper condition.

## 7. Heat Treatment

7.1 Unless otherwise specified by the purchaser, no heat treatment is required.

## 8. Chemical Composition

8.1 Stainless steel, Type 304, UNS S30400, in accordance with Table 1 shall be used.

8.2 *Heat Analysis*—An analysis of each heat of steel shall be made by the manufacturer from samples made during the pour. The chemical composition thus determined shall meet the requirements of Table 1.

8.3 *Product Analysis*—An analysis may be made by the purchaser from finished tubing. The chemical composition thus determined shall meet the requirements of Table 1.

## 9. Mechanical Properties

9.1 *Tensile Requirements*—The tubing shall meet the tensile properties specified in Table 2. Yield strength, elongation, and hardness tests are not required for needle tubing.

9.2 *Number of Tests*—Two tension tests for each 5000 ft of product per heat shall be performed.

## 10. Dimensions

10.1 *Sizes and Tolerances*—Needle tubing sizes and dimensions shall be in accordance with Table 3