



Designation: E755 – 08

Standard Test Method for Dicumyl Peroxide, Assay (Liquid Chromatography)¹

This standard is issued under the fixed designation E755; the number immediately following the designation indicates the year of original adoption or, in the case of revision, the year of last revision. A number in parentheses indicates the year of last reappraisal. A superscript epsilon (ϵ) indicates an editorial change since the last revision or reappraisal.

1. Scope*

1.1 This test method covers the assay of dicumyl peroxide² in commercially available refined grades of dicumyl peroxide. Technical grades can also be assayed, provided that impurities that interfere chromatographically are absent (see **Note 1**). These materials nominally contain approximately 99 and 92 % of dicumyl peroxide, respectively.

NOTE 1—In the assay of technical grade dicumyl peroxide, errors are possible if the product contains an impurity that elutes with the same retention time as the internal standard. A chromatogram obtained under the test conditions minus the internal standard will determine whether an interference situation exists in the assay of a particular technical grade product. If an impurity is noted, and its retention time is slightly different from that of the internal standard, the interference can often be eliminated by the use of a column known to have a high plate count.

1.2 Review the current material safety data sheets (MSDS) for detailed information concerning toxicity, first aid procedures, and safety precautions.

1.3 The values stated in SI units are to be regarded as the standard. No other units of measurement are included in this standard.

1.4 *This standard does not purport to address all of the safety concerns, if any, associated with its use. It is the responsibility of the user of this standard to establish appropriate safety and health practices and determine the applicability of regulatory limitations prior to use.* Specific precautionary statements are given in Section 7.

2. Referenced Documents

2.1 *ASTM Standards*:³

D1193 Specification for Reagent Water

E180 Practice for Determining the Precision of ASTM

¹ This test method is under the jurisdiction of ASTM Committee D16 on Aromatic Hydrocarbons and Related Chemicals and is the direct responsibility of Subcommittee D16.16 on Industrial and Specialty Product Standards.

Current edition approved Dec. 15, 2008. Published January 2009. Originally approved in 1980. Last previous edition approved in 2003 as E755 – 94 (2003). DOI: 10.1520/E0755-08.

² Dicumyl Peroxide; peroxide, bis(1-methyl-1-phenylethyl) C₁₈H₂₂O₂; CAS Registry No. 80-43-3.

³ For referenced ASTM standards, visit the ASTM website, www.astm.org, or contact ASTM Customer Service at service@astm.org. For *Annual Book of ASTM Standards* volume information, refer to the standard's Document Summary page on the ASTM website.

Methods for Analysis and Testing of Industrial and Specialty Chemicals (Withdrawn 2009)⁴

E682 Practice for Liquid Chromatography Terms and Relationships

E685 Practice for Testing Fixed-Wavelength Photometric Detectors Used in Liquid Chromatography

E300 Practice for Sampling Industrial Chemicals

3. Summary of Test Method

3.1 A solution of sample and internal standard in methanol is chromatographed on a reversed-phase ODS column using 85/15 methanol/water as the mobile phase and an ultraviolet (UV) detector at 254 nm. The percent of dicumyl peroxide in the sample is determined by the internal standard technique, using the peak height ratios of standard and sample chromatograms.

4. Significance and Use

4.1 This test method provides a means for determining the percent of dicumyl peroxide in technical and refined grades of this material. This test method is specific for dicumyl peroxide. No interference is encountered from dimethylbenzyl alcohol, acetophenone, or other minor impurities normally associated with commercial dicumyl peroxide.

5. Apparatus

5.1 *Liquid Chromatograph*, equipped with a 254-nm UV detector, an injection valve, and an isocratic solvent delivery system capable of operating to a gage pressure of 3000 psi (21 MPa). The detector should be equipped with an attenuator switch to change the sensitivity range as required.

5.2 *Recorder*, 0 to 10-mV range, or an electronic integrator with printer-plotter, or both.

5.3 *Chromatographic Column*, reversed-phase C-18, 250 by 4.6-mm inside diameter, containing octadecyldimethylsilane chemically bonded to spherical, 5- μ m microparticulate silica.⁵

⁴ The last approved version of this historical standard is referenced on www.astm.org.

⁵ The commercial guard and analytical columns found to be most satisfactory for use with this test method are Zorbax Rx-18, Part Nos. 820764.914 and 880967.9002, respectively, available from Mac Mod, 127 Commons Court, Chadds Ford, PA 19317. This column was selected for its separation characteristics and linear response of the dicumyl peroxide and internal standard.

*A Summary of Changes section appears at the end of this standard

NOTE 2—Commercial HPLC columns vary in physical dimensions, degree of substrate loading, and size and type of support material. Some modification in the operating parameters may be required to achieve optimum separation for these reasons.

5.4 *Guard Column*, reversed-phase C-18, 12.5 by 4.0 mm, with an inline filter.⁵

5.5 *Precision Sample Injection Valve*, with a 10- μ L loop and filler port.

5.6 *Syringe*, 250- μ L capacity.

5.7 *Sample Filter*, consisting of a syringe and 0.2- μ m filter assembly to remove microparticulate matter from the prepared sample solution.⁶

5.8 *Glass Bottles*, 120-mL, with polyethylene-lined screw caps.

6. Reagents

6.1 *Water*—Prepare ASTM Type II reagent water in accordance with Specification **D1193**, or distill deionized water. Filter through a 0.2- μ m, Nylon-66 filter, and store in a glass container. Alternatively, commercial multicartridge systems that produce water meeting or exceeding the requirements of Type II can be used.

6.2 *Methanol*, chromatographic grade, distilled in glass.

6.3 *Methanol-Water Mobile Phase*, 85:15—Mix 8.5 volumes of methanol with 1.5 volumes of water.

6.4 *Di-n-Heptyl Phthalate*, purified.⁷

6.5 *Dicumyl Peroxide, Recrystallized*—Transfer 25.0 g of commercial refined dicumyl peroxide into a 100-mL Erlenmeyer flask. Add 8.0 mL of methanol, and gently warm the solution in a water bath while swirling to effect complete solution. Cool to 0°C in an ice bath. Transfer the contents to a medium-porosity sintered glass crucible and vacuum filter. Allow air to pass through the filter for 10 to 15 min to dry the peroxide. Repeat the crystallization twice using approximately 1 mL of methanol solvent for every 3 g of peroxide. Place the recrystallized dicumyl peroxide in a tightly capped bottle, and store in a refrigerator (see Section 7).

7. Safety Precautions

7.1 Small quantities of solid or molten dicumyl peroxide can be handled safely at temperatures up to 55°C. Dicumyl peroxide should not be heated above 55°C because the rate of peroxide decomposition increases rapidly with increasing temperatures above this point.

7.2 A recirculating water bath or a water bath that has been preheated to the desired temperature and removed from the heat source should be used for warming vessels containing dicumyl peroxide. Electrically heated water baths should not be used since they may cause localized hot spots. Other sources

of heat considered unsafe for warming containers of dicumyl peroxide include ovens, hot plates, open flames, and direct steam.

7.3 Organic peroxides may ignite violently in contact with an open flame or electrical spark. These heat sources must be avoided for this reason.

8. Sampling

8.1 Prior to sampling technical and refined grades of dicumyl peroxide, it is essential that the sample be blended thoroughly after melting. This is best accomplished by placing the container in a 55°C water bath. After the sample has melted completely, mix thoroughly by swirling or stirring before withdrawing the sample for analysis (see 7.1 – 7.3). See **Note 3**.

NOTE 3—Refer to Practice **E300** for guidelines on sampling.

9. Procedure

9.1 Preparation of Standard Dicumyl Peroxide Solution:

9.1.1 To the nearest 0.1 mg, weigh 0.40 ± 0.05 g of recrystallized dicumyl peroxide and 0.20 ± 0.05 g of di-n-heptyl phthalate (internal standard) into a tared 120-mL glass bottle.

9.1.2 Add 100 mL of methanol, and mix well until the sample and internal standard have dissolved completely.

9.1.3 Filter the solution through a 0.2- μ m filter, collecting the filtrate in clean 17-mL vials equipped with PTFE-lined caps. Cap the vials and store in a cool, dark location. This solution should be used within 36 h, after which time a fresh solution should be prepared. Gradual peroxide decomposition will cause a change in the internal standard/dicumyl peroxide peak height ratio.

9.2 Preparation of Sample Solution:

9.2.1 To the nearest 0.1 mg, weigh 0.40 ± 0.05 g of melted dicumyl peroxide sample and 0.20 ± 0.05 g of di-n-heptyl phthalate (internal standard) into a tared 120-mL glass bottle.

9.2.2 Add 100 mL of methanol, and swirl until the sample and internal standard have dissolved completely.

9.2.3 Filter a portion of the solution through a 0.2- μ m filter, collecting the filtrate in a 17-mL vial equipped with a PTFE-lined cap. Cap the vial and store in a cool, dark location. This solution should be used within 36 h, after which time a fresh solution should be prepared. Gradual peroxide decomposition will cause a change in the internal standard/dicumyl peroxide peak height ratio.

9.3 Calibration:

9.3.1 Adjust the liquid chromatograph in accordance with the following parameters, and allow the instrument to equilibrate until a stable baseline is obtained.

Column oven	40°C
Detector	UV, 254 nm
Mobile phase	methanol:water, 85:15
Flow rate	1.0 mL/min
Recorder chart speed	0.5 cm/min

NOTE 4—The parameters given above apply to a liquid chromatograph equipped with a Zorbax Rx-18 C-18 reversed-phase column, 4.6-mm diameter by 25 cm in length. Other columns may require some modification in the flow rate or mobile phase composition (see **Note 2**).

⁶ Waters Associates Sample Clarification Kit, Catalog No. 26870, has been found to be satisfactory for this purpose.

⁷ Di-n-heptyl phthalate, Lancaster Synthesis, Cat. No. 5396, has been found to be satisfactory for use as an internal standard.