



Designation: C485 – 09

Standard Test Method for Measuring Warpage of Ceramic Tile¹

This standard is issued under the fixed designation C485; the number immediately following the designation indicates the year of original adoption or, in the case of revision, the year of last revision. A number in parentheses indicates the year of last reapproval. A superscript epsilon (ϵ) indicates an editorial change since the last revision or reapproval.

1. Scope

1.1 This test method covers procedures for measuring diagonal and edge warpages of the following categories of ceramic tile:

1.1.1 *Square Tile*, 2 by 2 in. (51 by 51 mm) or larger, that are nominally flat, of uniform overall thickness, and have a smooth face of one of the types: unglazed, bright glazed, matte glazed, or finely crystalline glazed.

1.1.2 *Oblong Tile*, no facial dimension smaller than 2 in. (51 mm), that are flat, of uniform overall thickness, and have a smooth face of one of the types: unglazed, bright glazed, matte glazed, or finely crystalline glazed.

1.1.3 *Square and Oblong Tile*, no facial dimension smaller than 2 in. (51 mm), that are flat, but have an irregular face such as embossed, sloped, bumpy, wavy, coarsely crystalline, or wire-cut textured.

1.1.4 *Nonrectilinear Tile*, larger than 4 in.² (26 cm²), that are flat and of uniform body thickness with smooth or irregular face, such as hexagonal, diamond, Spanish type, and so forth.

1.1.5 *Trim Tile* meeting one of the descriptions in 1.1.1-1.1.4 except that only a part of the tile surface is flat. (Surface trim tile should be treated as flat tile whenever possible.)

1.1.6 *Square or Oblong Tile* with facial area less than 4 in.² (26 cm²) and at least two straight sides equal to or greater than 1.0 in. (25 mm) long. (Modular 1- by 1-in. tile are not in the scope of this test method.)

1.2 This test method is not applicable to tile having embossed surfaces that are not flat, or that have a combination of variable body thickness and an irregular face.

1.3 The values stated in inch-pound units are to be regarded as standard. The values given in parentheses are mathematical conversions to SI units that are provided for information only and are not considered standard.

1.4 *This standard does not purport to address all of the safety concerns, if any, associated with its use. It is the*

responsibility of the user of this standard to establish appropriate safety and health practices and determine the applicability of regulatory limitations prior to use.

2. Referenced Documents

2.1 *ASTM Standards*:²

C242 *Terminology of Ceramic Whitewares and Related Products*

2.2 *ASTM Adjuncts*:

Warpage Gage for Ceramic Tile³

3. Terminology

3.1 *Definitions*:

3.1.1 *tile*—see Definitions C242.

3.1.2 *warpage*—curvature of a flat tile measured as deviation of the tile surface from a true plane along the edges or the diagonals. The deviation is measured at the mid-length of an edge or diagonal, expressed as a percentage of the length of the edge or diagonal, and called convex or concave with respect to the face of the tile.

4. Summary of Test Method

4.1 This test method consists of measuring the deviation from a straight line at the midpoint between reference points on the face or back of a tile. Measurements are made along the edges of a tile or along the diagonals, or both. The deviation is expressed as convex or concave warpage in relation to the tile face, and its magnitude is calculated as a percentage of the length of the edge or diagonal.

5. Significance and Use

5.1 This test method provides a means for determining whether or not a lot of ceramic tile meets the warpage requirements that may appear in specifications to assure satisfactory tile installations. In accordance with this test method, warpage is calculated as a percentage of the length of the edge or diagonal being tested. It is realized that the

¹ This method is under the jurisdiction of ASTM Committee C21 on Ceramic Whitewares and Related Products and is the direct responsibility of Subcommittee C21.06 on Ceramic Tile.

Current edition approved Jan. 1, 2009. Published January 2009. Originally approved in 1961. Last previous edition approved in 2003 as C485 – 83 (2003)^ε1. DOI: 10.1520/C0485-09.

² For referenced ASTM standards, visit the ASTM website, www.astm.org, or contact ASTM Customer Service at service@astm.org. For Annual Book of ASTM Standards volume information, refer to the standard's Document Summary page on the ASTM website.

³ Three drawings showing construction details are available from ASTM Headquarters. Order ADJC0485.

percentage values based on the overall edge length, or on the overall diagonal length of a tile will be slightly lower than those based on the distance between reference points. However, the ratio of the overall lengths to the distance between reference points will be practically constant for any particular size of tile and, therefore, the percentage values will be comparable and equally indicative of warpage.

6. Apparatus

6.1 *General Apparatus*—The size and arrangement of the apparatus for measuring the warpages vary, depending on the size and shape of the tile to be measured. In general, the apparatus consists of two stationary pins (reference pins) spaced apart $\frac{3}{4}$ in. (19 mm) less than the length of the edge or diagonal being tested, and a dial indicator tip midway between the stationary pins and in line with them. The pins and the dial indicator are mounted firmly on the same rigid metal bar. The pins may have a hemispherical tip, as described in 6.2.2, or they may be conical to a point. A more versatile apparatus for standard sizes of tile consists of a metal plate having three movable reference pins, three movable registry stops, and the necessary number of dial indicators. See Fig. 1 and Fig. 2.

6.2 Apparatus for Square Tile:³

6.2.1 *Metal Plate*—A flat metal plate, 6 by 6 in. (152 by 152 mm) square and $\frac{1}{4}$ in. (6.4 mm) thick, with a $\frac{7}{16}$ -in. (11-mm) wide slot starting at the midpoint of one side and running at right angles to that side for a distance of $2\frac{5}{8}$ in. (67 mm) toward the center of the plate. The plate also has a $\frac{7}{16}$ -in. diameter hole in the exact center of the plate. One side of the plate has two $\frac{1}{8}$ -in. (3.2-mm) thick, $\frac{1}{2}$ -in. (13-mm) wide, and 1-in. (25-mm) high projections, located not more than $\frac{1}{2}$ in. from the corners, and a similar projection located on an

adjacent side and not more than $\frac{1}{2}$ in. from one of the corners of the first side. These projections serve as permanent registry stops for 6- by 6-in. tile during measurement.

6.2.1.1 In addition, the plate has a series of tapped holes for insertion of removable reference pins and removable registry stops. The centers of the holes for the reference pins are located for each nominal size of tile near three of its corners, $\frac{3}{8}$ in. (9.5 mm) in from each side, when the tile is centered on the plate, except that for 2- by 2-in. (51- by 51-mm) tile the distance in from the edges is $\frac{1}{4}$ in. (6.4 mm). To receive the three registry stops, the centers of two holes are located for each nominal size of tile $\frac{1}{2}$ in. (13 mm) from the corners of one side and $\frac{1}{8}$ in. (3.2 mm) from the edge of the tile, while the center of a third hole is located on an adjacent side, $\frac{1}{2}$ in. from one of the corners of the first side and $\frac{1}{8}$ in. from the edge of the tile.

6.2.2 *Reference Pins*—Three movable reference pins $\frac{3}{8}$ in. (16 mm) high and $\frac{1}{4}$ in. (6.4 mm) in diameter, with the free end ground to a hemispherical tip and the other end threaded for a distance of $\frac{1}{4}$ in. The reference pins are inserted in the metal plate to support the tile during measurement.

6.2.3 *Registry Stops*—Three $\frac{1}{4}$ -in. (6.4-mm) diameter and $1\frac{1}{4}$ -in. (32-mm) high, movable, flat top registry stops with a $\frac{1}{16}$ -in. (1.6-mm) wide and $\frac{1}{8}$ -in. (3.2-mm) deep slot on one end for the insertion of a screwdriver and threaded on the other end for a distance of $\frac{1}{4}$ in. The registry stops are inserted in the metal plate to fix the horizontal position of the tile during measurement.

6.2.4 *Dial Indicators*—Two adjustable dial indicators, reading in 0.001-in. (0.025-mm) increments and accurate to ± 0.001 in. One is inserted from the bottom through the $\frac{7}{16}$ -in. (11-mm) hole in the center of the plate, permanently fastened to the underside of the metal plate, and used for measuring diagonal warpage. The other is inserted into the slot in the plate and fastened in any one of four positions which represent




FIG. 2 Apparatus as Shown in Fig. 1, Showing Arrangement of Stem Extender




FIG. 1 Apparatus for Square Tile, Set Up for Measurement of $4\frac{1}{4}$ - by $4\frac{1}{4}$ -in. (108- by 108-mm) Tile