



Designation: ~~C502-04~~ Designation: C 502 - 09

Standard Test Method for Wedging of Flat, Rectangular Ceramic Wall and Floor Tile¹

This standard is issued under the fixed designation C 502; the number immediately following the designation indicates the year of original adoption or, in the case of revision, the year of last revision. A number in parentheses indicates the year of last reapproval. A superscript epsilon (ϵ) indicates an editorial change since the last revision or reapproval.

1. Scope

1.1 This test method covers the determination of the wedging or deviation from rectangularity of flat, rectangular wall and floor tile. The test method covers tile as defined in Terminology C 242.

~~1.2 The values stated in inch-pound units are to be regarded as the standard. The values in parentheses are for information only.~~

1.2 The values stated in SI units are to be regarded as standard. No other units of measurement are included in this standard.

1.3 *This standard does not purport to address all of the safety concerns, if any, associated with its use. It is the responsibility of the user of this standard to establish appropriate safety and health practices and determine the applicability of regulatory limitations prior to use.*

2. Referenced Documents

2.1 *ASTM Standards:*²

C 242 [Terminology of Ceramic Whitewares and Related Products](#)

C 499 [Test Method for Facial Dimensions and Thickness of Flat, Rectangular Ceramic Wall and Floor Tile](#)

3. Terminology

3.1 *Definitions:*

3.1.1 *wedging of tile*—the difference between two spaced measurements of the length or width of a tile, expressed as a percentage of the distance between points of measurements.

3.2 For the definition of major and minor facial dimensions see Test Method C 499.

4. Significance and Use

4.1 Tile are normally pressed in dies having true 90° angle construction. However, minor variations in die fill, compacting pressure, and heat treatment can result in finished tile with acute and obtuse angles. This out-of-squareness results in a difference in length of opposite sides, and the tile may have the appearance of a keystone or wedge.

4.2 Excessive wedging presents difficulties in the installation of tile. This test method provides a means for determining the degree of wedging.

5. Apparatus

5.1 An apparatus as shown in Fig. 1 or other suitable apparatus. The dial gage (B) is used for measuring rectangularity.

5.2 A calibrating plate made of steel or aluminum of accurate dimensions and with straight, flat sides.

6. Test Specimens

6.1 At least ~~five~~^{ten} tile specimens shall be selected at random from the lot to be tested. The specimens shall be brushed to remove all adhering particles of clay and sand.

7. Procedure

7.1 Select an apparatus of the appropriate dimensions so that, when a tile is placed in the apparatus, the locating studs are 5 mm from each corner of the side adjacent to the side being measured. The plunger of the gage (B) shall also be 5 mm from the corner of the tile on the side being measured.

¹ This method is under the jurisdiction of ASTM Committee C21 on Ceramic Whitewares and Related Products and is the direct responsibility of Subcommittee C21.06 on Ceramic Tile.

Current edition approved April 1, 2004. Published May 2004. Originally approved 1962. Last previous edition approved in 1999 as C502-93a (1999).

Current edition approved Jan. 1, 2009. Published January 2009. Originally approved 1962. Last previous edition approved in 2004 as C 502 - 04.

² For referenced ASTM standards, visit the ASTM website, www.astm.org, or contact ASTM Customer Service at service@astm.org. For *Annual Book of ASTM Standards* volume information, refer to the standard's Document Summary page on the ASTM website.