

**SLOVENSKI STANDARD**  
**oSIST prEN ISO 28721-1:2018**  
**01-november-2018**

---

**Steklasti in keramični emajli - Emajlirane naprave za procesno opremo - 1. del:  
Zahteve za kakovost naprav, sestavnih delov, aparatov in pribora (ISO/DIS 28721-1:2018)**

Vitreous and porcelain enamels - Glass-lined apparatus for process plants - Part 1:  
Quality requirements for apparatus, components, appliances and accessories (ISO/DIS 28721-1:2018)

Emails und Emaillierungen - Emaillierte Apparate für verfahrenstechnische Anlagen - Teil  
1: Qualitätsanforderungen für Apparate, Apparateile, Einbau- und Zubehörteile  
(ISO/DIS 28721-1:2018)

Émaux vitrifiés - Appareils émaillés pour les installations industrielles - Partie 1:  
Exigences de qualité relatives aux appareillages, composants, appareils et accessoires  
(ISO/DIS 28721-1:2018)

**Ta slovenski standard je istoveten z: prEN ISO 28721-1**

---

**ICS:**

25.220.50      Emajlne prevleke      Enamels

**oSIST prEN ISO 28721-1:2018**      en



# DRAFT INTERNATIONAL STANDARD

## ISO/DIS 28721-1

ISO/TC 107

Secretariat: KATS

Voting begins on:  
2018-07-16Voting terminates on:  
2018-10-08

### Vitreous and porcelain enamels — Glass-lined apparatus for process plants —

Part 1:

### Quality requirements for apparatus, components, appliances and accessories

*Émaux vitrifiés — Appareils émaillés pour les installations industrielles —**Partie 1: Exigences de qualité relatives aux appareillages, composants, appareils et accessoires*

ICS: 25.220.50

**iTeh STANDARD PREVIEW**  
(standards.iteh.ai)

SIST EN ISO 28721-1:2019

<https://standards.iteh.ai/catalog/standards/sist/212021f0-5dfb-44d9-b28c-82e2efc70c5f/sist-en-iso-28721-1-2019>

THIS DOCUMENT IS A DRAFT CIRCULATED FOR COMMENT AND APPROVAL. IT IS THEREFORE SUBJECT TO CHANGE AND MAY NOT BE REFERRED TO AS AN INTERNATIONAL STANDARD UNTIL PUBLISHED AS SUCH.

IN ADDITION TO THEIR EVALUATION AS BEING ACCEPTABLE FOR INDUSTRIAL, TECHNOLOGICAL, COMMERCIAL AND USER PURPOSES, DRAFT INTERNATIONAL STANDARDS MAY ON OCCASION HAVE TO BE CONSIDERED IN THE LIGHT OF THEIR POTENTIAL TO BECOME STANDARDS TO WHICH REFERENCE MAY BE MADE IN NATIONAL REGULATIONS.

RECIPIENTS OF THIS DRAFT ARE INVITED TO SUBMIT, WITH THEIR COMMENTS, NOTIFICATION OF ANY RELEVANT PATENT RIGHTS OF WHICH THEY ARE AWARE AND TO PROVIDE SUPPORTING DOCUMENTATION.

This document is circulated as received from the committee secretariat.

### ISO/CEN PARALLEL PROCESSING



Reference number  
ISO/DIS 28721-1:2018(E)

© ISO 2018

## iTeh STANDARD PREVIEW (standards.iteh.ai)

SIST EN ISO 28721-1:2019

<https://standards.iteh.ai/catalog/standards/sist/212021f0-5dfb-44d9-b28c-82e2efc70c5f/sist-en-iso-28721-1-2019>



### **COPYRIGHT PROTECTED DOCUMENT**

© ISO 2018

All rights reserved. Unless otherwise specified, or required in the context of its implementation, no part of this publication may be reproduced or utilized otherwise in any form or by any means, electronic or mechanical, including photocopying, or posting on the internet or an intranet, without prior written permission. Permission can be requested from either ISO at the address below or ISO's member body in the country of the requester.

ISO copyright office  
CP 401 • Ch. de Blandonnet 8  
CH-1214 Vernier, Geneva  
Phone: +41 22 749 01 11  
Fax: +41 22 749 09 47  
Email: [copyright@iso.org](mailto:copyright@iso.org)  
Website: [www.iso.org](http://www.iso.org)

Published in Switzerland

# Contents

Page

<b>Foreword</b>	<b>iv</b>
<b>1 Scope</b>	<b>1</b>
<b>2 Normative references</b>	<b>1</b>
<b>3 Terms and definitions</b>	<b>2</b>
<b>4 Requirements</b>	<b>2</b>
4.1 General	2
4.2 Design and quality of enamel finish	2
4.3 Surface	2
4.4 Defects	2
4.4.1 General	2
4.4.2 Defects unacceptable in the finished product	2
4.4.3 Repairable defects	3
4.4.4 Vessels and columns	4
4.4.5 Accessories	4
4.4.6 Fittings and pump components	4
4.5 Coating thickness	4
4.6 General tolerances	4
4.7 Finish	4
<b>5 Testing</b>	<b>5</b>
5.1 General	5
5.2 Visual examination	5
5.3 High-voltage test	5
5.4 Testing for cracks	5
5.5 Coating thickness measurement	5
5.6 Measurement of dimensions	6
5.7 Determination of the concentricity of agitators and pump rotors	6
5.7.1 General	6
5.7.2 Agitators	6
5.7.3 Pump rotors	6
5.8 Performance testing	6
5.9 Completeness check	7
<b>6 Manufacturing stages and inspections</b>	<b>7</b>
<b>7 Repairing defects</b>	<b>8</b>
7.1 Repairing with plugs	8
7.2 Removing impurities	9
<b>8 Test report</b>	<b>9</b>
<b>9 Packaging and transportation</b>	<b>10</b>
<b>10 Inspection at delivery</b>	<b>11</b>
<b>Annex A (informative) Examples of test reports</b>	<b>12</b>
<b>Bibliography</b>	<b>19</b>

## ISO/DIS 28721-1:2018(E)

### Foreword

ISO (the International Organization for Standardization) is a worldwide federation of national standards bodies (ISO member bodies). The work of preparing International Standards is normally carried out through ISO technical committees. Each member body interested in a subject for which a technical committee has been established has the right to be represented on that committee. International organizations, governmental and non-governmental, in liaison with ISO, also take part in the work. ISO collaborates closely with the International Electrotechnical Commission (IEC) on all matters of electrotechnical standardization.

The procedures used to develop this document and those intended for its further maintenance are described in the ISO/IEC Directives, Part 1. In particular the different approval criteria needed for the different types of ISO documents should be noted. This document was drafted in accordance with the editorial rules of the ISO/IEC Directives, Part 2 (see [www.iso.org/directives](http://www.iso.org/directives)).

Attention is drawn to the possibility that some of the elements of this document may be the subject of patent rights. ISO shall not be held responsible for identifying any or all such patent rights. Details of any patent rights identified during the development of the document will be in the Introduction and/or on the ISO list of patent declarations received (see [www.iso.org/patents](http://www.iso.org/patents)).

Any trade name used in this document is information given for the convenience of users and does not constitute an endorsement.

For an explanation on the voluntary nature of standards, the meaning of ISO specific terms and expressions related to conformity assessment, as well as information about ISO's adherence to the World Trade Organization (WTO) principles in the Technical Barriers to Trade (TBT) see the following URL: [www.iso.org/iso/foreword.html](http://www.iso.org/iso/foreword.html).

This document was prepared by Technical Committee ISO/TC 107, Metallic and other inorganic coatings.

This second edition cancels and replaces the first edition (28721-1:2008), which has been technically revised. The main changes compared to the previous edition are as follows:

- Normative references updated;
- Revision of 6.3 " High-voltage test";
- Amendment in Clause 11 in order to add the 7 kV test voltage according to 6.3;
- Editorial changes and update of bibliography.

A list of all parts in the ISO 28721 series can be found on the ISO website.

# Vitreous and porcelain enamels — Glass-lined apparatus for process plants —

## Part 1: Quality requirements for apparatus, components, appliances and accessories

### 1 Scope

This document specifies the quality requirements for apparatus, components, appliances and accessories of glass-lined steel (including semi-crystallized enamel coatings) and glass-lined steel castings used for process plants. It specifies the quality requirements and the tests to be carried out by the manufacturer as well as the action to be taken to repair defects.

It is also applicable to glass-lined pumps, pump components and fittings.

It is not applicable to glass-lined flanged steel pipes or glass-lined flanged steel fittings.

NOTE 1 Provisions for glass-lined flanged steel pipes and glass-lined flanged steel fittings are given in ISO 28721-4[3].

The test methods specified cover checking the enamel, the dimensional accuracy and the performance of apparatus and components.

This document applies to new apparatus and components as well as used items that have been re-enamelled.

It does not contain requirements regarding the chemical or physical properties of vitreous and porcelain enamels.

NOTE 2 Examples of test reports are given in [Annex A](#).

### 2 Normative references

The following documents are referred to in the text in such a way that some or all of their content constitutes requirements of this document. For dated references, only the edition cited applies. For undated references, the latest edition of the referenced document (including any amendments) applies.

ISO 780, *Packaging — Distribution packaging — Graphical symbols for handling and storage of packages*

ISO 2178, *Non-magnetic coatings on magnetic substrates — Measurement of coating thickness — Magnetic method*

ISO 28721-2, *Vitreous and porcelain enamels — Glass-lined apparatus for process plants — Part 2: Designation and specification of resistance to chemical attack and thermal shock*

ISO 28721-3, *Vitreous and porcelain enamels — Glass-lined apparatus for process plants — Part 3: Thermal shock resistance*

ISO 2746, *Vitreous and porcelain enamels — High voltage test*

## ISO/DIS 28721-1:2018(E)

### 3 Terms and definitions

For the purposes of this document, the terms and definitions given in ISO 19496<sup>[1]</sup> apply.

ISO and IEC maintain terminological databases for use in standardization at the following addresses:

- IEC Electropedia: available at <http://www.electropedia.org/>
- ISO Online browsing platform: available at <http://www.iso.org/obp>

### 4 Requirements

#### 4.1 General

If the requirements given in this part of ISO 28721 are to be applied to glass-lined apparatus and components, this shall be stated as follows when ordering:

Prepared in accordance with ISO 28721-1.

Requirements differing from those stated in this part of ISO 28721 may be agreed upon between the parties at the time of ordering.

#### 4.2 Design and quality of enamel finish

The manufacturer shall be responsible for the appropriate design and construction.

The enamel quality (i.e. the type of enamel and, where relevant, the colour) shall be agreed upon between the interested parties at the time of ordering.

The characteristic composition of individual enamel layers shall correspond to that of specimens submitted for laboratory testing. The quality of the enamel shall meet the requirements specified in ISO 28721-2 and ISO 28721-3.

#### 4.3 Surface

The enamel coating shall have a uniform, smooth, fully-fused surface free from impurities.

#### 4.4 Defects

##### 4.4.1 General

Defects shall be examined visually (see 6.2).

##### 4.4.2 Defects unacceptable in the finished product

Defects unacceptable in the finished product are those which would render a component unusable. Such defects are typically as follows:

- a) defects which cannot be repaired by the means described in [Clause 8](#), such as:
  - defects extending over an area with a diameter > 8 mm,
  - defects on inaccessible spots,
  - defects concerning vessels and columns as described in 5.4.4;
- b) collapsed lines in the cover coat;
- c) bubble lines, i.e. fused-in bubbles arranged in a distinct line;



- d) fused strain lines (recognizable as lines with colours different from that of the surrounding enamel);
- e) areas not properly fused (a rough surface similar to a sandblasted one);
- f) devitrified areas in vitreous enamel or over crystallized areas in semi-crystallized enamel (recognizable as a dull or a rough surface);
- g) pull-through of ground coat (recognizable as e.g. spot-like discolorations);
- h) cracks detectable by e.g. a statiflux test;
- i) spots with a diameter > 30 mm caused by grinding and polishing during the removal of impurities (see also 5.4.3 and 8.2).

#### 4.4.3 Repairable defects

Repairable defects are imperfections in the enamel coating which allow, under certain circumstances (see below), further use of glass-lined equipment after repair. Common repairable defects are:

- a) depressions with a depth exceeding 25 % of the coating thickness;
- b) blisters, such as circular holes in the coating exposing the ground coat;
- c) areas with weak spots or defects detectable by high-voltage testing in accordance with 6.3;
- d) impurities in the enamel coating.

Isolated impurities, such as fire clay particles, shall be removed. Dust-like impurities on the surface may be accepted. Scale fused into the surface shall be removed where it extends parallel to the surface over a distance of more than 3 mm and/or is not a flat particle or is not fused parallel to the surface.

The maximum permissible number of defects repaired by plugging shall be as given in [Tables 1](#) and [2](#).

Further requirements, such as the maximum level of pores or use without plugging, shall be agreed upon between the interested parties at the time of ordering.

Defects as defined in 5.4.3 a) and 5.4.3 b) shall be repaired as described in 8.1.

Specifications regarding defects in various types of apparatus and components are given in 5.4.4 to 5.4.6.

**Table 1 — Maximum permissible number of plugged enamel defects in vessels**

Nominal volume  m <sup>3</sup>	Maximum permissible number of defects			
	Agitator vessels			Other vessels
	Type AE		Types BE and CE <sup>a</sup>	
	Lower part of vessel	Main cover		
up to 4	0	0	0	0
over 4 to 10	1	1	1	1
over 10 to 20	—	—	2	3
over 20 to 32	—	—	3	4
over 32 to 40	—	—	4	5
over 40 to 80	—	—	—	6
over 80	—	—	—	7

<sup>a</sup> Assembly covers shall be delivered without any plugs.

<sup>a</sup> Assembly covers shall be delivered without any plugs.

**Table 2 — Maximum permissible number of plugged enamel defects in columns**

Nominal diameter of column mm	Maximum permissible number of defects for unit lengths		
	up to 2 000 mm	over 2 000 mm up to 5 000 mm	over 5 000 mm
up to 600	0	0	0
over 600 to 1 200	0	1	2
over 1 200	1	2	3

#### 4.4.4 Vessels and columns

[Table 1](#) and [Table 2](#) list the number of repairable defects to be covered with plugs. Exceptions apply in the following cases:

- a) outlet nozzles and agitator nozzles, including the complete neck area around the nozzle, shall not be repaired by plugging (this also applies to other nozzles with a nominal diameter of 150 mm or less, including the neck area which extends out 30 mm beyond the inner nozzle diameter);
- b) convex and concave surfaces with a radius of 75 mm or less shall not be repaired by plugging;
- c) seal areas (gasket bearing surfaces) shall not be repaired by plugging.

#### 4.4.5 Accessories

Accessories such as agitators, baffles, thermo pipes, probes, inlet pipes, washers, manhole covers and dip-pipes shall not be repaired by plugging (see 8.1).

#### 4.4.6 Fittings and pump components

Fittings and pump components shall not be repaired by plugging (see 8.1).

### 4.5 Coating thickness

The thickness of enamel coatings on steel substrates shall range from 1,0 mm to 2,2 mm, with the following exceptions:

- a) maximum values may be exceeded by 0,2 mm on concave surfaces;
- b) the enamel coating may be 0,2 mm thinner than the specified minimum value in limited areas and on convex surfaces;
- c) coatings on small parts with very small radii  $\leq 5$  mm, such as valve stems or rotors of pumps, may have a minimum thickness of 0,6 mm.

Any changes in thickness shall be smooth.

### 4.6 General tolerances

General tolerances and tests for the concentricity of agitators (see 6.7.1 and 6.7.2) shall be agreed upon between the interested parties.

NOTE Examples of tolerances for vessels other than agitator vessels, agitator vessels and columns are given in DIN 28005-2 [[4]], DIN 28006-2 [[5]] and DIN 28007-2 [[6]], respectively. DIN 28159 [[7]] gives tolerances for agitator ends and DIN 2873 [[8]] gives permissible angular misalignments for flange surfaces.

### 4.7 Finish

Unless otherwise agreed, non-enamelled surfaces, except for those which are not to be coated, such as fitting surfaces, shall be protected by a primer.

Details shall be agreed upon between the interested parties at the time of ordering.

Corrosion protection of parts without a primer coating, e.g. connecting elements, shall be agreed upon between the interested parties at the time of ordering.

## 5 Testing

### 5.1 General

Tests carried out in accordance with this part of ISO 28721 shall be conducted only by skilled personnel and shall be documented.

NOTE Examples of test report formats are given in [Annex A](#).

The surfaces to be tested shall be clean, dry, sufficiently illuminated and easily accessible.

The components tested and the test reports shall be marked to allow proper identification. It is at the customer's discretion to have his/her own inspectors verify the test results by repeating the tests at the manufacturing site as described below.

Details of testing shall be agreed upon between the interested parties at the time of ordering.

### 5.2 Visual examination

The surfaces of glass-lined apparatus and components shall be checked visually. Optical instruments, such as magnifying glasses, may be used for closer examination.

### 5.3 High-voltage test

High-voltage tests shall be conducted in accordance with ISO 2746. When the enamelling of a component is complete, the manufacturer shall run a high-voltage test at 20 kV.

For subsequent tests, a voltage of maximum 12 kV shall be used.

By customer request, and with the agreement of the manufacturer, particular areas may be re-checked with a higher voltage. Totally glass-lined components shall be tested with pulsed DC voltage.

Exceptions apply in the following cases:

- a) enamelled probes shall be tested with a DC voltage of 7 kV;
- b) for components coated with conductive or dissipative enamel, the manufacturer shall run a high-voltage test at 7 kV; they shall be appropriately marked by the manufacturer.

### 5.4 Testing for cracks

Areas where cracks are presumed to have formed shall be sprayed with electrostatically charged talcum powder to make cracks more visible. Even fine cracks will then be clearly revealed.

### 5.5 Coating thickness measurement

Measurement of the coating thickness shall be carried out in accordance with ISO 2178, using a measuring instrument accurate to 5 % of the actual value. The thickness shall be measured using spot checks. Extra measurements shall, however, be taken at critical spots such as small radii, uneven surfaces and localized increases in thickness.