



**SLOVENSKI STANDARD**  
**oSIST prEN ISO 10863:2019**  
**01-januar-2019**

---

**Neporušitveno preskušanje zvarov - Ultrazvočna preiskava - Uporaba tehnike TOFD (ISO/DIS 10863:2018)**

Non-destructive testing of welds - Ultrasonic testing - Use of time-of-flight diffraction technique (TOFD) (ISO/DIS 10863:2018)

Zerstörungsfreie Prüfung von Schweißverbindungen - Ultraschallprüfung - Anwendung der Beugungslaufzeittechnik (TOFD) (ISO/DIS 10863:2018)

Contrôle non destructif des assemblages soudés - Contrôle par ultrasons - Utilisation de la technique de diffraction des temps de vol (méthode TOFD) (ISO/DIS 10863:2018)

**Ta slovenski standard je istoveten z: prEN ISO 10863**

---

**ICS:**

25.160.40	Varjeni spoji in vari	Welded joints and welds
-----------	-----------------------	-------------------------

**oSIST prEN ISO 10863:2019**

**en,fr,de**



# DRAFT INTERNATIONAL STANDARD

## ISO/DIS 10863

ISO/TC 44/SC 5

Secretariat: **AFNOR**Voting begins on:  
**2018-11-21**Voting terminates on:  
**2019-02-13**

### Non-destructive testing of welds — Ultrasonic testing — Use of time-of-flight diffraction technique (TOFD)

*Contrôle non destructif des assemblages soudés — Contrôle par ultrasons — Utilisation de la technique de diffraction des temps de vol (méthode TOFD)*

ICS: 25.160.40

iTeh STANDARD PREVIEW  
(standards.iteh.ai)

SIST EN ISO 10863:2020

<https://standards.iteh.ai/catalog/standards/sist/b4481450-1753-4d5a-b83f-587b66a8ced2/sist-en-iso-10863-2020>

THIS DOCUMENT IS A DRAFT CIRCULATED FOR COMMENT AND APPROVAL. IT IS THEREFORE SUBJECT TO CHANGE AND MAY NOT BE REFERRED TO AS AN INTERNATIONAL STANDARD UNTIL PUBLISHED AS SUCH.

IN ADDITION TO THEIR EVALUATION AS BEING ACCEPTABLE FOR INDUSTRIAL, TECHNOLOGICAL, COMMERCIAL AND USER PURPOSES, DRAFT INTERNATIONAL STANDARDS MAY ON OCCASION HAVE TO BE CONSIDERED IN THE LIGHT OF THEIR POTENTIAL TO BECOME STANDARDS TO WHICH REFERENCE MAY BE MADE IN NATIONAL REGULATIONS.

RECIPIENTS OF THIS DRAFT ARE INVITED TO SUBMIT, WITH THEIR COMMENTS, NOTIFICATION OF ANY RELEVANT PATENT RIGHTS OF WHICH THEY ARE AWARE AND TO PROVIDE SUPPORTING DOCUMENTATION.

This document is circulated as received from the committee secretariat.

### ISO/CEN PARALLEL PROCESSING



Reference number  
ISO/DIS 10863:2018(E)

© ISO 2018

# iTeh STANDARD PREVIEW (standards.iteh.ai)

SIST EN ISO 10863:2020

<https://standards.iteh.ai/catalog/standards/sist/b4481450-1753-4d5a-b83f-587b66a8ced2/sist-en-iso-10863-2020>



## **COPYRIGHT PROTECTED DOCUMENT**

© ISO 2018

All rights reserved. Unless otherwise specified, or required in the context of its implementation, no part of this publication may be reproduced or utilized otherwise in any form or by any means, electronic or mechanical, including photocopying, or posting on the internet or an intranet, without prior written permission. Permission can be requested from either ISO at the address below or ISO's member body in the country of the requester.

ISO copyright office  
CP 401 • Ch. de Blandonnet 8  
CH-1214 Vernier, Geneva  
Phone: +41 22 749 01 11  
Fax: +41 22 749 09 47  
Email: [copyright@iso.org](mailto:copyright@iso.org)  
Website: [www.iso.org](http://www.iso.org)

Published in Switzerland

# Contents

Page

<b>Foreword</b>	<b>v</b>
<b>1 Scope</b>	<b>1</b>
<b>2 Normative references</b>	<b>1</b>
<b>3 Terms and definitions</b>	<b>2</b>
<b>4 General remarks on the capabilities of the technique</b>	<b>2</b>
<b>5 Testing levels</b>	<b>3</b>
<b>6 Information required prior to testing</b>	<b>3</b>
6.1 Items to be defined by specification	3
6.2 Specific information required by the operator before testing	4
6.3 Written test instruction or procedure	4
<b>7 Requirements for test personnel and equipment</b>	<b>4</b>
7.1 Personnel qualifications	4
7.2 Test equipment	5
<b>8 Preparation for testing</b>	<b>5</b>
8.1 Volume to be tested	5
8.2 Setup of probes	5
8.3 Scan increment setting	6
8.4 Geometry considerations	6
8.5 Preparation of scanning surfaces	7
8.6 Temperature	7
8.7 Couplant	7
8.8 Provision of datum points	7
<b>9 Testing of base material</b>	<b>7</b>
<b>10 Range and sensitivity settings</b>	<b>7</b>
10.1 Settings	7
10.1.1 General	7
10.1.2 Time window	7
10.1.3 Time-to-depth conversion	8
10.1.4 Sensitivity settings	8
10.2 Checking of the settings	8
10.3 Reference blocks	9
10.3.1 General	9
10.3.2 Material	9
10.3.3 Dimensions and shape	9
10.3.4 Reference reflectors	9
<b>11 Weld testing</b>	<b>9</b>
<b>12 Interpretation and analysis of TOFD images</b>	<b>10</b>
12.1 General	10
12.2 Assessing the quality of the TOFD image	10
12.3 Identification of relevant TOFD indications	10
12.4 Classification of relevant TOFD indications	11
12.4.1 General	11
12.4.2 TOFD indications from surface-breaking discontinuities	11
12.4.3 TOFD indications from embedded discontinuities	11
12.4.4 Unclassified TOFD indications	12
12.5 Determination of location	12
12.6 Definition and determination of length and height	12
12.6.1 General	12
12.6.2 Determination of length	14
12.6.3 Determination of height	15

## ISO/DIS 10863:2018(E)

12.7	Evaluation against acceptance criteria.....	16
<b>13</b>	<b>Test report.....</b>	<b>16</b>
<b>Annex A</b> (informative)	<b>Reference blocks.....</b>	<b>18</b>
<b>Annex B</b> (informative)	<b>Examples of TOFD scans .....</b>	<b>23</b>
<b>Bibliography .....</b>		<b>37</b>

iTeh STANDARD PREVIEW  
(standards.iteh.ai)

SIST EN ISO 10863:2020

<https://standards.iteh.ai/catalog/standards/sist/b4481450-1753-4d5a-b83f-587b66a8ced2/sist-en-iso-10863-2020>

## Foreword

ISO (the International Organization for Standardization) is a worldwide federation of national standards bodies (ISO member bodies). The work of preparing International Standards is normally carried out through ISO technical committees. Each member body interested in a subject for which a technical committee has been established has the right to be represented on that committee. International organizations, governmental and non-governmental, in liaison with ISO, also take part in the work. ISO collaborates closely with the International Electrotechnical Commission (IEC) on all matters of electrotechnical standardization.

The procedures used to develop this document and those intended for its further maintenance are described in the ISO/IEC Directives, Part 1. In particular, the different approval criteria needed for the different types of ISO documents should be noted. This document was drafted in accordance with the editorial rules of the ISO/IEC Directives, Part 2 (see [www.iso.org/directives](http://www.iso.org/directives)).

Attention is drawn to the possibility that some of the elements of this document may be the subject of patent rights. ISO shall not be held responsible for identifying any or all such patent rights. Details of any patent rights identified during the development of the document will be in the Introduction and/or on the ISO list of patent declarations received (see [www.iso.org/patents](http://www.iso.org/patents)).

Any trade name used in this document is information given for the convenience of users and does not constitute an endorsement.

For an explanation of the voluntary nature of standards, the meaning of ISO specific terms and expressions related to conformity assessment, as well as information about ISO's adherence to the World Trade Organization (WTO) principles in the Technical Barriers to Trade (TBT), see [www.iso.org/iso/foreword.html](http://www.iso.org/iso/foreword.html).

This document was prepared by Technical Committee ISO/TC 44, *Welding and allied processes*, Subcommittee SC 5, *Testing and inspection of welds*.

This second edition cancels and replaces the first edition (ISO 10632:2011), which has been technically revised.

The main changes compared to the previous edition are as follows:

- the whole document was updated to the state of the art.

Any feedback, question or request for official interpretation related to any aspect of this document should be directed to the Secretariat of ISO/TC 44/SC 5 via your national standards body. A complete listing of these bodies can be found at [www.iso.org/members.html](http://www.iso.org/members.html). Official interpretations, where they exist, are available from this page: <https://committee.iso.org/sites/tc44/home/interpretation.html>.





# Non-destructive testing of welds — Ultrasonic testing — Use of time-of-flight diffraction technique (TOFD)

## 1 Scope

This International Standard specifies the application of the time-of-flight diffraction (TOFD) technique to the semi- or fully automated ultrasonic testing of fusion-welded joints in metallic materials of minimum thickness 6 mm. It applies to full penetration welded joints of simple geometry in plates, pipes, and vessels, where both the weld and the parent material are low-alloyed carbon steel. Where specified and appropriate, TOFD can also be used on other types of materials that exhibit low ultrasonic attenuation (especially that due to scatter).

Where material-dependent ultrasonic parameters are specified in this document, they are based on steels having a sound velocity of  $(5\,920 \pm 50)$  m/s for longitudinal waves, and  $(3\,255 \pm 30)$  m/s for transverse waves. It is necessary to take this fact into account when testing materials with a different velocity.

This document makes reference to the basic standard ISO 16828 and provides guidance on the specific capabilities and limitations of TOFD for the detection, location, sizing and characterization of discontinuities in fusion-welded joints. TOFD can be used as a stand-alone method or in combination with other non-destructive testing (NDT) methods or techniques, for manufacturing inspection, and for in-service inspection.

This document specifies four testing levels (A, B, C, D) in accordance with ISO 17635 and corresponding to an increasing level of testing reliability. Guidance on the selection of testing levels is provided.

This document permits assessment of TOFD indications for acceptance purposes. This assessment is based on the evaluation of transmitted, reflected and diffracted ultrasonic signals within a generated TOFD image.

This document does not include acceptance levels for discontinuities.

## 2 Normative references

The following documents are referred to in the text in such a way that some or all of their content constitutes requirements of this document. For dated references, only the edition cited applies. For undated references, the latest edition of the referenced document (including any amendments) applies.

ISO 5577, *Non-destructive testing — Ultrasonic testing — Vocabulary*

ISO 9712, *Non-destructive testing — Qualification and certification of NDT personnel*

ISO 16828, *Non-destructive testing — Ultrasonic testing — Time-of-flight diffraction technique as a method for detection and sizing of discontinuities*

ISO 17635, *Non-destructive testing of welds — General rules for metallic materials*

ISO 17640, *Non-destructive testing of welds — Ultrasonic testing — Techniques, testing levels, and assessment*

EN 12668 (all parts), *Non-destructive testing — Characterization and verification of ultrasonic examination equipment*

## ISO/DIS 10863:2018(E)

### 3 Terms and definitions

For the purposes of this document, the terms and definitions given in ISO 5577 and the following apply.

ISO and IEC maintain terminological databases for use in standardization at the following addresses:

- ISO Online browsing platform: available at <http://www.iso.org/obp>
- IEC Electropedia: available at <http://www.electropedia.org/>

#### 3.1

##### **time-of-flight diffraction setup**

##### **TOFD setup**

probe arrangement defined by probe characteristics (e.g. frequency, probe element size, beam angle, wave mode) and probe centre separation

#### 3.2

##### **probe centre separation**

##### **PCS**

distance between the index points of the two probes

Note 1 to entry: The PCS for two probes located on a curved surface is the straight-line, geometric separation between the two probe index points and not the distance measured along the surface.

#### 3.3

##### **beam intersection point**

point of intersection of the two main beam axes

#### 3.4

##### **time-of-flight diffraction indication**

##### **TOFD indication**

pattern or disturbance in the time-of-flight diffraction image which may need further evaluation

#### 3.5

##### **time-of-flight diffraction image**

##### **TOFD image**

two-dimensional image, constructed by collecting adjacent A-scans while moving the time-of-flight diffraction setup

Note 1 to entry: The signal amplitude of the A-scans is typically represented by grey-scale values.

#### 3.6

##### **offset scan**

scan parallel to the weld axis, where the beam intersection point is not on the centreline of the weld

### 4 General remarks on the capabilities of the technique

General principles of the TOFD technique are described in ISO 16828. For the testing of fusion-welded joints, some specific capabilities and limitations of the technique have to be considered.

The TOFD technique is an ultrasonic image-generating technique, which offers the capability of detection, location, and sizing. To a certain extent, characterization of discontinuities in the weld material as well as in the adjacent parent material is also possible.

Compared with purely reflection-based techniques, the TOFD technique, which is based upon diffraction as well as reflection, is less sensitive to the orientation of the discontinuity. Discontinuities oriented perpendicular to the surface, and at intermediate angles of tilt, are detectable as well as discontinuities in the weld fusion faces.

In certain circumstances (thickness, weld preparation, scope of testing, etc.) more than one single TOFD setup is required.

A typical TOFD image is linear in time (vertical axis) and probe movement (horizontal axis). Because of the V-configuration of the ultrasound paths, the location of a possible discontinuity is then non-linear. TOFD testing has to be carried out in a correct and consistent way, such that valid images are generated which can be evaluated correctly, e.g. coupling losses and data acquisition errors have to be avoided, see [12.2](#).

The interpretation of TOFD images requires skilled and experienced operators. Some typical TOFD images of discontinuities in fusion-welded joints are provided in [Annex B](#).

There is a reduced capability for the detection of discontinuities close to or connected with the scanning surface or with the opposite surface. This has to be considered especially for crack-sensitive steels or at in-service inspections. In cases where full coverage of these zones is required, additional measures shall be taken, e.g. TOFD can be accompanied by other NDT methods or techniques.

Diffraction signals from weld discontinuities can have small amplitude responses. The grain scatter effect from coarse-grained material can hinder the detection and evaluation of such responses. This shall be taken into account whenever testing such material.

## 5 Testing levels

This document specifies four testing levels (A, B, C and D, see [Table 1](#)). From testing level A to testing level C an increasing reliability is achieved.

**Table 1 — Testing levels**

Testing level	TOFD setup	Reference block for setup verification (see <a href="#">8.2</a> )	Reference block for sensitivity settings (see <a href="#">10.1.4</a> )	Offset scan	Written test procedure
A	As in <a href="#">Table 2</a>	No	No	No	This document
B	As in <a href="#">Table 2</a>	No	Yes	No	This document
C	As in <a href="#">Table 2</a>	Yes	Yes	a	Yes
D	As defined by specification	Yes	Yes	a	Yes

<sup>a</sup> The necessity, number and position of offset scans have to be determined.

If the specified acceptance level requires detection of a certain discontinuity size at both surfaces or one surface of the weld (see [Clause 4](#)), this can necessitate the use of techniques or methods outside the scope of this document.

For manufacturing inspections (see also ISO 17635), all testing levels are applicable. Level A is only applicable for wall thicknesses up to 50 mm. For in-service inspections, only testing level D shall be applied.

## 6 Information required prior to testing

### 6.1 Items to be defined by specification

Information on the following items is required:

- a) purpose and extent of TOFD testing (see [Clauses 5](#) and [8](#));
- b) testing levels (see [Clause 5](#)), e.g.:
  - 1) whether a written test procedure is required,
  - 2) whether reference blocks are required;
- c) specification of reference blocks, if required (see [10.3](#));

## ISO/DIS 10863:2018(E)

- d) manufacturing or operation stage at which the testing is to be carried out;
- e) requirements for: temperature, access and surface conditions (see [Clause 8](#));
- f) reporting requirements (see [Clause 13](#));
- g) acceptance criteria;
- h) personnel qualifications (see [7.1](#)).

### 6.2 Specific information required by the operator before testing

Before any testing of a welded joint can begin, the operator shall have access to all the information as specified in [6.1](#) together with the following additional information:

- a) written test instruction or procedure (see [6.3](#)), if required;
- b) type(s) of parent material and product form (i.e. cast, forged, rolled);
- c) joint preparation and dimensions;
- d) welding procedure or relevant information on the welding process;
- e) time of testing relative to any post-weld heat treatment;
- f) result of any parent metal testing carried out prior to and/or after welding;
- g) defect type and morphology to be detected.

### 6.3 Written test instruction or procedure

For testing levels A and B, this document satisfies the need for a written test procedure.

For testing levels C and D, or where the techniques described in this document are not applicable to the welded joint to be tested, a specific written test procedure shall be used.

When data collection is performed by personnel certified to Level 1 according to ISO 9712, a written test instruction shall be prepared. The written test instruction shall contain as a minimum the information listed in [Clause 13](#).

## 7 Requirements for test personnel and equipment

### 7.1 Personnel qualifications

In addition to a general knowledge of ultrasonic weld testing, all personnel shall be competent in the TOFD technique. Documented evidence of their competence (level of training and experience) is required.

Preparation of written test instructions, final off-line analysis of data, and acceptance of the report shall be performed by personnel qualified as a minimum to Level 2 in accordance with ISO 9712 or equivalent in ultrasonic testing in the relevant industrial sector. In accordance with a written instruction and under the supervision of Level 2 or Level 3 personnel, equipment setup, data acquisition, data storage, and report preparation can be performed by personnel certified to a minimum of Level 1 in accordance with ISO 9712 or equivalent in ultrasonic testing in the relevant industrial sector.

For data acquisition, the Level 1 personnel may be supported by an assistant technician.

In cases where the above minimum qualifications are not considered adequate, job-specific training shall be carried out.

## 7.2 Test equipment

**7.2.1 Ultrasonic instruments and display.** The ultrasonic instrument used for the TOFD technique shall, where applicable, comply with the requirements of EN 12668-1.

The TOFD software shall not mask any problems such as loss of coupling, missing scan lines, synchronization errors or electronic noise.

In addition, the requirements of ISO 16828 shall apply, taking into account the following:

- a) the instrument shall be able to select an appropriate portion of the time base within which A-scans are digitized;
- b) it is recommended that a sampling rate of the A-scan of at least 6 times the nominal probe frequency be used.

**7.2.2 Ultrasonic probes.** Probes used for the TOFD technique on welds shall comply with ISO 12668-2 and ISO 16828.

Adaptation of probes to curved scanning surfaces shall comply with ISO 17640.

A recommendation for the selection of probes is given in [Table 2](#).

**7.2.3 Scanning mechanisms.** The requirements of ISO 16828 shall apply. To achieve consistency of the images (collected data), guiding mechanisms may be used.

## 8 Preparation for testing

### 8.1 Volume to be tested

Testing shall be performed in accordance with ISO 16828. The purpose of the testing shall be defined by specification. Based on this, the volume to be tested shall be determined.

The volume to be tested is located between the probes. For testing levels A and B, the probes shall be placed symmetrically about the weld centreline. For testing levels C and D, additional offset scans may be required.

For manufacturing inspection, the examination volume is defined as the zone which includes weld and parent material for at least 10 mm on each side of the weld or the width of the heat-affected zone, whichever is greater. In all cases the whole examination volume shall be covered.

Normally these tests are performed in accordance with recognized standards applying acceptance levels for quality assurance. If fitness-for-purpose methods are applied, then corresponding acceptance criteria shall be specified.

For in-service inspections, the examination volume may be targeted to specific areas of interest, e.g. the inner third of the weld body. The acceptance criteria and minimum discontinuity size to be detected in the area of interest shall be specified.

### 8.2 Setup of probes

The probes shall be set up to ensure adequate coverage and optimum conditions for the initiation and detection of diffracted signals in the area of interest. For butt welds of simple geometry and with narrow weld crowns at the opposite surface, the testing shall be performed in one or more setups (scans) dependent upon the wall thickness (see [Table 2](#)). For other configurations, e.g. X-shaped welds, different base metal thickness at either side of the weld, or tapering, [Table 2](#) may be used as guidance. In this case, the effectiveness and coverage of the setup shall be verified by the use of reference blocks. Selection of probes for full coverage of the complete weld thickness should follow [Table 2](#). Care should