

---

---

**Preparation of steel substrates before  
application of paints and related  
products — Specifications for metallic  
blast-cleaning abrasives —**

Part 3:

**High-carbon cast-steel shot and grit**

iTeh STANDARD PREVIEW  
(standards.iteh.ai)

*Préparation des subjectiles d'acier avant application de peintures  
et de produits assimilés — Spécifications pour abrasifs métalliques  
destinés à la préparation par projection —*

ISO 11124-3:2018

*Partie 3: Grenaille ronde et angulaire en acier coulé à haut carbone*  
<https://standards.iteh.ai/catalog/standards/sist/c51e2c59-1e2c-475d-9c99-caac70cefeae/iso-11124-3-2018>



## iTeh STANDARD PREVIEW (standards.iteh.ai)

ISO 11124-3:2018

<https://standards.iteh.ai/catalog/standards/sist/c51c2e39-1eac-475d-9e99-caac70cefeae/iso-11124-3-2018>



### **COPYRIGHT PROTECTED DOCUMENT**

© ISO 2018

All rights reserved. Unless otherwise specified, or required in the context of its implementation, no part of this publication may be reproduced or utilized otherwise in any form or by any means, electronic or mechanical, including photocopying, or posting on the internet or an intranet, without prior written permission. Permission can be requested from either ISO at the address below or ISO's member body in the country of the requester.

ISO copyright office  
CP 401 • Ch. de Blandonnet 8  
CH-1214 Vernier, Geneva  
Phone: +41 22 749 01 11  
Fax: +41 22 749 09 47  
Email: [copyright@iso.org](mailto:copyright@iso.org)  
Website: [www.iso.org](http://www.iso.org)

Published in Switzerland

# Contents

	Page
Foreword .....	iv
<b>1 Scope .....</b>	<b>1</b>
<b>2 Normative references .....</b>	<b>1</b>
<b>3 Terms and definitions .....</b>	<b>2</b>
<b>4 Designation of abrasives .....</b>	<b>3</b>
<b>5 Sampling .....</b>	<b>3</b>
<b>6 Requirements for high-carbon cast-steel shot and grit abrasives .....</b>	<b>3</b>
<b>7 Package identification and lot traceability .....</b>	<b>4</b>
<b>8 Information to be provided by the manufacturer or supplier .....</b>	<b>4</b>
<b>Annex A (informative) Approximately equivalent codings for high carbon cast-steel shot and grit abrasives .....</b>	<b>7</b>
<b>Bibliography .....</b>	<b>9</b>

## iTeh STANDARD PREVIEW (standards.iteh.ai)

[ISO 11124-3:2018](https://standards.iteh.ai/catalog/standards/sist/c51c2e39-1eac-475d-9e99-caac70cefeae/iso-11124-3-2018)

<https://standards.iteh.ai/catalog/standards/sist/c51c2e39-1eac-475d-9e99-caac70cefeae/iso-11124-3-2018>

## Foreword

ISO (the International Organization for Standardization) is a worldwide federation of national standards bodies (ISO member bodies). The work of preparing International Standards is normally carried out through ISO technical committees. Each member body interested in a subject for which a technical committee has been established has the right to be represented on that committee. International organizations, governmental and non-governmental, in liaison with ISO, also take part in the work. ISO collaborates closely with the International Electrotechnical Commission (IEC) on all matters of electrotechnical standardization.

The procedures used to develop this document and those intended for its further maintenance are described in the ISO/IEC Directives, Part 1. In particular the different approval criteria needed for the different types of ISO documents should be noted. This document was drafted in accordance with the editorial rules of the ISO/IEC Directives, Part 2 (see [www.iso.org/directives](http://www.iso.org/directives)).

Attention is drawn to the possibility that some of the elements of this document may be the subject of patent rights. ISO shall not be held responsible for identifying any or all such patent rights. Details of any patent rights identified during the development of the document will be in the Introduction and/or on the ISO list of patent declarations received (see [www.iso.org/patents](http://www.iso.org/patents)).

Any trade name used in this document is information given for the convenience of users and does not constitute an endorsement.

For an explanation on the voluntary nature of standards, the meaning of ISO specific terms and expressions related to conformity assessment, as well as information about ISO's adherence to the World Trade Organization (WTO) principles in the Technical Barriers to Trade (TBT) see the following URL: [www.iso.org/iso/foreword.html](http://www.iso.org/iso/foreword.html). (standards.iteh.ai)

This document was prepared by Technical Committee ISO/TC 35, *Paints and varnishes*, Subcommittee SC 12, *Preparation of steel substrates before application of paints and related products*.

This second edition cancels and replaces the first edition (ISO 11124-3:1993), which has been technically revised.

The main changes compared to the previous edition are as follows:

- [Clause 7](#), [Tables 1, 2, 3](#) and [Annex A](#) have been technically revised.

A list of all parts in the ISO 11124 series can be found on the ISO website.

# Preparation of steel substrates before application of paints and related products — Specifications for metallic blast-cleaning abrasives —

## Part 3: High-carbon cast-steel shot and grit

**WARNING** — Equipment, materials and abrasives used for surface preparation can be hazardous. It is important to ensure that adequate instructions are given and that all required precautions are exercised.

### 1 Scope

This document specifies requirements for 14 grades of high-carbon cast-steel shot and 11 grades of high-carbon cast-steel grit, as supplied for blast-cleaning processes. Values are specified for hardness, density, defect/structural requirements and chemical composition.

The requirements specified in this document apply to abrasives supplied in the "new" condition only. They do not apply to abrasives either during or after use.

Test methods for metallic blast-cleaning abrasives are given in the various parts of ISO 11125.

High-carbon cast-steel shot and grit are used in both static and site blasting equipment. They are most often selected where a facility exists for the recovery and re-use of the abrasive.

NOTE 1 Information on commonly referenced national standards for metallic abrasives and their approximate relationship with ISO 11124 is given in [Annex A](#).

NOTE 2 Although this document has been developed specifically to meet requirements for preparation of steelwork, the properties specified will generally be appropriate for use when preparing other material surfaces, or components, using blast-cleaning techniques. These techniques are described in ISO 8504-2.

### 2 Normative references

The following documents are referred to in the text in such a way that some or all of their content constitutes requirements of this document. For dated references, only the edition cited applies. For undated references, the latest edition of the referenced document (including any amendments) applies.

ISO 439, *Steel and iron — Determination of total silicon content — Gravimetric method*

ISO 629, *Steel and cast iron — Determination of manganese content — Spectrophotometric method*

ISO 4935, *Steel and iron — Determination of sulfur content — Infrared absorption method after combustion in an induction furnace*

ISO 9556, *Steel and iron — Determination of total carbon content — Infrared absorption method after combustion in an induction furnace*

ISO 10714, *Steel and iron — Determination of phosphorus content — Phosphovanadomolybdate spectrophotometric method*

ISO 11125-1, *Preparation of steel substrates before application of paints and related products — Test methods for metallic blast-cleaning abrasives — Part 1: Sampling*

## ISO 11124-3:2018(E)

ISO 11125-2, *Preparation of steel substrates before application of paints and related products — Test methods for metallic blast-cleaning abrasives — Part 2: Determination of particle size distribution*

ISO 11125-3, *Preparation of steel substrates before application of paints and related products — Test methods for metallic blast-cleaning abrasives — Part 3: Determination of hardness*

ISO 11125-4, *Preparation of steel substrates before application of paints and related products — Test methods for metallic blast-cleaning abrasives — Part 4: Determination of apparent density*

ISO 11125-5, *Preparation of steel substrates before application of paints and related products — Test methods for metallic blast-cleaning abrasives — Part 5: Determination of percentage defective particles and of microstructure*

ISO 11125-6, *Preparation of steel substrates before application of paints and related products — Test methods for metallic blast-cleaning abrasives — Part 6: Determination of foreign matter*

ISO 11125-7, *Preparation of steel substrates before application of paints and related products — Test methods for metallic blast-cleaning abrasives — Part 7: Determination of moisture*

### 3 Terms and definitions

For the purposes of this document, the following terms and definitions apply.

ISO and IEC maintain terminological databases for use in standardization at the following addresses:

— ISO Online browsing platform: available at <https://www.iso.org/obp>

— IEC Electropedia: available at <https://www.electropedia.org/>

**3.1**  
**high-carbon cast-steel shot**  
metallic blast-cleaning abrasive produced by a casting process in which molten high-carbon steel is formed into *shot* (3.3) by means of an atomization process

**3.2**  
**high-carbon cast-steel grit**  
metallic blast-cleaning abrasive obtained by crushing various *high-carbon cast-steel shot* (3.1) sizes into sharp-edged angular particles

**3.3**  
**shot**  
particles that are predominantly round, that have a length of less than twice the maximum particle width and that do not have edges, broken faces or other sharp surface defects

**3.4**  
**grit**  
particles that are predominantly angular, that have fractured faces and sharp edges and that are less than half round in shape

**3.5**  
**defect**  
fault or weakness in an abrasive which, if present at or above a given level, can be detrimental to the performance characteristics of the abrasive

Note 1 to entry: See [Table 3](#).

**3.5.1**  
**void**  
smooth-surfaced internal cavity considered undesirable when greater than 10 % of the cross-sectional area of a particle

**3.5.2****shrinkage defect**

internal cavity with a rough dendritic surface or a zone of microporosity, considered undesirable when greater than 40 % of the cross-sectional area of a particle

**3.5.3****crack**

linear discontinuity that has a length-to-width ratio of 3:1 or greater, that extends over more than 20 % of the diameter or shortest dimension of a particle and that is radial in direction

**3.6****foreign matter**

material or particles mixed with the abrasive which are not attached to the abrasive particles and which are nonmagnetic

**4 Designation of abrasives**

High-carbon cast-steel shot and grit shall be identified by "Abrasive ISO 11124" and the abbreviation "M/HCS" indicating metallic, high-carbon cast-steel abrasive. The symbol "S" or "G" shall follow to indicate the required particle shape of the shot or grit as purchased. The designation shall be completed by a 3-digit number denoting the grade, or nominal particle size, required. If alternative hardnesses of abrasive are available, the particular Vickers hardness (HV) range required shall be specified (see Example 2).

## EXAMPLE 1

**iTeh STANDARD PREVIEW**

Abrasive ISO 11124 M/HCS/S140

**(standards.iteh.ai)**

denotes an abrasive of the metallic, high-carbon cast-steel type, conforming to the requirements of this document, of particle shape shot and grade 140 (i.e. nominal particle size 1,40 mm).

## EXAMPLE 2

<https://standards.iteh.ai/catalog/standards/sist/c51c2e39-1eac-475d-9e99-caac70cefeae/iso-11124-3-2018>

Abrasive ISO 11124 M/HCS/G140/570-710HV

denotes an abrasive of the metallic, high-carbon cast-steel type, conforming to the requirements of this document, of particle shape grit and grade 140 (i.e. nominal particle size 1,40 mm), and with a hardness range of 570 HV to 710 HV.

This full product designation shall be quoted on all orders.

NOTE 1 Grade requirements and codes are specified in [Tables 1](#) and [2](#). The grade code is based on a 3-digit number indicating the nominal size of the particle size range, for each grade, expressed in millimetres × 100.

NOTE 2 [Annex A](#) provides guidance on approximately equivalent grades and codings in other commonly referenced national standards for cast-metal abrasives.

**5 Sampling**

Sampling procedures shall be as specified in ISO 11125-1.

**6 Requirements for high-carbon cast-steel shot and grit abrasives**

The requirements for high-carbon cast-steel shot and grit abrasives shall be as specified in [Table 3](#).

## 7 Package identification and lot traceability

All supplies shall be clearly marked and identified using the designation system specified in [Clause 4](#). The unit of sale, i.e. commercial packaging unit, shall be clearly labelled with the full product coding, including hardness range, if applicable.

Sub-units, i.e. bags, shall be marked with the particle shape and grade codes.

Inclusion of additional marking to allow product traceability to a particular production period or lot is recommended. Traceability references should be included at least at the pallet, drum or box level of package marking.

## 8 Information to be provided by the manufacturer or supplier

The manufacturer or supplier shall provide, if requested, a test report detailing results for any relevant property as determined by the appropriate method specified in [Table 3](#).

Cast-steel shot and grit abrasives shall be supplied and used in a dry condition.

**Table 1 — Screening specifications by grade — High-carbon cast-steel shot — Cumulative % retained**

Code	Sieve mesh aperture																		
	mm																		
	4,75	4	3,35	2,8	2,36	2	1,7	1,4	1,18	1	0,85	0,71	0,60	0,50	0,425	0,355	0,300	0,180	0,125
S280	0	<30		>90	>97														
S236		0	<30		>90	>97													
S200			0	<30		>90	>97												
S170				0	<30		>90	>97											
S140					0	<30		>90	>97										
S118						0	<30		>90	>97									
S100							0	<30		>90	>97								
S085								0	<30		>90	>97							
S071									0	<30		>90	>97						
S060										0	<30		>90	>97					
S050											0	<30		>90	>97				
S035												0	<30			>90	>97		
S030													0	<30			>90	>97	
S018														0	<30			>90	>97

**Table 2 — Screening specifications by grade — High-carbon cast-steel grit — Cumulative % retained**

Code	Sieve mesh aperture																
	mm																
	2,8	2,36	2	1,7	1,4	1,18	1,00	0,85	0,71	0,60	0,50	0,425	0,355	0,300	0,180	0,125	0,075
G170	0	<30		>85	>95												
G140		0	<30		>85	>95											
G118			0	<30		>85	>95										
G100				0	<30		>85	>95									
G071					0	<30			>85	>95							



Table 2 (continued)

Code	Sieve mesh aperture																
	mm																
	2,8	2,36	2	1,7	1,4	1,18	1,00	0,85	0,71	0,60	0,50	0,425	0,355	0,300	0,180	0,125	0,075
G060						0	<30			>85	>95						
G050							0	<30			>85	>95					
G035								0	<30				>85	>95			
G030									0	<30				>85	>95		
G012											0	<30				>85	>95
G007													0	<30			>85

Table 3 — Requirements for high-carbon cast-steel shot and grit abrasives

Property	Requirement	Test method
Grade size	See <a href="#">Tables 1</a> and <a href="#">2</a> .	ISO 11125-2
Hardness	90 % of the particles tested shall have a hardness value within one of the ranges of <i>Standard hardnesses</i> specified below:	ISO 11125-3
	Hardness	
	Shot	390 HV to 530 HV
	Grit	390 HV to 530 HV
		470 HV to 610 HV
		570 HV to 710 HV
		700 HV minimum
	<i>Special hardnesses (shot and grit):</i>	
	Other hardness ranges can be specified by the purchaser, with a minimum of 90 % of the particles having a minimum range of approximately 140 HV.	
	Metallic abrasives sometimes contain internal shrinkage defects or voids which remain undetected beneath the surface in a mounted and polished sample. These hidden cavities cause a non-uniform hardness indentation and give an erroneous hardness reading. These indentations shall be ignored.	
Apparent density	min. $7,0 \times 10^3$ kg/m <sup>3</sup> (7,0 kg/dm <sup>3</sup> )	ISO 11125-4
Defects (see <a href="#">3.5</a> )	Defects present in the particles examined shall not exceed the following levels:	ISO 11125-5
Particle shape		
a) Shot	max. 5 % non-round	
b) Grit	max. 10 % shot or greater than half-round for grit up to 700 HV, max. 5 % for grit above 700 HV	
Voids		
a) Shot	max. 10 %	
Shrinkage defect		
a) Shot	max. 10 %	
Cracks		
a) Shot	max. 15 %	
b) Grit	max. 40 %	
Total defects		