

SLOVENSKI STANDARD oSIST prEN 17289-1:2019

01-februar-2019

[Not translated]

Characterization of bulk materials - Determination of a sizeweighted fine fraction and crystalline silica content - Part 1: General information and choice of test methods

Charakterisierung von Schüttgütern - Bestimmung einer größengewichteten Feinfraktion und des Anteils an kristallinem Quarz - Teil 1: Allgemeine Information und Auswahl der Prüfverfahren

Ta slovenski standard je istoveten z: prEN 17289-1

ICS:

13.040.30 Kakovost zraka na delovnem Workplace atmospheres

mestu

oSIST prEN 17289-1:2019 en,fr,de

oSIST prEN 17289-1:2019

EUROPEAN STANDARD NORME EUROPÉENNE EUROPÄISCHE NORM

DRAFT prEN 17289-1

January 2019

ICS 13.040.30

English Version

Characterization of bulk materials - Determination of a sizeweighted fine fraction and crystalline silica content - Part 1: General information and choice of test methods

Charakterisierung von Schüttgütern - Bestimmung einer größengewichteten Feinfraktion und des Anteils an kristallinem Quarz - Teil 1: Allgemeine Information und Auswahl der Prüfverfahren

This draft European Standard is submitted to CEN members for enquiry. It has been drawn up by the Technical Committee CEN/TC 137.

If this draft becomes a European Standard, CEN members are bound to comply with the CEN/CENELEC Internal Regulations which stipulate the conditions for giving this European Standard the status of a national standard without any alteration.

This draft European Standard was established by CEN in three official versions (English, French, German). A version in any other language made by translation under the responsibility of a CEN member into its own language and notified to the CEN-CENELEC Management Centre has the same status as the official versions.

CEN members are the national standards bodies of Austria, Belgium, Bulgaria, Croatia, Cyprus, Czech Republic, Denmark, Estonia, Finland, Former Yugoslav Republic of Macedonia, France, Germany, Greece, Hungary, Iceland, Ireland, Italy, Latvia, Lithuania, Luxembourg, Malta, Netherlands, Norway, Poland, Portugal, Romania, Serbia, Slovakia, Slovenia, Spain, Sweden, Switzerland, Turkey and United Kingdom.

Recipients of this draft are invited to submit, with their comments, notification of any relevant patent rights of which they are aware and to provide supporting documentation.

Warning: This document is not a European Standard. It is distributed for review and comments. It is subject to change without notice and shall not be referred to as a European Standard.



EUROPEAN COMMITTEE FOR STANDARDIZATION COMITÉ EUROPÉEN DE NORMALISATION EUROPÄISCHES KOMITEE FÜR NORMUNG

CEN-CENELEC Management Centre: Rue de la Science 23, B-1040 Brussels

Cont	tents	Page
Europ	oean foreword	3
Introd	duction	4
1	Scope	6
2	Normative references	6
3	Terms and definitions	6
4	Symbols and abbreviations	9
5	Test methods	9
6 6.1 6.2	Guidelines for the determination of crystalline silica Preparation of sample to be analysed Sample preparation for further analysis by XRD and FT-IR	11
7	Test report	11
Annex	x A (informative) Round robin test to establish a SWFF reference sample	13
A.1	General	13
A.2	Test material Evaluation and appraisal method	13
A.3	Evaluation and appraisal method	14
A.4	Results	15
Annex	x B (informative) Determination of CS in bulk samples using X-Ray diffraction (XRD or FT-IR spectroscopy	17
B.1	General	17
B.2	Preparation of bulk samples for determination of CS using XRDXRD	17
B.2.1	General	17
B.2.2	Method 1: Bulk method	17
B.2.2.	1 General	17
B.2.2.	2 Preparation	18
B.2.2.	3 Measurement	18
B.2.2.	4 Calculation	18
B.2.3	Method 2: Deposition method	19
B.3	Preparation of bulk samples for determination of CS using FT-IR	19
B.3.1	Identification of the interfering minerals	19
B.3.2	Interferences removal	20
B.3.3	Standards and sample preparation	20
B.3.4	Operating conditions	
B.3.5	Measurement	20
B.3.6	Determination of the quartz content	21
Biblio	ography	23

European foreword

This document (prEN 17289-1:2019) has been prepared by Technical Committee CEN/TC 137 "Assessment of workplace exposure to chemical and biological agents", the secretariat of which is held by DIN.

This document is currently submitted to the CEN Enquiry.

To half and standards to the standard of the s

Introduction

A method was developed in the industrial minerals industry for the purpose of determining the "size weighted relevant fine fraction" within the bulk material. This method provides the necessary information to the users and allows them to compare bulk materials, by measuring the fine fraction, in order for them to select the safest materials. It has been used in the industry and by institutes previously under the acronym SWeRF. EN 17289 (all parts) is based on that industrial method and describes the analytical methods to determine the difference between materials with coarse quartz and fine quartz, e.g. sands versus flour.

As further activities with the material (intentional or otherwise) might change the particle size distribution, the size weighted fine fraction might also change. Therefore, the method reports (in terms of the mass percentages in the bulk material) both, the total CS and the estimated size weighted fine fraction of CS.

Conventions as described in EN 481 can be used as input for this document. However, the output of this document is not related to the respirable fraction and cannot be used for workplace exposure measurements.

EN 17289 (all parts) describes two procedures that can be used to estimate the size weighted fine fraction (SWFF) in bulk materials. It also describes how the SWFF, once separated, can be further analysed to measure the content of crystalline silica (SWFF $_{cs}$). The method can be used for comparing the fine fraction in different bulk samples. EN 17289 (all parts) uses the term fine fraction to indicate that it does not analyse airborne particles, but it evaluates the proportion of particles in a bulk material that, based on their particle size, have a potential to be respirable if they were to become airborne.

EN 17289 (all parts) also allows for the size weighted fine fraction of crystalline silica (SWFF_{cs}) particles in bulk materials to be evaluated in terms of mass fraction in percent, if the fraction separated is subsequently analysed by a suitable method.

In comparison of similar bulk materials, in which the particle size distribution is the only variable, the SWFF can provide useful information to guide material selection. For example, leaving all other factors aside, a bulk material with a lower SWFF value can pose less of a risk in terms of potential occupational exposure. For the actual exposure at the workplace, the handling etc of the material, will play a major role

Concentrations of respirable dust, or respirable crystalline silica (RCS), in the workplace air, resulting from processing and handling of bulk materials, will depend on a wide variety of factors and these concentrations cannot be estimated using SWFF or SWFF $_{cs}$ values. SWFF and SWFF $_{cs}$ values are not to be used for occupational exposure assessments as they have no relationship with occupational exposure.

The evaluation of bulk materials using SWFF is complementary to determining the dustiness according to EN 15051-1 [1].

The difference between EN 17289 (all parts) and EN 15051-1 is that SWFF quantifies the fine fraction in a bulk material while dustiness quantifies the respirable, thoracic and inhalable dust made airborne from the bulk material after a specific activity (it characterizes the material with relation to the workplace atmosphere when working with the bulk material).

EN 17289 *Characterization of bulk materials* — *Determination of a size-weighted fine fraction and crystalline silica content* consists of the following parts:

- Part 1: General information and choice of test methods;
- Part 2: Calculation method;
- Part 3: *Sedimentation method*.

Part 1 gives information on how to choose the most appropriate method as well as a guideline for the determination of crystalline silica. A calculation method based on particle size distribution is described in Part 2. Part 3 describes a method using sedimentation.

Tehs AND ARD PREWITTING ARD COLUMN TO THE ART OF THE AR

1 Scope

This document specifies the the requirements and choice of test method for the determination of the size weighted fine fraction (SWFF) and the size weighted fine fraction of crystalline silica (SWFF $_{CS}$) in bulk materials.

This document gives also guidance on the preparation of the sample and determination of crystalline silica by XRD and FT-IR.

NOTE prEN 17289-2:2019 specifies a method to estimate the size-weighted fine fraction from a measured particle size distribution and assumes that the particle size distribution of the crystalline silica particles is the same as the other particles present in the bulk material. prEN 17289-3:2019 specifies a method using a liquid sedimentation technique to determine the size-weighted fine fraction of crystalline silica. Both methods are based upon a number of limitations and assumptions, which are listed in prEN 17289-2:2019 and prEN 17289-3:2019, respectively. The method in prEN 17289-3:2019 can also be used for other constituents, if investigated and validated.

This document is applicable for bulk materials which have been fully investigated and validated. The criteria for the materials are described in prEN 17289-2:2019 and prEN 17289-3:2019. This includes industrial minerals which can contain crystalline silica such as quartz, clay, kaolin, talc, feldspar, mica, cristobalite, vermiculite, diatomaceous earth, barite, andalusite, iron ore, chromite etc.

2 Normative references

The following documents are referred to in the text in such a way that some or all of their content constitutes requirements of this document. For dated references, only the edition cited applies. For undated references, the latest edition of the referenced document (including any amendments) applies.

EN 1540:2011, Workplace exposure - Terminology

prEN 17289-2:2019, Characterization of bulk materials – Determination of a size-weighted fine fraction and crystalline silica content — Part 2: Calculation method

prEN 17289-3:2019, Characterization of bulk materials – Determination of a size-weighted fine fraction and crystalline silica content — Part 3: Sedimentation method

ISO 16258-2, Workplace air — Analysis of respirable crystalline silica by X-ray diffraction — Part 2: Method by indirect analysis

ISO 24095, Workplace air — Guidance for the measurement of respirable crystalline silica

3 Terms and definitions

For the purposes of this document, the terms and definitions given in EN 1540:2011 and the following apply.

ISO and IEC maintain terminological databases for use in standardization at the following addresses:

- IEC Electropedia: available at http://www.electropedia.org/
- ISO Online browsing platform: available at http://www.iso.org/obp

3.1

between-samples standard deviation

Ss

standard deviation between the random samples used for homogeneity check

3.2

bulk density

ratio of the mass of a quantity of dry granular material to the total volume of its grains, including the volume of any closed pores within the grains

[SOURCE: ISO 836: 2001[3]]

3.3

bulk sample

portion that is representative of the bulk material

3.4

coefficient of variation of the reproducibility

 $CV_{\rm R}$

ratio of standard deviation to the mean of test results produced under reproducibility conditions, i.e. conditions where test results are obtained with the same method on identical test items in different laboratories with different operators using different equipment

[SOURCE: ISO 5725-1[4]]

3.5

complex refractive index

 $n_{\rm p}$

refractive index of a particle, consisting of a real and an imaginary (absorption) part

Note 1 to entry: The complex refractive index of a particle can be expressed mathematically as

$$n_p = m_p - i \times k_p$$

where

i is the square root of -1;

 $k_{\rm p}$ is the positive imaginary (absorption) part of the refractive index of a particle;

 $m_{\rm p}$ is the positive real part of the refractive index of a particle

[SOURCE: ISO 13320] [5]

3.6

crystalline silica

 SiO_2

silicon dioxide with Si and O orientated in a fixed pattern as opposed to a nonperiodic, random molecular arrangement defined as amorphous

Note 1 to entry: The three most common crystalline forms of silica are quartz, tridymite, and cristobalite.

3.7

D_{10}

particle diameter corresponding to 10 % of the cumulative undersize distribution (by volume or by mass)

[SOURCE: ISO 13320]

3.8

D₅₀ median particle diameter

particle diameter, where 50 % of the particles – by volume or by mass – are smaller than this diameter and 50 % are larger

[SOURCE: Adapted from ISO 13320]

3.9

D_{90}

particle diameter corresponding to 90 % of the cumulative undersize distribution (by volume or by mass)

[SOURCE: ISO 13320]

3.10

equivalent Stokes diameter

equivalent spherical diameter

diameter of a sphere having the same rate of sedimentation and density as the particle for laminar flow in a liquid

3.11

mineral phase

homogeneous substance with a well-defined set of physical and chemical properties; it defines a uniquely identifiable mineral

3.12

relative density ratio of the density of a substance to the density of a given reference material

3.13

size weighted fine fraction

proportion of mass of particles in a bulk material below a well-defined probability function

3.15

skeletal density

mass of a unit volume of the Diatomaceous Earth (DE) skeleton, inaccessible to Helium

3.16

standard deviation for proficiency assessment

measure of dispersion used in the assessment of proficiency, based on the available information

[SOURCE: ISO 13528[6]]

3.17

supernatant

column of liquid that is separated from the total sedimentation liquid column which contains the solid particles of interest

Note 1 to entry: See prEN 17289-3:2018, Figure A.2.